
FED. SUP CLASS
5306

MS9295 (ASG)



PART NUMBER	L	K	APPROX WEIGHT LB/100
MS9295-04	.375	.079-.099	1.29
MS9295-05	.438	.079-.099	1.36
MS9295-06	.500	.079-.099	1.43
MS9295-07	.562	.079-.099	1.50
MS9295-08	.625	.079-.099	1.57
MS9295-09	.688	.079-.099	1.64
MS9295-10	.750	.079-.099	1.71
MS9295-11	.812	.079-.099	1.79
MS9295-12	.875	.079-.125	1.86
MS9295-13	.938	.128-.188	1.93
MS9295-14	1.000	.190-.250	2.00
MS9295-15	1.062	.252-.312	2.07
MS9295-16	1.125	.315-.375	2.14
MS9295-17	1.188	.378-.438	2.22
MS9295-18	1.250	.440-.500	2.29
MS9295-19	1.312	.502-.562	2.36
MS9295-20	1.375	.565-.625	2.43
MS9295-21	1.438	.628-.688	2.50
MS9295-22	1.500	.690-.750	2.57
MS9295-23	1.562	.752-.812	2.65
MS9295-24	1.625	.815-.875	2.72
MS9295-25	1.688	.878-.938	2.79
MS9295-26	1.750	.940-1.000	2.86
MS9295-27	1.875	1.065-1.125	3.00
MS9295-28	2.000	1.190-1.250	3.15
MS9295-29	2.125	1.315-1.375	3.29
MS9295-30	2.250	1.440-1.500	3.43
MS9295-31	2.375	1.565-1.625	3.58
MS9295-32	2.500	1.690-1.750	3.72
MS9295-33	2.625	1.815-1.875	3.86
MS9295-34	2.750	1.940-2.000	4.01
MS9295-35	2.875	2.065-2.125	4.15
MS9295-36	3.000	2.190-2.250	4.29
MS9295-37	3.125	2.315-2.375	4.44
MS9295-38	3.250	2.440-2.500	4.58
MS9295-39	3.375	2.565-2.625	4.73
MS9295-40	3.500	2.690-2.750	4.87
MS9295-41	3.625	2.815-2.875	5.01
MS9295-42	3.750	2.940-3.000	5.16
MS9295-43	3.875	3.065-3.125	5.30
MS9295-44	4.000	3.190-3.250	5.44
MS9295-45	4.125	3.315-3.375	5.59
MS9295-46	4.250	3.440-3.500	5.73
MS9295-47	4.375	3.565-3.625	5.87
MS9295-48	4.500	3.690-3.750	6.02
MS9295-49	4.625	3.815-3.875	6.16
MS9295-50	4.750	3.940-4.000	6.30
MS9295-51	4.875	4.065-4.125	6.45
MS9295-52	5.000	4.190-4.250	6.59
MS9295-53	5.125	4.315-4.375	6.73
MS9295-54	5.250	4.440-4.500	6.88
MS9295-55	5.375	4.565-4.625	7.02
MS9295-56	5.500	4.690-4.750	7.16
MS9295-57	5.625	4.815-4.875	7.31
MS9295-58	5.750	4.940-5.000	7.45
MS9295-59	5.875	5.065-5.125	7.59
MS9295-60	6.000	5.190-5.250	7.74

1. HEAD TO SHANK FILLET SHALL BE COLD ROLLED AFTER HEAT TREATMENT TO REMOVE ALL VISUAL EVIDENCE OF GRINDING OR TOOL MARKS.
2. SHANK SHALL BE STRAIGHT WITHIN .003 PER INCH OF BOLT LENGTH.
3. THE CONCENTRICITY OF THREAD PD IN RELATION TO THE SHANK SHALL BE WITHIN .006 FIR.
4. THE CONCENTRICITY OF THE SHANK IN RELATION TO THE WASHER FACE DIAMETER AND HEXAGON SHALL BE WITHIN .013 FIR.
5. INCOMPLETE THREADS NOT TO ENTER FILLET.
6. MATERIAL: STEEL AMS 6322.
7. HARDNESS: ROCKWELL C26-32.
8. FINISH: BLACK OXIDE TREATMENT AMS 2485.
9. MANUFACTURING SPECIFICATION: AMS 7452 EXCEPT HEAD MUST BE UPSET.
10. MAGNETIC PARTICLE INSPECTION PER AMS 2640.
11. SURFACE ROUGHNESS: AS 291. UNLESS OTHERWISE SPECIFIED SURFACES TO BE 125 MICROINCHES EXCEPT HEXAGON.
12. BREAK SHARP EDGES .003-.015 UNLESS OTHERWISE SPECIFIED.
13. DIMENSIONS IN INCHES. UNLESS OTHERWISE SPECIFIED, TOLERANCES: LINEAR DIMENSIONS ±.010, ANGULAR DIMENSIONS ±5°.
14. DO NOT USE UNASSIGNED PART NUMBERS.

REVISED
APPROVED 24 Sep 65

AS & AMS ARE SOCIETY OF AUTOMOTIVE ENGINEERS, INC. PUBLICATIONS.
THIS STANDARD WAS DEVELOPED COOPERATIVELY WITH THE ENGINE AND PROPELLER UTILITY PARTS COMMITTEE OF THE SAE.

P.A. USAF - 11 Other Cust Navy - MP	TITLE BOLT, MACHINE-STEEL AMS 6322, BLACK OXIDE, DRILLED, 1 HOLE, HEXAGON HEAD, .250-28 UNJF-3A	MILITARY STANDARD MS 9295 (ASG)
PROCUREMENT SPECIFICATION None	SUPERSEDES:	SHEET 1 OF 1

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T13:14Z
Check the source to verify that this is the current version before use.