DDD–B–151b
15 JUNE 1951
SUPERSEDING
Fed. Spec. DDD-B-151a
5 JUNE 1947

FEDERAL SPECIFICATION

BEDSPREADS, COTTON

This specification was approved on the above date by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. CLASSIFICATION

1.1 Types, classes, and patterns.—Bedspreads covered by this specification shall be of the following types, classes, and patterns, as specified (see 3.3 and 6.2.)

Types VI.—Pique.
  Class A.—Sand and white.
Type VII.—Crinkle.
  Class A.—Bleached.
  Class B.—Unbleached.
  Class C.—Colored (see 3.6.2.3).
Type VIII.—Crochet.
  Class A.—Bleached.
    Pattern 1.—Fancy.
    Pattern 2.—Border.
Type IX.—Dimity.
  Class A.—Bleached.
  Class B.—Unbleached.
  Class C.—Colored (see 3.6.4.3).
Type X.—Striped (see 7.3.2).
  Class A.—White.
  Class B.—Colored (see 3.6.5.2).

1.2 Sizes.—The bedspreads shall be of the sizes shown in table I, as specified.

1.3 Grade.—Unless otherwise specified, the bedspreads shall be furnished in the grade known commercially as firsts. (See 3.10 and 6.2.)

2. APPLICABLE SPECIFICATIONS

2.1 The following Federal Specifications, of the issues in effect on date of invitation for bids, form a part of this specification:

V–T–276—Thread; Cotton.
TT–I–542—Ink; Marking, Indelible, Black, for Fabrics.
CCC–T–191—Textiles; General Specifications, Test Methods.
DDD–S–751—Stitches; Seams; and Stitching.

(Copies of Federal specifications and the Federal Specifications Index may be obtained upon application, accompanied by money order, coupon, or cash, to the Superintendent of Documents, Government Printing Office, Washington 25, D. C. Prices may be obtained from the Superintendent of Documents.)

2.2 Specifications and other publications applicable only to individual departments are listed in section 7.

3. REQUIREMENTS

3.1 Material.

3.1.1 *Yarn.*—The yarn shall be evenly spun of thoroughly clean cotton of a suitable grade and length of staple to meet the requirements for the finished fabric.

3.1.2 *Thread.*—The thread shall be bleached or fast-dyed to match the color of the bedspreads and shall conform to the requirements of Specification V–T–276 for type type IA2, 3-cord, ticket No. 40.

3.2 Construction.—Each bedspread shall be one piece of material with straight, even selvages on both sides. The ends shall be cut parallel to the filling yarns. The hems at each end shall be not less than ¾ inch wide, straight, and of uniform width. The turnunders on each hem shall be not less than ¼

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:34Z
Check the source to verify that this is the current version before use.

inch wide. All stitching shall be done with not less than eight stitches to the linear inch, using stitching type EFb–1 and stitch type 301 as described in Specification DDD–S–751.

3.3 Design.—Cotton bedspreads shall be furnished as selected from commercial designs, unless otherwise specified in the invitation for bids.

3.4 Weave.

3.4.1 *Type VI, pique.*—Type VI bedspreads shall be of any weave or combination of weaves that will produce a finished spread having an allover design of raised lozenges approximately ¼ inch by ⅜ inch, formed by four small squares; the lozenges shall be regularly spaced about $\frac{7}{16}$ inch apart, with a double panel in the center of the spread. When specified in the invitation for bids, an insignia shall be woven in the center of the double panel. (See 3.10, and 6.1.)

3.4.2 *Type VII, crinkle.*—Type VII bedspreads shall be of any weave or combination of weaves that will produce an alternate crinkle stripe and smooth stripe in the finished bedspread. The ground shall be reinforced as follows: Eight ground ends on each side and adjacent to all crinkle stripes measuring ⅜ inch or more, shall be drawn in so that two ends are woven as one (eight ends weaving as four). The stripes shall run lengthwise in the bedspreads.

3.4.3 *Type VIII, crochet.*—Type VIII bedspreads shall be of any weave or combination of weaves that will simulate a crochet or knit effect in the finished bedspread. When specified, an insignia shall be woven in the center of the bedspread.

3.4.4 *Type IX, dimity.*—Type IX bedspreads shall be of any weave or combination of weaves that will produce a series of narrow, medium, and wide corded stripes which run lengthwise in the bedspread.

3.4.5 *Type X, striped.*—Type X bedspreads shall be of any weave or combination of weaves that will produce stripes of various widths in the finished bedspread. The stripes shall run lengthwise of the bedspread. When specified in the invitation for bids, an insignia shall be woven in the center of the bedspread. (See 7.3.2.)

3.4.5.1 *Class A.*—Class A bedspreads shall be woven with white yarns in both the warp and the filling directions. (See 3.4.5.)

3.4.5.2 *Class B.*—Class B bedspreads shall be woven with a white warp and blue filling or with a blue warp and white filling so as to produce alternating blue and white stripes (see 3.4.5). The blue shall be the dominant color on the face of the fabric.

3.5 Physical requirements.—The bedspreads shall conform to the requirements shown in table I.

3.5.1 *Size.*—Bedspreads shall be furnished in such dimensions as to conform to the sizes shown in table I after laundering. (See 4.3.)

3.6 Finish.

3.6.1 *Type VI, pique.*—The color of type VI bedspreads shall be that commercially known as sand and white, equal in shade to the standard sample furnished by the procuring agency. (See 6.1.)

3.6.2 *Type VII, crinkle.*

3.6.2.1 *Class A.*—The fabric shall be bleached.

3.6.2.2 *Class B.*—The fabric shall be unbleached.

3.6.2.3 *Class C.*—The fabric shall be of the color specified. The bedspread shall have good color fastness to laundering, light, and bleaching when tested in accordance with 4.3.2.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:34Z
Check the source to verify that this is the current version before use.

TABLE I.—*Physical requirements*

Type	Pattern	Size before hemming, minimum	Weight of finished bedspreads, minimum	Yarns per inch, minimum		Breaking strength (grab method), minimum	
				Warp	Filling	Warp	Filling
		Inches	*Ounces*			*Pounds*	*Pounds*
VI—Pique	----------	63 x 90 72 x 90 81 x 90	35 40 45	86	42	70	85
VII—Crinkle	----------	63 x 90 63 x 99 72 x 90 72 x 99 72 x 108 81 x 90 81 x 99 90 x 90 90 x 99	21½ 24 25 27 29 28 30½ 31 34	72 (in plain ground) 62 (in crinkle stripe)	62	60	50
VIII—Crochet	1—Fancy	54 x 90 63 x 90 72 x 90 72 x 108 81 x 90	28½ 33 38 45 45	----------	----------	50	50
	2—Border	72 x 90 72 x 99 72 x 108 81 x 90	44 50 60 64	----------	----------	50	50
IX—Dimity	----------	63 x 90 63 x 99 72 x 90 72 x 99 81 x 90 81 x 99 90 x 90 90 x 99	21½ 24 25 27 28 30½ 31 34	70	60	75	45
X—Striped	----------	56 x 90 72 x 90	20 26½	69	40	65	65

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:34Z
Check the source to verify that this is the current version before use.

3.6.3 *Type VIII, crochet.*

3.6.3.1 *Class A.* — The fabric shall be bleached.

3.6.4 *Type IX, dimity.*

3.6.4.1 *Class A.* — The fabric shall be bleached.

3.6.4.2 *Class B.*—The fabric shall be unbleached.

3.6.4.3 *Class C.*—The fabric shall be of the color specified. The bedspreads shall have good color fastness to laundering, light, and bleaching when tested in accordance with 4.3.2.

3.6.5 *Type X, striped.*

3.6.5.1 *Class A.* — The fabric shall be bleached.

3.6.5.2 *Class B.*—The fabric shall be of the color specified (see 3.4.5.2). The bedspreads shall have good color fastness to laundering, light, and bleaching when tested in accordance with 4.3.2.

3.7 Finishing and nonfibrous materials.—The total of sizing, finishing, and other nonfibrous materials shall not exceed 2½ percent.

3.8 Identification stamp (type VIII, pattern 2 only).—When specified in the invitation for bids, each type VIII, pattern 2 bedspread shall be stamped on the reverse side at one corner, 1 inch from the side and 1 inch from the end, with the name of the design. Stamping shall be in black indelible ink complying with the requirements of Specification TT–I–542.

3.9 Workmanship.—The bedspreads shall be clean and free from defects which affect the appearance or which may impair the serviceability.

3.10 Seconds.—If "seconds" are permitted, they shall comply with the requirements of this specification, but may have slight imperfections of manufacture which affect only slightly the general appearance, but which shall in no way affect the serviceability or wearing quality of the bedspreads. "Seconds" may have pickouts, misweave, thread runs, oil spots, or kier stains which make them less attractive in finish and appearance than "firsts," but a combination of these defects, or an extreme instance of any of them, will be considered cause for rejection as "seconds." "Seconds" may not contain holes or tears. (See 6.2.)

4. SAMPLING, INSPECTION, AND TEST PROCEDURES

4.1 Sampling.—Unless otherwise specified, at least 1 bedspread shall be taken at random from each 1,000 bedspreads or fraction thereof delivered, except that when the shipment exceeds 10,000 bedspreads, a sample shall be taken from each one-tenth of the shipment.

4.2 Inspection.—Final inspection shall be made at the point of delivery or at the factory, at the discretion of the purchasing agent.

4.3 Tests.—Tests shall be conducted in accordance with the applicable methods described in Specification CCC–T–191 and as hereinafter specified.

4.3.1 *Breaking strength (type VII only).*—Warp breaking strength specimens shall be taken consecutively across the bedspreads. The average of the breaks on the 10 specimens so taken shall be recorded as the breaking strength.

4.3.2 *Color fastness (types VI, VII, IX, and X only).*

4.3.2.1 *Fastness to bleaching.*—Fastness to bleaching shall be determined by using sodium hypochlorite solution (bleach).

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:34Z
Check the source to verify that this is the current version before use.

4.3.2.2 *Fastness to light.*—Fastness to light shall be determined by the 40-hour-exposure test in a glass-enclosed carbon-arc lamp.

5. PREPARATION FOR DELIVERY

5.1 Packaging.—Unless otherwise specified, commercial packages will be acceptable.

5.2 Packing.—The bedspreads shall be prepared for shipment to permit acceptance by carrier for transportation at the lowest applicable rate, and to afford maximum protection from normal hazards of transportation.

5.3 Marking.—Unless otherwise specified, shipping containers shall be marked with the stock number, name, type, class (including color where applicable), pattern, and size of the commodity as defined by the contract or order under which the shipment is made, the unit and quantity contained therein, the name of the contractor, and the number of the contract or order.

6. NOTES

6.1 Ordering data. — Purchasers should specify the type, class, pattern (for type VIII), and size; color, if class C of types VII and IX or class B of type X is specified; detailed information relative to insignia for types VI, VIII, and X, and special identification marking for type VIII, pattern 2, if required; whether or not "seconds" will be accepted, what quantity and discount; location of standard sample, if type VI is specified; place of inspection; and should exercise any desired options offered herein. (See 1.1, 1.2, 1.3, 3.4.1, 3.4.3, 3.4.5, 3.6.1, 3.6.2.3, 3.6.4.3, 3.6.5.2, 3.8, 3.10, 4.1, 4.2, 5.1, 5.3, 6.2, and 7.2.4.1 (size of caduceus and letters for Army).)

6.2 "Seconds." — In the procurement of such commodities as bedspreads where the color, size, pattern, or insignia (see 3.4.1 and 7.3.2) are such that they cannot be readily disposed of through commercial outlets, it is customary to allow from 5 to 10 percent "seconds" at a predetermined discount.

Patent notice.—When Government drawings, specifications, or other data are used for any purpose other than in connection with a definitely related Government procurement operation, the United States Government thereby incurs no responsibility nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data, is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use, or sell any patented invention that may in any way be related thereto.

7. DEPARTMENTAL REQUIREMENTS

7.1 The following specifications, other publications and drawing, of the issues in effect on date of invitation for bids, and special requirements, form a part of this specification for purchases under this specification by the respective departments.

7.2 Army.

7.2.1 *Applicable specifications and drawing.*

Military Specifications:

JAN–P–105—Packaging and Packing for Overseas Shipment—Boxes, Wood, Cleated, Plywood.

JAN–P–106—Packaging and Packing for Overseas Shipment—Boxes; Wood, Nailed.

JAN–B–107—Boxes, Wood, Wirebound (Overseas Type).

JAN–P–125—Packaging and Packing for Overseas Shipment—Barrier-Materials, Waterproof, Flexible.

JAN–P–140—Packaging and Packing for Overseas Shipment — Adhesives, Water-Resistant, Case-Liner.

MIL–B–3149—Baling of Clothing and Equipage.

U. S. Army Specification:

100-2—Standard Specification for Marking Shipments by Contractors.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:34Z
Check the source to verify that this is the current version before use.

Armed Services Medical Procurement Agency Drawing:
1056—Joint Army-Navy Medical Department Insignia.

(Copies of specifications required for Army purchases may be obtained upon application to the procuring agency. Both the title and identifying symbol or number should be stipulated when requesting copies.

(Copies of ASMPA drawings may be obtained upon application to the Armed Services Medical Procurement Agency, 84 Sands Street, Brooklyn 1, N. Y.)

7.2.2 *Packaging.*

7.2.2.1 *Unit packaging.*—One bedspread of the type and class specified in the purchase order, contract, or invitation for bids constitutes one unit. Each unit shall be neatly folded to measure approximately 14 by 29 inches.

7.2.2.2 *Intermediate packaging.*—Six units, folded as specified in 7.2.2.1, shall be stacked to form a neat bundle and wrapped with kraft paper of suitable weight. Wrapper shall be adequately secured with cotton cord or kraft gummed paper tape to insure against additional opening.

7.2.3 *Packing for domestic and overseas shipment.*—A number of intermediate packages as indicated in table II, shall be either baled in accordance with Specification Mil-B-3149 or packed in boxes constructed, closed, and strapped in accordance with Specification JAN-P-105, JAN-P-106, or JAN-B-107. Each box shall be lined with a sealed barrier fabricated of material conforming to the requirements of Specification JAN-P-125. Closures shall be completely sealed with a continuous seam, at least ¾-inch wide, of water-resistant adhesive complying with Specification JAN-P-140.

7.2.3.1 *Packing variation permitted.* — If the number of units in any shipment is not the exact multiple of number of units specified to be contained in each shipping container, the units not constituting the nearest such multiple shall be packed in an exterior container of suitable size and design and so constructed as to insure safe delivery to specified destination.

TABLE II.—*Number of intermediate packages in shipping containers*

Type	Pattern	Size	Number of int. packages to be overpacked in each shipping container	Total number of units to be contained in each shipping container
VI—Pique	--------	63 x 90	8	48
		72 x 90	6	36
		81 x 90	6	36
VII—Crinkle	--------	63 x 90	10	60
		63 x 99	10	60
		72 x 90	8	48
		72 x 99	8	48
		72 x 108	8	48
		81 x 90	8	48
		81 x 99	8	48
		90 x 90	8	48
		90 x 99	8	48
VIII—Crochet	1—Fancy	54 x 90	8	48
		63 x 90	8	48
		72 x 90	8	48
		81 x 90	8	48
	2—Border	72 x 90	8	48
		72 x 99	6	36
		72 x 108	4	24
		81 x 90	4	24
IX—Dimity	--------	63 x 90	10	60
		63 x 99	10	60
		72 x 90	8	48
		72 x 99	8	48
		81 x 90	8	48
		81 x 99	8	48
		90 x 90	8	48
		90 x 99	8	48

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:34Z
Check the source to verify that this is the current version before use.

7.2.4 *Marking.*—In addition to the marking specified in section 5, shipping containers for the Army shall be marked in accordance with U. S. Army Specification 100-2.

7.2.4.1 *Marking of bedspreads for Medical Department procurements.*—Type VII, class A, and type VIII, class A, bedspreads shall have a caduceus centered between the letters "U" and "S" woven in the center of both types of bedspreads, conforming to Joint Army-Navy Medical Department Insignia Drawing No. 1056. The size of caduceus and letters shall be as specified in the invitation for bids, contract, or order.

7.3 Navy.

7.3.1 *Applicable specification and other publication.*

Navy Department Specification:

General Specifications for Inspection of Material.

Bureau of Supplies and Accounts Publication:

Navy Handbook on Packing and Materials Handling — Packaging, Packing, and Marking of Clothing, Small Stores and Textiles.

(Copies of Federal specifications required for Navy purchases, and Navy Department specifications may be obtained without cost upon application to the Bureau of Supplies and Accounts, Navy Department, Washington 25, D. C., except that Naval activities should make application to the Commanding Officer, Naval Supply Depot, Scotia 2, N. Y. Both the title and identifying symbol or number should be stipulated when requesting copies of specifications.

(Applicable sections of the Navy Handbook on Packing and Materials Handling—Packaging, Packing, and Marking of Clothing, Small Stores and Textiles may be obtained upon application to the Bureau of Supplies and Accounts, Navy Department, Washington 25, D. C. When requesting copies, bidders and contractors should state the specification number and complete nomenclature of the item to be packed, so that the proper sections may be forwarded.)

7.3.2 *Navy insignia.* — The Navy insignia shall be woven in the center of the bedspreads and shall consist of two concentric knotted-rope designs with the words "UNITED STATES NAVY" between the two circles in letters 1¾ inches high, and within the inner circle a fouled anchor set at an angle of approximately 30° to the vertical. The finished insignia shall measure between 11½ and 15 inches in outside diameter, with a 5⅜- to 7-inch diameter of the inner circle. (See fig. 1.)



Figure 1

7.3.3 *Packing, packing, and marking for shipment.*—The commodity shall be prepared for delivery in accordance with the Navy Handbook on Packing and Materials Handling—Packaging, Packing, and Marking of Clothing, Small Stores and Textiles.

NAVY INTEREST: Md Sh S

This specification is a part of Section IV, Part 5, of the Federal Standard Stock Catalog.

For sale by the Superintendent of Documents, Washington 25, D. C. Price cents.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:34Z
Check the source to verify that this is the current version before use.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:34Z
Check the source to verify that this is the current version before use.