DDD-B-151c
SEPTEMBER 9, 1957
SUPERSEDING
Fed. Spec. DDD–B–151b
June 15, 1951

FEDERAL SPECIFICATION

BEDSPREADS (COTTON)

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope.—This specification covers cotton bedspreads.

1.2 Classification.

1.2.1 *Types, classes, and patterns.*—Bedspreads shall be of the following types, classes, and patterns, as specified (see 6.2):

Type VI.—Pique.

Type VII.—Crinkle.
- Class A.—Bleached.
- Class B.—Unbleached.
- Class C.—Colored.

Type VIII.—Crochet.
- Class A.—Bleached.
  - Pattern 1. —Fancy.
  - Pattern 2.—Border.

Type IX.—Dimity.
- Class A.—Bleached.
- Class B.—Unbleached.
- Class C.—Colored.

Type X.—Striped.
- Class A.—White.
- Class B.—Colored.

1.2.2 *Grade.*—Unless otherwise specified, the bedspreads shall be furnished in the grade known commercially as firsts (see 3.8 and 6.3).

2. APPLICABLE SPECIFICATIONS, STANDARDS, AND OTHER PUBLICATIONS

2.1 The following specifications and standards, of the issues in effect on date of invitation for bids, form a part of this specification:

Federal Specifications:

V–T–276—Thread; Cotton.

TT–I–542 — Ink, Marking, Indelible, Black, for Fabrics.

CCC–T–191—Textile Test Methods.

DDD–S–751 — Stitches; Seams; and Stitching.

PPP–B–585—Boxes, Wood, Wirebound.

PPP–B–591 — Boxes, Fiberboard, Wood Cleated.

PPP–B–601—Boxes, Wood-Cleated-Ply-Plywood.

PPP–B–621—Boxes, Wood, Nailed and Lock-Corner.

PPP–B–636—Boxes, Fiber.

Federal Standards:

Fed. Std. No. 102—Preservation, Packaging, and Packing Levels.

(Activities outside the Federal Government may obtain copies of Federal Specifications and Standards as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:34Z
Check the source to verify that this is the current version before use.

of Documents, U. S. Government Printing Office, Washington 25, D. C.

(Single copies of this specification and other product specifications required by activities outside the Federal Government for bidding purposes are available without charge at the General Services Administration Regional Offices in Boston, New York, Atlanta, Chicago, Kansas City, Mo., Dallas, Denver, San Francisco, Los Angeles, Seattle, and Washington, D. C.

(Federal Government activities may obtain copies of Federal Specifications and Standards and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

Military Specifications:

MIL–B–10377 — Boxes: Wood-Cleated, Veneer, Paper Overlaid.

MIL–L–10547 — Liners, Case, Waterproof.

Military Standards:

MIL–STD–105 — Sampling Procedures and Tables for Inspection by Attributes.

MIL–STD–129 — Marking for Shipment and Storage.

(Copies of Military Specifications, Standards, Drawings, and Publications required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. — The following document forms a part of this specification. Unless otherwise indicated, the issue in effect on date of invitation for bids shall apply.

Consolidated Classification Committee Publication:

Consolidated Freight Classification Rules.

(Application for copies should be addressed to the Consolidated Classification Committee, 202 Chicago Union Station, Chicago 6, Illinois.)

3. REQUIREMENTS

3.1 Material.

3.1.1 *Yarn.*—The yarn shall be evenly spun of thoroughly cleaned cotton of a suitable grade and length of staple to meet the requirements for the finished fabric.

3.1.2 *Thread.* — The thread shall be bleached or fast-dyed to match the color of the bedspreads and shall conform to type IA2, 3-cord, ticket No. 40 of Federal Specification V–T–276.

3.2 Construction.—Each bedspread shall be one piece of fabric with straight, even selvages on both sides. The ends shall be cut parallel to the filling yarns. The hems at each end shall be not less than ¾ inch wide, straight, and of uniform width. The turnunders on each hem shall be not less than ¼ inch wide. All stitching shall be done with not less than eight stitches to the linear inch, using stitching type EFb–1 and stitch type 301 specified in Federal Specification DDD–S–751.

3.3 Design.—Unless otherwise specified in the contract or order, cotton bedspreads shall be furnished as selected from commercial designs.

3.4 Physical requirements. — The bedspreads shall conform to the requirements shown in table I for the size specified (see 3.4.1 and 6.2).

3.4.1 *Size.*—Bedspreads shall be furnished in such dimensions as to conform to the sizes shown in table I. Sizes indicated are after laundering.

3.5 Finishing and nonfibrous materials.— The total of sizing, finishing, and other nonfibrous materials shall not exceed 5 percent.

3.6 Weave and finish.

3.6.1 *Type VI, pique.*

3.6.1.1 *Weave.*—Type VI bedspreads shall be of any weave or combination of weaves that will produce a finished spread having an allover design of raised lozenges approximately ¼ by ⅜ inch, formed by four small squares; the lozenges shall be regularly spaced about 7/16 inch apart, with a double panel in the center of the spread. When specified (see 6.2), an insignia shall be woven in the center of the double panel.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:34Z
Check the source to verify that this is the current version before use.

TABLE I.—*Physical requirements*

Type	Pattern	Size before hemming, minimum (after laundering)	Weight of finished bedspreads, minimum	Yarns per inch, minimum		Breaking strength (grab method), minimum	
				Warp	Filling	Warp	Filling
VI—Pique	—	*Inches* 63 x 90 72 x 90 81 x 90	*Ounces* 35 40 45	86	42	*Pounds* 70	*Pounds* 85
VII—Crinkle	—	63 x 90 63 x 99 72 x 90 72 x 99 72 x 108 81 x 90 81 x 99 90 x 90 90 x 99	21½ 24 25 27 29 28 30½ 31 34	72 in plain ground 62 in crinkle stripe	62	50	50
VIII—Crochet	1—Fancy	54 x 90 63 x 90 72 x 90 72 x 108 81 x 90	28½ 33 38 45 45	—	—	50	50
	2—Border	72 x 90 72 x 99 72 x 108 81 x 90 81 x 105	44 50 60 64 74⅜	—	—	50	50
IX—Dimity	—	63 x 90 63 x 99 72 x 90 72 x 99 81 x 90 81 x 99 81 x 105 90 x 90 90 x 99	21½ 24 25 27 28 30½ 32⅜ 31 34	70	60	75	45
X—Striped	—	56 x 90 72 x 90	20 26½	66	40	65	65

3.6.1.2 *Finish.*—The color of type VI bedspreads shall be that commercially known as sand and white, equal in shade to the standard sample furnished by the procuring agency (see 6.2). The fabric shall have good colorfastness to laundering, light, and bleaching when tested in accordance with 4.3.

3.6.2 *Type VII, crinkle.*

3.6.2.1 *Weave.* — Type VII bedspreads shall be of any weave or combination of weaves that will produce an alternate crinkle stripe and smooth stripe in the finished bedspread. The ground shall be reinforced as follows: Eight ground ends on each side and adjacent to all crinkle stripes measuring ⅜ inch or more shall be drawn in so that two

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:34Z
Check the source to verify that this is the current version before use.

ends are woven as one (eight ends weaving as four). The stripes shall run lengthwise in the bedspreads.

3.6.2.2 *Finish.*

3.6.2.2.1 *Class A.* — The fabric shall be bleached.

3.6.2.2.2 *Class B.*—The fabric shall be unbleached.

3.6.2.2.3 *Class C.*—The fabric shall be of alternating bleached and yarn-dyed colored stripes. The color of the stripes shall be as specified (see 6.2). The colored stripes shall have good colorfastness to laundering, light, and bleaching when tested in accordance with 4.3.

3.6.3 *Type VIII, crochet.*

3.6.3.1 *Weave.* — Type VIII bedspreads shall be of any weave or combination of weaves that will simulate a crochet or knit effect in the finished bedspread. When specified (see 6.2), an insignia shall be woven in the center of the bedspread.

3.6.3.2 *Finish.* — The fabric shall be bleached (class A) and bedspreads shall be pattern 1 or 2, as specified (see 6.2).

3.6.3.3 *Identification stamp (type VIII, pattern 2 only).*—When specified (see 6.2), each type VIII, pattern 2 bedspread shall be stamped on the reverse side at one corner, 1 inch from the side and 1 inch from the end, with the name of the design. Stamping shall be in black indelible ink conforming to Federal Specification TT–I–542.

3.6.4 *Type IX, dimity.*

3.6.4.1 *Weave.*—Type IX bedspreads shall be of any weave or combination of weaves that will produce a series of narrow, medium, and wide corded stripes which run lengthwise in the bedspread.

3.6.4.2 *Finish.*

3.6.4.2.1 *Class A.* — The fabric shall be bleached.

3.6.4.2.2 *Class B.* — The fabric shall be unbleached.

3.6.4.2.3 *Class C.* — The fabric shall be of alternating bleached and yarn-dyed colored stripes. The color of the stripes shall be as specified (see 6.2). The colored stripes shall have good colorfastness to laundering, light, and bleaching when tested in accordance with 4.3.

3.6.4.3 *Insignia of bedspreads for Military Medical Supply Agency procurements.* — Type IX, class A bedspreads shall have a caduceus approximately 2¼ inches high, centered between the letters U and S of approximate size, as shown in figure 1.



FIGURE 1.—Military Medical Supply Agency insignia.

3.6.5 *Type X, striped.*

3.6.5.1 *Weave.*—Type X bedspreads shall be of any weave or combination of weaves that will produce stripes of various widths in the finished bedspread. The stripes shall run lengthwise of the bedspread. When specified (see 3.6.5.4 and 6.2), an insignia shall be woven in the center of the bedspread.

3.6.5.2 *Class A.* — Class A bedspreads shall be woven with white yarns in both the warp and the filling directions. The fabric shall be bleached.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:34Z
Check the source to verify that this is the current version before use.

3.6.5.3 *Class B.* — The fabric shall be of alternating bleached and yarn-dyed colored stripes. The bedspreads shall be woven with a white warp and colored filling or with a colored warp and white filling so as to produce alternating colored and white stripes. The colored stripes shall be the dominant color on the face of the fabric. Unless otherwise specified (see 6.2), the colored stripes shall be blue. The colored stripes shall have good colorfastness to laundering, light, and bleaching when tested in accordance with 4.3.

3.6.5.4 *Insignia of bedspreads for Navy and Coast Guard procurements.*—Type X, class B bedspreads shall have an insignia similar to figure 2 woven in the center. It shall consist of two concentric knotted rope designs with the letters "U.S." between the two circles. The height of the letters shall be one-third the distance between the outer and inner circles. Within the inner circle shall be a fouled anchor set at an angle of approximately 30 degrees from the vertical. The finished insignia shall measure between 11½ and 15 inches in outside diameter, with a 5⅜ to 8-inch diameter of the inner circle.




FIGURE 2.—Navy and Coast Guard insignia.

3.7 **Workmanship.**—The bedspreads shall be clean and free from defects which affect the appearance or which may impair the serviceability.

3.8 **Seconds.**—If "seconds" are permitted, they shall comply with this specification, but may have slight imperfections of manufacture which affect only slightly the general appearance, but which shall in no way affect the serviceability or wearing quality of the bedspreads. "Seconds" may have pickouts, misweave, thread runs, oil spots, or kier stains which make them less attractive in finish and appearance than "firsts," but a combination of these defects, or an extreme instance of any of them, will be considered cause for rejection as "seconds." "Seconds" may not contain holes or tears. (See 6.3.)

4. SAMPLING, INSPECTION, AND TEST PROCEDURES

4.1 Sampling for lot acceptance inspection.

4.1.1 *Lot.*—For purposes of sampling a lot shall consist of bedspreads of the same type, class, design pattern (for type VIII), and size presented at one time.

4.1.2 *Sampling for visual and dimensional examination.*—Except when otherwise specified by Civilian government agencies, a random sample of bedspreads shall be selected from each lot of material offered for inspection of visual and dimensional characteristics in accordance with Military Standard MIL–STD–105 at Inspection Level II. The Acceptable Quality Level shall be equal to 4.0 percent defective.

4.1.3 *Sampling for lot acceptance tests.*—Except when otherwise specified by Civilian government agencies, a random sample of bedspreads shall be selected from each lot offered for Government tests in accordance with the appendix to Military Standard MIL–STD–105 at inspection level L–4. The acceptable quality level shall be equal to 1.5 percent defective. However, the sample size shall be as specified in the table in the appendix and the acceptance number shall be zero until the acceptable quality level permits one or greater.

4.2 Inspection.

4.2.1 *Visual and dimensional examination.*—Each of the sample bedspreads selected in accordance with 4.1.2 shall be visually and dimensionally examined by the inspector to verify compliance with this specification. Any bedspread in the sample containing one or more visual or dimensional defects shall be re-

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:34Z
Check the source to verify that this is the current version before use.

jected, and if the number of defective bedspreads in any sample exceeds the acceptance number for that sample, the lot represented by the sample shall be rejected.

4.2.2 *Lot acceptance tests.*—Each of the sample bedspreads selected in accordance with 4.1.3 shall be subjected by the inspector to the tests specified in 4.3 to verify compliance with this specification. Any bedspread in the sample failing to comply with this specification shall be rejected, and if the number of defective bedspreads in any sample exceeds the acceptance number for that sample, the lot represented by the sample shall be rejected.

4.3 Test procedures.—Tests shall be conducted in accordance with the following methods of Federal Specification CCC–T–191, as applicable:

Test	Method No.
Nonfibrous materials	2611
Weight of cloth	5040 or 5041
Yarns per inch (except type VIII)	5050
Breaking strength[1]	5100
Colorfastness to laundering	5612
Colorfastness to light	5660
Colorfastness to bleaching	5600

[1] For type VII only, warp breaking strength specimens shall be taken consecutively across the bedspreads.

4.4 Rejected lots.—Rejected lots may be offered again for inspection and tests provided the contractor has removed or repaired all nonconforming bedspreads. The inspector shall again select and examine samples from such resubmitted lots to verify compliance with this specification.

5. PREPARATION FOR DELIVERY

5.1 Packaging.

5.1.1 *Level A.*—Each bedspread shall be neatly folded to measure approximately 14 by 29 inches. Six folded bedspreads of one type and class or pattern, as applicable, shall be stacked flat and wrapped with kraft paper of suitable weight. The wrapper shall be secured with cotton cord or kraft paper tape.

5.1.2 *Level C.*—Unless otherwise specified in the contract or order, commercial packaging will be acceptable.

5.2 Packing.

5.2.1 *Level A.*—Bedspreads, packaged in accordance with level A or C as specified (see 6.2), shall be packed in quantities as specified in table II in overseas type wood cleated fiberboard, nailed wood, wirebound wood, corrugated or solid fiberboard, wood cleated paper overlaid, or wood cleated plywood boxes conforming to Federal Specifications PPP–B–591, PPP–B–621 (class 2), PPP–B–585 (class 2 or 3), PPP–B–636 (class 3) Military Specification MIL–B–10377 or Federal Specification PPP–B–601, respectively, at the option of the contractor. Shipping containers shall have case liners conforming to Military Specification MIL–L–10547 and shall be closed and sealed in accordance with the appendix thereto. Case liners for boxes conforming to Federal Specification PPP–B–636 may be omitted provided all joints of the boxes are sealed with tape as specified in the specification or appendix thereto. The gross weight of wood boxes shall not exceed 200 pounds, that of fiberboard boxes shall not exceed the weight limitations of the applicable box specification.

5.2.2 *Level B.*—Bedspreads packaged in accordance with level A or C as specified (see 6.2), shall be packed in containers in quantities as specified in table II. Containers shall conform to domestic type requirements of Federal Specifications PPP–B–601, PPP–B–591, PPP–B–585 (class 2), Military Specification MIL–B–10377 or the special requirements of Federal Specification PPP–B–636 (class 3).

5.2.3 *Level C.*—Bedspreads, packaged in accordance with level A or C as specified (see 6.2), shall be packed in containers of the type, size, and kind commonly used for the purpose, in a manner that will insure acceptance by common carrier and safe delivery at destina-

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:34Z
Check the source to verify that this is the current version before use.

TABLE II.—*Number of packages in shipping containers*

Type	Pattern	Size	Number of packages to be overpacked in each shipping container	Total number of items to be contained in each shipping container
VI—Pique	—	63 x 90	8	48
		72 x 90	6	36
		81 x 90	6	36
VII—Crinkle	—	63 x 90	10	60
		63 x 99	10	60
		72 x 90	8	48
		72 x 99	8	48
		72 x 108	8	48
		81 x 90	8	48
		81 x 99	8	48
		90 x 90	8	48
		90 x 99	8	48
VIII—Crochet	1—Fancy	54 x 90	8	48
		63 x 90	8	48
		72 x 90	8	48
		81 x 90	8	48
	2—Border	72 x 90	8	48
		72 x 99	6	36
		72 x 108	4	24
		81 x 90	4	24
		81 x 105	4	24
IX—Dimity	—	63 x 90	10	60
		63 x 99	10	60
		72 x 90	8	48
		72 x 99	8	48
		81 x 90	8	48
		81 x 99	8	48
		81 x 105	8	48
		90 x 90	8	48
		90 x 99	8	48
X—Striped	—	56 x 90	5	30
		72 x 90	4	24

tion. Shipping containers shall comply with the Consolidated Freight Classification Rules and regulations of other carriers as applicable to the mode of transportation.

5.2.4 Federal Standard No. 102 shall be referred to for definitions and application of the various levels of packaging and packing protection for supplies and equipment.

5.3 Marking.

5.3.1 *Nonmilitary agencies.*—Unless otherwise specified in the contract or order, shipping containers shall be marked with the stock number, name, type, class (including color where applicable), pattern, and size of the commodity as defined by the contract or order under which the shipment is made, the unit and quantity contained therein, the name of the contractor, and the number of the contract or order.

5.3.2 *Military agencies.* — In addition to any special marking required by the contract or order, packages and shipping containers

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:34Z
Check the source to verify that this is the current version before use.

shall be marked in accordance with Military Standard MIL–STD–129.

6. NOTES

6.1 Military use.—The following bedspreads are for use by Military agencies:

(*a*) Type IX, class A (Medical).
(*b*) Type X, class B (Navy and Coast Guard).

6.2 Ordering data.—Purchasers should exercise any desired options offered herein and should specify the following:

(*a*) Title, number, and date of this specification.
(*b*) Type, class, and pattern required (see 1.2).
(*c*) Size required (see table I).
(*d*) Color required for class C of types VII and IX (see 3.6.2.2.3 and 3.6.4.2.3); color required for class B of type X, if other than blue (see 3.6.5.3).
(*e*) Detailed information relative to insignia for types VI, VIII, IX (class A), and X when insignia is required (see 3.6.1.1, 3.6.3.1, 3.6.4.3 and 3.6.5.1).
(*f*) Whether special identification marking for type VIII, pattern 2 is required (see 3.6.3.3).
(*g*) Whether or not "seconds" will be accepted; if so, what quantity and discount.
(*h*) Location of standard sample, if type VI is specified (see 3.6.1.2).
(*i*) Both the level of packaging and the level of packing (see 5.1 and 5.2).
(*j*) Sampling plan (see 4.1.2 and 4.1.3).

6.3 "Seconds".—In the procurement of such commodities as bedspreads where the color, size, pattern, or insignia are such that they cannot be readily disposed of through commercial outlets, it is customary to allow from 10 to 20 percent "seconds" at a predetermined discount.

6.4 This specification covers the following item appearing in the Armed Services Medical Stock List:

7210–715–4995 — Bedspread, Light Weight, Cotton, White.

6.5 Transportation description.—The transportation description applicable to this item is:

Spreads, bed, including spreads for beds and pillows, made wholly of cotton.
Carload minimum weight, any quantity.

Dry goods, not otherwise indexed.
Motor volume minimum weight, any quantity.

Notice. — When Government drawings, specifications, or other data are used for any purpose other than in connection with a definitely related Government procurement operation, the United States Government thereby incurs no responsibility nor any obligation whatsoever and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data is not to be regarded by implication or otherwise, as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use, or sell any patented invention that may in any way be related thereto.

MILITARY INTERESTS:
Army—QM
Navy—Sh CG S
Air Force.

Copies of this specification may be purchased for cents each.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:34Z
Check the source to verify that this is the current version before use.