DDD-B-331b
24 APRIL 1952
SUPERSEDING
Fed. Spec. DDD-B-331
18 March 1937, and
Int. Fed. Spec. DDD-B-331a (GSA-FSS)
12 December 1951

FEDERAL SPECIFICATION

BINDING; COTTON, BIAS-CUT

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 **Scope.**—The cotton binding covered by this specification is intended primarily for the binding of seams in wearing apparel.

1.2 **Classification.**

1.2.1 *Types.*—The bias-cut cotton binding shall be furnished in the following types, as specified (see 7.2.9.2 for Navy purchases):

Type I. —Cambric
Type II. —Percale
Type III.—Sateen
Type IV.—Twill

1.2.2 *Color.*—The binding shall be bleached or dyed, as specified (see 3.3).

1.2.3 *Grade.* — The grade shall be that known commercially as firsts.

2. APPLICABLE SPECIFICATIONS

2.1 The following Federal Specifications, of the issues in effect on date of invitation for bids, form a part of this specification:

V-T-276—Thread; Cotton.
CCC-P-191—Percale.
CCC-T-191—Textile Test Methods.
DDD-S-751—Stitches; Seams; and Stitching.

(Copies of Federal specifications and the Federal Specifications Index may be obtained upon application, accompanied by money order, coupon, or cash to the Superintendent of Documents, Government Printing Office, Washington 25, D. C., or to the GSA Regional Offices in Boston, New York, Atlanta, Chicago, Kansas City, Mo., Dallas, Denver, San Francisco, and Seattle. Prices may be obtained from the Superintendent of Documents or from the GSA Regional Offices.)

2.2 Specifications and other publications applicable only to individual departments are listed in section 7.

3. REQUIREMENTS

3.1 **Material.**

3.1.1 *Fabric.*—The fabric shall be made from cotton yarns free from waste, and shall be as specified hereinafter for each type.

3.1.2 *Thread.*—The thread shall be cotton 1A, 3 cord, ticket No. 60, conforming to Federal Specification V-T-276. The thread shall correspond to the shade of the fabric and shall be vat-dyed.

3.2 **Cutting.**—The fabrics to be made into bias binding shall have the selvages removed, and then shall be cut on an angle of 45 ± 5 degrees. The binding shall then be joined together. The seam of joining shall be securely sewed with not less than 10 nor more than 14 stitches per inch using stitch type 301 and seam type SSa-1 of Federal

Source: https://assist.dla.mil/ -- Downloaded: 2026-02-26T12:34Z
Check the source to verify that this is the current version before use.

952106-52-(305)

Specification DDD – S – 751, with seams pressed open.

3.3 Color.—The binding shall be bleached or dyed in colors. The color shall be as specified in the invitation for bids, which may state that vat-dyed binding is desired. It shall show good fastness to laundering, dry and wet cleaning, crocking, light, and perspiration. The dye used shall be free from sulphur.

3.4 Sizing. — The edges of the binding shall be treated to prevent raveling, and shall not be affected by dry-cleaning solvent or washing compound that might induce staining in the finished garment.

3.5 Length.—The binding shall be rolled on tubes of the same width as the binding. The length of the rolls shall be not less than 50 nor more than 100 yards, as specified.

3.6 Width.—The width of the binding shall be as specified.

3.7 Type I, cambric.—The fabric, prior to cutting, shall conform to the following requirements.

3.7.1 *Yarns per inch.*—The finished cambric shall have not less than 64 yarns per inch in the warp and 55 yarns per inch in the filling.

3.7.2 *Finish.*—The cambric shall contain sufficient sizing to produce a good cambric finish fabric.

3.8 Type II, percale.—The finished percale for type II binding shall conform to the requirements of Federal Specification CCC–P–191, and in addition it shall be bleached or dyed.

3.9 Type III, sateen.—The fabric prior to cutting shall conform to the following requirements:

3.9.1 *Yarns per inch.*—The finished sateen shall have not less than 88 yarns per inch in the warp and 140 yarns per inch in the filling.

3.9.2 *Weight.*—The sateen shall weigh not less than 2.8 ounces per square yard.

3.10 Type IV, twill.—The fabric prior to cutting shall conform to the following requirements:

3.10.1 *Weave.*—The weave shall be 1 up, 2 down twill.

3.10.2 *Yarns per inch.*—The finished twill shall have not less than 76 yarns per inch in the warp and not less than 114 yarns per inch in the filling.

3.10.3 *Weight.*—The weight shall be not less than 4.0 ounces per square yard.

3.11 Workmanship.—The finished binding shall be free from defects which affect its appearance or which may impair its serviceability.

4. SAMPLING, INSPECTION, AND TEST PROCEDURES

4.1 Sampling.—One roll shall be taken at random from each 1,000 rolls, or fraction thereof, offered for delivery, except that when the shipment exceeds 10,000 rolls, 1 roll shall be taken from each one-tenth of the shipment.

4.2 Inspection.—Inspection shall be made at the point of delivery or at the factory, at the discretion of the purchasing agent.

4.3 Tests.—Tests shall be conducted in accordance with the following applicable methods described in Federal Specification CCC–T–191.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:34Z
Check the source to verify that this is the current version before use.

Tests	Methods
Standard conditions	Section 4
Yarns per inch	5050
Weight per square yard	5041
Length of rolls	5010
Width of tape	5020
Colorfastness to:	
Laundering	5610
Dry cleaning	5620
Wet cleaning	5622
Crocking	5650
Light	5660
Perspiration	5680
Nonfibrous materials	2611
Length per pound (thread)	4010
Breaking strength (thread)	4100

5. PREPARATION FOR DELIVERY

5.1 **Packaging.**—Unless otherwise specified, commercial packages are acceptable under this specification.

5.2 **Packing.**—Unless otherwise specified, the subject commodity shall be prepared for shipment to permit acceptance by carrier for transportation at the lowest applicable rate, and to afford maximum protection from normal hazards of transportation.

5.3 **Marking.**—Unless otherwise specified, shipping containers shall be marked with the name of the material, the type, color, width, and the quantity contained therein, as defined by the contract or order under which the shipment is made, the name of the contractor, and the number of the contract or order.

6. NOTES

6.1 **Ordering data.** — Purchasers should specify the type, color, width, and length of binding required and should exercise any desired options offered herein. (See 1.2.1, 1.2.2, 3.5, 3.6, 4.2, 5.1, 5.2, 5.3, 6.2, and 7.2.9.)

6.2 It is believed that this specification adequately describes the characteristics necessary to secure the desired material, and that normally no samples will be necessary prior to award to determine compliance with this specification. If, for any particular purpose, samples with bids are necessary, they should be specifically asked for in the invitation for bids, and the particular purpose to be served by the bid sample should be definitely stated, the specification to apply in all other respects.

Patent notice.—When Government drawings, specifications, or other data are used for any purpose other than in connection with a definitely related Government procurement operation, the United States Government thereby incurs no responsibility nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data, is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use, or sell any patented invention that may in any way be related thereto.

7. DEPARTMENTAL REQUIREMENTS

7.1 The following specifications, standards, and other publication, of the issues in effect on date of invitation for bids, and special requirements, form a part of this specification for purchases made under this specification by the respective departments:

7.2 **Army, Navy, and Air Force.**

7.2.1 *Applicable specifications, standards, and other publication.*

Federal Specifications:

NN–B–591—Boxes; Fiberboard, Wood-Cleated (for Domestic Shipment).[1]

NN–B–601—Boxes; Wood-Cleated-Plywood, for Domestic Shipment.[1]

NN–B–621—Boxes; Wood, Nailed and Lock-Corner.[1]

UU–T–111—Tape; Paper, Gummed (Sealing and Securing).[1]

Military Specifications:

JAN–P–105—Packaging and Packing for Overseas Shipment — Boxes, Wood, Cleated, Plywood.[1]

[1] Applicable to Army and Air Force purchases only.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:34Z
Check the source to verify that this is the current version before use.

JAN-P-106—Packaging and Packing for Overseas Shipment — Boxes, Wood, Nailed.[1]

JAN-P-125—Packaging and Packing for Overseas Shipment — Barrier-Materials, Waterproof, Flexible.[1]

MIL-A-140—Adhesive, Water-Resistant, Waterproof Barrier-Material.[1]

Military Standards:

MIL-STD-105—Sampling Procedures and Tables for Inspection by Attributes.

MIL-STD-129—Marking of Shipments.

Navy Department Specification:

General Specifications for Inspection of Material.[2]

Bureau of Supplies and Accounts Publication:

Navy Handbook on Packing and Materials Handling — Packaging, Packing, and Marking of Clothing, Small Stores, and Textiles.[2]

(Copies of specifications, standards, and drawings required by the contractor in connection with specific procurement functions should be obtained from the procuring agency or as directed by the contracting officer.)

7.2.2 *Labeling.*—Each tube shall have the following information applied on one end:

Fed. Spec. DDD-B-331b
Stock number
Nomenclature
Gross yards
Name and address of manufacturer
Contract or order number

7.2.3 *Standard sample (Navy).* — For access to Navy standard sample, address the procuring office issuing the invitation for bids.

7.2.4 *Preproduction sample (Navy).*—Before production is begun for the Navy, the contractor shall submit one finished sample to the contracting officer for approval.

7.2.5 *Inspection.*

7.2.5.1 *Army and Air Force.*—The general inspection procedures shall be in accordance with Military Standard MIL-STD-105.

7.2.5.2 *Navy.*

7.2.5.2.1 *Contractor's inspection.*—The contractor should thoroughly inspect all finished bias binding for compliance with this specification prior to submitting it to the United States Government for final inspection.

7.2.5.2.2 *Government inspection.*—Inspection of the item covered herein, and the packaging, packing, and marking thereof may be made during the entire process of manufacture. Inspection shall be performed in accordance with sampling table contained in Military Standard MIL-STD-105; however, at the discretion of the agency concerned, a 100-percent inspection may be performed. The passing as satisfactory of any detail of construction or material shall not relieve the contractor of responsibility for faulty workmanship or material which may be discovered at any time prior to final acceptance. Final inspection of the finished item shall be made at place of manufacture, at point of delivery, or elsewhere, as specified in the contract or order. In case of factory inspection every facility shall be afforded inspectors by the manufacturer for the prosecution of their work. The Acceptable Quality Level will be furnished in the procurement document by the agency concerned.

7.2.6 *Packaging.*

7.2.6.1 *Army and Air Force.*—Each tube of binding shall be wrapped in kraft paper having a minimum basis weight of 40 pounds per ream (24 x 36 — 500). Each wrapped unit shall be securely sealed by applying

[1] Applicable to Army and Air Force purchases only.

[2] Applicable to Navy purchases only.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:34Z
Check the source to verify that this is the current version before use.

gummed kraft paper tape conforming to Federal Specification UU–T–111.

7.2.7 *Packing.*

7.2.7.1 *Army and Air Force.*

7.2.7.1.1 *For domestic shipment.* — The binding packaged as specified in 7.2.6.1 shall be packed in boxes conforming to the requirements of style A or B of Federal Specification NN–B–591, style A or B of NN–B–601, or style 2 or 4 of NN–B–621. Gross weight of each box shall not exceed 150 pounds.

7.2.7.1.2 *For overseas shipment.* — The binding packaged as specified in 7.2.6.1 shall be packed in boxes constructed and strapped in accordance with the requirements of style A or B of Military Specification JAN–P–105, or style 2 or 4 of JAN–P–106. The gross weight of each box shall not exceed 150 pounds.

7.2.7.1.2.1 Each box shall be provided with a sealed case liner or prefabricated bag of waterproof barrier-material conforming to type L–2 or M of Military Specification JAN–P–125. Closures shall be completely sealed with a continuous seam, at least ¾ inch wide, of water-resistant adhesive complying with Military Specification JAN–P–140.

7.2.7.2 *Navy.* — Shipments for the Navy shall be packed in accordance with the requirements of the Navy Handbook on Packing and Materials Handling — Packaging, Packing, and Marking of Clothing, Small Stores, and Textiles.

7.2.8 *Marking.* — Shipping containers shall be marked in accordance with Military Standard MIL–STD–129, except that service color marking shall not be required on containers for domestic shipment.

7.2.9 *Notes.*

7.2.9.1 *Ordering data.*—Procurement documents should specify the following:

Place of final inspection (see 7.2.5.2.2).
Acceptable Quality Level (see 7.2.5.2.2).
Whether domestic or overseas packing and marking are required (see 7.2.7 and 7.2.8).

7.2.9.2 *Navy.* — Procurement of bias-cut cotton binding for the Navy should be restricted to type IV, twill.

NAVY INTEREST: *MC* S

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:34Z
Check the source to verify that this is the current version before use.