DDD-P-351H
November 27, 1978
SUPERSEDING
Fed. Spec. DDD-P-351G
November 20, 1973

FEDERAL SPECIFICATION

PILLOWCASE, COTTON AND POLYESTER/COTTON

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers the requirements for cotton and polyester/cotton pillowcases.

1.2 Classification.

1.2.1 Types and classes. The pillowcases shall be of the following types and classes as specified (see 6.2):

Type		Class	Width inches	(mm)	Length hemmed inches	(mm)
I	Cotton	1 (140 count)	20-1/2	(521)	27-1/2	(698)
		2 (140 count)	20-1/2	(521)	32-1/2	(826)
		3 (140 count)	22-1/4	(565)	32-1/2	(826)
		4 (140 count)	20-1/2	(521)	30-1/2	(775)
		5 (180 count)	20-1/2	(521)	32-1/2	(826)
III	Polyester-Cotton (65/35)-Commercial designation No. 180 (percale)	1	20-1/2	(521)	30-1/2	(775)
IV	Polyester-Cotton (50/50)-Commercial designation No. 128 (muslin)	1	20-1/2	(521)	30-1/2	(775)
		2	20-1/2	(521)	32-1/2	(826)
		3	20-1/2	(521)	32-1/2	(826)
		4	20-1/2	(521)	27-1/2	(698)
		5	22-1/4	(565)	32-1/2	(826)

FSC 7210

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:34Z
Check the source to verify that this is the current version before use.

Type	Class	Width inches	(mm)	Length hemmed inches	(mm)
V Polyester-Cotton (50/50)- Commercial designation No. 180 (percale)	1	20-1/2	(521)	30-1/2	(775)
	2	20-1/2	(521)	32-1/2	(826)

2. APPLICABLE DOCUMENTS

2.1 The following documents of the issue in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein:

Federal Specifications.

V-T-276	-	Thread, Cotton.
CCC-C-430	-	Cloth, Sheeting, Cotton, and Polyester and Cotton.
DDD-L-20	-	Label: For Clothing, Equipage, and Tentage (General Use).
PPP-B-636	-	Boxes, Shipping, Fiberboard.

Federal Standards.

FED-STD-123	-	Marking for Shipment (Civil Agencies).
FED-STD-751	-	Stitches, Seams, and Stitchings.

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U.S. Government Printing Office, Washington, DC 20402.

(Single copies of this specification and other Federal specifications required by activities outside the Federal Government for bidding purposes are available without charge from Business Service Centers at the General Services Administration Regional Offices in Boston, New York, Washington, DC, Philadelphia, Atlanta, Chicago, Kansas City, MO, Houston, Fort Worth, Denver, San Francisco, Los Angeles, and Seattle, WA.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

Source: https://assist.dla.mil -- Downloaded: 202640-26T12:34Z
Check the source to verify that this is the currentversion before use.

Military Specifications:

MIL-B-17757	-	Boxes, Shipping, Fiberboard (Modular Sizes).
MIL-T-43548	-	Thread, Polyester, Cotton-Covered.
MIL-T-43624	-	Thread, Polyester, Spun.

Military Standards:

MIL-STD-105	-	Sampling Procedures and Tables for Inspection by Attributes
MIL-STD-129	-	Marking for Shipment and Storage.
MS 16686	-	Medical Services Symbol.

(Copies of specifications and standards required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless a specific issue is identified, the issue in effect on date of invitation for bids or request for proposal shall apply:

Rules and Regulations Under the Textile Fiber Products Identification Act

(Copies may be obtained, without charge, from the Federal Trade Commission, Washington, DC 20580.)

National Motor Freight Traffic Association, Inc., Agent

National Motor Freight Classification

(Application for copies should be addressed to the American Trucking Associations, Inc., Traffic Department, 1616 P Street, N.W., Washington, DC 20036.)

Uniform Classification Committee, Agent

Uniform Freight Classification

(Application for copies should be addressed to the Uniform Classification Committee, Room 1106, 222 South Riverside Plaza, Chicago, IL 60606.)

3. REQUIREMENTS

3.1 Materials (see 6.6).

3.1.1 Basic material.

Source: https://assist.dla.mil -- Downloaded: 202640-26T12:34Z
Check the source to verify that this is the currentversion before use.

3.1.1.1 Type I, classes 1, 2, 3, 4 and 5 pillowcases. The basic material for type I, classes 1, 2, 3 and 4 pillowcases shall be cotton sheeting conforming to type II, class 1, style A of CCC-C-430. The basic material for type I, class 5 pillowcase shall be cotton sheeting conforming to type II, class 1, style C of CCC-C-430.

3.1.1.2 Type III pillowcase. The basic material for type III pillowcase shall be polyester and cotton sheeting conforming to type II, class 1, style D of CCC-C-430.

3.1.1.3 Type IV pillowcase. The basic material for type IV pillowcase shall be polyester and cotton sheeting conforming to type II, class 1, style F of CCC-C-430.

3.1.1.4 Type V pillowcase. The basic material for type V pillowcase shall be polyester and cotton sheeting conforming to type II, class 1, style E of CCC-C-430.

3.1.1.5 Color of pillowcases. The color for all pillowcases shall be bleached white or dyed, as specified (see 6.2).

3.1.2 Thread.

3.1.2.1 Type I pillowcase. The thread for hemming and seaming type I pillowcase shall be ticket No. 50, 3 ply conforming to IA2 or IA3 of V-T-276.

3.1.2.1.1 Color. The color of the thread for type I pillowcases shall be the same as specified for the cloth employed for the pillowcases (see 3.1.1.5).

3.1.2.2 Types III, IV, and V pillowcases. The thread for hemming and seaming types III, IV, and V pillowcases shall be cotton-covered polyester thread conforming to ticket No. 70, 2 ply of MIL-T-43548, or spun polyester thread conforming to class 1 or 2, ticket No. 70, 2 or 3 ply of MIL-T-43624.

3.1.2.2.1 Color. The color of the thread for seaming the types III, IV, and V pillowcases shall be the same color as specified for the cloth employed for the pillowcases (see 3.1.1.5). The color of the thread for hemming the types III, IV, and V pillowcases shall be shade Orange TL, C.A. 66076 (see 3.3.1 and 6.4).

3.2 Dimensions. The dimensions of the pillowcases, after hemming, shall be as specified in table I.

Source: https://assist.dla.mil -- Downloaded: 202640-26T12:34Z
Check the source to verify that this is the currentversion before use.

TABLE I. Dimensions 1/

Type and class	Hems				Pillow case after hemming			
	Width		Tolerance		Width		Length	
	Inches	(mm)	Inch	(mm)	Inches	(mm)	Inches	(mm)
Type I								
1	1	(25)	± 1/4	(6)	20-1/2	(521)	27-1/2	(698)
2	3	(76)	± 1/4	(6)	20-1/2	(521)	32-1/2	(826)
3	3	(76)	± 1/4	(6)	22-1/4	(565)	32-1/2	(826)
4	1	(25)	± 1/4	(6)	20-1/2	(521)	30-1/2	(775)
5	3	(76)	± 1/4	(6)	20-1/2	(521)	32-1/2	(826)
Type III								
1	1	(25)	± 1/4	(6)	20-1/2	(521)	30-1/2	(775)
Type IV								
1	1	(25)	± 1/4	(6)	20-1/2	(521)	30-1/2	(775)
2	3	(76)	± 1/4	(6)	20-1/2	(521)	32-1/2	(826)
3	1	(25)	± 1/4	(6)	20-1/2	(521)	32-1/2	(826)
4	1	(25)	± 1/4	(6)	20-1/2	(521)	27-1/2	(698)
5	1	(25)	± 1/4	(6)	22-1/4	(565)	32-1/2	(826)
Type V								
1	1	(25)	± 1/4	(6)	20-1/2	(521)	30-1/2	(775)
2	3	(76)	± 1/4	(6)	20-1/2	(521)	32-1/2	(826)

1/ Finished tolerances for the width and length dimensions shall be ± 1/2 inch (± 13 mm) in each direction.

Source: https://assist.dla.mil -- Downloaded: 202640-26T12:34Z
Check the source to verify that this is the currentversion before use.

3.3 Stitches, seams, and stitching. All stitches, seams, and stitchings shall conform to FED-STD-751. All sewing shall be done with 10 to 16 stitches per inch (4 to 6 stitches/cm).

3.3.1 Hems. The hem shall be made with stitch type 301 and stitching type EFb-1, and shall be of uniform width as specified in table I. The turnunder shall be 1/2 ± 1/4 inch (13 ± 6 mm) (see 3.1.2.2.1 for types III, IV, and V pillowcases).

3.3.2 Seams. The pillowcases shall be seamed as specified in 3.3.2.1, 3.3.2.2, or 3.3.2.3, as applicable. Seams shall be straight when pillowcases are laid flat. Pillowcases shall be made of one piece of material.

3.3.2.1 Seaming two selvages. Where the seams are formed by joining two selvages, stitch type 301 or 401 and seam type SSa-1 shall be used with the stitching not less than 1/8 inch (3 mm) nor more than 5/8 inch (16 mm) from the selvage edges.

3.3.2.2 Seaming one or two raw edges. Where one or two raw edges are joined, they shall be stitched together with stitch type 503 or 504 (5/32 to 1/4 inch (4 to 6 mm) gage), seam type SSa-1, or they shall be seamed with seam type SSa-1, stitch type 301 or 401, 3/8 to 5/8 inch (10 to 16 mm) from the edges of the material.

3.3.2.3 Seaming one selvage and one nonselvage of shuttleless loom material. Where one selvage and one nonselvage are joined, they shall be stitched together with stitch type 503 or 504 (5/32 to 1/4 inch (4 to 6 mm) gage) or stitch type 401 (3/8 to 5/8 inch (10 to 16 mm) from the edges of the material, seam type SSa-1, trimming all loose ends of the filling yarn during the sewing operation.

3.3.3 Thread breaks and ends of seams. The ends of all seams and stitchings produced with 301 stitch type, when not caught in other seams and stitchings, shall be backtacked not less than 1/2 inch (13 mm). Thread breaks (all stitch types) shall be secured by stitching back of the break not less than 1/2 inch (13 mm).

3.4 Marking. The marking shall be in the format and size of characters specified in 3.4.1 or 3.4.2 and shall conform to type III or IV, class 9 of DDD-L-20. Markings shall not show strike-through to outside of pillowcase. As an alternate, the marking may be done with a sewn in label. The end item marking shall show fastness to laundering as specified for class 1 labels. The marking shall be placed on the inside of the pillowcase.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:34Z
Check the source to verify that this is the current version before use.

3.4.1 Medical procurements. When required, each pillowcase shall have a caduceus 1-7/8 ± 1/8 inches (48 ± 3 mm) in height centered between the block letters "U" and "S", 1/2 ± 1/16 inch (13 ± 2 mm) in height in accordance with type I of MS 16686 (see 6.2).

3.4.2 Ownership marking. Unless otherwise specified (see 6.2), each pillowcase shall have the block letters "US", 1/2 ± 1/16 inch (13 ± 2 mm) in height.

3.5 Fiber identification. Each pillowcase shall be labeled for fiber content in accordance with the Textile Fiber Products Identification Act.

3.6 Workmanship. The finished pillowcase shall conform to the quality and grade of product established by this specification. The occurrence of defects shall not exceed the applicable acceptable quality levels (AQLs).

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the supplier may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.2 Quality conformance inspection. Sampling for inspection shall be performed in accordance with MIL-STD-105, except where otherwise indicated hereinafter.

4.2.1 Inspection of components and materials. In accordance with 4.1, components and materials shall be inspected in accordance with all the requirements of referenced specifications, drawings, and standards unless otherwise excluded, amended, or modified, or qualified in this specification or applicable purchase document.

4.2.2 Examination of the end item.

4.2.2.1 Screening examination. The production of pillowcases shall be visually screened by the contractor and sorted into lots designated as first and second quality (see 6.5) in accordance with standard industrial practice.

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:34Z
Check the source to verify that this is the current version before use.

4.2.2.2 Examination for acceptance of first quality lots. Lots designated by the supplier as first quality (see 4.2.2.1) shall be examined for acceptance by the Government. The lot size shall be expressed in units of one pillowcase each. The sample unit shall be one completely fabricated pillowcase. The inspection lot shall consist of all pillowcases presented for inspection at one time.

4.2.2.2.1 Visual examination. The lot of pillowcases shall be sampled in accordance with inspection level I of MIL-STD-105 and visually inspected. Any pillowcase which is found to contain either or both of the following shall be classified as a defective unit:

Any major defect listed in table II.
More than two minor defects listed in table II.

The AQL for this examination shall be 4.0 percent defective.

TABLE II. Classification of visual defects

Examine	Defect	Classification Major	Minor
Material (cloth)	Hole, cut, tear, or smash	X	
	Floats or skips:		
	Multiple, 1/2 inch (13 mm) or more in length	X	
	Multiple, less than 1/2 inch (13 mm) in length		X
	Single, over 6 inches (152 mm) in length		X
	Broken or missing yarn:		
	Three or more, less than 9 inches (229 mm) apart regardless of length	X	
	Two, less than 9 inches (229 mm) apart regardless of length		X
	Single, over 6 inches (152 mm) in length		X
	Abrasion mark	X	
	Patchback		
	Distorted, 2 square inches (1290 mm^2) or more in area	X	
	Distorted area less than 2 square inches (1290 mm^2) and more than 1 square inch (645 mm^2)		X

Source: https://assist.dla.mil -- Downloaded: 202640-26T12:34Z
Check the source to verify that this is the current version before use.

TABLE II. Classification of visual defects (cont'd)

Examine	Defect	Classification Major	Minor
Material (cloth) (cont'd)	Slub, slug, gout, jerked-in filling, or slough off:		
	Over 1/8 inch (3 mm) in thickness	X	
	1/16 to 1/8 inch (2 to 3 mm) in thickness		X
	Spot, stain, or streak:		
	More than 1/4 (6 mm) but not exceeding 1 inch (25 mm) in longest dimension		X
	Over 1 inch (25 mm) in longest dimension	X	
	Accumulation of spots and stains, 1/4 inch (6 mm) or less in longest dimension (five or more per pillowcase)		X
	Heavy place or coarse filling bar		X
	Light, thin, or weak place:		
	3 inches (76 mm) or less		X
	Over 3 inches (76 mm)	X	
	Color not as specified	X	
Thread	Color not as specified	X	
Construction and workmanship	Not specified construction (unless otherwise indicated herein)	X	
	Any mend	X	
	Needle chew	X	
	Not made from one piece of material	X	
	Wrong seam type	X	
	Ends of seams and stitching (when not caught in other seams and stitching), backtacked less than 1/2 inch (13 mm)		X
	Thread break backstitched less than 1/2 inch (13 mm)		X
	More than 16 stitches per inch (6 stitches/cm)		X
	Wrong stitch type	X	
	Loose thread caught in stitching		X
	Needle perforations		X
Side or bottom seam	Open seam more than 1/2 inch (13 mm)	X	
	Open seam, 1/2 inch (13 mm) or less		X
	Seam not straight by more than 3/8 inch (10 mm) at any point		X

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:34Z
Check the source to verify that this is the current version before use.

TABLE II. Classification of visual defects (cont'd)

Examine	Defect	Classification Major	Minor
Side or bottom seam	Less than 10 stitches per inch (4 stitches/cm).	X	
	Loose tension resulting in a loosely secured seam	X	
	Tight tension; i.e., stitches break when normal strain is applied to the seam. (Puckering is evidence of tight tension. When evident, check by exerting pull on seam by hand.)	X	
	Stitching margin or gage of stitching not as specified	X	
	Loose ends of filling yarn not trimmed when shuttleless loom material is used		X
Hem	Open seam more than 1 inch (25 mm)	X	
	Open seam more than 1/2 inch (13 mm) but not more than 1 inch (25 mm)		X
	Raw edge 1 inch (25 mm) or more but seam is not open		X
	Seam not straight by more than 3/8 inch (10 mm) at any point		X
	Loose tension resulting in a loosely secured seam		X
	Tight tension, i.e , stitches break when normal strain is applied to the seam. (Puckering is evidence of tight tension. When evident, check by exerting pull on seam by hand.)		X
	Twisted, pleated, or puckered		X
	Turnunder not as specified		X
	Less than 10 stitches per inch (4 stitches/cm).	X	
Marking	Missing, incomplete, incorrect, misplaced, illegible, or not specified color	X	
	Strike-through on outside of pillow-case		X

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:34Z
Check the source to verify that this is the current version before use.

4.2.2.2.2 Dimensional examination. The lot of pillowcases shall be sampled in accordance with inspection level S-3 of MIL-STD-105 and examined for compliance with dimensions specified in table I. Any dimension that is not within the tolerance specified shall be classified as a defect. The AQL for this examination shall be 4.0 percent defective.

4.2.2.3 Examination for acceptance of second quality lots when applicable (see 6.5). Lots designated by the supplier as second quality (see 4.2.2.1) shall be examined for acceptance by the Government. The sample unit shall be one completely fabricated pillowcase. The inspection lot shall consist of all pillowcases presented for inspection at one time.

4.2.2.3.1 Visual examination. The lot of pillowcases shall be sampled in accordance with inspection level I of MIL-STD-105 and visually inspected. If any two pillowcases in the sample are found to contain either or both of the following, the lot shall be rejected:

More than three of the major defects listed in table II.
More than seven total defects (majors and minors combined).

4.2.2.3.2 Dimensional examination. The lot of pillowcases shall be examined for conformance with dimensional requirements in accordance with the procedures of 4.2.2.2.2.

4.2.3 Examination of preparation for delivery requirements. An examination shall be made to determine that the packaging, packing, and marking comply with the section 5 requirements Defects shall be scored in accordance with the list below. The sample unit shall be one shipping container fully prepared for delivery with the exception that it need not be closed. Defects of closure listed below shall be examined on shipping containers fully prepared for delivery. The lot size shall be the number of shipping containers in the end item inspection lot The inspection level shall be S-2 and the AQL shall be 2.5 defects per 100 units.

Examine	Defect
Marking (exterior and interior)	Omitted, incorrect, illegible, of improper size, location, sequence, or method of application.
Materials	Any component missing, damaged, or not as specified.
Workmanship	Inadequate application of components, such as: incomplete closure of container flaps, loose strapping, inadequate stapling, or improper taping. Improper heat-sealed seams and closure of polyethylene bags. Incorrectly fabricated bag. Omission of vent hole in polyethylene bag. Bulged or distorted container.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:34Z
Check the source to verify that this is the current version before use.

Examine	Defect
Content	Number of bundles per container is more or less than required.
	Number per bundle is more or less than required. 1/

1/ For this defect, one bundle shall be examined from each container in the sample.

5. PREPARATION FOR DELIVERY

5.1 Packaging. Packaging shall be level A, B, or C as specified (see 6.2).

5.1.1 Level A. Each pillowcase shall have the width folded into thirds and the length folded so that the pillowcase measures approximately 11-1/2 by 7-1/4 inches (292 by 184 mm). Twelve folded pillowcases of one type, class and size, and color only, shall be neatly stacked in a bundle and securely tied with cotton tape or twine approximately 2 inches (51 mm) in from each end. Each bundle of twelve pillowcases shall be packaged in a snug-fitting square style, clear polyethylene film bag of 0.003 inch (0.08 mm) thickness (± 20 percent). The polyethylene bag shall be formed with heat sealed seams that are straight, continuous, and parallel to each other and the formed edges of the bag. The bag closure shall be effected by heat sealing with the heat seal made as close as possible to the open end. The bag may be fabricated from polyethylene film tubing or sheeting. A 1/4-inch (6 mm) diameter hole shall be made at one corner of the polyethylene bag to allow excess air to escape.

5.1.2 Level B (Civil agencies). Pillowcases shall be packaged in accordance with 5.1.1 (see 6.2).

5.1.3 Level C. Pillowcases shall be packaged to afford adequate protection against physical damage during shipment from the supply source to the first receiving activity. The package and the quantity per package shall be the same as that normally used by the supplier for retail distribution

5.2 Packing. Packing shall be level A, B, or C as specified (see 6.2)

5.2.1 Level A packing

5.2.1.1 Type I. Ninety-six pillowcases (eight bundles) of one class, size, and color only, packaged as specified in 5.1, shall be packed in a fiberboard shipping container assembled, closed, and reinforced conforming to class weather-resistant, grade V2s, size 2A of MIL-B-17757, except that the inspection shall be in accordance with 4.2.3. The fiberboard for the liner shall conform to type CF, class weather-resistant, variety DW, grade V15c of MIL-B-17757.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:34Z
Check the source to verify that this is the current version before use.

5.2.1.2 Types III, IV, and V. Ninety-six pillowcases (eight bundles) of one type, class, size, and color only, packaged as specified in 5.1, shall be packed in a fiberboard shipping container conforming to style FOL-L, grade V2s of PPP-B-636. The inside of each container shall be fitted with a box liner conforming to type CF, class weather-resistant, variety DW, grade V15c of PPP-B-636. Level A packages shall be packed flat two in length, two in width, and two in depth within a shipping container. Inside dimensions of each shipping container shall approximate 23-1/2 inches (597 mm) in length, 15-1/2 inches (394 mm) in width, and 5-1/2 inches (140 mm) in depth. Approximate dimensions are furnished as a guide only. Each shipping container shall be closed in accordance with method III, waterproofed in accordance with method V, and reinforced as specified in the appendix of PPP-B-636, except that the inspection shall be in accordance with 4.2.3.

5.2.2 Level B packing.

5.2.2.1 Civil agencies. Ninety-six pillowcases (eight bundles) of one type, class, size, and color only, packaged as specified in 5.1, shall be packed in a snug-fitting fiberboard shipping container conforming to style OSC-L or FOL-L, type CF (variety SW) or SF, class domestic, grade 275 of PPP-B-636. The inside of each shipping container shall be fitted with a box liner conforming to type CF, class domestic, variety DW, grade 275 of PPP-B-636. Each shipping container shall be closed in accordance with method II as specified in the appendix of the container specification, except that the inspection shall be in accordance with 4.2.3.

5.2.2.2 Military requirements.

5.2.2.2.1 Type I. Ninety-six pillowcases (eight bundles) of one class, size, and color only, packaged as specified in 5.1, shall be packed in a fiberboard shipping container assembled and closed conforming to class domestic, grade 275, size 2A of MIL-B-17757, except that the inspection shall be in accordance with 4.2.3 The fiberboard for the box liner shall conform to type CF, class domestic, variety DW, grade 275 of MIL-B-17757.

5.2.2.2.2 Types III, IV, and V. Ninety-six pillowcases (eight bundles) of one type, class, size, and color only, packaged as specified in 5.1, shall be packed in a fiberboard shipping container conforming to style FOL-L, type CF (variety SW) or SF, class domestic, grade 275 of PPP-B-636. The inside of each container shall be fitted with a box liner conforming to type CF, class domestic, variety DW, grade 275 of PPP-B-636. Level A packages shall be packed flat two in length, two in width, and two in depth within a shipping container. Inside dimensions of each shipping container shall approximate 23-1/2 inches (597 mm) in length, 15-1/2 inches (394 mm) in width, and 5-1/2 inches (140 mm) in depth. Approximate dimensions are furnished as a guide only. Each shipping container shall be closed in accordance with method II as specified in the appendix of the container specification, except that the inspection shall be in accordance with 4.2.3.

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:34Z
Check the source to verify that this is the current version before use.

5.2.2.2.3 Weather-resistant shipping containers. When specified (see 6.2), the shipping container shall be grade V3c, V3s, or V4s fiberboard box fabricated in accordance with MIL-B-17757 or PPP-B-636, as applicable. Each shipping container shall be closed in accordance with method III as specified in the appendix of PPP-B-636, except that the inspection shall be in accordance with 4.2.3.

5.2.3 Level C packing. Pillowcases, packaged as specified in 5.1, shall be packed in a manner to insure carrier acceptance and safe delivery at destination at the lowest transportation rate for such supplies. The quantity per shipping container shall be the same as that normally used by the supplier for retail distribution. Containers shall be in accordance with Uniform Freight Classification or National Motor Freight Classification, as applicable.

5.3 Marking. Marking shall be in accordance with 5.3.1 or 5.3.2 as specified (see 6.2).

5.3.1 Civil agencies. In addition to any special marking required by the contract or order, shipping containers shall be marked in accordance with FED-STD-123.

5.3.2 Military requirements. In addition to any special marking required by the contract or order, shipping containers shall be marked in accordance with MIL-STD-129.

5.3.3 Polyethylene bagged packages. Polyethylene bagged packages shall have the required identification information legibly printed or stamped in black directly on the bag across the center face or on a white paper label inserted within the bag so as to permit ready identification.

6. NOTES

6.1 Intended use. The pillowcases are intended for use by the Military Services and Non-Military Agencies of the Federal Government.

6.2 Ordering data. Purchasers should select the preferred options permitted herein and include the following information in procurement documents:

(a) Title, number, and date of this specification
(b) Type, class, and color required (see 1.2.1 and 3.1.1.5).
(c) When caduceus is required (medical procurements) (see 3.4.1).
(d) When "US" marking specified in 3.4.2 is not required.
(e) Selection of applicable levels of packaging and packing (see 5.1 and 5.2).
(f) When weather-resistant grade fiberboard shipping containers are required for level L packing (see 5.2.2.2.3).
(g) Type of marking required (see 5.3).

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:34Z
Check the source to verify that this is the current version before use.

6.3 Type IV, class 4, and 5 pillowcase were added to the document.

6.4 Hem identification marking (types III, IV, and V pillowcases). Colored thread in sewing the hems (see 3.1.2.2.1) is for differentiating of polyester/cotton pillowcases from cotton pillowcases because of differences in laundering procedures.

6.5 Quantities and distribution of accepted second quality pillowcases shall be in accordance with the terms of the contract.

6.6 Recycled material. It is encouraged that recycled material be used when practical as long as it meets the requirements of this specification.

6.7 Metric equivalents. Metric equivalents, indicated in parentheses throughout this document, are based on practices, conversion factors, and symbols specified in ASTM E 380 Standard for Metric Practice, and are for information only. In each instance, the value stated in U.S. customary units shall be controlling.

Custodians

Army - GL
Navy - SA
Air Force - 99

Review activities

Army - MD
Navy - MS, SH
DLA - CT, DM

User activity

Navy - MC

Preparing activity:

Army - GL

Civil Agency Coordinating Activity.

GSA-FSS

Project No. 7210-0231

Orders for this publication are to be placed with General Services Administration, acting as an agent for the Superintendent of Documents. See section 2 of this specification to obtain extra copies and other documents referenced herein.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:34Z
Check the source to verify that this is the current version before use.