FEDERAL SPECIFICATION

INHIBITOR, CORROSION, LIQUID COOLING SYSTEM

This amendment, which forms a part of Federal Specification O–I–490, dated November 27, 1957, was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

Page 3, paragraph 4.4.1.1: Delete and substitute:

4.4.1.1 *Chlorides.*—Dissolve 0.25 gm. of the corrosion inhibitor in 10 ml. of warm 50% ethylene glycol (chloride free) and distilled water mixture. Add 5 ml. of a 50 percent aqueous solution of cupric nitrate, agitate for a few minutes and filter. To the filtrate add four drops of a 3 percent aqueous solution of silver nitrate. No precipitate shall form.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:13Z
Check the source to verify that this is the current version before use.