A-A-1280
September 3, 1980

COMMERCIAL ITEM DESCRIPTION

SORBENT, OIL (ROLL, SWEEP, PAD)

The General Services Administration has authorized the use of this commercial item description.

This commercial item description covers oil sorbents for pickup of small oil spills.

The oil sorbents shall be of the following types and classes.

Type I - Roll
Type II - Sweep
Type III - Pad

Class 1 - Reusable
Class 2 - Nonreusable

Salient characteristics:

The sorbents shall be nontoxic to aquatic life, and shall not pollute waters or shorelines.

Oil sorption capacity. (All types and classes) The oil sorption capacity shall not be less than 11 g of No. 2 Fuel Oil per gram of sorbent, and the sorbent shall retain its original form. Class 1 reusable sorbents shall be reused a minimum of 5 times while retaining its original form, and maintain no less than 60 percent of its oil sorption capacity.

Cut a 7 x 7 cm sample and weigh. Fill a pan (minimum 10 x 10 cm) with No. 2 Fuel Oil to a depth of 2.0 cm minimum and maintain it at 25° ±5° C. Place the sample on No. 2 Fuel Oil and let it stay for 3 minutes. Remove the sample using a screen tray and drain it for 2 minutes. Tare a weighing pan, put sample in the pan, weigh and calculate the oil sorption capacity as follows:

$$\text{Oil sorption capacity} = \frac{\text{wet weight - dry weight}}{\text{dry weight}}$$

Remove class 1 reusable sorbent from weighing pan, press the sorbent using a press with minimum pressure of 1 kg/cm^2, reweigh the sorbent, repeat the above test for four more times and calculate the oil sorption capacity as follows:

$$\text{Oil sorption capacity} = \frac{\text{wet weight - squeezed weight}}{\text{squeezed weight}}$$

Replenish the test oil after each test to maintain a constant oil layer thickness.

Water pickup. (All types and classes) The water pickup shall be a maximum of 1 g of water per gram of sorbent. The sorbents shall not sink below the water surface. Same procedure as in oil sorption capacity test shall be used except tap water shall take the place of the test oil and class 1 sorbents shall be tested only once.

$$\text{Water pickup} = \frac{\text{wet weight - dry weight}}{\text{dry weight}}$$

Ignition temperature. The sorbent shall have a self-ignition temperature greater than 149° C. using ASTM D 1929 Method.

The issue of ASTM D 1929 in effect on the date of the solicitation shall be used to determine compliance with stated requirements.

FSC 9330

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:13Z
Check the source to verify that this is the current version before use.

Certification. The contractor shall certify that the product offered meets the salient characteristics of this description and that the product conforms to the producer's own drawings, specifications, standards and quality assurance practices and is the same product offered for sale in the commercial marketplace. The Government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

Packaging, packing and marking. The packaging and packing shall be in accordance with normal commercial practice and shall assure acceptance by common carrier and provide product protection against loss and damage during multiple shipments, handling, and storage. The shipping container shall be in compliance with the National Motor Freight Classification and Uniform Freight Classification. Marking shall be as specified in the contract or order.

ASTM standards are available from the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

NOTE: In order to aid in the selection of a type, the recommended use of each type is provided below.

Type I Oil sorbent in roll form is recommended for use on shorelines, as well as open water.

Type II Oil sorbent sweeps are recommended for use over a large area for control, collection and pickup of oil.

Type III Oil sorbent pads are recommended for use in shallow waters, in congested areas, and along rocky shorelines.

The above types shall be Class 1 - Reusable or Class 2 - Nonreusable.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:13Z
Check the source to verify that this is the current version before use.