MIL-N-8550
AMENDMENT -2
14 DECEMBER 1954

Superseding
Amendment -1
14 September 1953

MILITARY SPECIFICATION

NICKEL ALLOY, BARS, AND FORGINGS, 1,200° to 1,500°F
OPERATING TEMPERATURES

This amendment forms a part of Military Specification MIL-N-8550, dated 6 May 1953, and has been approved by the Department of Defense for use of the Departments of the Army, the Navy, and the Air Force.

Page 2, paragraph 3.2 Chemical composition: Change the composition limits of table I as follows:

Element	Composition percent
Manganese from "0.30 - 1.00" to	"1.00 (max)"
Chromium from "14.00 - 16.00" to	"14.00 - 17.00"
Copper (max) from "0.20" to	"0.50"

Page 2, paragraph 3.3.2 Solution treatment plus high-temperature aging (condition D): Add the following at the end of the paragraph:

"and air cooling"

Page 2, paragraph 3.3.3 Full heat treatment (condition E): In the third line change "24 hours" to "20 hours." Add the following at the end of the paragraph: "provided cooling from 1,500°F to 1,300°F does not exceed 2 hours."

Page 3, paragraph 3.4.3 Stress-rupture properties: In the second line delete "materials" and substitute "bars and forging stock."

Page 3, paragraph 3.4.3.1: Delete the last sentence and substitute the following:

"In either case, the elongation after rupture, measured at room temperature, shall be not less than 5 percent in a gage length of four times the diameter of the specimen."

Page 3, TABLE II Permissible variations for hot-finished bars 1/: For rounds "3/8 to 1, excl." under the headings "Plus" and "Minus" change "0.016" to "0.005." In the second column under "Condition" add "C," "D," and "E" to all six listings.

Page 4, paragraph 3.6.1 Bars 1/2 inch, or more, in diameter of 3/8 inch, or more, in width of flat face: Delete the heading and first sentence and substitute the following:

"3.6.1 Bars 1/2 inch, or more, in diameter or thickness.- When specified, or for direct procurement by the Government, bars 1/2 inch, or more in diameter or thickness shall be legibly marked along the entire length with a row of recurring symbols."

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T10:29Z
Check the source to verify that this is the current version before use.

Page 4, paragraph 3.6.2: Delete paragraph in its entirety and substitute the following:

"3.6.2 Bars less than 1/2 inch in diameter or thickness.- Bars shall be securely bundled and tagged with the above information, using a metal tag."

Page 6, paragraph 6.1 Intended use.- Add the following at the end of the paragraph:

"Primarily for parts where machining and heat treatment are to be applied by the fabricator of the parts."

Custodians:
Army - Corps of Engineers
Navy - Bureau of Aeronautics
Air Force

Other interest:
Navy - Sh

-oOo-

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T10:29Z
Check the source to verify that this is the current version before use.