MIL-C-21881G
12 July 1988
SUPERSEDING
MIL-C-21881F
6 January 1984

MILITARY SPECIFICATION

CLOTH, POPLIN, POLYESTER AND COTTON

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers the requirements for polyester and cotton blend poplin fabrics.

* 1.2 Classification. The polyester and cotton fabrics shall be of the following types and classes (see 6.2):

Type II - 4.1 to 4.6 oz.

Class 1 - Khaki 3729
Class 2 - White 3013

Type III - 4.7 to 5.3 oz. (Water Repellent Treated)

Class 1 - Khaki 3726
Class 2 - Green 3452

2. APPLICABLE DOCUMENTS

2.1 Government documents.

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Officer in Charge, Navy Clothing and Textile Research Facility, 21 Strathmore Road, Natick, MA 01760-2490 by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

AMSC N/A FSC 8305

*DISTRIBUTION STATEMENT A. Approved for public release, distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T10:42Z
Check the source to verify that this is the current version before use.

* 2.1.1 Specifications, standards, and handbooks. The following specifications, standards, and handbooks form a part of this specification to the extent specified herein. Unless otherwise specified, the issues of these documents shall be those listed in the issue of the Department of Defense Index of Specifications and Standards (DODISS) and supplement thereto, cited in the solicitation.

SPECIFICATIONS

FEDERAL

V-T-276	- Thread, Cotton
PPP-P-1134	- Packaging and Packing of Cotton and Cotton-Synthetic Fiber Blend Fabrics (Excluding Duck Fabrics)

MILITARY

MIL-T-43548	- Thread, Polyester Core: Cotton-, Rayon-, or Polyester-covered

STANDARDS

FEDERAL

FED-STD-4	- Glossary of Fabric Imperfections
FED-STD-191	- Textile Test Methods

MILITARY

MIL-STD-105	- Sampling Procedures and Tables for Inspection by Attributes

(Copies of specifications, standards, drawings, and publications required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

* 2.1.2 Other Government documents, drawings, and publications. The following other Government documents, drawings, and publications form a part of this specification to the extent specified herein. Unless otherwise specified, the issues shall be those in effect on the date of the solicitation.

LAWS AND REGULATIONS

Rules and Regulations Under the Textile Fiber Products Identification Act

(Application for copies should be addressed to the Federal Trade Commission, Washington, DC 20580.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T10:42Z
Check the source to verify that this is the current version before use.

* 2.2 Other publications. The following document(s) form a part of this specification to the extent specified herein. Unless otherwise specified, the issues of the documents which are DOD adopted shall be those listed in the issue of the DODISS specified in the solicitation. Unless otherwise specified, the issues of documents not listed in the DODISS shall be the issue of the nongovernment documents which is current on the date of the solicitation.

AMERICAN ASSOCIATION OF TEXTILE CHEMISTS AND COLORISTS (AATCC)

Method No. 8 Colorfastness to Crocking: AATCC Crockmeter Method
Chromatic Transference Scale

(Application for copies should be addressed to the AATCC National Headquarters, P.O. Box 12215, Research Triangle Park, NC 27709-9989.)

* 2.3 Order of precedence. In the event of a conflict between the text of this specification and the references cited herein, the text of this specification shall take precedence. Nothing in this specification, however, shall supersede applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

* 3.1 Standard sample. The finished cloth shall match the standard and shall be equal to or better than the standard sample with respect to all characteristics for which the standard sample is referenced (see 6.3). The standard sample for khaki 3729 is piece number 88189. The standard sample for white 3013 is piece number 88064. The standard sample for khaki 3726 is piece number 87155. The standard sample for green 3452 is piece number 2543.

3.2 First article. When specified, the contractor shall furnish sample unit(s) for first article inspection and approval (see 4.3 and 6.2).

3.3 Materials. (see 6.6)

3.3.1 Fibers.

3.3.1.1 Polyester fiber. The fiber shall be polyethylene glycol terephthalate (see 4.4.1).

3.3.1.2 Cotton fiber. The cotton shall be combed (see 4.4.1).

3.3.2 Yarns. The yarns shall be a blend of polyester and cotton drawn and spun into singles yarn for both the warp and the filling when tested as specified in 4.5.

3.3.3 Fiber content. The finished cloth shall contain 65 percent, plus or minus 5 percent, polyester fiber and not less than 30 percent cotton based on the dry weight of the desized specimens when tested as specified in 4.5.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T10:42Z
Check the source to verify that this is the current version before use.

3.4 Physical requirements. The finished cloth shall conform to the physical requirements shown in Table I when tested as specified in 4.5.

TABLE I. Physical requirements

Characteristics	Type II	Type III
Weight oz/sq yd (g/sq m)		
Minimum	4.1 (139.0)	4.7 (159.3)
Maximum	4.6 (155.9)	5.3 (179.6)
Yarns per inch (2.54 cm) (min)		
Warp	102 (102)	105 (105)
Filling	50 (50)	55 (55)
Breaking strength lbs (N) (min)		
Warp	120 (534)	150 (667)
Filling	50 (223)	70 (311)
Weave	Plain	Plain

* 3.4.1 Width. The width of the finished cloth shall be as specified (see 6.2) and shall be the minimum acceptable width, inclusive of selvages when fly shuttle looms or shuttleless with tuck-in selvage looms are used. For all other shuttleless looms the width measurement shall be made between the last warp yarn on each side excluding the protruding fringe.

3.5 Color

* 3.5.1 Type II, class 1. The finished cloth shall be khaki 3729 and shall match the standard sample (see 3.1 and 6.3).

* 3.5.2 Type II, class 2. The finished cloth shall be white 3013 and shall match the standard sample. The cloth shall be fully bleached and may be supplemented with fluorescent optical brightener (see 4.4.1). The white finished cloth shall not discolor in light to a degree greater than that shown by the standard sample when tested as specified in 4.5. As a limit of acceptability or when no standard sample is available, the discoloration in light shall be not less than "fair" when tested as specified in 4.5 (see 3.1 and 6.3).

3.5.3 Type III, class 1. The finished cloth shall be khaki 3726 and shall match the standard sample (see 3.1 and 6.3).

3.5.4 Type III, class 2. The finished cloth shall be green 3452 and shall match the standard sample (see 3.1 and 6.3).

3.5.5 Sulfur content. The use of dyes and compounds containing elementary sulfur capable of oxidation to sulfuric acid is prohibited. The dyestuff shall be chosen and applied so that the dyed and finished cloth shall contain no more labile sulfur than shown by the standard sample when tested as specified in 4.5. When a standard sample is not available, the dyed cloth shall show no more than a slight trace of labile sulfur as defined in the test method specified in 4.5.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T10:42Z
Check the source to verify that this is the current version before use.

* 3.5.6 Matching. The finished cloth shall match the standard sample when viewed under filtered tungsten lamps which approximate artificial daylight having a correlated color temperature of 7500 + 200 K, with illumination of 100 + 20 foot candles, and shall be a good match to the standard sample under incandescent lamplight at 2300 + 200 K (see 4.4.2.5 and 4.4.2.6).

* 3.5.7 Colorfastness. The type II, class 1, finished cloth shall show colorfastness to light, laundering (after three cycles), perspiration, and crocking equal to or better than the standard sample when tested as specified in 4.5. As a limit of acceptability or when no standard sample is available, the finished cloth shall show a minimum of "good" fastness to laundering, wet dry cleaning, and perspiration, and shall have a AATCC Chromatic Transference Scale rating not lower than 3.0 for wet and dry crocking. The type III cloth shall have the same colorfastness requirements, except that combined laundering and bleaching shall be substituted for the three laundering cycles. Tests shall be performed as specified in 4.5. As a limit of acceptability or when no standard sample is available, the cloth shall show "good" fastness to combined laundering and bleaching.

* 3.6 Nonfibrous material. Prior to the application of the water repellent treatment, the type III cloth shall contain no more than 2.0 percent starch and protein content including chloroform-soluble and water-soluble material, when tested as specified in 4.5.

3.7 pH. The pH value of the water extract of the finished cloth shall be no less than 5.0 nor more than 8.0 when tested as specified in 4.5.

3.8 Dimensional stability. The finished cloth shall not shrink or elongate more than 2.0 percent in either the warp or filling direction when tested as specified in 4.5. The preshrinking process used shall not be identified by name or by trademark either on the cloth, ticket, or package.

3.9 Seam efficiency. The cloth shall have a seam efficiency of not less than 80 percent when tested as specified in 4.5.

3.10 Finish. The cloth shall be desized, scoured, heat set, and dyed or bleached (as applicable) to meet the requirements of the standard sample (see 4.4.2.5 and 4.4.2.6). The type III cloths shall be given an approved durable water repellent treatment (see 6.4) to meet the requirements of 3.10.1 and 3.10.2.

3.10.1 Spray rating. The results of the three individual determinations on the sample unit for spray rating shall be equal to or better than ratings 90, 90, 80 when tested as specified in 4.5.

3.10.2 Dynamic absorption. The initial dynamic absorption shall be an average of 25 percent, maximum. The dynamic absorption after three launderings shall be an average of 35 percent, maximum. Tests shall be performed as specified in 4.5.

3.11 Length and put-up. Unless otherwise specified (see 5.1.1 and 6.2), the finished cloth shall be furnished in continuous lengths, each not less than 40 yards (36.4 m). Each length shall be put-up on full width rolls as specified in PPP-P-1134 with the face inward.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T10:42Z
Check the source to verify that this is the current version before use.

* 3.12 Face identification. The face side of the cloth shall be identified by stamping on that side with the word "Face" at each end of the roll (see 4.4.2.4).

3.13 Fiber identification. Each piece shall be labeled, or ticketed for fiber content in accordance with the Rules and Regulations Under the Textile Fiber Products Identification Act (see 4.4.2.4).

3.14 Workmanship. The finished cloth shall conform to the quality established by this document. The occurrence of defects shall not exceed the applicable point level specified.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the contractor may use his own or any other facilities suitable for performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Responsibility for compliance. All items must meet all requirements of sections 3 and 5. The inspection set forth in this specification shall become a part of the contractor's overall inspection system or quality program. The absence of any inspection requirements in the specification shall not relieve the contractor of the responsibility of assuring that all products or supplies submitted to the Government for acceptance comply with all requirements of the contract. Sampling in quality conformance does not authorize submission of known defective material, either indicated or actual, nor does it commit the Government to acceptance of defective material.

* 4.1.2 Certificate of compliance. Where certificates of compliance are submitted, the Government reserves the right to check test such items to determine the validity of the certification.

4.2 Classification of inspection. The inspection requirements specified herein are classified as follows:

1. First article inspection (see 4.3).
2. Quality conformance inspection (see 4.4).

4.3 First article inspection. When required (see 3.2 and 6.2), the first article shall be visually examined for appearance, color and finish, and shall be tested for physical and chemical properties in accordance with methods specified in 4.5.

4.4 Quality conformance inspection. Sampling for inspection shall be performed in accordance with MIL-STD-105, except where otherwise indicated.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T10:42Z
Check the source to verify that this is the current version before use.

4.4.1 Component and material inspection. In accordance with 4.1 above, components and materials shall be tested in accordance with all the requirements of referenced specifications, drawings, and standards unless otherwise excluded, amended, modified, or qualified in this specification or applicable procurement documents. In addition, the contractor shall furnish a certificate of compliance for the polyester fiber identification, the cotton fiber identification, the combing of the cotton fibers and the bleaching and fluorescent whitener for the type II, class 2 cloth (see 3.3.1.1, 3.3.1.2, and 3.5.2).

4.4.2 Examination of the end item. Examination of the end item shall be in accordance with 4.4.2.1 through 4.4.2.4.

* 4.4.2.1 Yard-by-yard examination. The required yardage of each roll in the sample shall be examined on the face side only. When the total yardage in the roll does not exceed 100 yards (91.4m), the entire yardage in the roll shall be examined. When the total yardage in the roll exceeds 100 yards (91.4m), only 100 yards (91.4m) shall be examined. All defects as defined in Section III of FED-STD-4, which are clearly noticeable at normal inspection distance (3 feet) (0.91m) shall be scored and assigned demerit points as listed in 4.4.2.1.1, except that only those slubs and knots which exceed the limits shown on Sears Fabric Defect Scale (see 6.5), "D" or 3 1/2 as applicable for slubs and "C" for knots, shall be scored. No linear yard (increments of 1 yard (0.91m) on the measuring device of the inspection machine) from any one roll within the sample shall be penalized more than 4 points. The sample size shall be 20 rolls selected from 20 containers. The lot shall be unacceptable if the points per 100 square yards (83.6 m^2) of the total yardage examined exceeds 25.0 points. The lot shall be unaceptable if the points per 100 square yards (83.6 m^2) of two or more individual rolls exceed 38.0 points. If one roll exceeds the point level, a second sample of 20 rolls shall be examined only for individual roll quality examination. If one or more rolls in the second sample of 20 exceed the individual point value, the lot shall be rejected.

Point computation for lot quality and individual roll quality shall be as follows:

$$\frac{\text{Total points scored in sample X 3600}}{\text{Contracted width of cloth (inches) X total yards inspected}} = \text{Points per 100 } yd^2 \text{ (83.6 } m^2\text{)}$$

4.4.2.1.1 Demerit points. Demerit points shall be assigned as follows:

For defects up to and including 3 inches in any dimension	- one point
For defects exceeding 3 inches but not exceeding 6 inches in any dimension	- two points
For defects exceeding 6 inches but not exceeding 9 inches in any dimension	- three points
For defects exceeding 9 inches in any dimension	- four points

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T10:42Z
Check the source to verify that this is the current version before use.

NOTE: The following defects, when present, shall be scored 4 points for each yard (0.91 m) in which they occur:

Baggy, ridgy, or wavy cloth
Width less than specified
Non-uniformity of shade (poor dye penetration, mottled, streaky or cloudy)
Excessive neppiness

4.4.2.2 Examination for length.

4.4.2.2.1 Individual rolls. During the yard by yard examination, each roll in the sample shall be examined for length. Any length found to be less than the minimum specified, or more than two yards less than the length marked on the ticket shall be considered a defect with respect to length. The lot shall be unacceptable if two or more rolls in the sample are defective in respect to length.

4.4.2.2.2 Total yardage in sample. The lot shall be unacceptable if the total of the actual length of rolls in the sample is less than the total of the lengths marked on the ticket. The rolls examined shall be those selected for the examination of individual rolls.

* 4.4.2.3 Examination for shade variation. During the yard-by-yard examination, each roll in the sample shall be examined for shade variation. Any roll in the sample exhibiting uneven shade, shaded variation side to side, side to center or end to end shall be cause for rejection of the entire lot represented by the sample.

4.4.2.4 Examination for face identification, identification of preshrinkage process and non-conformance with the Textile Fiber Products Identification Act. During the yard by yard examination, each roll in the sample shall be examined for these defects. The lot shall be unacceptable if two or more rolls in the sample have face identification missing from either or both ends, two or more rolls in the sample contain identification of the preshrinkage process by name or trademark on the cloth or ticket or two or more rolls in the sample are not labeled or ticketed in accordance with the Textile Fiber Products Identification Act (see 3.12 and 3.13).

* 4.4.2.5 Examination for shade match and finish, individual rolls (type II only). A sample from each roll in the lot shall be examined visually for shade (see 3.5.6) and finish appearance (see 3.10). A roll shall be unacceptable if it fails to meet the requirements for shade, finish or appearance. The sample shall be a 4 inch by 20 inch swatch of cloth drawn from each roll in the lot.

* 4.4.2.6 Examination for shade match and finish (type III only). Each lot shall be examined visually for shade match (see 3.5.6) and finish appearance (see 3.10) in accordance with the table listed below and the provisions contained in the contract. The lot shall be unacceptable if one or more piece fails to meet the requirement for shade match or finish appearance. The sample unit shall be a 4 inch by 20 inch swatch of the cloth. The sample unit shall be drawn from each piece in the sample size:

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T10:42Z
Check the source to verify that this is the current version before use.

Lot size	Piece to be Sampled
1 - 8 pieces	each piece
9 - 25 pieces	8 pieces
26 - 90 pieces	20 pieces
91 - 160 pieces	32 pieces
over 160 pieces	1 of 5 pieces

4.4.3 Examination of packaging requirements. An examination shall be made in accordance with the provisions of PPP-P-1134 to determine that preservation, packaging, packing, and marking comply with section 5 requirements.

4.5 Testing of the end item. The methods of testing specified in FED-STD-191, wherever applicable, and as listed in Table II shall be followed. The physical and chemical values specified in Section 3, except where otherwise specified, apply to the average of the determinations made on the sample unit for test purposes as specified in the applicable test methods. All test reports shall contain the individual values utilized in expressing final results. The sample unit for test purposes of type II cloths shall be 4 continuous yards (3.64 m), full width of the finished cloth. The sample unit for test purposes of type III cloths shall be 5 continuous yards (4.55 m) full width of the finished cloth and 1/4 yard (0.22 m) full width of the cloth prior to water repellent treatment for determination of starch and protein content. The lot size shall be expressed in units of one yard. The lot shall be unacceptable if one or more sample units fail to meet any of the test requirements specified. The sample size shall be in accordance with the following:

Lot size, yards (.91 meter)	Sample size (units)
800 or less	2
801 up to and including 22,000	3
22,001 and over	5

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T10:42Z
Check the source to verify that this is the current version before use.

*TABLE II. - Test Methods

Characteristic	Requirement Paragraph	Test Method
Yarn (singles)		
Warp	3.3.2	Visual 1/
Filling	3.3.2	Visual 1/
Fiber content		
Polyester (percent)	3.3.3	2100, 4.5.1
Cotton (percent)	3.3.3	2100, 4.5.1
Weight	3.4	5041
Yarns per inch		
Warp	3.4	5050
Filling	3.4	5050
Breaking strength		
Warp	3.4	5100
Filling	3.4	5100
Weave	3.4	Visual 1/
Discoloration	3.5.2	5660 1/ 2/ 3/
Sulfur content	3.5.5	2020
Colorfastness to:		
Light	3.5.7	5660 3/
Laundering (after 3 cycles) (type II only)	3.5.7	5610 4/ 5/
Perspiration	3.5.7	5680
Crocking	3.5.7	AATCC TM 8-1985
Laundering and bleaching (type III only)	3.5.7	5605 5/
Nonfibrous materials (type III only)	3.6	2611
pH	3.7	2811
Dimensional stability	3.8	5556 6/
Seam efficiency	3.9	5110 7/
Water resistance (type III only)		
Spray rating	3.10.1	5526
Dynamic absorption		
Initial	3.10.2	5500
After 3 launderings	3.10.2	5500 & 5518

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T10:42Z
Check the source to verify that this is the current version before use.

1/ One determination per sample unit and the result reported as "pass" or "fail".
2/ Method 5660 shall be used except that exposure of the specimen standard sample shall be for 20 standard fading hours. Any specimen showing discoloration less than or equal to that of the standard sample shall be rated "satisfactory". Any specimen showing discoloration greater than that of the standard sample shall be rated "unsatisfactory". When no standard sample is available the discoloration of the specimen shall be rated as "excellent", "good", "fair", or "poor", as defined in method 5660.
3/ The calibration of the fadeometer and the definition of AATCC Fading Units shall be according to AATCC Test Method 16-1982. Using the formula below, 16 to 22 AFU's are acceptable as 20 SFH's.

$$\text{AATCC Fading Units} = \frac{(\Delta E^*)\ (20)}{1.7}$$

Where (ΔE^*) is the color difference in CIELAB* units of color difference.
4/ The specimens must be dried after each of the 3 laundering cycles.
5/ Only the stain on the cotton and polyester fibers of the color transfer cloth shall be evaluated.
6/ Cotton laundering procedure shall be followed.
7/ The needle size shall be 0.036 (± 0.001) inch (0.91 ± 0.025 mm) across the blade eye. The thread shall be polyester covered conforming to MIL-T-43548, Ticket No. 50, 3 ply for the needle and Ticket No. 70, 2 ply for the looper. As an alternate, a cotton thread conforming to Type 1A1 of V-T-276 may be used. Ticket No. 60, 3 ply for the needle and Ticket No. 70, 3 ply for the looper. The use of polyester covered polyester-core thread is not allowed.

4.5.1 Polyester and cotton fiber content. The general procedures of method 2100 shall be followed with the fiber content percentages calculated as follows:

$$\text{Polyester, percent} = \frac{\text{Weight of dry residual fiber X 100}}{\text{Weight of dry desized specimen}}$$

Percent cotton = 100 - percent polyester

4.5.1.1 Report. Two specimens shall be tested from each sample unit and the average percent polyester and the average percent cotton of the two specimens shall be reported to the nearest 1.0 percent.

5. PACKAGING

5.1 Put-up and preservation. Put-up and preservation packaging shall be level A or Commercial as specified (see 6.2).

5.1.1 Levels A and C. The cloth shall be put-up (see 3.11) and packaged in accordance with the applicable requirements of PPP-P-1134.

5.2 Packing. Packing shall be level A, B or Commercial as specified (see 6.2).

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T10:42Z
Check the source to verify that this is the current version before use.

5.2.1 Levels A, B and C. The cloth shall be packed in accordance with the applicable requirements of PPP-P-1134.

5.3 Marking. In addition to any special marking required by the contract or order, shipments shall be marked in accordance with the applicable requirements of PPP-P-1134.

6. NOTES

6.1 Intended use. Type II cloths covered by this specification are intended for use in shirts worn by Naval personnel. Type III cloths are intended for use by all services in swimming and general utility trunks for both male and female personnel.

6.2 Ordering data. Procurement documents should specify the following:

a. Title, number and date of this document.
b. Type and class required (see 1.2)
c. When a first article inspection is required (see 3.2 and 4.3). The item will be tested and should be a first article sample. The contracting officer should include specific instruction in acquisition documents regarding arrangements for examinations, quantity, testing, and approval of the first article.
d. Width required (see 3.4.1).
e. Length required if other than specified (see 3.11).
f. Levels of put-up and preservation, and packing (see 5.1 and 5.2).

6.3 Standard sample. For access to standard sample, address the procuring office issuing the invitation for bids (see 3.1 and 3.5).

6.4 Durable water repellent. Durable water repellent treatment (see 3.10) for use on type III cloth is the responsibility of the U.S. Army Natick Research, Development, and Engineering Center, Natick, MA 01760, and is based on extensive tests including those for toxity, which are not set forth in this specification. Because of the time necessary to conduct full evaluation only those treatments already approved and so listed in the invitation for bids or request for proposal shall be considered acceptable for related procurement. Information on currently approved material may be obtained from Defense Personnel Support Center, Philadelphia, PA 19101.

6.5 Fabric defect scales. Sears Fabric Defect Scales are available from Sears, Roebuck and company, Department 817, (Attn: 23-29), Sears Tower, Chicago, IL 60684. (see 4.4.2.1)

6.6 Recycled material. It is encouraged that recycled material be used when practical as long as it meets the requirements of the specification (see 3.3).

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T10:42Z
Check the source to verify that this is the current version before use.

6.7 Changes from previous issue. The margins of this specification are marked with an asterisk to indicate where changes (additions, modifications, corrections, deletions) from the previous issue were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous issue.

* 6.8 Subject term (key word) listing.
Cloth, plain weave
Cloth, polyester and cotton
Cloth, poplin
Cloth, water repellent treated

Custodian:
Army - GL
Navy - NU
Air Force - 99

Review Activities:
Army - MD
Air Force - 82
DLA - CT

User Activities:
Navy - CG, MC
Air Force - 45

Preparing Activity:
Navy - NU

Project No.
8305-0231

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T10:42Z
Check the source to verify that this is the current version before use.