MIL-HDBK-228A(AS)
23 July 1982

SUPERSEDING
MIL-HDBK-228 (AS)
21 JULY 1970

# MILITARY STANDARDIZATION HANDBOOK

# PRESSURE-SENSITIVE ADHESIVE, SOLVENT ACTIVATED AND MISCELLANEOUS TAPES

FSC 7690

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:38Z
Check the source to verify that this is the current version before use.

DEPARTMENT OF THE NAVY
NAVAL AIR SYSTEMS COMMAND
Washington, D.C. 20360

MIL-HDBK-228A (AS)
Pressure-Sensitive Adhesive, Solvent Activated and Miscellaneous Tapes

1. This standardization handbook was developed by the Naval Air Systems Command, Department of the Navy.

2. This publication was approved for printing and inclusion in the military standardization handbook series.

3. This document provides basic and fundamental information on pressure-sensitive adhesive, solvent activated, miscellaneous tapes and their uses. It will provide valuable information and guidance to personnel concerned with the preparation of specifications and the procurement of tape products. The handbook is not intended to be referenced in purchase specifications except for informational purposes, nor shall it supersede any specification requirements.

4. Every effort has been made to reflect the latest information on tape products. It is the intent to review this handbook periodically to insure its completeness and currency. Users of this document are encouraged to report any errors discovered and any recommendations for changes or inclusions to the Commanding Officer, Naval Air Engineering Center, Engineering Specifications and Standards Department (Code 93), Lakehurst, NJ 08733.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:38Z
Check the source to verify that this is the current version before use.

CONTENTS


| | | | Page |
|---|---|---|---|
| Paragraph | 1. | SCOPE | 1 |
| | 1.1 | Scope | 1 |
| | 1.2 | Purpose | 1 |
| | 1.3 | Application | 1 |
| | 2. | QUALIFICATION OF TAPES | 1 |
| | 3. | INVESTIGATION OF PROBLEMS ENCOUNTERED IN USE | |
| | 4. | REQUESTS FOR USE OF EMERGENCY ALTERNATES | 2 |
| | 5. | STORAGE INSTRUCTIONS | 2 |
| | | APPENDICES | |
| APPENDIX A | | PRESSURE SENSITIVE TAPES | 4 |
| | 10. | DESCRIPTION | 4 |
| | 20. | ELECTRICAL INSULATORS AND INSULATING MATERIALS | 4 |
| | 20.1 | Insulating tapes | 4 |
| | 30. | PHOTOGRAPHIC SUPPLIES | 5 |
| | 30.1 | Photographic use | 5 |
| | 40. | GENERAL SUPPLIES | 5 |
| | 50. | PRESERVATION, PACKAGING AND SEALING TAPES | 6 |
| | 60. | DETAIL INFORMATION ON SPECIFICATIONS IN APPENDIX A | 7 |
| APPENDIX B | | SOLVENT ACTIVATED TAPES | 58 |
| | 10. | DESCRIPTION | 58 |
| | 20. | SUPPLIES | 58 |
| | 30. | PACKAGING AND PACKING BULK MATERIALS | 58 |
| | 40. | DETAILED INFORMATION ON SPECIFICATIONS IN APPENDIX B | 58 |
| APPENDIX C | | MISCELLANEOUS TAPES | 62 |
| | 10. | DESCRIPTION | 62 |
| | 20. | ELECTRICAL INSULATORS AND INSULATING MATERIALS | 62 |
| | 20.1 | Insulation tapes | 62 |
| | 30. | DETAILED INFORMATION ON SPECIFICATIONS LISTED IN APPENDIX C | 62 |




Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:38Z
Check the source to verify that this is the current version before use.

## 1. SCOPE

1.1 Scope. This handbook contains the intended use, description, method of application, and national stock numbers of active items, of limited and fully coordinated federal and military specifications covering pressure-sensitive, solvent activated, and miscellaneous tapes. These specification tapes are used by the majority of Naval activities and have been found to be satisfactory. The use of these materials, for the operations discussed in the text and appendices, is recommended in the interest of efficiency, economy, safety, and ease of procurement.

1.2 Purpose. The purpose of this handbook is to provide the user with the capability to quickly determine the existence of a specification item with the physical and functional capability to meet his present requirement. The recommended use of the materials covered by this handbook is not intended to prohibit the use of other tapes which station materials engineering divisions or other duly appointed engineering authorities have approved for certain specific use. However, it is recommended that the Naval Air Systems Command be advised of such use of other tapes in order that they may be tested and, if found suitable, be made available to other activities. If a specification item is available, future purchases of the item should be made under the specification in order that the Naval Air Systems Command may be safeguarded against buying tapes which may be harmful to personnel or equipment, as well as overpricing due to the direct purchase method of procurement instad of competitive bidding when purchased under definite specifications.

1.3 Application. The various tapes are initially categorized into the following three groups:

Appendix A - Pressure sensitive tapes.

Appendix B - Solvent activated tapes.

Appendix C - Miscellaneous tapes.

Each applicable specification is then described in detail, to include description, intended use, method of application, sizes, types, and classes. Specifications are arranged in the following sequence: "Federal" and "Military".

## 2. QUALIFICATION OF TAPES

2.1 Qualification tests are those tests accomplished on samples submitted for qualification under a specification to determine its acceptance as a satisfactory product. When required in a specification, qualification tests on the particular materials are conducted at a qualified Government laboratory designated in the specification. In the event that material furnished in the field is found to deviate from the composition, structure or performance aspects as specified in the specification, qualification approval of such material may be subject to immediate withdrawal. Communications concerning such deviations or failure in service should be directed to the Materials and Processes Branch (AIR-5304), Naval Air Systems Command,



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:38Z
Check the source to verify that this is the current version before use.

Department of the Navy, Washington, DC 20360. This publication lists only specifications which are used by the Naval Air Systems Command. National Stock Numbers exist only for those materials which have a continuing demand. Other materials can, however, be procured on a local basis from qualified producers. If a large enough demand for a tape exists, the particular item should be given a stock number by requesting same from the Aviation Supply Office, 700 Robbins Ave., Philadelphia, PA 19111.

## 3. INVESTIGATION OF PROBLEMS ENCOUNTERED IN USE

3.1 Attention is directed to the fact that the Naval Air Systems Command is always interested in problems that Naval activities encounter in the use of any materials listed in this handbook. It is recommended that Naval activities refer their material problems to the Naval Air Systems Command for investigation. Comments relative to the contents of this handbook should be referred to: Commanding Officer, Naval Air Engineering Center, Engineering Specifications and Standards Department (Code 93), Lakehurst, NJ 08733.

If warranted, the Command will assign a project to a qualified government laboratory for test and development evaluations, with the aim of obtaining carefully analyzed recommendations for field use. It is requested that Naval activities include, along with their problems, ambient and equipment temperatures and humidity, at application; describe the type of surface to which the materials has been applied; the length of useful life of the material after application, if any; and the conditions the materials encountered during useful life. Also submit any other information that would be of help for proper evaluation of the problem, to include storage data, such as the conditions where the material has been stored, and the length of time stored before use.

## 4. REQUESTS FOR USE OF EMERGENCY ALTERNATIVES

4.1 It is recognized that under specific unique service conditions, such as atmosphere conditions of extreme temperatures and humidities, activities may require tapes with special properties. Such special cases should be brought to the attention of the Naval Air Systems Command and adequate permissible emergency alternate materials will be suggested.

## 5. STORAGE INSTRUCTIONS

5.1 Tapes should be stored in the original container, preferably in a cool, dry, dark location. Ordinarily, recommended storage conditions are 70 degrees Fahrenheit or lower, and 40 to 60 percent relative humidity. However, pressure-sensitive tapes can be stored at temperatures below 32 degrees Fahrenheit with no deleterious effects. Freezing temperatures will retard the natural aging of tapes. After cold storage, the material must be conditioned to optimum application temperatures (60 to 80 degrees Fahrenheit) before use.



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:38Z
Check the source to verify that this is the current version before use.

It should not be stored in close proximity to steam pipes, radiators, or other heated surfaces. Since certain adhesives lose some of their initial quality with increasing age, and since these tapes are generally semiperishable, supplies and purchases should be adjusted, if possible, to avoid storage for more than 6 months. Stocks must be rotated. These instructions apply to the tapes discussed in this handbook.

Preparing activity:
Navy - AS
(Project No. 7690-N059)



Source: https://assist.dla.mil -- Downloaded: 202610-26T13:38Z
Check the source to verify that this is the current version before use.

# APPENDIX A

## PRESSURE SENSITIVE TAPES

10. DESCRIPTION.

10.1 This appendix covers pressure sensitive tapes. The appendix is subdivided by typical uses.

10.2 Individual specifications are described in detail in subparagraphgs of 60.

20. ELECTRICAL INSULATORS AND INSULATING MATERIALS.

20.1 Insulation tapes.

20.1.1 This group consists of pressure-sensitive tapes designed to provide electrical insulation of wires and cables, with varying dielectric strengths and operating temperatures.

| Federal | | Paragraph |
|---|---|---|
| HH-I-510 | Insulation Tape, Electrical, Friction | 60.5 |
| HH-I-533 | Insulation Tape, Electrical (Rubber Natural and Synthetic) | 60.6 |
| HH-I-595 | Insulation Tape, Electrical, Pressure-Sensitive Adhesive, Plastic for Low-Temperature Application | 60.7 |
| **Military** | | |
| MIL-I-3374 | Insulation Cloth and Tape, Electrical, Varnished Cambric | 60.21 |
| MIL-I-3825 | Insulation Tape, Electrical, Self-Fusing, for use in Electronic Communications and Allied Equipment | 60.22 |
| MIL-I-15126 | Insulation Tape, Electrical, Pressure-Sensitive Adhesive and Pressure-Sensitive Thermosetting Adhesive | 60.25 |
| MIL-I-19166 | Insulation Tape, Electrical, High Temperature, Glass Fiber, Pressure-Sensitive | 60.26 |
| MIL-I-22444 | Insulation Tape, Electrical, Self-Bonding | 60.29 |
| MIL-I-23594 | Insulation Tape, Adhesive, Electrical, High Temperature Polytetrafluoroethylene, Pressure-Sensitive | 60.32 |
| MIL-I-24391 | Insulation Tape, Electrical, Plastic, Pressure-Sensitive | 60.33 |



Source: https://assist.dla.mil -- Downloaded: 202610-26T13:38Z
Check the source to verify that this is the current version before use.

30. PHOTOGRAPHIC SUPPLIES.

30.1 Photographic use. This group consists of pressure-sensitive tapes for photographic use such as film splicing.

| Federal | | Paragraph |
|---|---|---|
| UU-T-123 | Tape, Pressure-Sensitive Adhesive, Paper, Photographic | 60.13 |
| **Military** | | |
| MIL-T-26317 | Tape, Pressure-Sensitive Adhesive, Transparent, Film Splicing | 60.34 |
| MIL-T-40620 | Tape, Pressure-Sensitive, Lithograph | 60.37 |

40. GENERAL SUPPLIES.

40.1 This group covers pressure-sensitive tapes with a wide variety of uses. Examples are cited below.

a. Drafting operations.
b. Permanent mending of paper books.
c. General office use.
d. Covering identification tapes and labels.
e. Use where two-sided adhesion is required.
f. Holding.

| Federal | | Paragraph |
|---|---|---|
| L-T-80 | Tape, Pressure-Sensitive Adhesive (Aluminum Backed) | 60.1 |
| L-T-90 | Tape, Pressure-Sensitive Adhesive (Cellophane and Cellulose Acetate) | 60.2 |
| L-T-99 | Tape, Pressure-Sensitive Identification | 60.3 |
| L-T-100 | Tape, Pressure-Sensitive, Polyester Film | 60.4 |
| HH-T-25 | Tape, Pressure-Sensitive Adhesive, Plastic (For Electroplating) | 60.8 |
| HH-T-29 | Tape, Adhesive, Lead Foil | 60.9 |
| UU-T-91 | Tape, Pressure-Sensitive Adhesive, Double Coated | 60.10 |
| UU-T-93 | Tape, Pressure-Sensitive, Paper, Drafting | 60.11 |
| PPP-T-66 | Tape, Pressure-Sensitive Adhesive, Vinyl Plastic Film | 60.16 |



Source: https://assist.dla.mil -- Downloaded: 202610-26T13:38Z
Check the source to verify that this is the current version before use.

| Military | | Paragraph |
|---|---|---|
| MIL-T-27730 | Tape, Antiseize, Polytetrafluoroethylene, With Dispenser | 60.35 |
| MIL-T-60394 | Tape, Pressure-Sensitive Adhesive Film, Double Coated (For Use With Ammunition) | 60.39 |
| MIL-T-83284 | Tape, Thermal Radiation Resistant, Pressure-Sensitive Aluminum Coated Fiberglass Cloth | 60.40 |

50. PRESERVATION; PACKAGING AND SEALING TAPES.

50.1 This group consists of pressure-sensitive tapes designed for preservation, packaging and sealing operations, with varying properties and uses, such as:

a. High temperature application.
b. Masking for painting operations.
c. Dissimilar metal separation.
d. Sealing joints.
e. Packaging of supplies which will be overpacked in exterior containers.
f. Protection of aircraft, missiles, and rockets during handling, shipment, and storage.
g. Closing and sealing fiberboard containers.
h. Reinforcing bundles and containers.
i. Attaching, covering, and protecting labels.

| Federal | | Paragraph |
|---|---|---|
| PPP-T-42 | Tape, Packaging, Masking, Paper | 60.14 |
| PPP-T-60 | Tape, Pressure-Sensitive, Waterproof for Packaging | 60.15 |
| PPP-T-70 | Tape, Packaging, Plastic Film | 60.17 |
| PPP-T-75 | Tape, Preservation and Sealing | 60.18 |
| PPP-T-76 | Tape, Preservation, Adhesive Paper (For Carton Sealing) | 60.19 |
| PPP-T-97 | Tape, Pressure-Sensitive Adhesive, Filament Reinforced | 60.20 |



Source: https://assist.dla.mil -- Downloaded: 202640-26T13:38Z
Check the source to verify that this is the currentversion before use.

| Military | | Paragraph |
|---|---|---|
| MIL-T-4053 | Tape, Pressure-Sensitive, Adhesion (Corrosion-Resistant) | 60.23 |
| MIL-T-21595 | Tape, Pressure-Sensitive Adhesive, Paper, Masking, Nonstaining | 60.27 |
| MIL-P-22085 | Paper, Pressure-Sensitive, Adhesive, Preservation and Sealing | 60.28 |
| MIL-T-23142 | Tape, Pressure-Sensitive Adhesive, for Dissimilar Metal Separation | 60.30 |
| MIL-T-23397 | Tape, Pressure-Sensitive Adhesive for Masking During Paint Stripping Operations | 60.31 |
| MIL-T-38727 | Tape, Adhesive Coated, Protective | 60.36 |
| MIL-T-43036 | Tape, Pressure-Sensitive Adhesive, Plastic Film Filament Reinforced (For Sealing Fiber Containers and Cans) | 60.38 |

60. DETAIL INFORMATION ON SPECIFICATIONS IN APPENDIX A.



Source: https://assist.dla.mil -- Downloaded: 202610-26T13:38Z
Check the source to verify that this is the current version before use.

60.1 TAPE, PRESSURE-SENSITIVE ADHESIVE (ALUMINUM BACKED).

60.1.1 Description. An aluminum foil backed tape coated on one side with pressure sensitive adhesive.

60.1.2 Intended use. This tape is intended for use in sealing applications where the properties of good weather resistance, reflectivity and vapor transmission resistance are required.

60.1.3 Method of application. Apply to clean, dry surface, press on firmly, making sure that it makes good contact.

| Width | Length | Core Diameter | Stock Number |
|---|---|---|---|
| .5 | 60 yd | 3" | 7510-00-806-4669 |
| 1 | 60 yd | 3" | 7510-00-720-7516 |
| 1.5 | 60 yd | 3" | 7510-00-754-2522 |
| 2 | 60 yd | 3" | 7510-00-684-8803 |
| 2 | 60 yd | 3" | 7510-01-043-5026 |
| 3 | 60 yd | 3" | 7510-00-816-8077 |
| 3 | 46 in | 3.062" | 7510-01-042-2538 |
| 6 | 60 yd | 3" | 7510-00-235-0745 |



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:38Z
Check the source to verify that this is the current version before use.

## 60.2 TAPE, PRESSURE-SENSITIVE, ADHESIVE, (CELLOPHANE AND CELLULOSE ACETATE) L-T-90

60.2.1 Description. A cellophane or cellulose acetate film base coated on one side with a pressure-sensitive adhesive. Colors are resistant to bleeding. Available in two types.

Type I - Cellophane:
Class A - transparent
Class B - colored

Type II - Cellulose acetate:
Class A - transparent, low reflectance
Class B - transparent, glossy backed

Colors for Type I, Class B: Red, white, black, medium green, yellow, medium blue, light green, light blue, orange-yellow, orange, dark blue.

60.2.2 Intended use. Type I, Class A: Non-permanent appliations such as holding, covering, light packaging, sealing, shielding, and general office use.

Type I, Class B: Non-permanent applications such as identification, charting, decorating, holding, light packaging, and sealing. Available in colors specified in table below.

Type II, Class A: Permanent mending of paper, documents, books, maps, etc. Will accept typing and writing in pencil, pen, or other common marking devices, and appears invisible when copied.

Type II, Class B: Permanent application such as light holding, covering, shielding, sealing, and protection of labels.

60.2.3 Method of application. Apply to clean, dry surface, press on firmly, making sure that it makes good contact.

TYPE I, CLASS A

TRANSPARENT CELLOPHANE TAPE

| Color | Width (inches) | Core (inches) | Length (yds) | Stock Number |
|---|---|---|---|---|
| Clear | 1/2 | 1 | 400 in. | 7510-00-551-9822 |
| Clear | 1/2 | 1 | 36 | 7510-00-551-9821 |
| Clear | 1/2 | 3 | 72 | 7510-00-551-9820 |
| Clear | 3/4 | 1 | 36 | 7510-00-551-9818 |
| Clear | 3/4 | 3 | 72 | 7510-00-551-9816 |
| Clear | 1 | 3 | 72 | 7510-00-551-9817 |
| Clear | 1 1/2 | 3 | 72 | 7510-00-551-9826 |
| Clear | 2 | 3 | 72 | 7510-00-234-7960 |
| Opaque | 2 | - | - | 7510-00-680-0151 |
| Aluminum | 2 | - | 60 | 7510-00-234-7960 |



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:38Z
Check the source to verify that this is the current version before use.

TYPE I, CLASS B

COLORED CELLOPHANE TAPE

| Color | Width (inches) | Core (inches) | Length (yds) | Stock Number |
|---|---|---|---|---|
| Yellow | 1/8 | 3 | 72 | 7510-00-558-1520 |
| White | 1/8 | 3 | 72 | 7510-00-558-1530 |
| Dark Blue | 1/8 | 3 | 72 | 7510-00-558-1537 |
| Med Green | 1/8 | 3 | 72 | 7510-00-558-1542 |
| Orange Yellow | 1/8 | 3 | 72 | 7510-00-558-1516 |
| Blue | 1/8 | 3 | 72 | 7510-00-550-7721 |
| Green | 1/8 | 3 | 72 | 7510-00-550-7725 |
| Orange | 1/8 | 3 | 72 | 7510-00-558-1512 |
| Black | 1/8 | 3 | 72 | 7510-00-558-1555 |
| Med Blue | 1/8 | 3 | 72 | 7510-00-577-4877 |
| Red | 1/8 | 3 | 72 | 7510-00-634-3253 |
| Red | .25 | 3 | 72 | 7510-00-634-3264 |
| Lt Blue | .25 | 3 | 72 | 7510-00-550-7722 |
| Lt Green | .25 | 3 | 72 | 7510-00-550-7726 |
| White | .25 | 3 | 72 | 7510-00-558-1529 |
| Black | .25 | 3 | 72 | 7510-00-504-5640 |
| Lt Green | .25 | 3 | 72 | 7510-00-504-5639 |
| Orange | .25 | 3 | 72 | 7510-00-504-5638 |
| Blue | .25 | 3 | 72 | 7510-00-504-5637 |
| White | .25 | 3 | 72 | 7510-00-502-6578 |
| Drk Blue | .25 | 3 | 72 | 7510-00-478-3588 |
| Yellow | .25 | 3 | 72 | 7510-00-558-1519 |
| Black | 1/2 | 3 | 72 | 7510-00-551-8474 |
| Drk Blue | 1/2 | 3 | 72 | 7510-00-550-7124 |
| Med Green | 1/2 | 3 | 72 | 7510-00-550-7129 |
| Orange Yellow | 1/2 | 3 | 72 | 7510-00-550-7128 |
| Red | 1/2 | 3 | 72 | 7510-00-550-7126 |
| White | 1/2 | 3 | 72 | 7510-00-550-7127 |
| Yellow | 1/2 | 3 | 72 | 7510-00-550-7125 |
| Black | 1/2 | 3 | 36 | 7510-00-558-1543 |
| Med Blue | 1/2 | 3 | 72 | 7510-00-577-4881 |
| Lt Green | 1/2 | 3 | 72 | 7510-00-558-1521 |
| Lt Blue | 1/2 | 3 | 72 | 7510-00-634-3267 |
| White | .719-.731 | 1 | 60 | 7510-00-835-1247 |
| White | 3/4 | 1 | 324" | 7510-00-551-9819 |
| Med Blue | 3/4 | 3 | 72 | 7510-00-577-4883 |
| Black | 3/4 | 3 | 72 | 7510-00-558-1304 |
| White | 3/4 | 3 | 72 | 7510-00-558-1314 |
| Lt Green | 3/4 | 3 | 72 | 7510-00-558-1321 |
| Red | 3/4 | 3 | 72 | 7510-00-634-3252 |
| White | 3/4 | 1 | 60 | 7510-00-835-1247 |
| Med Green | 1 | 3 | 72 | 7510-00-558-1526 |
| Lt Green | 1 | 3 | 72 | 7510-00-558-1320 |
| Red | 1 | 3 | 72 | 7510-00-634-3260 |
| Med Blue | 1 | 3 | 72 | 7510-00-577-4884 |
| Blue | 1 | 3 | 72 | 7510-00-558-1323 |
| Med Green | 1 | 3 | 72 | 7510-00-558-1526 |
| White | 1 | 3 | 72 | 7510-00-559-1755 |
| Med Blue | 1 | 3 | 72 | 7510-00-577-4884 |



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:38Z
Check the source to verify that this is the current version before use.

TYPE I, CLASS B (continued)

COLORED TRANSPARENT TAPE

| Color | Width (inches) | Core (inches) | Length (yds) | Stock Number |
|---|---|---|---|---|
| Brown | 1 | 3 | 72 | 7510-00-558-1297 |
| Dk Blue | 1 | 3 | 72 | 7510-00-558-1312 |
| Yellow | 1 | 3 | 72 | 7510-00-558-1317 |
| Lt Green | 1 | 3 | 72 | 7510-00-558-1320 |
| Black | 1 | 3 | 72 | 7510-00-558-1305 |
| Red | 1 1/2 | 3 | 72 | 7510-00-634-3261 |
| Black | 2 | 3 | 72 | 7510-00-558-1527 |
| Med Blue | 2 | 3 | 72 | 7510-00-577-4886 |
| Lt Green | 2 | 2 | 72 | 7510-00-559-4502 |
| Red | 2 | 3 | 72 | 7510-00-634-3262 |
| White | 2 | 3 | 72 | 7510-00-634-0293 |
| Pink | 7 | 3 | 72 | 7510-01-057-3612 |

TYPE II, CLASS A

TRANSPARENT, LOW REFLECTANCE CELLULOSE ACETATE

| Color | Width (inches) | Core (inches) | Length (yds) | Stock Number |
|---|---|---|---|---|
| Clear | 1/2 | 1 | 400" | 7510-00-082-2521 |
| Clear | 1/2 | 3 | 72 | 7510-00-813-4951 |
| Clear | 1/2 | 1 | 36 | 7510-00-551-9825 |
| Clear | 3/4 | 1 | 300" | 7510-00-082-2520 |
| Clear | 3/4 | 1 | 36 | 7510-00-551-9825 |
| Clear | 3/4 | 1 | 180" | 7510-00-721-9680 |
| Clear | 3/4 | 3 | 72 | 7510-00-551-9824 |
| Clear | 1 | 3 | 72 | 7510-00-551-9823 |
| Clear | 1.5 | 3 | 72 | 7510-00-868-4713 |
| Clear | 4 | 3 | 72 | 7510-00-576-9762 |
| Clear | 8 | 2.875 | 72 | 7510-00-724-7002 |

TYPE II, CLASS B

TRANSPARENT, GLOSSY BACKED CELLULOSE ACETATE

| Color | Width (inches) | Core (inches) | Length (yds) | Stock Number |
|---|---|---|---|---|
| Clear | 1/4 | 3 | 72 | 7510-00-728-5754 |
| Clear | 1/2 | 3 | 72 | 7510-00-181-8239 |
| Clear | 1/2 | 3 | 72 | 7510-00-634-3029 |
| Clear | 1 | 3 | 72 | 7510-00-663-9043 |



Source: https://assist.dla.mil -- Downloaded: 202610-26T13:38Z
Check the source to verify that this is the current version before use.

## 60.3 TAPE, PRESSURE SENSITIVE ADHESIVE, IDENTIFICATION

L-T-99

60.3.1 Description. This tape is a printable pressure-sensitive adhesive tape. The backing for tapes I and II is either polyester film or a cellulose acetate plastic film laminated to paper (reinforcing tissue) with a continuous film of water insoluble pigmented or unpigmented pressure-sensitive adhesive. The functional (exterior) adhesive is on the paper side. For Type III, the backing material consists of an unplasticized polyvinyl chloride film. The tape backing is coated on one side with a pressure sensitive pigmented or unpigmented adhesive which requires no moisture, heat, or other preparation prior to application.

60.3.2 Intended use.

Type I. Type I tape is intended for interior use as an identification medium. In the printed form it may be used for labeling applications, including files, containers of all types, charts, etc. Colored tape, with or without printing can be used for identifying the metal in metal shapes, color coding, etc. It is not recommended for edging purposes.

Type II. Type II tape is suited for edging of documents, maps, charts, etc., to protect the edges from tearing or other damage during handling and storage.

Type III. Type III tape is intended for both interior and exterior identification applications such as air mail tape and other special markings required in packaging. Office use and similar applications. It is not recommended for edging purposes.

60.3.3 Method of application. Tape is applied to clean, dry surface, preferably at 60 to 80 degrees Fahrenheit. Press on firmly, making sure the entire surface of the tape makes good contact.

TYPE I

| Color | Width (inches) | Core (inches) | Length (yds) | Stock Number |
|---|---|---|---|---|
| Transparent | 2 | 3 | 72 | 7510-00-501-6919 |

TYPE II

| Color | Width (inches) | Core (inches) | Length (yuds) | Stock Number |
|---|---|---|---|---|
| White | .375 | 3 | 72 | 7510-00-273-9837 |
| Lt Blue | 1/2 | 3 | 72 | 7510-00-634-2940 |
| White | 1 | 3 | 72 | 7510-00-269-8962 |
| Orange Yellow | 1 | 3 | 72 | 7510-00-234-7973 |
| Black | 1 | 3 | 72 | 7510-00-093-4798 |
| Gray | 1 | 3 | 72 | 7510-00-272-9441 |
| Clear | 1 | 3 | 72 | 7510-00-634-3050 |
| Orange | 2 | 3 | 72 | 7510-00-273-9835 |
| Blue | 2 | 3 | 72 | 7510-00-264-3699 |
| Clear | 3 | 3 | 72 | 7510-00-634-0284 |



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:38Z
Check the source to verify that this is the current version before use.

## 60.4 TAPE, PRESSURE-SENSITIVE ADHESIVE, POLYESTER FILM

L-T-100

60.4.1 Description. A nonhygroscopic solvent-resistant polyester film coated on one side with a solvent resistant water insoluble pressure-sensitive adhesive. Available in two types:

Type I - Transparent
Type II - Colored (gold, silver, or as specified)

60.4.2 Intended use. Type I is to be used where a high degree of resistance to solvents, oils and hydraulic fluids is required. Examples of such applications are in dissimilar metal separation on aircraft and covering of pressure-sensitive identification tapes on fluid lines and wiring harnesses in aircraft and vehicles. It is also recommended for covering of labels on shipping containers where exterior exposure is anticipated. When printed on the adhesive side, this type is intended for use where the printed message must be protected from weathering, solvents and abrasion.

Type II is to be used where a weather resistant, long aging label or decorative striping or color coding is required. For a solvent resistant printed label, Type II, printed and overlaid with Type I, should be used.

60.4.3 Method of application. Apply to a clean, dry surface, press tape firmly, making sure of complete contact.

TYPE I

| Color | Width (inches) | Core (inches) | Length (yds) | Stock number |
|---|---|---|---|---|
| Clear | 1/2 | 3 | 72 | 7510-00-105-3092 |
| Clear | 1/2 | 3 | 72 | 7510-01-011-2484 |
| Clear | 3/4 | 3 | 72 | 7510-00-987-6661 |
| Clear | 1 | 3 | 72 | 7510-00-149-0732 |
| Clear | 1 | 3 | 72 | 7510-00-049-8608 |
| Clear | 1 | 3 | 72 | 7510-01-038-1045 |
| Clear | 1 1/2 | 3 | 72 | 7510-00-721-9756 |
| Clear | 1 1/2 | 3 | 72 | 7510-00-105-3091 |
| Clear | 2 | 3 | 72 | 7510-00-846-8674 |
| Clear | 3 | 3 | 72 | 7510-00-105-3090 |

TYPE II

| Color | Width (inches) | Core (inches) | Length (yds) | Stock Number |
|---|---|---|---|---|
| Silver | .375 | 3 | 72 | 7510-00-838-5222 |
| Silver | .5 | 3 | 72 | 7510-00-827-5700 |
| Silver | 3/4 | 3 | 72 | 7510-00-941-0671 |
| Silver | 1 | 3 | 72 | 7510-01-040-5784 |
| Silver | 1 | 3 | 72 | 7510-01-039-4091 |
| Silver | 1 | 3 | 72 | 7510-00-816-1020 |
| Gold | 1 | 3 | 72 | 7510-00-262-1677 |



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:38Z
Check the source to verify that this is the current version before use.

60.5 INSULATION TAPE, ELECTRICAL, FRICTION

HH-I-510

60.5.1 Description. The tape consists of cotton sheeting impregnated with a tacky adhesive insulating compound which covers both sides evenly. The tape has a dielectric strength of at least 1000 volts.

60.5.2 Intended use. The tape is used for protecting and binding in place insulation applied to joints of electrical wires and cables and for other similar purposes.

60.5.3 Method of application. Press onto a clean, dry surface, then continue to lap onto itself.

| Color | Length (feet) | Width (inches) | Stock Number |
|---|---|---|---|
| Black | 85 | 3/4 | 5970-00-644-3167 |
| Black | 85 | 1 | 5970-00-185-8531 |
| Black | 85 | 1-1/2 | 5970-00-198-8621 |
| Black | 85 | 2 | 5970-00-230-5124 |



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:38Z
Check the source to verify that this is the current version before use.

## 60.6 INSULATION TAPE, ELECTRICAL (RUBBER, NATURAL AND SYNTHETIC)

HH-I-553

### 60.6.1 Description.

Grade A. This grade consists of an unvulcanized self-amalgamating compound of natural rubber, synthetic rubber or a mixture of the two.

Grade B. This grade consists of an unvulcanized or partially vulcanized compound of natural rubber, synthetic rubber of a mixture of the two.

### 60.6.2 Intended use.

Grade A. This grade is ozone resistant, designed primarily for splicing electrical wires and cables operating at high voltages.

Grade B. This grade is not ozone resistant and is used for splicing wires and cables operating at voltages of 600 volts maximum.

GRADE A

| Color | Width (inches) | Length (feet) | Stock Number |
|---|---|---|---|
| Black | 3/4 | 30 | 5970-00-184-2002 |
| | 3/4 | 30 | 5970-00-644-3166 |
| AA | 3/4 | 30 | 5970-00-995-2313 |
| Black | 2 | 15 | 5970-00-681-8236 |
| AA | 2 | 30 | 5970-01-070-9444 |



Source: https://assist.dla.mil -- Downloaded: 202610-26T13:38Z
Check the source to verify that this is the currentversion before use.

## 60.7 INSULATION TAPE, ELECTRICAL, PRESSURE-SENSITIVE ADHESIVE, PLASTIC, FOR LOW-TEMPERATURE APPLICATION

HH-I-595

60.7.1 Description. The tape is made of a pigmented plastic film backing, coated on one side with a pressure-sensitive, water insoluble adhesive, which requires no solvent, heat, or other preparation prior to application.

60.7.2 Intended use. Insulating electrical conductors and splices in electrical wiring, in low-temperature applications (10°F, -12.2°C).

60.7.3 Length, thickness and core size. Unless otherwise specified, the roll contains 36 linear yards of black tape on a 1 inch I.D. core, from 0.006 to 0.011 inch thick, in the widths specified below.

| Color | Width (inches) | Length (yards) | Stock Number |
|---|---|---|---|
| Black | 1/2 | 36 | 5970-00-644-2636 |
| Black | 1/2 | 36 | 5970-00-926-7219 |
| Black | 3/4 | 22 | 5970-00-816-7218 |
| Black | 3/4 | 36 | 5970-00-816-6056 |
| Black | 1 | 36 | 5970-00-926-7220 |



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:38Z
Check the source to verify that this is the current version before use.

## 60.8 TAPE, PRESSURE-SENSITIVE ADHESIVE, PLASTIC (FOR ELECTROPLATING)

HH-T-25

60.8.1 Description. The tape backing is a transparent plastic that is resistant to water and most chemicalsd used in electroplating operations. One side is completely coated with a pressure-sensitive water resistant homogeneous adhesive applied in a smooth layer. The tape is capable of performing satisfactorily in plating baths up to 170°F.

60.8.2 Intended use. The tape is primarily inatended for stop off masking during electroplating operations, including both flat strip and overlapping masks. It may also be used to give abrasion resistance to protect parts during rough handling.

60.8.3 Method of application. Tape is applied to clean, dry surfaced, preferably at 60 to 80 degrees Fahrenheit. Press on firmly, making sure the entire surface of the tape makes good contact.

| Color | Width (inches) | Length (yds) | Core (inches) | Stock Number |
|---|---|---|---|---|
| Natural | 1/2 | 36 | 3 | 7510-00-636-0871 |
| Natural | 3/4 | 36 | 3 | 7510-00-685-5566 |
| Natural | 1 | 36 | 3 | 7510-00-833-7311 |
| Natural | 2 | 36 | 3 | 7510-00-833-7310 |
| Yellow | 1 1/2 | 36 | 3 | 7510-01-030-6800 |
| Yellow | 1 1/2 | 36 | 3 | 7510-01-058-1126 |



Source: https://assist.dla.mil -- Downloaded: 202640-26T13:38Z
Check the source to verify that this is the currentversion before use.

60.9 TAPE, ADHESIVE, LEAD FOIL

HH-T-29

60.9.1 Description. Oil and moisture-resistant, easily molded. Seals out moisture in double-pane windows and in the construction of moisture-proof rooms and buildings. Unaffected by extreme humidity and natural weathering.

60.9.2 Intended use. Effective for hard chromeplating work. Forms tight seal, eliminates "thieving action."

| Color | Width (inches) | Length (yds) | Core (inches) | Stock Number |
|---|---|---|---|---|
| Natural | 1/4 | 36 | 3 | 7510-00-584-5953 |
| Natural | 1/2 | 36 | 3 | 7510-00-530-5511 |
| Natural | 3/4 | 36 | 3 | 7510-00-530-5512 |
| Natural | 1 | 36 | 3 | 7510-00-530-5514 |
| Natural | 1-1/2 | 36 | 3 | 7510-00-841-5394 |
| Natural | 2 | 36 | 3 | 7510-00-664-0001 |



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:38Z
Check the source to verify that this is the current version before use.

## 60.10 TAPE, PRESSURE-SENSITIVE ADHESIVE, DOUBLE COATED

UU-T-91

60.10.1 Description. Available in three types. The tape backing is a transparent film for Type I, an opaque flat stock paper sheeting for Type II and a translucent, porous paper tissue for Type III. The backing is coated on both sides with a water insoluble pressure-sensitive adhesive. Type I, Class 1 and Type II and Type III have an easily removable liner. Type I, Class 2 does not have a liner.

60.10.2 Intended use. Mounting work for photographic reproduction; mounting drawings, plastic, rubber or metal plates, and other uses where two sided adhesion is required.

60.10.3 Method of application. Apply, adhesive side down, to dry, clean surface, preferably at 60 to 80 degrees Fahrenheit. Press tape down firmly, making sure that the entire surface makes contact. Remove liner, to bare opposite side.

TYPE I, CLASS 1

| Color | Width (inches) | Length (yds) | Core (inches) | Stock Number |
|---|---|---|---|---|
| Clear | 1/4 | 26 | 3 | 7510-00-935-4096 |
| Clear | 1/2 | 250 in. | 1 | 7510-01-017-1509 |
| Clear | 1/2 | 36 | 3 | 7510-00-634-1547 |
| Clear | 1/2 | 36 | 3 | 7510-01-058-8037 |
| Clear | 3/4 | 36 | 3 | 7510-00-634-1548 |
| Clear | 1 | 36 | 3 | 7510-00-634-1549 |
| Clear | 2 | 36 | 3 | 7510-00-634-1536 |
| Clear | 2 | 36 | 3 | 7510-01-058-8038 |
| Clear | 3 | 36 | 3 | 7510-00-687-8185 |
| Clear | 4 | 36 | 3 | 7510-01-058-8039 |

TYPE I, CLASS 2

| Color | Width (inches) | Length (yds) | Core (inches) | Stock Number |
|---|---|---|---|---|
| Clear | 1/2 | 36 | 3 | 7510-00-550-7815 |
| Clear | 3/4 | 36 | 3 | 7510-00-904-2663 |
| Clear | 1 | 36 | 3 | 7510-00-550-7814 |



Source: https://assist.dla.mil -- Downloaded: 202640-26T13:38Z
Check the source to verify that this is the currentversion before use.

TYPE II

| Color | Width (inches) | Length (yds) | Core (inches) | Stock Number |
|---|---|---|---|---|
| Natural | 1/4 | 36 | 3 | 7510-00-061-1110 |
| Natural | 1/2 | 36 | 3 | 7510-00-634-1563 |
| Natural | 3/4 | 36 | 3 | 7510-00-634-1564 |
| Natural | 1 | 36 | 3 | 7510-00-634-1565 |
| Natural | 1-1/2 | 36 | 3 | 7510-00-634-3254 |
| Natural | 2 | 36 | 3 | 7510-00-634-1566 |

TYPE III, CLASS 2

| Color | Width (inches) | Length (yds) | Core (inches) | Stock Number |
|---|---|---|---|---|
| A/A | 1-1/2 | 36 | 3 | 7510-00-965-5848 |



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:38Z
Check the source to verify that this is the current version before use.

60.11 TAPE, PRESSURE-SENSITIVE ADHESIVE, PAPER, DRAFTING

UU-T-93

60.11.1 Description. The tape is an opaque creped paper backing coated on one side with a pressure-sensitive adhesive. It is easily removed from drafting and tracing papers.

60.11.2 Intended use. Securing of drawings or tracing paper in drafting operations.

60.11.3 Method of application. Apply to a clean, dry surface, preferably at 60 to 80 degrees Fahrenheit. Press on firmly, making sure that the entire surface of tape makes good contact.

| Width (inches) | Length (yds) | Core (inches) | Stock Number |
|---|---|---|---|
| 3 | 60 | 3 | 7510-01-093-3732 |
| 1 | 60 | 3 | 7510-00-198-5831 |



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:38Z
Check the source to verify that this is the current version before use.

60.12 TAPE, PRESSURE-SENSITIVE ADHESIVE, MASKING, PAPER

UU-T-106

60.12.1 Description. Available in two types. Type I is a creped paper backing which is coated on one side with a pressure-sensitive adhesive. Type II is a flat paper backing which is coated on one side with a pressure-sensitive adhesive.

60.12.2 Intended use. Use with paint, varnish, or other finishing materials to protect surface areas not to be covered by the finishing material. Type I is for use where curved areas are to be masked. Type II is for straight line masking.

60.12.3 Method of application. Apply to clean surface, preferably at 60 to 90 degrees Fahrenheit. Press on firmly, making sure that the entire surface of tape makes good contact.

TYPE II

| Color | Width (inches) | Length (yds) | Core (inches) | Stock Number |
|---|---|---|---|---|
| Natural | 1/2 | 60 | 3 | 7510-01-026-4661 |
| Natural | 1 | 60 | 3 | 7510-01-027-3936 |
| Natural | 2 | 60 | 3 | 7510-01-027-3937 |



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:38Z
Check the source to verify that this is the current version before use.

## 60.13 TAPE, PRESSURE-SENSITIVE ADHESIVE, PAPER, PHOTOGRAPHIC

UU-T-123

60.13.1 Description. A dull, black creped paper coated on one side with a pressure-sensitive adhesive.

60.13.2 Intended use. Photographic work such as edging and blocking out in the development and printing of negatives, sealing cans of photographic film and sealing and repairing camera bellows, darkroom walls, cracks and holes against unwanted light. Also used for binding lantern slides.

60.13.3 Method of application. Apply to a clean, dry surface, preferable at 60 to 80 degrees Fahrenheit. Press firmly, making sure that the entire surface of tape makes good contact.

| Color | Width (inches) | Length (yds) | Core (inches) | Stock Number |
|---|---|---|---|---|
| Black | 1/2 | 60 | 3 | 7510-00-285-2930 |
| Black | 3/4 | 60 | 3 | 7510-00-272-9458 |
| Black | 1 | 60 | 3 | 7510-00-285-2931 |
| Black | 2 | 60 | 3 | 7510-00-728-5755 |



Source: https://assist.dla.mil -- Downloaded: 202610-26T13:38Z
Check the source to verify that this is the current version before use.

60.14 TAPE, PACKAGING/MASKING PAPER

PPP-T-42

60.14.1 Description. This tape consists of paper backing covered on one side with an adhesive that requires no moisture, heat, or other preparation prior to application.

60.14.2 Intended use. Type I tape is primarily intended for light-duty bundling, holding, and packaging applications such as bundling small parts to be overpacked, holding small parts to larger assemblies, and for temporary closing of chipboard boxes and fiberboard boxes that are not to be shipped between bases. This tape is not intended to be a substitute for PPP-T-76, carton sealing tape. Type I tape is also for use in temporarily masking surfaces from being covered by paint, varnish, or other finishing materials. For masking applications, type I is for use on contoured or rounded surfaces. Type II tape is only for use in temporarily masking surfaces from being covered by paint, varnish, or other finishing materials. Type II is for use where straight line color separation is desired.

60.14.3 Method of application. Tape is applied to clean, dry surfaces, preferably at 60 to 80 degrees Fahrenheit. Press on firmly, making sure the entire surface of the tape makes good contact.

| Color | Width (inches) | Length (yds) | Core (inches) | Stock Number |
|---|---|---|---|---|
| Natural | 1/2 | 60 | 3 | 7510-00-266-6714 |
| Natural | 1/2 | 60 | 3 | 7510-00-290-2023 |
| Natural | 1 | 60 | 3 | 7510-00-283-0612 |
| Natural | 1 | 60 | 3 | 7510-00-266-6712 |
| Natural | 1-1/2 | 60 | 3 | 7510-00-290-2027 |
| Opaque | 1-1/2 | 60 | 3 | 7510-00-266-6709 |
| Natural | 2 | 60 | 3 | 7510-00-266-6710 |
| Opaque | 3 | 60 | 3 | 7510-00-266-6694 |
| Natural | 3 | 60 | 3 | 7510-00-266-6707 |



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:38Z
Check the source to verify that this is the current version before use.

## 60.15 TAPE: PRESSURE-SENSITIVE ADHESIVE, WATERPROOF, FOR PACKAGING

PPP-T-60

60.15.1 Description. The materials used in the construction of this tape are such as to insure performance in the temperature range from minus 65 degrees to plus 160 degrees Fahrenheit. The tape is coated on one side with a pressure-sensitive, water insoluble adhesive. Two types and two classes are available:

Type III - Film (polyethylene terephathalate) backings
Class 1 - Colored
Class 2 - Transparent

Type IV - Woven (cotton) cloth backings
Class 1 - Colored

Type III, Class 1 and Type IV, Class 1, colors correspond to color card numbers as specified in Federal Standard 595. Type III, Class 2 tape is sufficiently clear and transparent to allow easy reading of 5 point type when tape is applied directly over it.

60.15.2 Intended use. Packaging and sealing applications, for waterproofing operations where protection to water penetration, and performance at extremely low temperature, are desired.

Type III, Class 1 - Packaging applications where water vaporproofness, high strength, and resistance to exposure to rain, sunlight, and other deteriorating elements are required.

Type III, Class 2 - Attaching, covering, and protecting labels on both interior and exterior containers. May be used for closing and sealing containers where a transparent packaging tape is desirec.

Type IV, Class 1 - Less critical packaging uses where a cloth tape may be desired.

60.15.3 Method of application. Apply to a clean, dry surface at any temperature from minus 65 to plus 160 degrees Fahrenheit. Press on firmly, making sure the entire surface of the tape makes good contact.

TYPE III, CLASS 1

| Color | Width (inches) | Length (yds) | Core (inches) | Stock Numbers |
|---|---|---|---|---|
| Black | 3/8 | 60 | 3 | 7510-00-282-7902 |
| Black | 1/2 | 60 | 3 | 7510-00-282-7901 |
| Olive | 1/2 | 60 | 3 | 7510-00-975-1186 |
| White | 1 | 60 | 3 | 7510-00-663-0198 |
| Black | 1 | 72 | 3 | 7510-00-118-1213 |
| Black | 1 | 60 | 3 | 7510-00-680-2133 |
| Gray | 1 | 60 | 3 | 7510-00-663-9052 |
| Dk Green | 1 | 60 | 3 | 7510-00-269-8088 |



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:38Z
Check the source to verify that this is the current version before use.

TYPE III, CLASS 1 (continued)

| Color | Width (inches) | Length (yds) | Core (inches) | Stock Number |
|---|---|---|---|---|
| Olive | 1 | 60 | 3 | 7510-00-663-0199 |
| Red | 1 | 60 | 3 | 7510-00-266-5008W |
| White | 1-1/2 | 60 | 3 | 7510-00-838-8810 |
| Black | 1-1/2 | 60 | 3 | 7510-00-454-9384 |
| Black | 1-1/2 | 60 | 3 | 7510-00-680-2134 |
| Black | 2 | 60 | 3 | 7510-00-663-0197 |
| Dk Green | 2 | 60 | 3 | 7510-00-269-8090 |
| Olive | 2 | 60 | 3 | 7510-00-663-0196 |
| Red | 2 | 60 | 3 | 7510-00-579-8492 |
| White | 2 | 60 | 3 | 7510-00-663-0195 |
| Brown | 2 | 60 | 3 | 7510-01-017-6140 |
| Tan | 2 | 60 | 3 | 7510-00-079-7906 |
| Olive | 2-1/2 | 60 | 3 | 7510-00-266-5026 |
| Red | 2-1/2 | 60 | 3 | 7510-00-663-3739 |
| Black | 3 | 60 | 3 | 7510-00-663-0194 |
| Olive | 3 | 60 | 3 | 7510-00-663-3738 |
| Red | 3 | 60 | 3 | 7510-00-663-0193 |
| White | 3 | 60 | 3 | 7510-00-266-5039 |
| Tan | 3 | 60 | 3 | 7510-00-079-7905 |
| Black | 3 | 60 | 3 | 7510-00-931-2017 |
| Green | 4 | 60 | 3 | 7510-00-269-8092 |
| Olive | 4 | 60 | 3 | 7510-00-551-1245 |
| Tan | 4 | 60 | 3 | 7510-00-079-7907 |
| Dk Green | 4 | 60 | 3 | 7510-00-269-8091 |
| Green | 6 | 60 | 3 | 7510-00-269-8094 |
| Olive | 6 | 60 | 3 | 7510-00-559-1531 |
| Red | 6 | 60 | 3 | 7510-00-514-3082 |

TYPE III, CLASS 2

| Color | Width (inches) | Length (inches) | Core (inches) | Stock Number |
|---|---|---|---|---|
| Clear | 1/2 | 60 | 3 | 7510-00-266-6716 |
| Clear | 1 | 60 | 3 | 7510-00-663-3732 |
| Clear | 2 | 60 | 3 | 7510-00-266-6715 |
| Clear | 3 | 60 | 3 | 7510-00-281-2700 |
| Black | 4 | 60 | 3 | 7510-00-221-3476 |
| Black | 5 | 60 | 3 | 7510-00-216-5311 |
| Black | 6 | 60 | 3 | 7510-00-221-3478 |

TYPE IV, CLASS 1

| Color | Width (inches) | Length (inches) | Core (inches) | Stock Number |
|---|---|---|---|---|
| O.D. | 1/2 | 60 | 3 | 7510-00-501-6384 |
| Lt Blue | 1 | 60 | 3 | 7510-00-836-0810 |
| Black | 1 | 60 | 3 | 7510-00-074-4960 |
| Gray | 1 | 60 | 3 | 7510-00-789-3368 |
| Green | 1 | 60 | 3 | 7510-00-074-5122 |
| O.D. | 1 | 60 | 3 | 7510-00-890-9872 |

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:38Z
Check the source to verify that this is the current version before use.

TYPE IV CLASS 1 (continued)

| Color | Width (inches) | Length (yds) | Core (inches) | Stock Number |
|---|---|---|---|---|
| Red | 1 | 60 | 3 | 7510-00-074-4966 |
| White | 1 | 60 | 3 | 7510-00-074-4946 |
| White | 1-1/2 | 60 | 3 | 7510-01-043-2297 |
| O.D. | 1-1/2 | 60 | 3 | 7510-00-501-6383 |
| O.D. | 2 | 10 | 1.062 | 7510-00-104-9741 |
| O.D. | 2 | 10 | 1.062 | 7510-00-926-9186 |
| Gray | 2 | 60 | 3 | 7510-00-501-6373 |
| O.D. | 2 | 60 | 3 | 7510-01-266-5016 |
| Red | 2 | 60 | 3 | 7510-00-026-1690 |
| Black | 2 | 60 | 3 | 7510-00-074-4961 |
| Green | 2 | 60 | 3 | 7510-00-074-5124 |
| Red | 2 | 60 | 3 | 7510-00-074-4969 |
| White | 2 | 60 | 3 | 7510-00-074-4952 |
| O.D. | 2-1/2 | 60 | 3 | 7510-00-074-5100 |
| Black | 2-1/2 | 60 | 3 | 7510-00-074-4962 |
| Dk Green | 2-1/2 | 60 | 3 | 7510-00-074-5157 |
| Red | 2-1/2 | 60 | 3 | 7510-00-074-4978 |
| White | 2-1/2 | 60 | 3 | 7510-00-074-4953 |
| Olive | 3 | 60 | 3 | 7510-00-890-9874 |
| Black | 3 | 60 | 3 | 7510-00-074-4963 |
| Dk Green | 3 | 60 | 3 | 7510-00-074-5160 |
| Red | 3 | 60 | 3 | 7510-00-074-4996 |
| White | 3 | 60 | 3 | 7510-00-074-4954 |
| Black | 4 | 60 | 3 | 7510-00-074-4964 |
| Green | 4 | 60 | 3 | 7510-00-074-5174 |
| O.D. | 4 | 60 | 3 | 7510-00-890-9875 |
| Red | 4 | 60 | 3 | 7510-00-074-5029 |
| White | 4 | 60 | 3 | 7510-00-074-4955 |
| Black | 6 | 60 | 3 | 7510-00-074-4965 |
| Green | 6 | 60 | 3 | 7510-00-074-5178 |
| O.D. | 6 | 60 | 3 | 7510-00-074-9876 |
| Red | 6 | 60 | 3 | 7510-00-074-5058 |
| White | 6 | 60 | 3 | 7510-00-074-4957 |



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:38Z
Check the source to verify that this is the current version before use.

60.16 TAPE: PRESSURE-SENSITIVE ADHESIVE, VINYL PLASTIC FILM

PPP-T-66

60.16.1 Description. A plastic film pressure-sensitive adhesive tape. The backing materials consists of modified polyvinyl chloride or polyvinyl chloride-vinyl acetate film. The backing is coated on one side with a water insoluble pressure-sensitive adhesive. The following classes and types are furnished.

Type I - General purpose
Class 1 - Transparent
Class 2 - Colored (Blue, green, yellow, orange, red, brown, black, white or other commercially available colors)

Type II - Printable (white or yellow)

60.16.2 Intended use. Both Type I and Type II tapes can be used for sealing out moisture and applications requiring the flexibility, toughness, conformability, and resistance to sunlight, salts, water, oil, solvents, acids, alkalis, abrasives, and other properties normally possessed by a plasticized vinyl film. Some typical applications are as follows:

a. Sealing screw caps, stoppers, or slip cover closures of plastic, metal, glass, or combinations thereof. The tape widths recommended are 3/4 and 1 inch.

b. Lane marking stripping materials for designating traffic aisles, loading and storage areas, etc. The tape widths recommended are 2 and 3 inches.

c. Sealing openings such as examination ports in dehydrated containers or openings on mechanical equipment.

d. Protection of pipe not buried underground from corrosion by moisture, acids, alkalis, and salts.

e. Color code identification of pipelines, e.g., steam lines and water lines.

f. For sealing photographic film cans and magazines, use Type I, class 2, black.

g. Printed Type II tape is suitable for use on the applications mentioned in a, c, e, and other similar applications where a printed legend and the properties of a vinyl plastic tape are required.

60.16.3 Method of application. Apply to clean, dry surface. Press firmly, making sure that the entire surface of tape makes good contact.



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:38Z
Check the source to verify that this is the current version before use.

TYPE I, CLASS 1

| Color | Width (inches) | Length (yds) | Core (inches) | Stock Number |
|---|---|---|---|---|
| Clear | 3/4 | 36 | 3 | 7510-00-634-2951 |
| Clear | 1 | 36 | 3 | 7510-00-515-2856 |
| Clear | 1 | 36 | 3 | 7510-00-246-9934 |
| Clear | 1-1/2 | 36 | 3 | 7510-00-634-3285 |
| Clear | 2 | 83 1/3 | 3 | 7510-00-142-9813 |
| Clear | 3 | 36 | 3 | 7510-00-634-3211 |

TYPE I, CLASS 2

| Color | Width (inches) | Length (yds) | Core (inches) | Stock Number |
|---|---|---|---|---|
| Black | 1/4 | 36 | 3 | 7510-00-634-1334 |
| Blue | 1/4 | 36 | 3 | 7510-00-634-2786 |
| Brown | 1/4 | 36 | 3 | 7510-00-634-2787 |
| Canary yellow | 1/4 | 36 | 3 | 7510-00-634-2788 |
| Green | 1/4 | 36 | 3 | 7510-00-634-1341 |
| Orange | 1/4 | 36 | 3 | 7510-00-634-2789 |
| Red | 1/4 | 36 | 3 | 7510-00-634-2790 |
| White | 1/4 | 36 | 3 | 7510-00-634-2791 |
| Blue | 1/2 | 36 | 3 | 7510-00-474-7023 |
| Yellow | 1/2 | 36 | 3 | 7510-00-926-2033 |
| Red | 1/2 | 36 | 3 | 7510-00-105-0645 |
| White | 1/2 | 36 | 1 | 7510-00-836-9899 |
| Yellow | 1/2 | 36 | 1 | 7510-00-836-9903 |
| Orange | 1/2 | 36 | 3 | 7510-01-045-5866 |
| Black | 3/4 | 36 | 3 | 7510-00-634-2802 |
| Red | 3/4 | 36 | 3 | 7510-00-634-2951 |
| Yellow | 3/4 | 36 | 3 | 7510-00-664-0472 |
| Red | 1/2 | 36 | 3 | 7510-00-149-1951 |
| Brown | 1/2 | 36 | 3 | 7510-00-079-7873 |
| Blue | 1/2 | 36 | 3 | 7510-00-079-7871 |
| Yellow | 1 | 36 | 1 | 7510-00-664-0473 |
| Brown | 1 | 36 | 3 | 7510-00-836-9901 |
| Brown | 1 | 36 | 3 | 7510-01-020-8769 |
| Blue | 1 | 36 | 3 | 7510-00-634-2943 |
| Black | 1 | 36 | 3 | 7510-00-634-2946 |
| Yellow | 1 | 36 | 1 | 7510-00-634-0828 |
| Blue | 1 | 36 | 3 | 7510-00-634-2943 |
| Black | 1 | 36 | 3 | 7510-00-634-2946 |
| Red | 1 | 36 | 3 | 7510-00-664-2941 |
| White | 1 | 36 | 3 | 7510-00-043-5024 |
| Yellow | 1-1/4 | 36 | 3 | 7510-00-664-0474 |
| Green | 1-1/2 | 60 | 3 | 7510-00-839-0904 |
| Yellow | 1-1/2 | 36 | 3 | 7510-00-634-3292 |
| Red | 1-1/2 | 36 | 3 | 7510-00-634-3293 |
| Orange | 1-1/2 | 36 | 3 | 7510-00-634-3286 |
| Brown | 1-1/2 | 36 | 3 | 7510-00-634-3287 |
| Green | 1-1/2 | 36 | 3 | 7510-00-634-3288 |
| Blue | 1-1/2 | 36 | 3 | 7510-00-634-3289 |



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:38Z
Check the source to verify that this is the current version before use.

TYPE I, CLASS 2 (continued)

| Color | Width (inches) | Length (yds) | Core (inches) | Stock Number |
|---|---|---|---|---|
| Black | 1-1/2 | 36 | 3 | 7510-00-634-3290 |
| Green | 1-1/2 | 60 in. | 3 | 7510-00-839-0899 |
| Brown | 2 | 36 | 3 | 7510-00-355-7154 |
| Olive | 2 | 36 | 3 | 7510-00-145-0002 |
| Black | 2 | 34 | 3 | 7510-00-880-7351 |
| Green | 2 | 36 | 3 | 7510-00-220-3803 |
| White | 2 | 36 | 3 | 7510-00-181-7398 |
| Orange | 2 | 36 | 3 | 7510-00-634-3331 |
| Green | 2 | 36 | 3 | 7510-00-634-3332 |
| Blue | 3 | 36 | 3 | 7510-00-850-5079 |
| Green | 3 | 36 | 3 | 7510-00-778-6383 |
| White | 3 | 36 | 3 | 7510-01-017-7880 |
| Brown | 3 | 36 | 3 | 7510-00-850-5078 |
| Yellow | 3 | 36 | 3 | 7510-00-850-5077 |
| Orange | 3 | 36 | 3 | 7510-00-634-3215 |
| White | 3 | 36 | 3 | 7510-00-634-3210 |
| Green | 3 | 36 | 3 | 7510-00-634-3216 |
| Black | 3 | 36 | 3 | 7510-00-634-3226 |
| Yellow | 4 | 36 | 3 | 7510-00-134-8830 |

TYPE II

| Color | Width (inches) | Length (yds) | Core (inches) | Stock Number |
|---|---|---|---|---|
| Yellow | 1-1/2 | 36 | 3 | 7510-00-472-3268 |
| White | 2 | 36 | 3 | 7510-00-829-1239 |
| Yellow | 6 | 36 | 3 | 7510-00-066-8555 |



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:38Z
Check the source to verify that this is the current version before use.

60.17 TAPE, PACKAGING, PLASTIC FILM

PPP-T-70

60.17.1 Description. This is a plastic film backed adhesive tape.

60.17.2 Intended use. The tape is intended for the closure and sealing of interior and exterior domestic containers. Printed on the adhesive side in an appropriate manner and supplier on a liner, it may be used as a packing list enclosure. It also is intended for label attaching and as a label covering material to protect labels from moisture and weathering. It is ideal for miscellaneous holding and sealing applications where a transparent, water-resistant, weather-resistant material is desired.

| Color | Width (inches) | Length (yds) | Core (inches) | Stock Number |
|---|---|---|---|---|
| Clear | 1/2 | 72 | 3 | 7510-00-995-0453 |
| Clear | 3/4 | 72 | 3 | 7510-00-995-0454 |
| Clear | 1 | 72 | 3 | 7510-00-995-0455 |
| Clear | 4 | 72 | 3 | 7510-00-073-6094 |
| Clear | 5 | 72 | 3 | 7510-00-073-6095 |
| Clear | 6 | 72 | 3 | 7510-00-073-6096 |



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:38Z
Check the source to verify that this is the current version before use.

## 60.18 TAPE, PRESERVATION AND SEALING

PPP-T-75

60.18.1 Description. The adhesive for both Types I and II is pressure-sensitive, water insoluble and requires no solvent, moisture, heat, or other preparation prior to or after application to clean, dry surfaces. The backing for Type II is a single ply of plastic film.

60.18.2 Intended use. Type I tape is intended primarily for use in the preservation and sealing of military vehicles, aircraft, missiles, and other related equipment where a water vapor proof seal, excellent conformability to irregular surfaces, oil resistance, and clean removability after short, medium and long term outdoor aging is required. Type II tape is intended for use in the preservation and sealing of the same type of military equipment as type I tape. It is intended for use in less critical applications which require a water vapor resistant seal, good conformability to irregular surfaces, and clean removability after short, medium, or long term aging.

60.18.3 Method of application. When applying type I tape, it is recommended that a plastic squeegee applicator be used to obtain an optimum bond between the type and the applied surface. Type I tape can be applied in a temperature range of 0°C (+32°F) to +50°C (122°F) and will perform in a temperature range of -54°C (-65.2°F) +60°C (+140°F). Dut to its elastic characteristics, type II tape should always be applied in its released state to eliminate any unnecessary shear forces caused by stretching of the backing. Type II tape can be applied and will perform in the same teperature range as type I tape.

| Color | Width (inches) | Length (yds) | Core (inches) | Stock Number |
|---|---|---|---|---|
| Black | 1 | 60 | 3 | 7510-00-926-8738 |
| Black | 2 | 60 | 3 | 7510-00-914-1614 |
| Black | 3 | 60 | 3 | 7510-00-926-8939 |
| Black | 6 | 60 | 3 | 7510-00-926-8941 |



Source: https://assist.dla.mil -- Downloaded: 202610-26T13:38Z
Check the source to verify that this is the currentversion before use.

60.19 TAPE, PRESSURE-SENSITIVE ADHESIVE PAPER (FOR CARTON SEALING)

PPP-T-76

60.19.1 Description. The tape consists of 100 percent sulphate kraft paper, treated to resist water, coated on one side with a pressure-sensitive, water resistant homogeneous adhesive. The tape performs adequately over the temperature range of -54° to 71° centigrade (-65° to 160° Fahrenheit). Unless otherwise specified, the color of the tape is that of unbleached kraft paper.

60.19.2 Intended use. To be used in packaging and packing and is adapeted for closing and sealing fiberboard containers.

60.19.3 Method of application. Apply to a clean, dry surface, preferably at 50 to 80 degrees Fahrenheit, press on firmly, making sure that the entire surface of tape makes good contact.

| Color | Width (inches) | Length (yds) | Core (inches) | Stock Number |
|---|---|---|---|---|
| Tan | 3/4 | 120 | 3 | 7510-00-656-0467 |
| Natural | 1 | 120 | 3 | 7510-00-810-0468 |
| Natural | 2 | 120 | 3 | 7510-00-297-6655 |
| Natural | 3 | 120 | 3 | 7510-00-297-6656 |



Source: https://assist.dla.mil -- Downloaded: 202640-26T13:38Z
Check the source to verify that this is the current version before use.

60.20 TAPE, PRESSURE-SENSITIVE ADHESIVE, FILAMENT REINFORCED (FSC 8135)

PPP-T-97

60.20.1 Description. A backing material, reinforcing filaments, and a pressure-sensitive adhesive. Available in four types and two classes.

Type I - Low tensile strength

Type II - Medium tensile strength
Class A - Opaque
Class B - Transparent

Type III - High tensile strength

Type IV - High tensile strength, weather resistant

The color of Types I, II Class A, and III is as manufactured except that in no case shall the color be black. Type II, Class B is sufficiently transparent to allow reading of 10 point type when tape is applied over it. Type IV is black.

60.20.2 Intended use. For closing and reinforcing containers, for bundling, for holding, for unitizing, and for other applications requiring a strong, flexible pressure-sensitive adhesive tape. Type II is intended for carton closure, shortstrip reinforcing, holding, and bundling. The Type II, Class B which is transparent should be used where there is a possibility that the tape will cover identification markings. Type III is intended for applications where high strength is required such as for bundling, palletizing, unitizing, and closing of triple wall containers. Type I should be used in place of Type II when severe abrasion of the tape may be encountered. Type IV is recommended for all uses where extensive exterior exposure is anticipated.

60.20.3 Method of application. Press tape firmly making sure it makes complete contact.

TYPE I

| Color | Width (inches) | Length (yds) | Core (inches) | Stock Number |
|---|---|---|---|---|
| AA | 1/2 | 60 | 3 | 7510-00-290-8034 |
| Natural | 1 | 60 | 3 | 7510-00-290-8036 |

TYPE II, CLASS B

| Color | Width (inches) | Length (yds) | Core (inches) | Stock Number |
|---|---|---|---|---|
| AA | 1/2 | 60 | 3 | 7510-00-582-4771 |
| AA | 1 | 60 | 3 | 7510-00-582-4772 |
| AA | 3/4 | 60 | 3 | 7510-00-802-8311 |
| AA | 2 | 60 | 3 | 7510-00-228-0535 |
| AA | 2 | 60 | 3 | 7510-00-159-4450 |
| AA | 2 | 60 | 3 | 7510-01-026-1649 |
| AA | 3 | 60 | 3 | 7510-01-023-8545 |



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:38Z
Check the source to verify that this is the current version before use.

TYPE III

| Color | Width (inches) | Length (yds) | Core (inches) | Stock Number |
|---|---|---|---|---|
| AA | 1/2 | 60 | 3 | 7510-00-526-6658 |
| AA | 1 | 72 | 3 | 7510-00-285-2021 |

TYPE IV

| Color | Width (inches) | Length (yds) | Core (inches) | Stock Number |
|---|---|---|---|---|
| Black | 1/2 | 60 | 3 | 7510-00-584-5838 |
| AA | 1 | 60 | 3 | 7510-00-053-0942 |
| AA | 1-1/4 | 60 | 3 | 7510-00-952-7212 |
| Black | 2 | 60 | 3 | 7510-00-427-2568 |



Source: https://assist.dla.mil -- Downloaded: 202610-26T13:38Z
Check the source to verify that this is the current version before use.

60.21 TAPES FROM INSULATION CLOTH AND TAPE, ELECTRICAL, VARNISHED CAMBRIC

MIL-I-3374

60.21.1 Description. The base material is a closely and uniformly woven cotton material with a varnish coating.

60.21.2 Intended use. This insulation tape is intended for repair and maintenance.

TYPE II, CLASS 1

| Color | Width (inches) | Thickness | Length (ft) | Stock Number |
|---|---|---|---|---|
| Yellow | 1/2 | 6 mil | 25 | 5970-00-889-4079 |
| Yellow | 1/2 | 7 mil | 106 | 5970-00-238-4621 |
| Black | 1/2 | 6 mil | 25 | 5970-00-681-9605 |
| Yellow | 3/4 | 7 mil | 216 | 5970-00-222-6383 |
| Yellow | 3/4 | 10 mil | 106 | 5970-00-238-4624 |
| - | 3/4 | 7 mil | 106 | 5970-00-188-4615 |
| Yellow | 1 | 7 mil | 216 | 5970-00-222-6384 |
| - | 1 | 10 mil | 106 | 5970-00-222-6375 |
| Yellow | 1 | 10 mil | 216 | 5970-00-199-2997 |
| Yellow | 1 1/4 | 7 mil | 216 | 5970-00-222-6385 |
| - | 1 1/4 | 10 mil | 106 | 5970-00-222-6377 |
| Yellow | 1 1/2 | 10 mil | 216 | 5970-00-199-2999 |



Source: https://assist.dla.mil -- Downloaded: 202610-26T13:38Z
Check the source to verify that this is the current version before use.

60.22 INSULATION TAPE, ELECTRICAL, SELF-FUSING; FOR USE IN ELECTRONIC, COMMUNICATIONS, AND ALLIED EQUIPMENT

MIL-I-3825

60.22.1 Description. The tape is a soft, self-fusing, hand-splicing, ozone resistant electrical insulating tape with an average dielectric strength of 800 volts per mil. The tape is suitable for use at temperatures from -67 degrees to 140 degrees Fahrenheit. Self-fusion is accomplished without the addition of an adhesive to any surface of the tape. It may require protection by wrapping a more abrasion-resistant tape over the self-fusing tape. Available in black, white, or non-pigmented.

60.22.2 Intended use. Used for repairing and splicing wire and cable, including polyethylene-insulated wire and cable, in electronic, communications and allied equipment. Will provide a tight, form-fitting, high-grade insulation for bare wires and irregular shapes.

60.22.3 Method of application. Stretch a piece of the tape to double its original length and, using a steady pull, apply to dry surfaces to be repaired or spliced.

| Color | Thickness (inches) | Width (inches) | Length (ft) | Stock Number |
|---|---|---|---|---|
| Black | .02 | 3/4 | 30 | 5970-00-685-9059 |
| White | .02 | 3/4 | 30 | 5970-00-240-0620 |
| Black | .02 | 3/4 | 30 | 5970-00-240-0617 |
| Black | .02 | 1 | 30 | 5970-00-547-0966 |



Source: https://assist.dla.mil -- Downloaded: 202610-26T13:38Z
Check the source to verify that this is the current version before use.

60.23 TAPE, PRESSURE-SENSITIVE, ADHESIVE (CORROSION RESISTANT)

MIL-T-4053

60.23.1 Description. A high grade, plain weave glass cloth coated on one side with a pressure-sensitive, thermosetting adhesive. The tape does not cause corrosion.

60.23.2 Intended use. Sealing joints in low pressure, hot-air ducts where the temperature does not exceed 350 degrees Fahrenheit.

60.23.3 Method of application. Apply to clean, dry surface, preferably at 60 to 80 degrees Fahrenheit. Press on firmly, making sure that the entire surface of the tape makes good contact.

| Color | Width (inches) | Length (yds) | Core (inches) | Stock Number |
|---|---|---|---|---|
| Natural | 1 | 60 | 3 | 7510-00-530-6375 |
| Natural | 2 | 60 | 3 | 7510-00-515-0319 |



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:38Z
Check the source to verify that this is the current version before use.

## 60.24 INSULATION TAPE, ELECTRICAL, PRESSURE-SENSITIVE ADHESIVE, PLASTIC

MIL-I-7798 (see also MIL-I-24391)
(Use MIL-I-24391 when supplies are exhausted)

60.24.1 Description. An elastomeric film backing of plastic such as polyvinyl chloride or its copolymers, coated on one side with a pressure-sensitive adhesive. Available in black, yellow with transparent backing or yellow with opaque backing.

60.24.2 Intended use. Suitable for use in applications requiring high electrical resistance, such as the insulation of electical conductors and splices in electrical wiring. Available for either hand taping or machine application.

60.24.3 Method of application. Start on outer electrical insulating portion of the wire or cable and wrap the tape circumferentially with an approximate 50 percent overlap until all the bare conductor is safely covered. A slight tension should be exerted on the tape during the wrapping while bringing a force toward the center of the wire or cable. Make sur that the entire surface of the tape makes good contact.

| Color | Thickness | Width (inches) | Length (feet) | Stock Number |
|---|---|---|---|---|
| Black | 7 mil | .375 | 108 | 5970-00-802-6893 |
| Black | 7 mil | .75 | 108 | 5970-00-644-3169 |
| Black | 10 mil | .75 | 108 | 5970-00-188-5477 |
| Yellow Opaque | 7 mil | 1 | 108 | 5970-00-660-91790 |



Source: https://assist.dla.mil -- Downloaded: 202640-26T13:38Z
Check the source to verify that this is the current version before use.

60.2 INSULATION TAPE, ELECTRICAL, PRESSURE-SENSITIVE ADHESIVE AND PRESSURE SENSITIVE THERMOSETTING ADHESIVE

MIL-I-15126

60.25.1 Description. Pressure-sensitive adhesive and pressure-sensitive thermosetting adhesive electrical insulation tapes. Available in the following types:

Type AFT - Acetate film backing, thermosetting adhesive.

Type ACT - Acetate cloth backing, thermosetting adhesive.

Type CFT - Cotton fabric backing, thermosetting adhesive.

Type GFT - Glass fabric backing, thermosetting adhesive.

Type PCT - Paper backing-crepe, thermosetting adhesive.

Type PFT - Paper backing-flat, thermosetting adhesive.

Type EF-7 - Polyethylene backing, pressure-sensitive adhesive.

Type EF-9 - Polyethylene backing, pressure-sensitive adhesive.

Type EF-20 - Polyethylene backing, pressure-sensitive adhesive.

Type MFT-2.5 - Polyethylene terephthalate film backing, thermosetting adhesive.

Type MF-2.5 - Polyethylene terephthalate film backing, pressure-sensitive adhesive.

Type MFT-3.5 - Polyethylene terephthalate film backing, thermosetting adhesive.

60.25.2 Intended use. Construction and repair of electrical and electronic equipment.

Type AFT is used for internal coil applications and other uses requiring high dielectric strength, good insulation resistance and good moisture resistance.

Type ACT is used in all types of fine wire coils and transformers where good strength characteristics, fine electrical properties and non-corrosiveness are desired.

Type CFT is uses for small motors, dynamotor armatures, generators and transformer coils where good varnish penetration and high tensile strength are desired.

Type GFT is used in high heat locations where other adhesive tapes cannot be used.

Types PCT and PFT are used for motor insulating, coil winding, repair of electric motors and reinforcing slot insulation.



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:38Z
Check the source to verify that this is the current version before use.

Types EF-7, EF-9, and EF-20 are used where high dielectric strength and non-corrosiveness are desired.

Types MFT-2.5, MF-2.5, and MFT-3.5 are suitable for internal coil applications and other uses requiring high dielectric strength, good insulation and moisture resistance. They are suitable for use at higher temperatures than Type AFT.

60.24.3 Method of application. Tape is applied to clean, dry surface, preferably at 60 to 80 degrees Fahrenheit. Press on firmly, making sure the entire surface of the tape makes good contact.

TYPE CFT

| Color | Length (ft) | Nominal Thickness | Width (inches) | Stock Number |
|---|---|---|---|---|
| - | 180 | 10.5 mil | .5 | 5970-00-246-5310 |
| White | 180 | 10.5 mil | .75 | 5970-00-538-5843 |
| - | 180 | 10.0 mil | 1 | 5970-00-257-2973 |

TYPE GFT

| Color | Length (ft) | Nominal Thickness | Width (inches) | Stock Number |
|---|---|---|---|---|
| - | 180 | 7 mil | .5 | 5970-00-840-6695 |
| AA | 180 | 7 mil | .625 | 5970-00-403-8225 |
| White | 180 | 7 mil | .75 | 5970-00-284-8565 |
| White | 180 | 7 mil | 1 | 5970-00-686-9151 |
| - | 180 | 7 mil | 1 | 5970-00-840-6697 |
| White | 180 | 7 mil | 2 | 5970-00-568-0543 |
| White | 180 | 7 mil | 6 | 5970-00-113-0913 |

TYPE PFT

| Color | Length (ft) | Nominal Thickness | Width (inches) | Stock Number |
|---|---|---|---|---|
| Yellow | 180 | 6 mil | .5 | 5970-00-825-8971 |
| AA | 180 | 6 mil | .5 | 5970-00-503-2423 |

TYPE ACT

| Color | Length (ft) | Nominal Thickness | Width (inches) | Stock Number |
|---|---|---|---|---|
| Black | 216 | 8 mil | .625 | 5970-00-137-9501 |

TYPE EF7

| Color | Length (ft) | Nominal Thickness | Width (inches) | Stock Number |
|---|---|---|---|---|
| Black | 216 | 8 mil | .5 | 5970-00-306-9483 |
| - | 216 | 8 mil | .5 | 5970-00-538-5844 |
| White | 216 | 8 mil | .75 | 5970-00-295-8161 |



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:38Z
Check the source to verify that this is the current version before use.

TYPE EF9 mil

| Color | Length (ft) | Nominal Thickness | Width (inches) | Stock Number |
|---|---|---|---|---|
| Black | 108 | 9 mil | .75 | 5970-00-636-2549 |
| Black | 54 | 9 mil | 1 | 5970-00-583-6097 |

TYPE MF2.5

| Color | Length (ft) | Nominal Thickness | Width (inches) | Stock Number |
|---|---|---|---|---|
| Natural | 216 | 2.5 mil | .625 | 5970-00-070-1187 |
| Orange | 216 | 2.5 mil | .625 | 5970-01-044-4181 |
| AA | 216 | 2.5 mil | .75 | 5970-00-837-3765 |
| Yellow | 216 | 2.5 mil | .937 | 5970-00-116-3957 |
| - | 216 | 2.5 mil | 1 | 5970-00-739-7842 |
| AA | 216 | 2.5 mil | 1 | 5970-00-837-3764 |
| Yellow | 216 | 2.5 mil | 1.188 | 5970-00-080-9524 |
| AA | 216 | 2.5 mil | 1.25 | 5970-00-007-5272 |
| Yellow | 216 | 2.5 mil | 1.5 | 5970-00-606-4892 |
| - | 216 | 2.5 mil | 2 | 5970-00-344-2489 |
| AA | 216 | 2.5 mil | 3 | 5970-00-881-3657 |
| AA | 216 | 2.5 mil | 5 | 5970-00-897-8983 |

TYPE MFT 3.5

| Color | Length (ft) | Nominal Thickness | Width (inches) | Stock Number |
|---|---|---|---|---|
| Clear | 216 | 3.5 mil | .75 | 5970-00-478-0045 |
| Orange | 216 | 3.5 mil | .75 | 5970-00-439-8844 |
| AA | 216 | 3.5 mil | 1 | 5970-00-754-9362 |
| Unpigmented | 216 | 3.5 mil | 1 | 5970-00-139-5205 |
| Yellow | 216 | 3.5 mil | 1 | 5970-00-926-2510 |
| AA | 216 | 3.5 mil | 1.125 | 5970-00-969-6337 |
| - | 216 | 3.5 mil | 1.5 | 5970-00-930-0224 |
| AA | 216 | 3.5 mil | 2.5 | 5970-00-480-1328 |

Other

| Color | Length (ft) | Nominal Thickness | Width (inches | Stock Number |
|---|---|---|---|---|
| Black | 216 | 4 mil | 1 | 5970-00-930-0225 |
| - | 216 | 3 mil | 1.5 | 5970-00-232-6333 |
| - | 216 | 3 mil | 1.5 | 5970-00-495-1196 |



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:38Z
Check the source to verify that this is the current version before use.

60.26 INSULATION TAPE, ELECTRICAL, HIGH TEMPERATURE, GLASS FIBER, PRESSURE SENSITIVE

MIL-I-19166

60.26.1 Description. This specification covers glass fiber, silicone adhesive, pressure-sensitive tape for construction and repair of electrical equipment operating at high temperatures. The tape consists of glass fiber textile fabricated from continuous filament yarn, and is coated on one side with a silicone prssure-sensitive adhesive. It is natural in color.

60.26.2 Intended use. Principally for securing coils and electric windings where tape having good high-temperature-resistant adhesive and backing is required.

| Width (inches) | Length (feet) | Thickness | Stock Number |
|---|---|---|---|
| .25 | 108 | 7 mil | 5970-00-933-1406 |
| .375 | 108 | 10 mil | 5970-00-880-9942 |
| .5 | 108 | 7 mil | 5970-00-180-6087 |
| .5 | 108 | 10 mil | 5970-00-231-8456 |
| .625 | 108 | 7 mil | 5970-00-709-0045 |
| .75 | 108 | 7 mil | 5970-00-543-1597 |
| .75 | 108 | 10 mil | 5970-00-877-8591 |
| 1 | 108 | 7 mil | 5970-01-049-9571 |
| 1 | 108 | 10 mil | 5970-00-612-8492 |
| 1.5 | 108 | 10 mil | 5970-00-583-9528 |
| 3 | 108 | 10 mil | 5970-00-814-9606 |



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:38Z
Check the source to verify that this is the current version before use.

## 60.27 TAPE, PRESSURE SENSITIVE ADHESIVE, PAPER, MASKING, NONSTAINING

MIL-T-21595

60.27.1 Description. A green paper backing, coated on one side with a 8ater insoluble, pressure sensitive adhesive. Available in two types.

Type I - Creped

Type II - Flat

60.27.2 Intended use. Masking surfaced where a nonstaining character is desired for use in the protection of aircraft surfaces from acrylic-nitro-cellulose lacquer, acrylic lacquer, and epoxy-polyamide coating finishing materials.

60.27.3 Method of application. Apply to clean, dry surface, press tape firmly making sure it makes complete contact preferably at temparatures of 60 to 80 degrees Fahrenheit.

TYPE I

| Color | Width (inches) | Length (yds) | Core (inches) | Stock Number |
|---|---|---|---|---|
| Green | 1/2 | 60 | 3 | 7510-00-680-2450 |
| Green | 3/4 | 60 | 3 | 7510-00-680-2470 |
| Green | 1 | 60 | 3 | 7510-00-685-4963 |
| Green | 1-1/2 | 60 | 3 | 7510-00-684-8784 |
| Green | 2 | 60 | 3 | 7510-00-680-2395 |
| Green | 3 | 60 | 3 | 7510-00-680-2471 |



Source: https://assist.dla.mil -- Downloaded: 202640-26T13:38Z
Check the source to verify that this is the currentversion before use.

## 60.28 TAPES, PRESSURE-SENSITIVE ADHESIVE, PRESERVATION AND SEALING

MIL-T-22085

60.28.1 Description. A backing coated on one side with a water insoluble pressure-sensitive adhesive. Available in two types.

Type I - Oil and weather resistant (for application to irregular and flat surfaces)

Type II - Weather resistant (for application to non-oil contaminated flat surfaces)

This tape will perform in a temperature range of minus 65 to plus 125 degrees Fahrenheit. The color is black or natural.

60.28.2 Intended use. The protection of aircraft, missiles and rockets during storage, handling and shipment. It is suitable for application at 32 degrees Fahrenheit. Also to be used for exterior preservation and sealing. Type II tape should not be used on surfaces which are or may become oil contaminated. Type I may be used as a Type II; however, Type II may not be used as a Type I tape.

60.28.3 Method of application. Press tape firmly making sure it makes complete contact.

TYPE I

| Color | Width (inches) | Length (yds) | Core (inches) | Stock number |
|---|---|---|---|---|
| Black | AA | 36 | 3 | 7510-01-019-9491 |
| Black | 1 | 60 | 3 | 7510-00-926-8938 |
| Black | 2 | 60 | 3 | 7510-00-914-1613 |
| Black | 3 | 60 | 3 | 7510-00-926-8939 |
| Black | 4 | 60 | 3 | 7510-00-926-8940 |
| Black | 6 | 60 | 3 | 7510-00-926-8941 |

TYPE II

| Color | Width (inches) | Length (yds) | Core (inches) | Stock number |
|---|---|---|---|---|
| AA Opaque Black or Yellow | 1 | 36 | 3 | 7510-00-852-8179 |
| | 1 | 36 | 3 | 7510-00-117-5519 |
| Opaque | 2 | 36 | 3 | 7510-00-852-8180 |
| Black | 2 | 36 | 3-1/4 | 7510-00-117-5520 |
| Opaque | 3 | 36 | 3 | 7510-00-059-9062 |
| Black | 3 | 36 | 3-1/4 | 7510-00-117-5523 |
| Aluminum | 4 | 36 | 3 | 7510-00-916-9659 |



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:38Z
Check the source to verify that this is the current version before use.

## 60.29 INSULATION TAPE, ELECTRICAL, SELF-BONDING

MIL-I-22444

60.29.1 Description. Tape consists of bias sinusoidal woven glass cloth backing, the weave of which has been filled and coated uniformly on both sides.

60.29.2 Intended use. Tape is suitable as an insulation and binder in making splices in shipboard power and control cables.

| Width (inches) | Thickness | Length (yds) | Stock Number |
|---|---|---|---|
| .5 | 18 mil | 20 | 5970-00-446-8928 |
| 1 | 18 mil | 20 | 5970-00-841-1172 |



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:38Z
Check the source to verify that this is the current version before use.

60.30 TAPE, PRESSURE-SENSITIVE ADHESIVE, FOR DISSIMILAR METAL SEPARATION

MIL-T-23142

60.30.1 Description. A non-corrosive material coated on one side with a water insoluble, pressure-sensitive adhesive.

60.30.2 Intended use. Used as a separator for the prevention of galvanic attack between dissimilar metals.

60.30.3 Method of application. Press tape firmly making sure that it makes good contact preferably at 60 to 80 degrees Fahrenheit.

| Color | Width (inches) | Length (yds) | Core (inches) | Stock Number |
|---|---|---|---|---|
| Any | 1/2 | 72 | 3 | 7510-01-060-8518 |
| Any | 1 | 72 | 3 | 7510-00-474-4021 |



Source: https://assist.dla.mil -- Downloaded: 202640-26T13:38Z
Check the source to verify that this is the current version before use.

60.31 TAPE, PRESSURE-SENSITIVE ADHESIVE, FOR MASKING DURING PAINT STRIPPING OPERATIONS

MIL-T-23397

60.31.1 Description. A pressure-sensitive adhesive tape, with water insoluble adhesive on one side; wound in rolls, adhesive side in, on cores.

60.31.2 Intended use. This is one type of tape that is suitable for use for masking during paint stripping operations. It is designed to effectively protect aircraft surfaces and parts, and be capable of resisting paint remover without any infiltration through or seepage under it. The tape will have no deleterious effect on materials used in aircraft construction.

60.31.3 Method of application. Apply the tape to clean, dry surfaces between 60 and 80 degrees Fahrenheit. The edges should be carefully and firmly smoothed after application of the tape.

| Color | Width (inches) | Length (yds) | Core (inches) | Stock Number |
|---|---|---|---|---|
| AA | 1/2 | 60 | 3 | 7510-00-476-8841 |
| AA | 1 | 60 | 3 | 7510-00-473-9855 |
| AA | 1 1/2 | 60 | 3 | 7510-00-476-8842 |
| AA | 2 | 60 | 3 | 7510-00-473-9513 |



Source: https://assist.dla.mil -- Downloaded: 202610-26T13:38Z
Check the source to verify that this is the current version before use.

## 60.32 INSULATION TAPE, ELECTRICAL; HIGH TEMPERATURE, POLYTETRAFLUOROETHYLENE, PRESSURE-SENSITIVE

MIL-I-23594

60.32.1 Description. A virgin, fused, polytetrafluoroethylene resin backing, coated on one side with a pressure-sensitive adhesive. The adhesive shall be a pressure-sensitive silicone polymer capable of maintenance of adhesion for continuous operation at 500 degrees Fahrenheit.

Type I - Smooth backing, for splicing insulation on polytetrafluoroethylene coated electrical wire

Type II - Treated backing, capable of receiving impregnation with insulation varnish

60.32.2 Intended use. General underwater demolition use such as watertight seals around blasting caps and detonating cord, leg splicing of firing cable to prevent shorting out of firing circuit, watertight seals around junction of non-electric caps and safety fuses. Also suitable for electrical systems of aircraft, missile and other weapons systems within the limitations of performance requirements.

60.32.3 Method of application. Press tape firmly making sure that it makes complete contact.

TYPE I

| Color | Length (feet) | Width (inches) | Thickness (mils) | Stock Number |
|---|---|---|---|---|
| White | 108 | .25 | 3.5 | 5970-00-816-7164 |
| White | 108 | .25 | 4.6 | 5970-00-144-7420 |
| - | 108 | .312 | 6 | 5970-00-144-7725 |
| AA | 108 | .5 | - | 5970-01-052-4941 |
| AA | 216 | .5 | 3.5 | 5970-00-812-7387 |
| AA | 216 | .5 | 6 | 5970-00-833-1703 |
| White | 216 | .5 | 6 | 5970-00-117-3704 |
| - | 216 | .5 | 6.9 | 5970-00-950-7400 |
| AA | 216 | .5 | 7 | 5970-01-012-1054 |
| - | 216 | .75 | 3.5 | 5970-00-139-5157 |
| - | 54 | .75 | 6.5 | 5970-00-051-4041 |
| - | 180 | 1 | 4.8 | 5970-00-069-2730 |
| AA | 108 | 1 | 6 | 5970-00-833-1702 |
| AA | 108 | 1 | 6 | 5970-00-848-8683 |
| Unpigmented | 108 | 1 | 6.5 | 5970-01-012-4280 |
| AA | 108 | 1.375 | 6.5 | 5970-00-067-6527 |
| AA | 108 | 1.5 | 2 | 5970-00-477-8353 |
| AA | 108 | 1.5 | 4.8 | 5970-00-089-1881 |
| AA | 108 | 1.5 | 6.6 | 5970-01-067-2916 |
| AA | 108 | 2 | 6 | 5970-00-761-3655 |
| AA | 108 | 2 | 6.5 | 5970-00-019-5620 |
| AA | 108 | 2 | - | 5970-01-083-3739 |
| AA | 108 | 3.156 | 5 | 5970-00-755-8982 |



Source: https://assist.dla.mil - Downloaded: 202610-26T13:38Z
Check the source to verify that this is the current version before use.

## 60.33 INSULATION TAPE, ELECTRICAL, PLASTIC PRESSURE-SENSITIVE

MIL-I-24391

60.33.1 Description. The tape backing is a plastic film. The adhesive is pressure-sensitive, homogeneous, and coated on one side of the backing.

60.33.2 Intended use. This tape is suitable for the insulation of electrical conductors and splices in electrical wiring within an application temperature range of 10°F to 150°F and is intended for use where self-extinguishing tape is required.

60.33.3 Method of application. Tape is applied to clean, dry surfaces, preferably at 60 to 80 degrees Fahrenheit. Press on firmly, making sure the entire surface of the tape makes good contact.

| Color | Width (inches) | Length (yds) | Thickness (mils) | Stock Number |
|---|---|---|---|---|
| Yellow | 1/2 | 36 | 8.5 | 5970-00-147-5674 |
| Black | 1/2 | 36 | 8.0 | 5970-00-419-4290 |
| Yellow | 3/4 | 36 | 8.5 | 5970-00-163-5122 |
| Black | 3/4 | 36 | 8.0 | 5970-00-419-4291 |
| Yellow | 1 | 36 | 8.5 | 5970-01-047-4340 |
| Black | 1 | 36 | 8.5 | 5970-00-419-3164 |
| Silver | 1 | 36 | 8.5 | 5970-01-062-3651 |
| Black | 1 | 36 | 10 | 5970-00-188-5478 |
| Black | 1-1/4 | 36 | 10 | 5970-00-518-3991 |
| Black | 1-1/2 | 36 | 8.5 | 5970-00-150-2009 |



Source: https://assist.dla.mil -- Downloaded: 202640-26T13:38Z
Check the source to verify that this is the currentversion before use.

60.34 TAPE, PRESSURE SENSITIVE ADHESIVE, TRANSPARENT, FILM SPLICING

MIL-T-23617

60.34.1 Description. The tape is a nonhygroscopic, solvent resistant polyester film coated on one side with a pressure-sensitive, water-insoluble and sulfur-free adhesive. The tape is transparent and colorless.

60.34.2 Intended use. The tape is designed for the splicing of photographic film, paper and leader during and after processig through high speed, high temperature, automatic film developing equipment. The tape may also be used for repairing processed film, splicing leader to film, connecting film to spools and similar holding applications. It is not intended for sealing cans of photographic film.

60.34.3 Method of application. When splicing film, paper, etc., the tape should be applied completely around the film so there is tape on both sides of the splice. The film should be dry when making splices, and should be applied with a firm pressure. Avoid wrinkles.

| Color | Width (inches) | Length (yds) | Core (inches) | Stock Number |
|---|---|---|---|---|
| Clear | 1 | 72 | 3 | 7510-00-687-4383 |



Source: https://assist.dla.mil -- Downloaded: 202640-26T13:38Z
Check the source to verify that this is the current version before use.

60.35 TAPE, ANTISEIZE, POLYTETRAFLUORETHYLENE, WITH DISPENSER

MIL-T-27730

60.35.1 Description. Antiseize product is at least 99% polytetrafluoroethylene and contains no materials that are combustible in the presence of oxygen or that produce toxic vapors at temperatures up to 260°F. Dispenser is as small in size and as light in weight as practical. Is designed to prevent contamination with oils, greases, dirt and any other contaminants. Dispenser also has provision for cutting tape to desired length.

60.35.2 Intended use. The tape is used as an antiseize and sealant of pipe threads of liquid and gaseous oxygen systems of 2000 psi and less.

60.35.3 Method of application.

1. Throughly clean male and female threads assuring the removal of all previously applied antiseize compound or tape.
2. Wrap tape in direction of thread spiral of male pipe thread beginning with first thread. In no case will the tape be permitted to extend beyond the first thread.
3. Using care not to contaminate the tape, encircle the threads and join together with a very slight overlap.
4. Size I tape, 1/4 inch wide shall be used on 1/8, 1/4, and 3/8 inch pipe threads. Size II tape, 1/2 inch wide shall be used on 1/2 inch and larger pipe threads.
5. The tape shall not be used on fittings which have flared or coned ends.

| Width (inches) | Length (yds) | Core (inches) | Stock Number |
|---|---|---|---|
| 1/4 | 7 | | 8030-00-889-3534 |
| 1/4 | 36 | | 8030-01-070-6279 |
| 1/2 | 7 | | 8030-00-889-3535 |
| 1 | 7 | | 8030-00-398-4130 |



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:38Z
Check the source to verify that this is the current version before use.

60.36 TAPE, ADHESIVE COATED, PROTECTIVE

MIL-T-38727

60.36.1 Description. The backing for this tape is paper coated on one side with pressure-sensitive adhesive, wound in rolls on cords adhesive side in.

60.36.2 Intended use. These tapes are intended for use in protecting polished or finished surfaces of stainless steel, aluminum (non-anodized), all nonferrous metals (except copper and copper alloys), and methyl methylacrylate plastic against scratching, marring, or other abrasive type damage during fabrication, handling, storage, item assembly, repair, maintenance, and shop work. Type I tape is intended to provide protection during interior storage up to 9 months for metals and up to 6 months for plastic. Type I and type II tapes will provide protection during interior storage up to 12 months. Type I tape is intended to provide protection in areas subject to high abrasion such as surfaces of aircrft where workmen might walk during overhaul and repair.

60.36.3 Method of application. Tape is applied to clean, dry surfaces, preferably at 60 to 80 degrees Fahrenheit. Press on firmly, making sure the entire surface of the tape makes good contact.

| Color | Width (inches) | Length (yds) | Core (inches) | Stock Number |
|---|---|---|---|---|
| White | As specified | As specified | 3 | 7510-01-010-0118 |
| White | 12 | 30 | 3 | 7510-01-054-4067 |



Source: https://assist.dla.mil -- Downloaded: 202610-26T13:38Z
Check the source to verify that this is the currentversion before use.

60.37 TAPE, PRESSURE-SENSITIVE ADHESIVE, LITHOGRAPH

MIL-T-40620

60.37.1 Description. The tape is a ruby red tinted translucent plastic film, free of pinholes and coated on one side with a pressure-sensitive adhesive.

60.37.2 Intended use. The tape is intended for masking, edging, and stripping photographic and lithograpic negatives.

60.37.3 Method of application. Apply to clean, dry surfaces, preferably at 60 to 80 degrees Fahrenheit. The tape should be firmly pressed in place and care should be taken that there is no air entrapped under the tape.

| Color | Width (inches) | Length (yds) | Core (inches) | Stock Number |
|---|---|---|---|---|
| Ruby | 1/4 | 72 | 3 | 7510-00-902-3566 |
| Clear | 1/2 | 72 | 3 | 7510-00-285-6403 |



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:38Z
Check the source to verify that this is the current version before use.

60.38 TAPE, PRESSURE SENSITIVE ADHESIVE, PLASTIC FILM, FILAMENT REINFORCED (FOR SEAING FIBER CONTAINERS AND CANS)

MIL-T-43036

60.38.1 Description. The tape consists of a polyester film, coated on one side with a pressure-sensitive, water insoluble adhesive containing longitudinal reinforcing filaments. The adhesive is not affected by asphaltic coatings found on some fiber tubes. It can be removed from fiber tubes or cans without breaking over a temperature range of -54.3° centigrade to 68.3° centigrade (-66° to 155° Fahrenheit). The tape is furnished in gray, black, or light green.

60.38.2 Intended use. The tape is intended for waterproof, water vaporproof sealing of fiber containers and cans meeting MIL-C-2439 and MIL-C-3955 and metal slip cover cans. Because of its high stretch for a filament reinforced tape, it is suitable for sealing any type of container where the tape can be wrapped around the container. It is particularly suited for applications where the tape must be removable at low temperature.

60.38.3 Method of application. The tape should be applied to clean, dry surfaces. When applied around a tube of similar type container, the tape should be lapped on itself one-fourth of a turn.

| Color | Width (inches) | Length (yds) | Core (inches) | Stock Number |
|---|---|---|---|---|
| Black | 1 | 60 | 3 | 7510-00-823-8071 |
| Black | 1-1/2 | 60 | 3 | 7510-00-823-8073 |
| Black | 2 | 60 | 3 | 7510-00-823-8072 |



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:38Z
Check the source to verify that this is the current version before use.

60.39 TAPE, PRESSURE-SENSITIVE ADHESIVE FILM FOAM, DOUBLE-COATED (FOR (USE WITH AMMUNITION)

MIL-T-60394

60.39.1 Description. This tape consists of a non-rigid foam coated on both sides with a pressure-sensitive adhesive that is suitable for adhering two similar or dissimilar materials together. The tape is salt water resistant.

60.39.2 Intended use. This tape is intended for use with the M112 demolition charge, M118 demolition charge, and M186 demolition charge. It is also used for holding and mounting objects, and in aluminum applications.

60.39.3 Method of application. The tape can be applied to clean, dry surfaces above freezing and does not require any solvent, heat or other preparation prior to or after application.

| Color | Width (inches) | Length (yds) | Core (inches) | Stock number |
|---|---|---|---|---|
| Natural | 3/4 | 36 | 3 | 7510-01-005-5489 |
| Natural | 1 | 36 | 3 | 7510-00-181-7551 |
| Natural | 2 | 36 | 3 | 7510-01-003-9353 |
| Natural | 2 | 72 | 3 | 7510-01-003-9352 |
| Natural | 3 | 72 | 3 | 7510-01-057-0096 |
| | | | | 7510-01-068-5660 |



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:38Z
Check the source to verify that this is the current version before use.

60.40 TAPE, THERMAL RADIATION RESISTANT, PRESSURE SENSITIVE ALUMINUM COATED FIBERGLASS CLOTH

MIL-T-83284

60.40.1 Description.

60.40.2 Intended use. This tape is intended primarily for repair of thermal curtains conforming to MIL-C-27347.

60.40.3 Method of application. Tape is applied to clean dry surfaces, preferably at 60 to 80 degrees Fahrenheit. Press on firmly, making sure the entire surface of the tape makes good contact.

| Color | Width (inches) | Length (yds) | Core (inches) | Stock Number |
|---|---|---|---|---|
| Aluminum | 1/2 | 36 | 3 | 7510-00-502-9147 |
| Silver | 1-1/2 | 36 | 3 | 7510-00-996-6097 |
| Silver | 2 | 36 | 1 | 7510-00-403-5544 |
| Aluminum | 2 | 36 | 3 | 7510-00-502-9143 |
| Silver | 3 | 36 | 3 | 7510-00-106-9842 |
| Aluminum | 4 | 36 | 3 | 7510-00-007-4551 |
| Silver | 4-1/2 | 36 | 3 | 7510-00-996-6102 |



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:38Z
Check the source to verify that this is the current version before use.

# APPENDIX B

## SOLVENT ACTIVATED TAPES

10. DESCRIPTION

10.1 This appendix covers solvent activated tapes. The appendix is subdivided by typical uses.

10.2 All specifications included in Appendix B are listed in paragraph 40.

10.3 Individual specifications are described in detail in subparagraphs of 40.

20. SUPPLIES

20.1 Mending and reinforcing tapes.

20.1.1 This group consists of water soluble, gummed paper and cloth tape for mending and reinforcing applications.

| Federal | | Paragraph |
|---|---|---|
| UU-T-101 | Tape, Gummed; Mending and Reinforcing (Paper and Cloth | 40.1 |

30. PACKAGING AND PACKING BULK MATERIALS

30.1 Sealing and securing tapes.

30.1.1 This group consists of water soluble, gummed paper tape for sealing, securing and banding of paper and paper products.

| Federal | | Paragraph |
|---|---|---|
| PPP-T-45 | Tape, Gummed, Paper Reinforced and Plain for Sealing and Securing | 40.2 |

40. DETAILED INFORMATION ON SPECIFICATIONS LISTED IN APPENDIX B

See subparagraphs of 40. on the following pages. Specification descriptions are arranged in the sequence listed in 20.1.1 and 30.1.1 above.



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:38Z
Check the source to verify that this is the current version before use.

40.1 TAPE, GUMMED; MENDING AND REINFORCING, (PAPER AND CLOTH)

UU-T-101

40.1.1 Description. A water-soluble gummed paper or cloth tape. Available in three types.

Type I - A transparent glassine paper backing

Type III - A transparent, lightweight cloth backing

Type IV - A non-transparent, lightweight cloth backing

40.1.2 Intended use. Mending, reinforcing, and securing papers such as maps, books, and drawings. Type III has a surface satisfactory for writing on with ink.

40.1.3 Method of application. Gum is thoroughly wet with water and evenly applied.

TYPE I

| Color | Width (inches) | Length (yds) | Core (inches) | Stock Number |
|---|---|---|---|---|
| Clear | 5/8 | 12 | 1 | 7510-00-222-3436 |
| Clear | 1 | 12 | 1 | 7510-00-893-6188 |
| Clear | 1 | 100 | 1 | 7510-00-272-9661 |

TYPE II

| Color | Width (inches) | Length (yds) | Core (inches) | Stock Number |
|---|---|---|---|---|
| Clear | 3/4 | 36 | 1 | 7510-00-253-2520 |
| Clear | 1 | 72 | 3 | 7510-00-273-9836 |
| Clear | 2 | 72 | 3 | 7510-00-223-3590 |

TYPE III

| Color | Width (inches) | Length (yds) | Core (inches) | Stock Number |
|---|---|---|---|---|
| Clear | 3/4 | 10 | 1 | 7510-00-292-9612 |



Source: https://assist.dla.mil -- Downloaded: 202640-26T13:38Z
Check the source to verify that this is the currentversion before use.

40.2 TAPE, GUMMED, PAPER, REINFORCED AND PLAIN, FOR SEALING AND SECURING

PPP-T-45

40.2.1 Description. Types I and II tapes consist of a laminate of two strips of 100 percent unbleached or semi-bleached chemical wood pulp paper reinforced with glass, sisal or rayon. The two strips are laminated with a layer of asphalt in Type I tapes, and nonasphaltic, water resistant, flexible, and nonstaining material in Type II tapes. Type III tapes consist of one strip of paper. All types of tape are coated on one side with a water activated adhesive. Available in the types, classes, and grades specified below.

Type I - Reinforced, asphalt laminated

Type II - Reinforced, nonasphalt laminated
Class 1 - Strippable
Class 2 - Nonstrippable

Type III - Plain, single ply
Grade A - Light duty, for light-weight packages
Grade B - Medium duty, for medium-sized packages
Grade C - Heavy duty, for heavy, bulky packages

40.2.2 Intended use.

Type I (Asphaltic). Sealing fiberboard boxes for domestic shipment and storage, securing wrappers of packages and other uses such as: Securing wrappings of textile bolt packages on porcelain enamel products as protection against abrasion, and banding of tubing, wire, pipe, hose, etc.

Type II (Non-Asphaltic). As above, and where the presence of asphalt would have a deleterious effect on the product, such as food products. Class 1 is intended for use where ease of opening containers and removal of tape are required. Class 2 is intended for use where it is not necessary to remove tape from boxes for reuse.

Type III (Plain, single ply). General sealing of cartons and fiberboard boxes, wrapping of packages and banding of paper and paper products.

40.2.3 Method of application. Adhesive must be thoroughly wet with water and evenly applied.

TYPE I, CLASS 2

| Width (inches) | Length (feet) | Core (inches) | Stock Number |
|---|---|---|---|
| 1-1/2 | 450 | | 8135-00-926-4858 |
| 3 | 450 | | 8135-00-598-6097 |



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:38Z
Check the source to verify that this is the current version before use.

TYPE II, CLASS 1

| Width (inches) | Length (feet) | Core (inches) | Stock Number |
|---|---|---|---|
| 2 | 375 | 1/2 | 8135-00-926-8989 |
| 3 | 375 | 1/2 | 8135-00-155-5473 |

TYPE II, CLASS 2

| Width (inches) | Length (feet) | Core (inches) | Stock Number |
|---|---|---|---|
| 3 | 375 | | 8135-01-023-1235 |

TYPE III, CLASS 2, GRADE A

| Width (inches) | Length (feet) | Core (inches) | Stock Number |
|---|---|---|---|
| 1 | 800 | .625 | 8135-00-271-1444 |
| 1 | 500 | 1/2 | 8135-00-272-2503 |
| 1-1/2 | 800 | .438 | 8135-00-270-8726 |
| 2 | 800 | .438 | 8135-00-271-1445 |

TYPE III, CLASS 2, GRADE B

| Width (inches) | Length (feet) | Core (inches) | Stock number |
|---|---|---|---|
| 1 | 600 | | 8135-00-579-8558 |
| 1-1/2 | 600 | .438 | 8135-00-664-0080 |
| 2 | 450 | | 8135-00-854-4052 |
| 2 | 600 | .438 | 8135-00-272-9346 |
| 2-1/2 | 600 | .625 | 8135-00-271-1446 |
| 3 | 600 | 1/2 | 8135-00-270-8717 |
| 4 | 600 | 1/2 | 8135-00-290-0354 |

TYPE III, CLASS 2, GRADE C

| Width (inches) | Length (feet) | Core (inches) | Stock number |
|---|---|---|---|
| 3 | 375 | .438 | 8135-00-272-9347 |



Source: https://assist.dla.mil -- Downloaded: 202610-26T13:38Z
Check the source to verify that this is the current version before use.

# APPENDIX C

## MISCELLANEOUS TAPES

10. DESCRIPTION

10.1 This appendix covers miscellaneous tapes which cannot be classified as "pressure-sensitive," or "solvent-activated."

20. ELECTRICAL INSULATORS AND INSULATING MATERIALS

20.1 Insulation tapes. (Also see Appendix A.)

20.1.1 This group consists of tapes designed to provide electrical insulation of wires and cables, with varying dielectric strengths and operating temperatures. (See 10.1 above.)

| Military | | Paragraph |
|---|---|---|
| MIL-I-631 | Insulation, Electrical Synthetic Resin Composition, Non-rigid | 30.1 |
| MIL-I-3158 | Insulation Tape, Electrical Glass-Fiber (Resin-Filled) and Cord, Fibrous Glass | 30.2 |
| MIL-I-17205 | Insulation Cloth and Tape, Electrical, Glass Fiber, Varnished | 30.3 |
| MIL-I-18746 | Insulation Tape, Glass Polytetrfluoro-ethylene Coated | 30.4 |

30. DETAILED INFORMATION ON SPECIFICATIONS LISTED IN APPENDIX C

See subparagraphs of 30. on the following pages. Specification descriptions are arranged in the sequence as listed in 20.1.1 above.



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:38Z
Check the source to verify that this is the current version before use.

30.1 INSULATION, ELECTRICAL, SYNTHETIC-RESIN COMPOSITION, NON-RIGID

MIL-I-631

30.1.1 Description. The tape is made of synthetic insulation material.

Type A - Polyethylene.
Type B - Cellulose acetate butyrate.
Type C - Cellulose acetate or cellulose triacetate.
Type D - Ethylcellulose.
Type E - Vinylidene chloride copolymer.
Type F - Polyvinyl chloride and its copolymers.
Type G - Polyethylene terephthalate.

Form T - Tape.

30.1.2 Intended use.

Type A. This type of materials is intended for ultra high frequency applications. It possesses excellent electrical properties which remain practically constant over a wide range of frequencies, temepratures, and humidities, and hs a very low loss factor.

Type B. This type of materials is intended for applications requiring a good dielectric strength, fairly low loss factor, good moisture resistance, and good insulation resistance.

Type C. This type of materials is intended for applications requiring good dielectric strength, fairly low loss factor, and a relatively high degree of heat resistnce with some sacrifice in moisture resistance.

Type D. This type of material is intended for radio-frequency applications requiring very good dry dielectric strength, fairly low loss factor, and fair moisture resistance.

Type E. This type of material is intended for applications having excellent mechanical strength and excellent bursting strength. It is intended for general-purpose electrical applications but is more rigid than type F.

Type F, grade a. This type of material is intended as a high-elongation, elastic material with good electrical properties, suitable as an alternate for rubber insulating tape in cable or other applications.

Type F, grade b. This type of material is intended as a high-elongation, elastic material similar to type F, grade a, with less rigidity at low temperatures and other characteristics required for aeronautical applications.

Type F, grade c. This type of material is intended as a high-elongation, elastic material similar to type F, grade a, but suitable for operation at higher temperatures (105°C).



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:38Z
Check the source to verify that this is the current version before use.

Type G. This type of material is intended for applications requiring good dielectric strength, fairly low loss factor, excellent mechanical strength and heat resistance.

| Color | Width (in) | Thickness (mils) | Length (in) | Type | Stock Number |
|---|---|---|---|---|---|
| Black | 1/2 | 12 | 1800 | F | 5970-00-296-3294 |
| Unpigmented | 1/2 | 20 | 1080 | G | 5970-00-768-9188 |
| Unpigmented | 1/2 | 20 | 1080 | F | 5970-00-198-8638 |
| Unpigmented | 5/8 | 5 | 600 | G | 5970-00-177-1653 |
| Unpigmented | 3/4 | 8 | AA | F | 5970-00-818-5248 |
| Black | 3/4 | 10 | 2160 | F | 5970-00-300-9001 |
| Black | 3/4 | 12 | 1800 | F | 5970-00-296-3293 |
| Black | 3/4 | 20 | 1080 | F | 5970-00-198-8639 |
| Unpigmented | 1 | 4 | 7200 | F | 5970-00-245-1880 |
| Unpigmented | 1 | 5 | AA | G | 5970-01-042-3543 |
| Black | 1 | 10 | 1800 | F | 5970-00-296-3292 |
| - | 1 | 20 | AA | | 5970-00-222-2017 |
| - | 1 | 40 | 1200 | F | 5970-01-067-6823 |
| Clear | 1-1/4 | 2 | 11,160 | A | 5970-00-465-6161 |
| Unpigmented | 1-1/2 | 8 | 3000 | F | 5970-00-284-8715 |
| | 2 | 5 | 3984 | Polyester | 5970-00-007-9596 |



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:38Z
Check the source to verify that this is the current version before use.

30.2 INSULATION TAPE, ELECTRICAL GLASS-FIBER (RESIN FILLED) AND CORD, FIBROUS-GLASS

MIL-I-3158

30.2.1 Description. This tape is resin treated glass-fiber electrical insulation for use on electric cables. Avialable in the following types.

Tape: Type SR-1 - Coated, frayproof (for cable sealing).

30.2.1 Intended use. Type SR-1 - This tape is intended for general use in the installation of electric cables, but particularly for cable sealing to prevent fraying.

30.2.3 Method of application. Wrap around item to be insulated.

| Tape | Width (in) | Core Diameter (in) | Length (yds) | Stock Number |
|---|---|---|---|---|
| Type SR-1 | 6 | 1-1/2 | 25 | 5970-00-290-8303 |



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:38Z
Check the source to verify that this is the current version before use.

## 30.3 INSULATION CLOTH AND TAPE, ELECTRCAL, GLASS FIBER, VARNISHED

MIL-I-17205

30.3.1 Description. Varnished glass fiber cloth and tape for electrical insulation. Tape and cloth in the following forms and grades:

FORM C - Cloth
Grade O - Varnished with organic varnish - yellow
Grade S - Varnished with silicone varnish for use in motors, generators, and transformers

FORM T - Tape
Grade O - Varnished with organic varnish - yellow
Grade S - Varnished with silicone varnish for use in motors, generators and transformers

30.3.2 Intended use. This insulation cloth and tape is intended for use in coils of electrical and electronic equipment such as motors, generators, and transformers. The 0.002 inch thick Grade S material shall be limited to applications where a considerable effect of high humidity on electrical properties and a low dielectric strength at elevated temperatures can be tolerated.

| Color | Width (inches) | Thickness (mils) | Length (yds) | Stock Number |
|---|---|---|---|---|
| | 1/2 | 4 | 36 | 5970-00-188-4597 |
| Yellow | 1/2 | 5 | 36 | 5970-00-188-4606 |
| | 1/2 | 7 | 36 | 5970-00-188-5472 |
| Yellow | 1/2 | 7 | 36 | 5970-00-188-4616 |
| Clear | 3/4 | 4 | 36 | 5970-00-188-5475 |
| | 3/4 | 7 | 36 | 5970-00-188-5471 |
| Yellow | 1 | 5 | 36 | 5970-00-188-4608 |
| | 1 | 7 | 36 | 5970-00-188-5470 |
| Yellow | 1 | 7 | 36 | 5970-00-198-8744 |



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:38Z
Check the source to verify that this is the current version before use.

## 30.4 INSULATION TAPE, GLASS FABRIC, POLYTETRAFLUOROETHULENE COATED

MIL-I-18746

30.4 Description. Electrical insulation tape effective at temperatures up to 260°C (400°F). The tape is of woven glass fabric, coated on both sides with polytetrafluorethylene resin.

30.4.2 Intended use. Electrical insulation, where temperatures exceeding 150°C (300°F), are prevalent.

30.4.3 Method of application. Wrap around item to be insulated.

| Color | Width (inches) | Thickness (mils) | Length (yds) | Stock Number |
|---|---|---|---|---|
| AA | 1/2 | 5 | 36 | 5970-00-226-9722 |
| AA | 3/4 | 5.5 | 36 | 5970-00-082-4273 |
| AA | 1 | 5 | 36 | 5970-00-181-0306 |
| AA | 1 | 10 | 36 | 5970-00-542-7025 |
| AA | 1 | 15 | 36 | 5970-00-935-0098 |
| AA | 1-1/2 | 10 | 100 | 5970-00-138-8825 |



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:38Z
Check the source to verify that this is the current version before use.

# STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

OMB Approval
No. 22-R255

INSTRUCTIONS: The purpose of this form is to solicit beneficial comments which will help achieve procurement of suitable products at reasonable cost and minimum delay, or will otherwise enhance use of the document. DoD contractors, government activities, or manufacturers/vendors who are prospective suppliers of the product are invited to submit comments to the government. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements. Attach any pertinent data which may be of use in improving this document. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity.

DOCUMENT IDENTIFIER AND TITLE
MIL-HDBK-228(AS) Pressure-Sensitive Adhesive, Solvent Activated and Miscellaneous Tapes

NAME OF ORGANIZATION AND ADDRESS

CONTRACT NUMBER

MATERIAL PROCURED UNDER A
☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE DOCUMENT CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?
   A. GIVE PARAGRAPH NUMBER AND WORDING.

   B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY DOCUMENT REQUIREMENT CONSIDERED TOO RIGID

3. IS THE DOCUMENT RESTRICTIVE?
   ☐ YES ☐ NO (If "Yes", in what way?)

4. REMARKS

SUBMITTED BY (Printed or typed name and address - Optional)

TELEPHONE NO.

DATE

DD FORM 1 JAN 72 1426 REPLACES EDITION OF 1 JAN 66 WHICH MAY BE USED

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:38Z
Check the source to verify that this is the current version before use.