The documentation and process conversion measures necessary to comply with this revision shall be completed by 14 December 2007.

INCH-POUND

MIL-PRF-19500/652A
14 September 2007
SUPERSEDING
MIL-PRF-19500/652
4 May 2001

* PERFORMANCE SPECIFICATION SHEET

SEMICONDUCTOR DEVICE, TRANSISTOR, HIGH VOLTAGE, FIELD EFFECT, N-CHANNEL, SILICON, TYPE 2N7387 AND 2N7387U1, JAN, JANTX, JANTXV, AND JANS

This specification is approved for use by all Departments and Agencies of the Department of Defense.

* The requirements for acquiring the product described herein shall consist of this specification sheet and MIL-PRF-19500.

1. SCOPE

1.1 Scope. This specification covers the performance requirements for a high voltage N-channel, enhancement-mode, power MOSFET transistor, with avalanche energy maximum ratings (E_{AS}) and maximum avalanche current (I_{AS}). Four levels of product assurance are provided for each encapsulated device type as specified in MIL-PRF-19500.

1.2 Physical dimensions. See figure 1 (TO-254AA), and figure 2 for surface mount (U1).

* 1.3 Maximum ratings. (T_A = +25°C, unless otherwise specified).

Type	P_T (1) T_C = +25°C	P_T T_A = +25°C	$R_{\theta JC}$	$V_{(BR)DSS}$ min V_{GS} = 0 V dc I_D = 1.0 mA dc	I_{D1} (2) T_C = +25°C	I_{D2} (2) T_C = +100°C	I_S	I_{DM} (3)	T_J and T_{STG}
	W	W	°C/W	V dc	A dc	A dc	A dc	A(pk)	°C
2N7387, 2N7387U1	125	4	1.0	1,000	3	1.9	3	9	-55 to +150

See notes on next page.

* Comments, suggestions, or questions on this document should be addressed to Defense Supply Center, Columbus, ATTN: DSCC-VAC, P.O. Box 3990, Columbus, OH 43218-3990, or emailed to Semiconductor@dscc.dla.mil. Since contact information can change, you may want to verify the currency of this address information using the ASSIST Online database at http://assist.daps.dla.mil/.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:30Z
Check the source to verify that this is the current version before use.

1.3 Maximum ratings - Continued.

Type	I_{AR} (2)	V_{GS}	E_{AS}	$r_{DS(on)}$max (4) V_{GS} = 10V dc; I_D = 1.9A	
				T_J = +25°C	T_J = +150°C
	A	V dc	mj	ohms	ohms
2N7387, 2N7387U1	3	±20	245	4.00	9.60

(1) Derate linearly 1.0 W/°C for T_C > +25°C.
(2) ID = sqrt {[$T_{J(max)}$ - T_C]/[$R_{\theta JX}$ x ($R_{ds(on)}$ at $T_{J(max)}$)]}
(3) I_{DM} = 3*I_{D1} as calculated in footnote (2).
(4) Pulsed (see 4.5.1).

1.4 Primary electrical characteristics. T_C = +25°C (unless otherwise specified).

Type	$V_{(BR)DSS}$ min V_{GS} = 0 V dc I_D = 1.0 mA dc	$V_{GS(th)1}$ $V_{DS} \geq V_{GS}$ I_D = 0.25 mA dc		I_{DSS1} max V_{GS} = 0 V dc V_{DS} = 800 V dc	$r_{DS(on)}$ (1) V_{GS} = 10 V dc I_D = 1.9 A dc
	V dc	V dc		µA dc	ohms
		min	max		
2N7387, 2N7387U1	1,000	2.0	4.0	25	4.00

(1) Pulsed (see 4.5.1).

2. APPLICABLE DOCUMENTS

* 2.1 General. The documents listed in this section are specified in sections 3, 4, or 5 of this specification. This section does not include documents cited in other sections of this specification or recommended for additional information or as examples. While every effort has been made to ensure the completeness of this list, document users are cautioned that they must meet all specified requirements of documents cited in sections 3, 4, or 5 of this specification, whether or not they are listed.

2.2 Government documents.

* 2.2.1 Specifications, standards, and handbooks. The following specifications, standards, and handbooks form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those cited in the solicitation or contract.

* DEPARTMENT OF DEFENSE SPECIFICATIONS

MIL-PRF-19500 - Semiconductor Devices, General Specification for.


* DEPARTMENT OF DEFENSE STANDARDS

MIL-STD-750 - Test Methods for Semiconductor Devices.

* (Copies of these documents are available online at http://assist.daps.dla.mil/quicksearch/ or http://assist.daps.dla.mil/ or from the Standardization Document Order Desk, 700 Robbins Avenue, Building 4D, Philadelphia, PA 19111-5094.)

2.3 Order of precedence. In the event of a conflict between the text of this document and the references cited herein, the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:30Z
Check the source to verify that this is the current version before use.




Dimensions				
Symbol	Inches		Millimeters	
	Min	Max	Min	Max
BL	.535	.545	13.59	13.84
CH	.249	.260	6.32	6.60
LD	.035	.045	0.89	1.14
LL	.510	.550	12.95	13.97
LO	.150 typ		3.81 typ	
LS	.150 bsc		3.81 bsc	
MHD	.139	.149	3.53	3.78
MHO	.665	.685	16.89	17.40
TL	.790	.800	20.07	20.32
TT	.040	.050	1.02	1.27
TW	.535	.545	13.59	13.84
Term 1	Drain			
Term 2	Source			
Term 3	Gate			

NOTES:
1. Dimensions are in inches.
2. Millimeters are given for general information only.
3. All terminals are isolated from case.
4. In accordance with ASME Y14.5M, diameters are equivalent to ϕx symbology.
5. All terminals are isolated from the case.

FIGURE 1. Physical dimensions (TO-254AA).

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:30Z
Check the source to verify that this is the current version before use.



Symbol	Dimensions			
	Inches		Millimeters	
	Min	Max	Min	Max
BL	.620	.630	15.74	16.00
BW	.445	.455	11.30	11.55
CH	.129	.139	3.27	3.53
LH	.010	.020	0.25	0.51
LW1	.370	.380	9.39	9.65
LW2	.135	.145	3.43	3.68
LL1	.410	.420	10.41	10.66
LL2	.152	.162	3.86	4.11
LS1	.200	.220	5.08	5.59
LS2	.100	.110	2.54	2.79
Q1	.035		0.89	
Q2	.050		1.27	
TERM 1	Drain			
TERM 2	Gate			
TERM 3	Source			

NOTES:
1. Dimensions are in inches.
2. Millimeters are given for general information only.

FIGURE 2. Physical dimensions for 2N7387U1 (surface mount).

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:30Z
Check the source to verify that this is the current version before use.

3. REQUIREMENTS

* 3.1 General. The individual item requirements shall be as specified in MIL-PRF-19500 and as modified herein.

3.2 Qualification. Devices furnished under this specification shall be products that are manufactured by a manufacturer authorized by the qualifying activity for listing on the applicable qualified manufacturer's list (QML) before contract award (see 4.2 and 6.3).

3.3 Abbreviations, symbols, and definitions. Abbreviations, symbols, and definitions used herein shall be as specified in MIL-PRF-19500.

* 3.4 Interface and physical dimensions. The interface and physical dimensions shall be as specified in MIL-PRF-19500, and on figures 1 and 2 herein. Methods used for electrical isolation of the terminal feedthroughs shall employ materials that contain a minimum of 90 percent Al_20_3 (ceramic). Examples of such construction techniques are metallized ceramic eyelets or ceramic walled packages.

3.4.1 Lead material, finish, and formation. Lead material shall be Kovar or Alloy 52; a copper core or plated core is permitted. Lead finish shall be solderable in accordance with MIL-PRF-19500, MIL-STD-750, and herein. Where a choice of lead formation, material or finish is desired, it shall be specified in the acquisition document (see 6.2). When lead formation is performed, as a minimum, the vendor shall perform 100 percent hermetic seal in accordance with screen 14 of table II of MIL-PRF-19500 and 100 percent dc testing in accordance with table I, subgroup 2 herein.

3.4.2 Internal construction. Multiple chip construction shall not be permitted.

3.5 Marking. Marking shall be in accordance with MIL-PRF-19500.

3.6 Electrostatic discharge protection. The devices covered by this specification require electrostatic protection.

3.6.1 Handling. MOS devices must be handled with certain precautions to avoid damage due to the accumulation of static charge. However, the following handling practices are recommended.

a. Devices should be handled on benches with conductive and grounded surfaces.

b. Ground test equipment, tools, and personnel handling devices.

c. Do not handle devices by the leads.

d. Store devices in conductive foam or carriers.

e. Avoid use of plastic, rubber, or silk in MOS areas.

f. Maintain relative humidity above 50 percent if practical.

g. Care should be exercised, during test and troubleshooting, to apply not more than maximum rated voltage to any lead.

h. Gate must be terminated to source. $R \leq 100K\Omega$, whenever bias voltage is to be applied drain to source.

3.7 Electrical performance characteristics. Unless otherwise specified herein, the electrical performance characteristics are as specified in 1.3, 1.4, and table I herein.

3.8 Electrical test requirements. The electrical test requirements shall be as specified in table I.

3.9 Workmanship. Semiconductor devices shall be processed in such a manner as to be uniform in quality and shall be free from other defects that will affect life, serviceability, or appearance.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:30Z
Check the source to verify that this is the current version before use.

4. VERIFICATION

4.1 Classification of inspections. The inspection requirements specified herein are classified as follows:

a. Qualification inspection (see 4.2).

b. Screening (see 4.3).

* c. Conformance inspection (see 4.4 and tables I and II).

4.2 Qualification inspection. Qualification inspection shall be in accordance with MIL-PRF-19500 and as specified herein. Alternate flow is allowed for qualification inspection in accordance with figure 4 of MIL-PRF-19500.

* 4.2.1 Group E qualification. Group E inspection shall be performed for qualification or re-qualification only. In case qualification was awarded to a prior revision of the specification sheet that did not request the performance of table II tests, the tests specified in table II herein that were not performed in the prior revision shall be performed on the first inspection lot of this revision to maintain qualification.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:30Z
Check the source to verify that this is the current version before use.

* 4.3 Screening (JANTX, JANTXV, and JANS levels). Screening shall be in accordance with table E-IV of MIL-PRF-19500, and as specified herein. The following measurements shall be made in accordance with table I herein. Devices that exceed the limits of table I herein shall not be acceptable.

Screen (see table E-IV of MIL-PRF-19500) (1) (2)	Measurement	
	JANS level	JANTX and JANTXV levels
(3)	Gate stress test (see 4.3.1)	Gate stress test (see 4.3.1)
(3)	Method 3470 of MIL-STD-750, (see 4.3.2)	Method 3470 of MIL-STD-750, (see 4.3.2)
(3) 3c	Method 3161 of MIL-STD-750, (see 4.3.3)	Method 3161 of MIL-STD-750, (see 4.3.3)
9	Subgroup 2 of table I herein, I_{DSS1}, I_{GSSF1}, I_{GSSR1}	Not applicable
10	Method 1042 of MIL-STD-750, test condition B	Method 1042 of MIL-STD-750, test condition B
11	I_{GSSF1}, I_{GSSR1}, I_{DSS1}, $r_{DS(ON)1}$, $V_{GS(TH)1}$. Subgroup 2 of table I herein. ΔI_{GSSF1} = ±20 nA dc or ±100 percent of initial value, whichever is greater. ΔI_{GSSR1} = ±20 nA dc or ±100 percent of initial value, whichever is greater. ΔI_{DSS1} = ±25 μA dc or ±100 percent of initial value, whichever is greater.	I_{GSSF1}, I_{GSSR1}, I_{DSS1}, $r_{DS(ON)1}$, $V_{GS(TH)1}$. Subgroup 2 of table I herein.
12	Method 1042 of MIL-STD-750, condition A	Method 1042 of MIL-STD-750, condition A
13	Subgroups 2 and 3 of table I herein. ΔI_{GSSF1} = ±20 nA dc or ±100 percent of initial value, whichever is greater. ΔI_{GSSR1} = ±20 nA dc or ±100 percent of initial value, whichever is greater. ΔI_{DSS1} = ±25 μA dc or ±100 percent of initial value, whichever is greater. $\Delta r_{DS(ON)1}$ = ±20 percent of initial value. $\Delta V_{GS(TH)1}$ = ±20 percent of initial value.	Subgroup 2 of table I herein. ΔI_{GSSF1} = ±20 nA dc or ±100 percent of initial value, whichever is greater. ΔI_{GSSR1} = ±20 nA dc or ±100 percent of initial value, whichever is greater. ΔI_{DSS1} = ±25 μA dc or ±100 percent of initial value, whichever is greater. $\Delta r_{DS(ON)1}$ = ±20 percent of initial value. $\Delta V_{GS(TH)1}$ = ±20 percent of initial value.

(1) At the end of the test program, I_{GSSF1}, I_{GSSR1}, and I_{DSS1} are measured.
(2) An out-of-family program to characterize I_{GSSF1}, I_{GSSR1}, I_{DSS1}, and $V_{GS(th)1}$ shall be invoked.
(3) Shall be performed anytime after temperature cycling, screen 3a; and does not need to be repeated in screening requirements.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:30Z
Check the source to verify that this is the current version before use.

* 4.3.1 Gate stress test. Apply V_{GS} = 30 V minimum for t = 250 µs minimum.

* 4.3.2 Single pulse unclamped inductive switching.

a. Peak current, I_{AS} ..... 3 A.

b. Peak gate voltage, V_{GS} ..... 10 V.

c. Gate to source resistor, R_{GS} ..... $25 \leq R_g \leq 200$ ohms.

d. Initial case temperature ..... +25°C, +10°C, -5°C.

e. Inductance, L ..... 51.72 mH minimum.

f. Number of pulses to be applied ... 1 pulse minimum.

g. Supply voltage (V_{DD}) ..... 50 V.

* 4.3.3 Thermal impedance. The thermal impedance measurements shall be performed in accordance with method 3161 of MIL-STD-750 using the guidelines in that method for determining I_M, I_H, t_H, t_{SW}, (and V_H where appropriate). (See figure 3 herein.) Measurement delay time (t_{MD}) = 70 µs max. See table II, group E, subgroup 4 herein.

4.4 Conformance inspection. Conformance inspection shall be in accordance with MIL-PRF-19500 and as specified herein.

* 4.4.1 Group A inspection. Group A inspection shall be conducted in accordance with MIL-PRF-19500, and table I herein. Electrical measurements (end-points) shall be in accordance with table I, subgroup 2 herein.

* 4.4.2 Group B inspection. Group B inspection shall be conducted in accordance with the conditions specified for subgroup testing in table E-VIA (JANS) and table E-VIB (JAN, JANTX, and JANTXV) of MIL-PRF-19500 and as follows. Electrical measurements (end-points) shall be in accordance with table I, subgroup 2 herein.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:30Z
Check the source to verify that this is the current version before use.

* 4.4.2.1 Group B inspection, table E-VIA (JANS) of MIL-PRF-19500.

Subgroup	Method	Conditions
B3	1051	Test condition G.
B4	1042	Test condition D, 2,000 cycles. The heating cycle shall be 30 seconds minimum. No heat sink nor forced air cooling on the device shall be permitted during the "on" cycle.
B5	1042	A separate sample may be pulled for each test. Condition B, V_{GS} = rated, T_A = +175°C, t = 24 hours min. or T_A = +150°C, t = 48 hours min. Condition A, V_{DS} = rated, T_A = +175°C, t = 120 hours min. or T_A = +150°C, t = 240 hours min.

* 4.4.2.2 Group B inspection, table E-VIB (JAN, JANTX, and JANTXV) of MIL-PRF-19500.

Subgroup	Method	Conditions
B2	1051	Test condition G.
B3	1042	Test condition D, 2,000 cycles. The heating cycle shall be 30 seconds minimum. No heat sink nor forced air cooling on the device shall be permitted during the "on" cycle.

4.4.3 Group C inspection. Group C inspection shall be conducted in accordance with the conditions specified for subgroup testing in table E-VII of MIL-PRF-19500, and as follows. Electrical measurements (end-points) shall be in accordance with table I, subgroup 2 herein.

Subgroup	Method	Conditions
C2	2036	Test condition A; weight = 10 pounds, t = 15 s. Not applicable to surface mount version.
* C5	3161	See 4.3.3, $R_{\theta JC}$ = 0.60 °C/W.
C6	1042	Test condition D, 6,000 cycles. The heating cycle shall be 30 seconds minimum. No heat sink nor forced air cooling on the device shall be permitted during the "on" cycle.

* 4.4.4 Group E inspection. Group E inspection shall be conducted in accordance with the conditions specified for subgroup testing in table E-IX of MIL-PRF-19500 and as specified in table II herein. Electrical measurements (end-points) shall be in accordance with table I, subgroup 2 herein.

4.5 Methods of inspection. Methods of inspection shall be as specified in the appropriate tables and as follows.

4.5.1 Pulse measurements. Conditions for pulse measurement shall be as specified in section 4 of MIL-STD-750.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:30Z
Check the source to verify that this is the current version before use.

* TABLE I. Group A inspection.

Inspections 1/	MIL-STD-750		Symbol	Limits		Unit
	Method	Conditions		Min	Max	
Subgroup 1						
Visual and mechanical examination	2071					
Subgroup 2						
Thermal impedance 2/	3161	See 4.3.3	$Z_{\theta JC}$			°C/W
Breakdown voltage, drain to source	3407	Bias condition C, V_{GS} = 0 V dc, I_D = 1.0 mA dc	$V_{(BR)DSS}$	1000		V dc
Gate to source voltage (threshold)	3403	$V_{DS} \geq V_{GS}$, I_D = 0.25 mA dc	$V_{GS(th)1}$	2.0	4.0	V dc
Gate reverse current	3411	Bias condition C, V_{DS} = 0 V dc, V_{GS} = +20 V dc	I_{GSSF1}		+100	nA dc
Gate reverse current	3411	Bias condition C, V_{DS} = 0 V dc, V_{GS} = -20 V dc	I_{GSSR1}		-100	nA dc
Drain current	3413	Bias condition C, V_{GS} = 0 V dc, V_{DS} = 800 V dc	I_{DSS1}		25	µA dc
Static drain to source on-state resistance	3421	Condition A, pulsed (see 4.5.1); V_{GS} = 10 V dc, I_D = 1.9 A dc	$r_{DS(on)1}$		4.0	ohm
Static drain to source on-state resistance	3421	Condition A, pulsed (see 4.5.1); V_{GS} = 10 V dc, I_D = 3 A dc	$r_{DS(on)2}$		4.2	ohm
Forward voltage (source drain diode)	4011	Pulsed (see 4.5.1), V_{GS} = 10 V dc, I_D = 3 A dc	V_{SD}		1.8	V dc
Subgroup 3						
High temperature operation:		$T_C = T_J$ = +125°C				
Gate reverse current	3411	Bias condition C, V_{GS} = +20 V dc and -20 V dc, V_{DS} = 0 V dc	I_{GSS2}		±200	nA dc
Drain current	3413	Bias condition C, V_{GS} = 0 V dc, V_{DS} = 1,000 V dc	I_{DSS2}		1.0	mA dc
		V_{DS} = 800 V dc	I_{DSS3}		0.5	mA dc
Gate to source voltage (threshold)	3403	$V_{DS} \geq V_{GS}$, I_D = 0.25 mA dc	$V_{GS(th)2}$	1.0		V dc
Static drain to source on-state resistance	3421	Condition A, pulsed (see 4.5.1); V_{GS} = 10 V dc, I_D = 1.9 A dc	$r_{DS(on)3}$		8.0	ohm

See footnotes at end of table.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:30Z
Check the source to verify that this is the current version before use.

* TABLE I. Group A inspection - Continued.

Inspections 1/	MIL-STD-750		Symbol	Limits		Unit
	Method	Conditions		Min	Max	
Subgroup 3 - Continued						
Low temperature operation:		$T_C = T_J = -55°C$				
Gate to source voltage (threshold)	3403	$V_{DS} \geq V_{GS}$, $I_D = 0.25$ mA dc	$V_{GS(th)3}$		5.0	V dc
Subgroup 4						
Switching time test	3472	V_{GS} = 10 V dc pulsed, V_{DD} = 400 V dc, RG = 9.1 ohms, I_D = 3.0 A dc				
Turn-on delay time			$t_{d(on)}$		25	ns
Rise time			t_r		45	ns
Turn-off delay time			$t_{d(off)}$		150	ns
Fall time			t_f		65	ns
Subgroup 5						
Safe operating area test	3474	See figure 4, V_{DS} = 200 V dc, t_p = 10 ms				
Electrical measurements		See table 1, subgroup 2 herein.				
Subgroup 6						
Not applicable						
Subgroup 7						
Gate charge	3471	Condition B				
On-state gate charge			$Q_{g(on)}$		120	nC
Gate to source charge			Q_{gs}		16	nC
Gate to drain charge			Q_{gd}		75	nC
Reverse recovery time	3473	$V_{DD} \leq 30$ V, $d_i/d_t \leq 100$ A/µs, I_D = 3 A dc	t_{rr}		1100	ns

1/ For sampling plan, see MIL-PRF-19500.
2/ This test required for the following end-point measurements only:
Group B, subgroups 2 and 3 (JANTXV).
Group B, subgroups 3 and 4 (JANS).
Group C, subgroup 2 and 6.
Group E, subgroup 1.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:30Z
Check the source to verify that this is the current version before use.

* TABLE II. Group E inspection (all quality levels) for qualification only.

Inspection	MIL-STD-750		Sampling plan
	Method	Conditions	
Subgroup 1			45 devices c = 0
Temperature cycling	1051	500 cycles, test condition G	
Hermetic seal	1071		
Electrical measurements		See table 1, subgroup 2 herein.	
Subgroup 2 1/			45 devices c = 0
Steady state reverse bias	1042	Condition A, 1,000 hours	
Electrical measurements		See table 1, subgroup 2 herein.	
Steady-state gate bias	1042	Condition B, 1,000 hours	
Electrical measurements		See table 1, subgroup 2 herein.	
Subgroup 4			Sample size N/A
Thermal impedance	3161	See MIL-PRF-19500.	
Subgroup 5			3 devices c = 0
Barometric pressure (reduced)	1001	Condition C	

1/ A separate sample for each test may be pulled.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:30Z
Check the source to verify that this is the current version before use.




FIGURE 3. Thermal impedance curves.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:30Z
Check the source to verify that this is the current version before use.




FIGURE 4. Safe operating area graph.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:30Z
Check the source to verify that this is the current version before use.

5. PACKAGING

* 5.1 Packaging. For acquisition purposes, the packaging requirements shall be as specified in the contract or order (see 6.2). When packaging of materiel is to be performed by DoD or in-house contractor personnel, these personnel need to contact the responsible packaging activity to ascertain packaging requirements. Packaging requirements are maintained by the Inventory Control Point's packaging activities within the Military Service or Defense Agency, or within the Military Service's system commands. Packaging data retrieval is available from the managing Military Department's or Defense Agency's automated packaging files, CD-ROM products, or by contacting the responsible packaging activity.

6. NOTES

* (This section contains information of a general or explanatory nature that may be helpful, but is not mandatory. The notes specified in MIL-PRF-19500 are applicable to this specification.)

* 6.1 Intended use. Semiconductors conforming to this specification are intended for original equipment design applications and logistic support of existing equipment.

* 6.2 Acquisition requirements. Acquisition documents should specify the following:

a. Title, number, and date of this specification.

b. Packaging requirements (see 5.1).

c. Lead material, finish, and formation (see 3.4.1).

d. Product assurance level and type designator.

* 6.3 Qualification. With respect to products requiring qualification, awards will be made only for products which are, at the time of award of contract, qualified for inclusion in Qualified Manufacturers List (QML 19500) whether or not such products have actually been so listed by that date. The attention of the contractors is called to these requirements, and manufacturers are urged to arrange to have the products that they propose to offer to the Federal Government tested for qualification in order that they may be eligible to be awarded contracts or orders for the products covered by this specification. Information pertaining to qualification of products may be obtained from Defense Supply Center, Columbus, ATTN: DSCC/VQE, P.O. Box 3990, Columbus, OH 43218-3990 or e-mail vqe.chief@dla.mil.

* 6.4 Changes from previous issue. The margins of this specification are marked with asterisks to indicate where changes from the previous issue were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous issue.

Custodians:
Army - CR
Navy - EC
Air Force - 11
NASA - NA
DLA - CC

Preparing activity:
DLA - CC

(Project 5961-2007-037)

* NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using the ASSIST Online database at http://assist.daps.dla.mil/ .

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:30Z
Check the source to verify that this is the current version before use.