A-A-51950A
29 August 1988
SUPERSEDING
A-A-0051950(DM)
23 April 1987

COMMERCIAL ITEM DESCRIPTION

GAUZE, OIL EMULSION IMPREGNATED

The General Services Administration has authorized the use of this Commercial Item Description as a replacement for Military Specification MIL-G-36285C which is cancelled.

This commercial item description covers an Oil Emulsion Impregnated primary dressing.

Salient characteristics.

Shall be sterile dressing which shall be suitable for use as a primary surgical dressing. The dressing shall be sterile when tested in accordance with the USP. The dressing shall be single ply, knitted, cellulose acetate fabric impregnated with a water-in-oil emulsion. The dressings shall be of the following sizes:

SIZE	MINIMUM WIDTH (INCHES)	MINIMUM UNFOLDED LENGTH (INCHES)
1	2-3/4	2-3/4
2	2-3/4	7-5/8
3	2-3/4	15-1/2

Size 3 shall be folded once to approximately half its length.

Size 2 may be folded once to approximately half its length.

The fabric shall be white, shall be a flat warp knit of multifilament yarns and shall meet the following requirements:

Front end (wales) per inch	23 ± 1	1/
Back ends (wales) per inch	22 ± 1	1/
Courses per inch	26 ± 2	1/
Weight, grams/linear yard	6.8 minimum	2/

AMSC/NA FSC 6510

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:03Z
Check the source to verify that this is the current version before use.

1/ When tested in accordance with method 5070 Federal Test Method Standard 191.

2/ When tested in accordance with method 5040 Federal Test Method Standard 191.

Both edges of the dressings shall be selvage and shall be non-fraying. When cut straight or on the bias, the knitted fabric shall not fray or shed loose threads. The fabric shall be free of broken filaments, runs, cuts, dirt, smudges, stains, foreign matter and other manufacturing defects. The fabric shall have a soft hand and good drapeability and the courses and whales shall be evenly spaced. The fabric shall have a pH of water extract of 4.5 to 8.3 when tested in accordance with method 2811 of Federal Test Method Standard 191.

The Petrolatum used in the preparation of the water-in-oil emulsion shall be white petrolatum, a purified unctuous mixture of semisolid hydrocarbons obtained from petroleum. The white petroleum shall be wholly or nearly decolorized and shall meet the following requirements:

Congeling Range	44-55°C	1/
Residue on Ignition	0.05 percent maximum	1/
Organic Acids	Pass	1/
Alkalinity	Pass	1/
Acidity	Pass	1/
Fixed Oils, Fats and Rosin	Pass	1/
Viscosity, Saybolt 60-80 seconds at 210°F		2/

1/ When tested in accordance with the U.S.P.
2/ When tested in accordance with the ASTM D88-56.

The fabric shall be evenly and uniformly impregnated with the emulsion. The weight of the emulsion in the impregnated fabric shall be a minimum of 120 percent of the weight of the untreated fabric prior to the dressings being packaged. The dressings shall be non-adherent to wounds, burns, and ulcers; shall not permit clotting to occur within the dressings; shall be porous to drainage; shall prevent maceration; shall be conforming; and shall be nontoxic and nonirritating.

One hundred ml of distilled water shall pass through the dressing in not more than 30 seconds when a single layer of the dressing is pressed over the rim and to the base of a fluted glass 60° funnel having a top diameter of 50 millimeters and a stem 150 millimeters long.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:03Z
Check the source to verify that this is the current version before use.

The dressing shall overcome the surface tension of water drops and permit passage of the water through the dressing in less than 60 seconds when tested as follows. Place a 4 inch square gauze sponge on a flat surface and place a single layer of 3 inch square dressing over the sponge. Place a 7½ inch square of ¼ inch plexiglass having a ½ inch diameter hole in its center over the dressing. Place one drop of 0.1 percent aqueous crystal violet solution on the dressing, in the center of the hole. Measure the time required for the dye solution to pass through the dressing and be absorbed by the sponge.

The dressings shall not wick within five minutes when tested as follows. Cut a 1 by 3 inch single layer strip of the dressing with the long dimension parallel to a selvage. Suspend the short end of the strip in a beaker containing 0.025 percent aqueous crystal violet solution so that 2 to 3 mm of the strip is immerged.

Workmanship. The dressings shall be free from defects which detract from their appearance or impair their serviceability.

Unit.

For Class 1 - Package (PG). Each dressing shall be supplied in a sealed peel-open type container capable of maintaining sterility of contents unless package is damaged or opened. One package containing 24 individually packaged dressings, as specified, constitutes one unit.

For Class 2 - Package (PG). Each dressing shall be supplied in a sealed peel-open type container capable of maintaining sterility of contents unless package is damaged or opened. One package containing 50 individually packaged dressings, as specified, constitutes one unit.

For Class 3 - Package (PG). Each dressing shall be supplied in a sealed peel-open type container capable of maintaining sterility of contents unless package is damaged or opened. One package containing 36 individually packaged dressings, as specified, constitutes one unit.

For Class 4 - Package (PG). Three dressings shall be supplied in a sealed peel-open type container capable of maintaining sterility of contents unless package is damaged or opened. One package containing 36 packages (108 dressings), as specified, constitutes one unit.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:03Z
Check the source to verify that this is the current version before use.

For Class 5 - Box (BX). Each dressing shall be supplied in a sealed peel-open type container capable of maintaining sterility of contents unless package is damaged or opened. Fifty individually packaged dressing shall be packaged in a box. One box containing 6 boxes (300 dressings), as specified, constitutes one unit.

Quality Assurance Provisions.

Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

Records. Records of examinations and tests performed by or for the contractor shall be maintained by the contractor and made available to the Government upon the Government's request, at any time, or from time to time, during the performance of the contract and for a period of three years after delivery of the supplies to which such records relate.

Inspection. Inspection, as used herein, is defined as both examination (such as visual or auditory investigation without the use of special laboratory appliances or procedures) and testing (determination by technical means of physical and chemical properties) of the item. Testing and examination shall be conducted to determine compliance with all specification requirements. Test methods shall be suitable, accurate and reproducible.

Sampling for examination. Sampling for examination shall be conducted in accordance with MIL-STD-105 and as specified herein. The unit of product for examination shall be one dressing. Unless otherwise specified, sampling for examination shall be conducted at inspection level II, AQL 2.5 maximum percent defective.

Source: https://assist.dla.mil -- Downloaded: 202610-26T09:03Z
Check the source to verify that this is the currentversion before use.

Certificate of viscosity for petrolatum and certificate of water passage for dressing, surface tension of water drops for dressing and nonwicking for dressing. If these particular tests have been successfully performed previously the contractor may, in lieu of testing current production, submit to the procuring activity a certificate stating that current lots of dressings (or petrolatum for viscosity) offered to the Government are composed of the same materials and manufactured identically as production lots originally tested and found to comply. The certificate shall include the current lot number(s) and the lot number(s) originally tested.

Contractor certification. The contractor shall certify that the product offered meets the salient characteristics of this description and conforms to the producers' own drawings, specifications, standards, and quality assurance practices. The Government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

Metric products. Products manufactured to metric dimensions will be considered on an equal basis with those manufactured using inch-pound units, providing they fall within the tolerances specified using conversion tables contained in the latest revision of Federal Standard No. 376, and all other requirements of this document are met.

If a product is manufactured to metric dimensions and those dimensions exceed the tolerances specified in the inch/pound units, a request should be made to the contracting officer to determine if the product is acceptable.

The contracting officer has the option of accepting or rejecting the product.

Regulatory requirements.

Federal Food, Drug and Cosmetic Act. If the product covered by this document has been determined by the U.S. Food and Drug Administration to be under its jurisdiction, the offeror/contractor shall comply, and be responsible for compliance by its subcontractors/suppliers, with the requirements of the Federal Food, Drug and Cosmetic Act, as amended, and regulations promulgated thereunder. In addition, the offeror/contractor shall comply, and be responsible for compliance by its subcontractors/suppliers, with the requirements of all other applicable Federal, State, and local statutes, ordinances, and regulations.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:03Z
Check the source to verify that this is the current version before use.

Recovered materials. The offeror/contractor is encouraged to use recovered material in accordance with Public Law 94-580, as amended, and as implemented by Federal Acquisition Regulation Subpart 23.4 to the maximum extent practical.

Preservation, packaging, packing, labeling, and marking. Unless otherwise specified, preservation, packaging, and packing shall be to a degree of protection to preclude damage to containers and/or contents thereof under normal shipping conditions, handling, etc., involving shipment from the supply source to the receiving activity, plus reshipment from receiving activity, and shall conform to applicable carrier's rules and regulations. Intermediate and exterior package quantities and labeling and marking shall be as specified in the contract and/or order.

NOTE: The following National Stock Numbers are covered by this document:

NSN	ITEM IDENTIFICATION	CLASS	SIZE
6510-00-115-0075	GAUZE, OIL EMULSION Impregnated, 3 by 8 inches, 24s	1	2
6510-00-890-1893	GAUZE, OIL EMULSION Impregnated, 3 by 3 inches, 50s	2	1
6510-00-890-1894	GAUZE, OIL EMULSION Impregnated, 3 by 16 inches, 36s	3	3
6510-00-890-1895	GAUZE, OIL EMULSION Impregnated, 3 by 8 inches, 108s	4	2
6510-01-228-6000	GAUZE, OIL EMULSION Impregnated, 3 by 8 inches, 300s	5	2

Ordering data. Inspection/Test dating required intermediate/exterior package quantities and labeling and marking must be specified in the contract and/or order.

Source: https://assist.dla.mil -- Downloaded: 202610-26T09:03Z
Check the source to verify that this is the current version before use.

A-A-51950A

MILITARY INTERESTS:

Custodians:

Army - MD
Navy - MS
Air Force - 03

PREPARING ACTIVITY:

DoD - MB

Agent:

DLA-DM

CIVIL AGENCY COORDINATING ACTIVITY:

VA-OSS
PHS
FDA-MPQAS

PGC 05211

Project No. 6510-0746

Source: https://assist.dla.mil -- Downloaded: 202610-26T09:03Z
Check the source to verify that this is the current version before use.