The documentation and process conversion measures necessary to comply with this revision shall be completed by 9 January 2002.

INCH-POUND
MIL-PRF-19500/420F
9 October 2001
SUPERSEDING
MIL-PRF-19500/420E
26 August 1999

PERFORMANCE SPECIFICATION

SEMICONDUCTOR DEVICE, DIODE, SILICON, POWER, RECTIFIER, GENERAL PURPOSE
TYPES 1N5550 THROUGH 1N5554, 1N5550US THROUGH 1N5554US
JAN, JANTX, JANTXV, JANJ, JANS, JANHC, AND JANKC

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers the performance requirements for silicon, general purpose, semiconductor diodes. Five levels of product assurance are provided for each encapsulated device type as specified in MIL-PRF-19500. Two levels of product assurance are provided for each unencapsulated device type.

1.2 Physical dimensions. See figure 1 (similar to D0-41) for 1N5550 through 1N5554, figure 2 for 1N5550US through 1N5554US, and figures 3, 4, 5, 6, and 7 for JANHC and JANKC die.

1.3 Maximum ratings. Unless otherwise specified, T_A = +25°C and ratings apply to all case outlines.

Type	$V_{(BR)min}$	V_{RWM}	I_{O1} T_L = +55°C; L = .375 inch (1) (2) (3)	I_{FSM} I_O = 2 A dc t_p = 1/120 s T_A = +55°C	T_{op}, T_{STG} (T_J)	I_{O2} T_A = +55°C (2) (4)
		V dc	A dc	A(pk)	°C	A dc
1N5550, 1N5550US	240	200	5	100	-65 to +175	3
1N5551, 1N5551US	460	400	5	100	-65 to +175	3
1N5552, 1N5552US	660	600	5	100	-65 to +175	3
1N5553, 1N5553US	880	800	5	100	-65 to +175	3
1N5554, 1N5554US	1,100	1,000	5	100	-65 to +175	3

(1) Derate linearly at 41.6 mA/°C above T_L = +55°C at L = .375 inch (9.53 mm).

(2) An I_O of up to 6 A dc is allowable provided that appropriate heat sinking or forced air cooling maintains the maximum junction temperature at or below +175°C as proven by the junction temperature rise test (see 6.5). Barometric pressure reduced:
1N5550, 1N5551, 1N5552 - 8 mmHg (100,000 feet).
1N5553, 1N5554 - 33 mmHg (70,000 feet).

(3) Does not apply to surface mount devices.

(4) Derate linearly at 25 mA/°C above T_A = +55°C.

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Defense Supply Center, Columbus, ATTN: DSCC-VAC, P.O. Box 3990, Columbus, OH 43216-5000, by using the Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

AMSC N/A FSC 5961
DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T16:48Z
Check the source to verify that this is the current version before use.

1.4 Primary electrical characteristics. Unless otherwise specified, T_A = +25°C.

Type	V_f at I_f = 9.0 A(pk) 2 percent duty cycle, 8.3 ms max pulse width		I_{R1}		I_{R2} at T_A = +100°C		$R_{\theta JL}$ $R_{\theta JEC}$
	Min V(pk)	Max V(pk)	∝A dc (max) at V_R (V dc)		∝A dc (max) at V_R (V dc)		See (1)
1N5550, 1N5550US	0.6	1.2	1.0	200	75	200	
1N5551, 1N5551US	0.6	1.2	1.0	400	75	400	
1N5552, 1N5552US	0.6	1.2	1.0	600	75	600	
1N5553, 1N5553US	0.6	1.3	1.0	800	75	800	
1N5554, 1N5554US	0.6	1.3	1.0	1,000	75	1,000	

(1) $R_{\theta JL} \leq 22$°C/W for L = .375.
$R_{\theta JEC} \leq 11$°C/W for L= 0 (US version).

2. APPLICABLE DOCUMENTS

2.1 General. The documents listed in this section are specified in sections 3 and 4 of this specification. This section does not include documents cited in other sections of this specification or recommended for additional information or as examples. While every effort has been made to ensure the completeness of this list, document users are cautioned that they must meet all specified requirements documents cited in sections 3 and 4 of this specification, whether or not they are listed.

2.2 Government documents.

2.2.1 Specifications, standards, and handbooks. The following specifications, standards, and handbooks form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those listed in the issue of the Department of Defense Index of Specifications and Standards (DoDISS) and supplement thereto, cited in the solicitation (see 6.2).

SPECIFICATION

DEPARTMENT OF DEFENSE

MIL-PRF-19500 - Semiconductor Devices, General Specification for.

STANDARD


DEPARTMENT OF DEFENSE

MIL-STD-750 - Test Methods for Semiconductor Devices.

(Unless otherwise indicated, copies of the above specifications, standards, and handbooks are available from the Document Automation and Production Services (DAPS), Building 4D (DPM-DODSSP), 700 Robbins Avenue, Philadelphia, PA 19111-5094.)

2.3 Order of precedence. In the event of a conflict between the text of this document and the references cited herein, the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T16:48Z
Check the source to verify that this is the current version before use.




Ltr	Dimensions				Notes
	Inches		Millimeters		
	Min	Max	Min	Max	
BL	.130	.300	3.30	7.62	3
BD	.115	.180	2.92	4.57	3, 4
LD	.037	.042	0.94	1.07	
LL	.900	1.300	22.86	33.02	

NOTES:
1. Dimensions are in inches.
2. Metric equivalents are given for general information only.
3. Dimensions BL and BD include all components of the diode periphery except the sections of leads over which the diameter is controlled.
4. Dimension BD shall be measured at the largest diameter.

FIGURE 1. Physical dimensions of diode 1N5550 through 1N5554, (similar to DO-41).

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T16:48Z
Check the source to verify that this is the current version before use.




Ltr	Dimensions			
	Inches		Millimeters	
	Min	Max	Min	Max
BL	.200	.275	5.08	6.99
BD	.137	.180	3.48	4.57
ECT	.019	.034	0.48	0.86
S	.003		0.08	

NOTES:
1. Dimensions are in inches.
2. Metric equivalents are given for general information only.
3. Dimensions are pre-solder dip.
4. Minimum clearance of glass body to mounting surface on all orientations.

FIGURE 2. Physical dimensions of 1N5550US through 1N5554US.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T16:48Z
Check the source to verify that this is the current version before use.




Ltr	Dimensions			
	Inches		Millimeters	
	Min	Max	Min	Max
A	.085	.091	2.16	2.31
B	.072	.078	1.83	1.98
C	.008	.014	0.20	0.36

NOTES:
1. Dimensions are in inches.
2. Metric equivalents are given for general information only.

FIGURE 3. JANHCA and JANKCA (A-version) die dimensions.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T16:48Z
Check the source to verify that this is the current version before use.




Ltr	Dimensions			
	Inches		Millimeters	
	Min	Max	Min	Max
A	.088	.092	2.24	2.34
B	.070	.077	1.78	1.96
C	.007	.035	0.18	0.89

NOTES:
1. Dimensions are in inches.
2. Metric equivalents are given for general information only.

FIGURE 4. JANHCB (B-version) die dimensions.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T16:48Z
Check the source to verify that this is the current version before use.




Ltr	Dimensions			
	Inches		Millimeters	
	Min	Max	Min	Max
A	.060	.065	1.52	1.65
B	.052	.058	1.32	1.47
C	.008	.014	0.20	0.36

NOTES:
1. Dimensions are in inches.
2. Metric equivalents are given for general information only.

FIGURE 5. JANHCC (C-version) die dimensions.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T16:48Z
Check the source to verify that this is the current version before use.




Letter	Inches		Millimeters	
	Min	Max	Min	Max
A	.081	.087	2.05	2.20
B	.055	.061	1.40	1.55
C	.007	.012	0.18	0.30

Notes:
1. Anode is Aluminum at 60,000 Å minimum.
2. Cathode is gold at 2,500 Å nominal.

FIGURE 6. JANHCD and JANKCD (D-version) die dimensions.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T16:48Z
Check the source to verify that this is the current version before use.



Letter	Inches		Millimeters	
	Min	Max	Min	Max
A	.081	.087	2.05	2.20
B	.055	.061	1.40	1.55
C	.007	.012	0.18	0.30

Notes:
1. Anode is Aluminum at 60,000 Å minimum.
2. Cathode is Al/Ti/Ni/Ag..

FIGURE 7. JANHCE and JANKCE (E-version) die dimensions.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T16:48Z
Check the source to verify that this is the current version before use.

3. REQUIREMENTS

3.1 General. The requirements for acquiring the product described herein shall consist of this document and MIL-PRF-19500.

3.2 Qualification. Devices furnished under this specification shall be products that are manufactured by a manufacturer authorized by the qualifying activity for listing on the applicable qualified manufacturer's list (QML) before contract award (see 4.2 and 6.3).

3.3 Abbreviations, symbols, and definitions. Abbreviations, symbols, and definitions used herein shall be as specified in MIL-PRF-19500.

3.4 Interface and physical dimensions. The interface and physical dimensions shall be as specified in MIL-PRF-19500 and on figure 1 (similar to DO-41) for 1N5550 through 1N5554, figure 2 for 1N5550US through 1N5554US, and figures 3, 4, 5, 6 and 7 (JANHC and JANKC).

3.4.1 Lead finish. Unless otherwise specified, lead finish shall be solderable in accordance with in MIL-PRF-19500, MIL-STD-750, and herein. Where a choice of lead finish is desired, it shall be specified in the acquisition document (see 6.2).

3.4.2 Diode construction. These devices shall be constructed utilizing non-cavity double plug construction with high temperature metallurgical bonding between both sides of the silicon die and terminal pins. Metallurgical bond shall be in accordance with the requirements of category I in MIL-PRF-19500. US version devices shall be structurally identical to the non-surface mount devices except for lead terminations.

3.5 Marking. Marking shall be in accordance with MIL-PRF-19500.

3.5.1 Marking of US version. For US version only, all marking may be omitted from the device except for the cathode marking. All marking which is omitted from the body of the device shall appear on the label of the initial container.

3.5.2 Polarity. The polarity shall be indicated with a contrasting color band to denote the cathode end. Alternately for surface mount (US) devices, a minimum of three evenly spaced contrasting color dots around the periphery of the cathode end may be used. No color coding will be permitted.

3.6 Electrical performance characteristics. Unless otherwise specified herein, the electrical performance characteristics are as specified in 1.3, 1.4, and table I herein.

3.7 Electrical test requirements. The electrical test requirements shall be the subgroups specified in table I, group A herein.

3.8 Workmanship. Semiconductor devices shall be processed in such a manner as to be uniform in quality and shall be free from other defects that will affect life, serviceability, or appearance.

4. VERIFICATION

4.1 Classification of inspections. The inspection requirements specified herein are classified as follows:

a. Qualification inspection (see 4.2).

b. Screening (see 4.3).

c. Conformance inspection (see 4.4).

4.2 Qualification inspection. Qualification inspection shall be in accordance with MIL-PRF-19500 and as specified herein.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T16:48Z
Check the source to verify that this is the current version before use.

4.2.1 Group E inspection. Group E inspection shall be conducted in accordance with MIL-PRF-19500 and table III herein for qualification or requalification only. In case qualification was awarded to a prior revision of the slash sheet that did not request the performance of table II tests, the tests specified in table II herein must be performed to maintain qualification. Electrical measurements (end-points) shall be in accordance with the applicable steps of table I, subgroup 2 herein and for delta measurements see table III when applicable.

4.2.2 JANHC and JANKC die. Qualification shall be in accordance with appendix H of MIL-PRF-19500.

4.2.3 JANJ devices. For JANJ level, 3.3.1 through 3.3.1.3 of MIL-PRF-19500 shall apply, except as modified herein. Supplier imposed requirements as well as alternate screens, procedures, and/or controls shall be documented in the QM plan and must be submitted to the qualifying activity for approval. When alternate screens, procedures, and/or controls are used, in lieu of the JANJ screens herein equivalency shall be proven and documented in the QM plan. Radiation characterization may be submitted in the QM plan at the option of the manufacturer, however, paragraph 3.3.1.1 of MIL-PRF-19500 is not required. Die lot control and rework shall be in accordance with 3.13 and D 3.13.2.1, for MIL-PRF-19500 JANS level. Lot formation and conformance inspection requirements for JANJ shall be those used for JANTXV devices as a minimum.

4.2.4 JANJ qualification. For JANJ qualification, 4.4.2.1 herein shall be performed as required by the qualifying activity.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T16:48Z
Check the source to verify that this is the current version before use.

4.3 Screening (JANS, JANJ, JANTXV and JANTX levels only). Screening shall be in accordance with table IV of MIL-PRF-19500 (appendix E,), and as specified herein. Specified electrical measurements shall be made in accordance with table I herein. Devices that exceed the limits of table I herein shall not be acceptable.

Screen (see Table IV of MIL-PRF-19500)	JANS Level	JANJ Level	JANTXV and JANTX Level
1a 1b	Required Required	Not required Required	Not required Required (JANTXV only)
2	Not required	Not required	Not required
3a 3b (1) 3c	Required Not applicable Thermal impedance (see 4.3.3)	Required Not applicable Thermal impedance (see 4.3.3)	Required Not applicable Thermal impedance (see 4.3.3)
4	Not applicable	Not applicable	Not applicable
5	Not applicable	Not applicable	Not applicable
6	Not applicable	Not applicable	Not applicable
7a 7b	Not applicable Required	Not applicable Required	Not applicable Required
8	Required	Not required	Not required
9	V_{f1} and I_{R1}	V_{f1} and I_{R1}	Not Applicable
10	Method 1038 of MIL-STD-750 condition A	Method 1038 of MIL-STD-750 condition A	Method 1038 of MIL-STD-750 condition A
11	V_{f1} and I_{R1}; $\Delta V_{f1} \leq \pm 0.1$ V dc ΔI_{R1} ±250 nA dc or 100 percent of initial value whichever is greater.	V_{f1} and I_{R1}; $\Delta V_{f1} \leq \pm 0.1$ V dc ΔI_{R1} ±250 nA dc or 100 percent of initial value whichever is greater.	V_{f1} and I_{R1}
12	Required, see 4.3.1	Required, T = 240 hours see 4.3.1	Required, see 4.3.1
(2) 13	Subgroups 2 and 3 of table I herein; $\Delta I_{R1} \leq 100$ percent of initial reading or 250 nA dc, whichever is greater. $\Delta V_{f1} \leq \pm .1$ V dc change from initial value. Scope display evaluation (see 4.5.3)	Subgroups 2 and 3 of table I herein; $\Delta I_{R1} \leq 100$ percent of initial reading or 250 nA dc, whichever is greater. $\Delta V_{f1} \leq \pm .1$ V dc change from initial value. Scope display evaluation (see 4.5.3)	Subgroup 2 of table I herein; $\Delta I_{R1} \leq 100$ percent of initial reading or 250 nA dc, whichever is greater. $\Delta V_{f1} \leq \pm .1$ V dc change from initial value. Scope display evaluation (see 4.5.3)
14a 14b	Not applicable Optional	Not applicable Optional	Not applicable Optional
15	Required	Not required	Not required
16	Required	Required	Not required
17	Not required	Required subgroup 2 of table I herein	Not required

(1) Thermal impedance shall be performed any time after sealing provided temperature cycling is performed in accordance with MIL-PRF-19500, screen 3 prior to this thermal test.

(2) $Z_{\theta JX}$ is not required in screen 13, if already previously performed.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T16:48Z
Check the source to verify that this is the current version before use.

4.3.1 Power burn-in test conditions. Power burn-in conditions (all levels) are as follows (see 4.5.1): T_A = 50°C max. apply V_R = full rated V_{RWM} (see 1.3); f = 50-60 Hz, I_O = I_{O2} rated (minimum) (see 4.5.1.1).

4.3.2 Screening (JANHC and JANKC). Screening of die shall be in accordance with appendix H of MIL-PRF-19500. As a minimum, die shall be 100-percent probed to ensure compliance with group A, subgroup 2. Burn-in duration for the JANKC level follows JANS requirements; the JANHC follows JANTX requirements.

4.3.3 Thermal impedance $Z_{\theta JX}$ measurements for screening. The $Z_{\theta JX}$ measurements shall be performed in accordance with method 3101 of MIL-STD-750. The maximum screen limit shall be developed by the supplier using statistical methods and it shall not exceed the group A, subgroup 2 herein.

4.3.3.1 Thermal impedance ($Z_{\theta JX}$ measurements) for initial qualification or requalification. The $Z_{\theta JX}$ measurements shall be performed in accordance with method 3101 of MIL-STD-750 (read and record date $Z_{\theta JX}$). $Z_{\theta JX}$ shall be supplied on one lot (500 pieces minimum and a thermal response curve shall be submitted.) Twenty-two of these samples shall be serialized and provided to the qualifying activity for correlation prior to shipment of parts. Measurements conditions shall be in accordance with 4.4.1.

4.4 Conformance inspection. Conformance inspection shall be in accordance with MIL-PRF-19500 and as specified herein. If alternate screening is being performed in accordance with E.5.3.1d of MIL-PRf-19500, a sample of screened devices shall be submitted to and pass the requirements of group A1 and A2 inspection only (table VIb, group B, subgroup 1 is not required to be performed again if group B has already been satisfied in accordance with 4.4.2).

4.4.1 Group A inspection. Group A inspection shall be conducted in accordance with MIL-PRF-19500 and table I herein. The following test conditions shall be used for $Z_{\theta JX}$, group A inspection: $Z_{\theta JX} \leq 1.5$°C/W.

a. I_M ..... 1 mA to 10 mA.

b. I_H ..... 5 A minimum.

c. t_H ..... 10 ms.

d. t_{MD} ..... 100 ∝s maximum.

e. t_{SW} ..... 5 ∝s maximum.

4.4.2 Group B inspection. Group B inspection shall be conducted in accordance with the tests and conditions specified for subgroup testing in table VIa (JANS) and table VIb (JAN, JANJ JANTX and JANTXV) of MIL-PRF-19500. Electrical measurements (end-points) requirements shall be in accordance with the applicable inspections of table I, group A, subgroup 2 herein except $Z_{\theta JX}$ shall be performed after intermittent life only. For delta requirements see table III herein.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T16:48Z
Check the source to verify that this is the current version before use.

4.4.2.1 Group B inspection, table VIa (JANS) of MIL-PRF-19500. For B5 if a failure occurs resubmission shall be at the test conditions of the original sample.

Subgroup	Method	Condition
B3	4066	I_{FSM} = 100 A(pk), 10 surges of 8.3 ms each at 1-minute intervals, superimposed on I_O = 2 A dc; V_R = rated V_{RWM} (see 1.3); T_A = +55°C. This test shall be performed on each sublot.
B4	1037	I_O = 3 A dc (min); apply V_R = maximum rated V_{RWM} (see 1.3 and 4.5.1); 2,000 cycles.
B5	1027	I_O = I_O (rated) dc minimum; T_A =100°C max. apply V_R = rated V_{RWM} (see 1.3 and 4.5.2); adjust T_A and I_O to achieve T_J = +275°C minimum; f = 50-60 Hz.
	or	I_O = I_O (rated) dc minimum; T_A = +50°C max. apply V_R = rated V_{RWM} (see 1.3 and 4.5.2); adjust T_A and I_O to achieve T_J = +200°C minimum for 1,000 hours at double the sample size.; f = 50-60 Hz.
B6	3101 or 4081	+25°C ≤ T_A ≤ +35°C (recorded before test is performed); $R_{\theta JL}$ (maximum) ≤ 22°C/W; L = .375 inch (9.53 mm). For surface mount devices (UL and US versions), $R_{\theta JEC}$ ≤ 11°C/W.
B7		Peak reverse power, see 4.5.5 herein. P_{RM} ≥ 1,000 W. Test shall be performed on each sublot; sampling plan n = 10, c = 0, end points, see table I, subgroup 2 and table III herein. Delta limits: ΔI_R ≤ 100 percent or 50 nA, whichever is greater.

4.4.2.2 Group B inspection, table VIb (JAN, JANJ, JANTX and JANTXV of MIL-PRF-19500.

Subgroup	Method	Condition
B3	1027	I_O = 3 A dc minimum; T_A = +50°C max. adjust T_A and I_O to achieve the required T_J; apply V_R = rated V_{RWM} (see 1.3), f = 50-60 Hz (see 4.5.1.1).

4.4.3 Group C inspection. Group C inspection shall be conducted in accordance with the tests and conditions specified for subgroup testing in table VII of MIL-PRF-19500. Electrical measurements (end-points) shall be in accordance with table I, group A, subgroup 2 herein; except, $Z_{\theta JX}$ need not be performed. See table III herein for delta limits when applicable.

4.4.3.1 Group C inspection, table VII of MIL-PRF-19500.

Subgroup	Method	Condition
C2	2036	Tension: Test condition A; weight = 5 pounds; t = 30 seconds. Lead fatigue: Test condition E; weight 2 pounds. NOTE: Both tension and lead fatigue are not applicable for US devices.
C6	1026	I_O = I_{O2} 3 A dc minimum; T_A = +50°C max. adjust T_A and I_O to achieve the required T_J; apply V_R = rated V_{RWM} (see 1.3), f = 50-60 Hz (see 4.5.1.1).

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T16:48Z
Check the source to verify that this is the current version before use.

4.4.4 Group E inspection. Group E inspection shall be performed for qualification or re-qualification only. In case qualification was awarded to a prior revision of the associated specification that did not request the performance of group E inspection . The tests specified herein must be performed to maintain qualification. Group E inspection shall be conducted in accordance with the conditions specified for subgroup testing in appendix E, table IX of MIL-PRF-19500 and as specified herein. Electrical measurements (end-points) shall be in accordance with table I, group A, subgroup 2 herein; except, $Z_{\theta JX}$ need not be performed. See table III for delta limits when applicable.

4.5 Methods of inspection. Methods of inspection shall be as specified in appropriate tables and as follows.

4.5.1 Burn-in and life tests. These tests shall be conducted with a half-sine waveform of the specified peak voltage impressed across the diode in the reverse direction followed by a half-sine waveform of the specified average rectified current. The forward conduction angle of the rectified current shall be neither greater than 180 degrees, nor less than 150 degrees.

4.5.1.1 Mounting conditions. Any clips or heat sink mounting configurations may be utilized provided that I_O is adjusted such that the junction temperature of each diode is maintained at T_J = 135°C minimum for burn-in and T_J = 150°C minimum for life testing.

4.5.2 Pulse measurements. Conditions for pulse measurement shall be as specified in section 4 of MIL-STD-750.

4.5.3 Scope display evaluation. Scope display evaluation shall be sharp and stable in accordance with method 4023 of MIL-STD-750. Scope display may be performed on ATE (automatic test equipment) for screening only with the approval of the qualifying activity. Scope display in group A shall be performed on a scope.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T16:48Z
Check the source to verify that this is the current version before use.

4.5.4 Thermal resistance. Thermal resistance measurements shall be conducted in accordance with test method 3101 or 4081 of MIL-STD-750. Read and record data in accordance with group E herein and shall be included in the qualification report. Forced moving air or draft shall not be permitted across the devices during test. The maximum limit for $R_{\theta JL}$ under these test condition shall be $R_{\theta JL} \leq 22°C/W$ for L = .375; $R_{\theta JEC} \leq 11°C/W$ for L= 0 (US version). The following conditions shall apply:

a. I_H ..... 2 A minimum.

b. t_H ..... Thermal equilibrium.

c. I_M ..... 1.0 mA to 10 mA.

d. t_{MD} ..... 100 ∝s maximum.

The device shall be allowed to reach equilibrium at current I_H before the measurement shall be made ($t_H \geq 25$ sec).

LS = Lead spacing = .375 inch (9.53) mm minimum for leaded devices and LS = 0 minimum for unleaded devices as defined (see figure 8) (Metric equivalents are given for general information only):




FIGURE 8. Mounting arrangement.

4.5.5 Peak reverse power test. This test shall be measured in the circuit on figure 9 or equivalent. A 20 microsecond half-sine wave of current shall be used and peak reverse power shall be determined by the product of peak reverse voltage and peak reverse current.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T16:48Z
Check the source to verify that this is the current version before use.

TABLE I. Group A inspection.

Inspection 1/	MIL-STD-750		Symbol	Limits		Unit
	Method	Conditions		Min	Max	
Subgroup 1						
Visual and mechanical inspection	2071					
Subgroup 2						
Thermal impedance	3101	See 4.3.3	$Z_{\theta JX}$		1.5	°C/W
Forward voltage	4011	I_f = 9.0 A(pk); duty cycle ≤ 2 percent (pulsed); t_p ≤ 8.3 ms	V_{f1}			
1N5550, 1N5550US				0.6	1.2	V(pk)
1N5551, 1N5551US				0.6	1.2	V(pk)
1N5552, 1N5552US				0.6	1.2	V(pk)
1N5553, 1N5553US				0.6	1.3	V(pk)
1N5554, 1N5554US				0.6	1.3	V(pk)
Forward voltage	4011	I_F = 1.5 A dc	V_{F1}	0.5	1.0	V dc
Reverse current leakage	4016	DC method	I_{R1}			
1N5550, 1N5550US		V_R = 200 V dc				∝A dc
		V_R = 400 V dc			1.0	∝A dc
1N5551, 1N5551US		V_R = 600 V dc			1.0	∝A dc
1N5552, 1N5552US		V_R = 800 V dc			1.0	∝A dc
1N5553, 1N5553US		V_R = 1,000 V dc			1.0	∝A dc
1N5554, 1N5554US					1.0	
Breakdown voltage (diodes)	4021		V_{BR1}			
1N5550, 1N5550US		I_R = 50 ∝A dc		240		V dc
1N5551, 1N5551US		I_R = 50 ∝A dc		460		V dc
1N5552, 1N5552US		I_R = 50 ∝A dc		660		V dc
1N5553, 1N5553US		I_R = 50 ∝A dc		880		V dc
1N5554, 1N5554US				1,100		V dc
Subgroup 3						
High temperature operation:		T_A = +100°C				

See footnotes at end of table.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T16:48Z
Check the source to verify that this is the current version before use.

TABLE I. Group A inspection - Continued.

Inspection 1/	MIL-STD-750		Symbol	Limits		Unit
	Method	Conditions		Min	Max	
Subgroup 3 - Continued						
Reverse current leakage		DC method	I_{R2}			
Reverse current leakage	4016	DC method				
1N5550, 1N5550US		V_R = 200 V dc			75	∝A dc
1N5551, 1N5551US		V_R = 400 V dc			75	∝A dc
1N5552, 1N5552US		V_R = 600 V dc			75	∝A dc
1N5553, 1N5553US		V_R = 800 V dc			75	∝A dc
1N5554, 1N5554US		V_R = 1,000 V dc			75	∝A dc
Forward voltage	4011	I_f = 9.0 A(pk); duty cycle ≤ 2 percent (pulsed); t_p ≤ 8.3 ms	V_{f2}			
1N5550, 1N5550US					1.2	V(pk)
1N5551, 1N5551US					1.2	V(pk)
1N5552, 1N5552US					1.2	V(pk)
1N5553, 1N5553US					1.3	V(pk)
1N5554, 1N5554US					1.3	V(pk)
Low temperature operation:		T_A = -55°C				
Forward voltage	4011	I_f = 9.0 A(pk); duty cycle ≤ 2 percent (pulsed); t_p ≤ 8.3 ms	V_{f3}		1.5	V(pk)
Forward voltage	4011	I_F = 1.5 A dc	V_F	0.5	1.2	V dc
Breakdown voltage (diodes)	4021		V_{BR2}			
1N5550, 1N5550US		I_R = 50 ∝A dc		200		V dc
1N5551, 1N5551US		I_R = 50 ∝A dc		400		V dc
1N5552, 1N5552US		I_R = 50 ∝A dc		600		V dc
1N5553, 1N5553US		I_R = 50 ∝A dc		800		V dc
1N5554, 1N5554US				1,000		V dc
Subgroup 4						
Reverse recovery time	4031	Condition B-1	t_{rr}		2.0	∝s
Scope display	4023	See 4.5.3 n = 116, c = 0				

See footnotes at end of table.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T16:48Z
Check the source to verify that this is the current version before use.

TABLE I. Group A inspection - Continued.

Inspection 1/	MIL-STD-750		Symbol	Limits		Unit
	Method	Conditions		Min	Max	
Subgroups 5 Not applicable						
Subgroup 6 Surge current	4066	I_{FSM} = 100 A(pk), 10 surges of 8.3 ms each at 1-minute intervals, superimposed on I_O = 2 A dc; V_R = rated V_{RWM} (see 1.3); T_A = +55°C. This test shall be performed on each sublot.				
Subgroup 7 Not applicable						

1/ For sampling plan, see MIL-PRF-19500.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T16:48Z
Check the source to verify that this is the current version before use.

TABLE II. Group E inspection (all quality levels) for qualification only.

Inspection	MIL-STD-750		Sampling plan
	Method	Conditions	
Subgroup 1			22 devices c = 0
Temperature cycling	1051	500 cycles, condition C	
Electrical measurements 1/		See table I, group A, subgroup 2	
Subgroup 2			22 devices c = 0
Steady-state dc blocking life	1038	1,000 hours, condition A $V_R = V_{RWM}$	
Electrical measurements 1/		See table I, group A, subgroup 2	
Subgroup 3			
Not applicable			
Subgroup 4			22 devices c = 0
Thermal resistance	3101 or 4081	See 4.5.4; $R_{\theta JL}$ = 22°C/W $R_{\theta JEC}$ = 11°C/W	
Junction temperature rise (see 4.5.4)		See figures 10, 11 and 12; $\Delta T_J \leq 120°C$; L = .375 inch; T_L = 55°C; I_O = 5 A dc 2/	
Subgroup 5			22 devices c = 0
Barometric pressure, reduced (altitude operation)	1001	Pressure (see 1.3); t = 1 min. DC method; $V_R = V_{RWM}$ (see 1.3) I_{R1} = 1.0 ∝A dc maximum	
Subgroup 6			
Not applicable			
Subgroup 7			n = 22, c = 0
Peak reverse power		See 4.5.5 herein. $P_{RM} \geq$ 1,000 W. Test shall be performed on each sublot; sampling plan:, , end-points see table I, subgroup 2 and table III delta limits herein.	

1/ $Z_{\theta JX}$ not applicable.

2/ For surface mount device, I_O = 5 A dc and T_{EC} (end cap temperature) = 75°C.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T16:48Z
Check the source to verify that this is the current version before use.

TABLE III. Delta requirements. 1/ 2/ 3/ 4/

Step	Inspection	MIL-STD-750		Symbol	Limits		Unit
		Method	Conditions		Min	Max	
1.	Reverse current leaking change	4016	DC method	ΔI_{R1} 4/		±100 percent of initial value or ±250 nA dc, whichever is greater.	
2.	Forward voltage change	4011	I_F = 1.5 A dc; pulsed (see 4.5.2)	ΔV_{F1} 4/		±50 mV dc maximum change from previous measured value.	


1/ The electrical measurements for table VIa (JANS) of MIL-PRF-19500 are as follows:
- a. Subgroup 3, see table III herein, step 2.
- b. Subgroup 4, see table III herein, step 2.
- c. Subgroup 5, see table III herein, steps 1 and 2.

2/ The electrical measurements for table VIb (JAN, JANJ, JANTX and JANTXV) of MIL-PRF-19500 are as follows:
- a. Subgroup 3, see table III herein, step 1.
- b. Subgroup 6, see table III herein, step 1.

3/ The electrical measurements for table VII of MIL-PRF-19500 are as follows:
- a. Subgroup 2, see table III herein, step 1 (JANS).
- b. Subgroup 6, see table III herein, step 1 and 2 (JANS), step 1 (JAN, JANTX, JANTXV and JANJ).

4/ Devices which exceed the group A limits for this test shall not be accepted.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T16:48Z
Check the source to verify that this is the current version before use.



NOTES:

1. L = 13T H22 on 1 inch diameter form (air core).
2. C = 1 to 10 ∝F to give 20 ∝s pulse width.
3. V = Adjustable to 200 volts for power desired in device under test.





FIGURE 9. Typical peak reverse power measurement circuit and waveforms.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T16:48Z
Check the source to verify that this is the current version before use.



NOTE: Blocking diode shall have a forward current rating ≥ 6 A dc.

FIGURE 10. Junction temperature rise test circuit.




FIGURE 11. Junction temperature test oxcillogram (typical).

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T16:48Z
Check the source to verify that this is the current version before use.




FIGURE 12. Expanded oscillogram of V_F.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T16:48Z
Check the source to verify that this is the current version before use.

5. PACKAGING

5.1 Packaging. For acquisition purposes, the packaging requirements shall be as specified in the contract or order (see 6.2). When actual packaging of materiel is to be performed by DoD personnel, these personnel need to contact the responsible packaging activity to ascertain requisite packaging requirements. Packaging requirements are maintained by the Inventory Control Point's packaging activity within the Military Department or Defense Agency, or within the Military Department's System Command. Packaging data retrieval is available from the managing Military Department's or Defense Agency's automated packaging files, CD-ROM products, or by contacting the responsible packaging activity.

6. NOTES

(This section contains information of a general or explanatory nature that may be helpful, but is not mandatory.)

6.1 Intended use. The notes specified in MIL-PRF-19500 are applicable to this specification.

6.2 Acquisition requirements. Acquisition documents must specify the following:

a. Title, number, and date of this specification.

b. Issue of DODISS to be cited in the solicitation and if required, the specific issue of individual documents referenced (see 2.2.1).

c. The lead finish as specified (see 3.4.1).

d. Type designation and quality assurance level.

e. Packaging requirements (see 5.1).


f. For die acquisition, the JANHC or JANKC letter version shall be specified (see figures 3 and 4).

6.3 Qualification. With respect to products requiring qualification, awards will be made only for products which are, at the time of award of contract, qualified for inclusion in Qualified Manufacturer’s List (QML) No.19500 whether or not such products have actually been so listed by that date. The attention of the contractors is called to these requirements, and manufacturers are urged to arrange to have the products that they propose to offer to the Federal Government tested for qualification in order that they may be eligible to be awarded contracts or orders for the products covered by this specification. Information pertaining to qualification of products may be obtained from, Defense Supply Center Columbus, ATTN: DSCC-VQE, P.O. Box 3990, Columbus, OH 43216-5000.

6.4 Supersession information. Devices covered by this specification supersede the manufacturers' and users' Part or Identifying Number (PIN). This information in no way implies that the manufacturers' PIN's are suitable as a substitute for the military PIN.

6.5 Applications data. See figure 13 for maximum power in watts as a function of lead temperature at a distance "L" from the diode body. Device current capability with lead-dissipators or body forced-air-cooling, may be determined from figure 14, which shows maximum average rectified current versus lead temperature as a function of the distance L from the diode body at which lead temperature is measured.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T16:48Z
Check the source to verify that this is the current version before use.




Maximum lead temperature in °C (T_L) at point "L" from body (for maximum operating junction temperature of +175°C with equal two-lead conditions).

L		$R_{\theta JL}$
Inches	mm	°C/W
.000	0.00	11
.250	6.35	16.5
.375	9.53	22
.500	12.70	26
.750	19.05	35.5

NOTES:
1. Dimensions are in inches.
2. Metric equivalents are given for general information only.

FIGURE 13. Maximum power in watts versus lead temperature.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T16:48Z
Check the source to verify that this is the current version before use.



NOTES

1. Dimensions are in inches.
2. Metric equivalents are given for general information only.

FIGURE 14. Maximum current vs lead temperature.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T16:48Z
Check the source to verify that this is the current version before use.

6.6 Suppliers of die. The qualified die suppliers with the applicable letter version (example JANHCA1N5550) will be identified on the QML.

JANC ordering information					
PIN	Manufacturer				
	14552	60211	13409	33178	33178
1N5550	JANHCA1N5550 JANKCA1N5550	JANHCB1N5550	JANHCC1N5550	JANHCD1N5550	JANHCE1N5550
1N5551	JANHCA1N5551 JANKCA1N5551	JANHCB1N5551	JANHCC1N5551	JANHCD1N5551	JANHCE1N5551
1N5552	JANHCA1N5552 JANKCA1N5552	JANHCB1N5552	JANHCC1N5552	JANHCD1N5552	JANHCE1N5552
1N5553	JANHCA1N5553 JANKCA1N5553	JANHCB1N5553	JANHCC1N5553	JANHCD1N5553	JANHCE1N5553
1N5554	JANHCA1N5554 JANKCA1N5554	JANHCB1N5554	JANHCC1N5554	JANHCD1N5554	JANHCE1N5554

6.7 Changes from previous issue. Marginal notations are not used in this revision to identify changes with respect to the previous issue due to the extensiveness of the changes.

Custodians:
Army - CR
Navy - NW
Air Force - 11
DLA - CC

Review activities:
Army - AR, MI, SM
Navy - AS, MC
Air Force - 19, 84, 99

Preparing activity:
DLA - CC

(Project 5961-2437)

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T16:48Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS

1. The preparing activity must complete blocks 1, 2, 3, and 8. In block 1, both the document number and revision letter should be given.

2. The submitter of this form must complete blocks 4, 5, 6, and 7.

3. The preparing activity must provide a reply within 30 days from receipt of the form.

NOTE: This form may not be used to request copies of documents, nor to request waivers, or clarification of requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

I RECOMMEND A CHANGE:	1. DOCUMENT NUMBER MIL-PRF-19500/420F	2. DOCUMENT DATE 011009

3. **DOCUMENT TITLE**
SEMICONDUCTOR DEVICE, DIODE, SILICON, POWER, RECTIFIER, GENERAL PURPOSE TYPES 1N5550 THROUGH 1N5554, 1N5550US THROUGH 1N5554US JAN, JANTX, JANTXV, JANJ, JANS, JANHC, AND JANKC

4. NATURE OF CHANGE (Identify paragraph number and include proposed rewrite, if possible. Attach extra sheets as needed.)

5. REASON FOR RECOMMENDATION

6. SUBMITTER

a. NAME (Last, First, Middle initial)	b. ORGANIZATION	
c. ADDRESS (Include Zip Code)	d. TELEPHONE (Include Area Code) COMMERCIAL DSN FAX EMAIL	7. DATE SUBMITTED

8. PREPARING ACTIVITY

a. Point of Contact Alan Barone	b. TELEPHONE Commercial 614-692-0510 DSN 850-0510 FAX 614-692-6939 EMAIL alan.barone@dscc.dla.mil
c. ADDRESS Defense Supply Center, Columbus ATTN: DSCC-VAC, P.O. Box 3990 Columbus, OH 43216-5000	IF YOU DO NOT RECEIVE A REPLY WITHIN 45 DAYS, CONTACT: Defense Standardization Program Office (DLSC-LM) 8725 John J. Kingman, Suite 2533, Fort Belvoir, VA 22060-6221 Telephone (703) 767-6888 DSN 427-6888

DD Form 1426, Feb 1999 (EG) Previous editions are obsolete WHS/DIOR, Feb 99

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T16:48Z
Check the source to verify that this is the current version before use.