INCH-POUND
MIL-G-23983A(SH)
17 September 1992
SUPERSEDING
MIL-G-23983(SHIPS)
24 January 1964
(See 6.6)

MILITARY SPECIFICATION

# GASKET AND PACKING MATERIAL, OIL RESISTANT RUBBER, ACCESS HULL APPLICATIONS

This specification is approved for use by the Naval Sea Systems Command, Department of the Navy, and is available for use by all Departments and Agencies of the Department of Defense.

## 1. SCOPE

1.1 Scope. This specification establishes the requirements for synthetic rubber gasket and packing material for use in hatches, torpedo tube doors and other hull penetrations of underwater vehicles.

## 2. APPLICABLE DOCUMENTS

2.1 Government documents.

2.1.1 Specifications, standards and handbooks. The following specifications, standards and handbooks form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those listed in the issue of the Department of Defense Index of Specifications and Standards (DODISS) and supplement thereto, cited in the solicitation (see 6.2).

SPECIFICATIONS

FEDERAL
PPP-F-320 - Fiberboard, Corrugated and Solid, Sheet Stock (Container Grade), and Cut Shapes.

MILITARY
MIL-P-116 - Preservation, Method of.
MIL-P-4861 - Packing, Preformed, Rubber, Packaging of.
MIL-L-19140 - Lumber and Plywood, Fire-Retardant Treated.

STANDARDS

FEDERAL
FED-STD-601 - Rubber: Sampling and Testing.

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Commander, ATTN: SEA 05Q42, Naval Sea Systems Command, 2531 National Center Building 3, Washington, DC 20362-5160 by using the Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

AMSC N/A FSC 5330

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T18:39Z
Check the source to verify that this is the current version before use.

MILITARY

MIL-STD-190 - Identification Marking of Rubber Products.
MIL-STD-289 - Visual Inspection Guide for Rubber Sheet.
MIL-STD-407 - Visual Inspection Guide for Rubber Molded Items.
MIL-STD-413 - Visual Inspection Guide for Rubber O-Rings.
MIL-STD-2073-1 - DoD Material Procedures for Development and Application of Packaging Requirements.

(Unless otherwise indicated, copies of federal and military specifications, standards, and handbooks are available from the Standardization Documents Order Desk, Bldg. 4D, 700 Robbins Avenue, Philadelphia, PA 19111-5094.)

2.2 Non-Government publications. The following documents form a part of this document to the extent specified herein. Unless otherwise specified, the issues of the documents which are DOD adopted are those listed in the issue of the DODISS cited in the solicitation. Unless otherwise specified, the issues of documents not listed in the DODISS are the issues of the documents cited in the solicitation (see 6.2).

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

D412 - Rubber Properties in Tension.
D1390 - Method of Test for Stress Relaxation of Vulcanized Rubber in Compression.
D3951 - Standard Practice for Commercial Packaging. (DOD adopted)

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.)

(Non-Government standards and other publications are normally available from the organizations that prepare or distribute the documents. These documents also may be available in or through libraries or other informational services.)

2.3 Order of precedence. In the event of a conflict between the text of this document and the references cited herein (except for related associated detail specifications, specification sheets or MS standards), the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 Material. The material shall be a synthetic rubber compound furnished in the form of sheets, strips, gaskets, cut, extruded or molded items of the dimensions and tolerances specified (see 6.2).

3.2 Physical requirements. The synthetic rubber compound shall conform to the requirements in table I.



Source: https://assist.dla.mil -- Downloaded: 202610-19T18:39Z
Check the source to verify that this is the current version before use.

TABLE I. Physical requirements.

| Test | Requirement | Paragraphs |
|---|---|---|
| Tensile strength, initial, p.s.i., minimum | 1500 | 4.5.1 |
| Tensile strength, aged, retention, percent, minimum | 80 | 4.5.10 |
| Ultimate elongation, initial, percent, minimum | 300 | 4.5.2 |
| Ultimate elongation, aged retention, percent, minimum | 80 | 4.5.2, 4.5.10 |
| Hardness, Shore A units | 65 ± 5 | 4.5.3 |
| Sealing pressure, p. s. i. , minimum | 250 | 4.5.4 |
| Sealing pressure, aged, p.s.i. , minimum | 200 | 4.5.4, 4.5.10 |
| Stress relaxation (initial back stress) p.s.i., minimum | 175 | 4.5.5 |
| Stress relaxation, aged, percent of initial, maximum | 40 | 4.5.5 |
| Compression set, percent, maximum | 30 | 4.5.6, 4.5.10 |
| Volume change (water), percent, (no shrinkage) | 0 to plus 10 | 4.5.7, 4.5.11 |
| Volume change (oil), percent, (no shrinkage) | 0 to plus 5 | 4.5.7, 4.5.11 |
| Flexibility, grams, maximum | | |
| 1 inch | 25 | 4.5.8 |
| 2inches | 35 | 4.5.8 |
| Ozone resistance | shall not crack | 4.5.9 |

3.2.1 Identification. Material supplied under this specification shall be identified in accordance with MIL-STD-190. The material shall be marked with a blue and a green color. The marking shall be accomplished by molding when the size and shape of the item permits this to be done without damage to critical surfaces of the item itself. All surfaces of an O-ring are considered critical. If molding cannot be done a suitable permanent marking material shall be used or in the case of individual one-item packaging, the marking may be put on the package.

## 4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements (examinations and tests) as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in this specification where such inspections are deemed necessary to ensure supplies and services conform to prescribed requirements.



Source: https://assist.dla.mil -- Downloaded: 2026-10-19T18:39Z
Check the source to verify that this is the current version before use.

4.1.1 Responsibility for compliance. All items shall meet all requirements of sections 3 and 5. The inspection set forth in this specification shall become a part of the contractor's overall inspection system or quality program. The absence of any inspection requirements in the specification shall not relieve the contractor of the responsibility of ensuring that all products or supplies submitted to the Government for acceptance comply with all requirements of the contract. Sampling inspection, as part of the manufacturing operations, is an acceptable practice to ascertain conformance to requirements, however, this does not authorize submission of known defective material, either indicated or actual, nor does it commit the Government to accept defective material.

4.2 Classification of inspections. The inspection requirements specified herein are classified as follows:

(a) First article inspection (not applicable).
(b) Quality conformance inspection (see 4.4).

4.3 Sampling for quality conformance inspection.

4.3.1 Lot. For purposes of sampling and examination, all items of the same dimensions produced from a single batch or production run and offered for delivery at one time shall be considered a lot.

4.3.1.1 Gaskets extruded, cut and molded items. The lot size shall be the number of gaskets, extruded, cut or molded items in the lot.

4.3.1.2 Sheets and strips. The lot size shall be the number of unit areas in all sheets or strips of the lot. A unit area is defined as an area of 1 square foot; thus a sheet 2-feet wide and 20-feet long would be 40 units and a strip 4-inches wide by 20-feet long would be 7 units.

4.3.2 Sampling for examination. The sample size (number of samples to be selected from a lot and examined as specified in 4.4.1) shall be as follows:

TABLE II. Sampling for examination.

| Lot size | Sample size | | Accept | Reject 1/ 2/ 3/ |
|---|---|---|---|---|
| | Major defects | Total defects (major plus minor) | | |
| 1 to 15 | 6 | 4 | 0 | 1 |
| 16 to 25 | 8 | 6 | 0 | 1 |
| 26 to 90 | 13 | 10 | 0 | 1 |
| 91 to 150 | 20 | 15 | 0 | 1 |
| 151 to 280 | 32 | 20 | 0 | 1 |
| 281 to 500 | 50 | 30 | 0 | 1 |
| 501 to 1200 | 80 | 50 | 0 | 1 |
| 1201 to 3200 | 125 | 90 | 0 | 1 |
| 3201 and over | 200 | 100 | 0 | 1 |



Source: https://assist.dla.mil -- Downloaded: 202610-19T18:39Z
Check the source to verify that this is the current version before use.

1/ All defective items shall be replaced with acceptable items prior to lot acceptance.
2/ Inspect sample size until reject criteria is reached. If reject criteria is reached, the entire lot shall be rejected.
3/ Reject lots may be screened and resubmitted for inspection and test.

4.3.2.1 The specified samples shall be selected at random from the lot. The sampling of the sheet and strip material shall be divided among all rolls in the lot.

4.3.3 Sampling for tests. For the tests specified in 4.4.2 and 4.4.3, representative samples from different portions of each lot shall be selected as follows:

| Lot size | Number of samples |
|---|---|
| 2 to 8 | 1 |
| 9 to 150 | 2 |
| 151 to 500 | 3 |
| 501 to 1200 | 5 |
| 1201 to 3200 | 8 |
| 3201 and over | 13 |

4.3.3.1 All the tests required by 4.4.2 or 4.4.3, as applicable, shall be conducted on each sample. If the size of the sample item is not large enough to provide the material necessary for conducting all required tests, sufficient additional samples shall be selected. If molded, extruded, or cut items are of such size or shape that test specimens cannot be cut from them, the required number of test specimens shall be molded from material identical in composition and equivalent in cure and prepared at the same time from material used in the lot of finished material offered for delivery.

4.4 Quality conformance inspection.

4.4.1 Examination. Each of the samples selected in accordance with 4.3.2 shall be examined in conformance with the requirements of 3.2 and all other requirements of the specification which do not involve tests. The following visual inspection guides shall be used to determine and evaluate visual defects:

MIL-STD-289 - Sheet rubber.
MIL-STD-407 - Molded rubber.
MIL-STD-413 - O-rings.

4.4.1.1 Rejection (for visual examination). Any defective pieces in any sample shall be cause for rejection of the entire lot.



Source: https://assist.dla.mil -- Downloaded: 2026-10-19T18:39Z
Check the source to verify that this is the current version before use.

4.4.2 Tests. Each sample selected in accordance with 4.3.3 shall be subjected to the following tests:

| Test | Paragraph |
|---|---|
| Tensile strength, initial and aged | 4.5.1, 4.5.10 |
| Ultimate elongation, initial and aged | 4.5.2, 4.5.10 |
| Hardness | 4.5.3 |
| Compression set | 4.5.6, 4.5.10 |

4.4.2.1 Rejection. If any one of the samples representing a lot is found to be not in conformance with this specification, this shall be cause for rejection of the lot represented by the sample.

4.4.3 Production check tests. Production check tests shall be conducted on the first lot of material offered for delivery under a contract or order and on every fifth lot thereafter. Each sample selected in accordance with 4.3.3 shall be subjected to the following tests:

| Test | Paragraph |
|---|---|
| Sealing pressure, initial and aged | 4.5.4, 4.5.10 |
| Stress relaxation, initial and aged | 4.5.5 |
| Volume change (water) | 4.5.7, 4.5.11 |
| Volume change (oil) | 4.5.7, 4.5.11 |
| Flexibility | 4.5.8 |
| Ozone resistance | 4.5.9 |

4.4.3.1 Rejection. If any one of the samples is found not to be in conformance with this specification, the lot represented by the sample shall be rejected. Furthermore, additional samples shall be selected from (or to represent) each subsequent lot and shall be subjected to the test or tests wherein failure occurred. A lot shall then be accepted only upon completion of the test or tests by all the samples selected to represent the lot. This additional testing shall be discontinued when four successive lots have passed the test or tests.

4.5 Test procedures.

4.5.1 Tensile strength. Initial and after oven aging tensile strength shall be determined in accordance with method 4111 of FED-STD-601.

4.5.2 Ultimate elongation. Initial and after oven aging ultimate elongation shall be determined in accordance with ASTM D 412.

4.5.3 Hardness. Hardness shall be determined in accordance with method 3021 of FED-STD-601 using a Shore A durometer and a 15 second reading.

4.5.4 Sealing pressure. Initial and after oven aging sealing pressure shall be determined in accordance with method 3211 of FED-STD-601 except the aging time and temperature shall be as specified in 4.5.10.



Source: https://assist.dla.mil -- Downloaded: 2026-10-19T18:39Z
Check the source to verify that this is the current version before use.

4.5.5 Stress relaxation. The initial and after oven aging stress relaxation (back stress) shall be determined in accordance with ASTM D 1390 except that the oven aging period shall be for 166 hours plus or minus 2 hours at 90° plus or minus 1°C (194° plus or minus 1.8°F).

4.5.6 Compression set. Compression set shall be determined in accordance with method 3311 of FED-STD-601 except the aging time and temperature shall be as specified in 4.5.10.

4.5.7 Volume change. Volume change after liquid immersion shall be determined in accordance with method 6211 of FED-STD-601. The immersion mediums, time, and temperature shall be as specified in 4.5.11.

4.5.8 Flexibility. Flexibility shall be determined in accordance with method 5211 of FED-STD-601 except that the exposure temperature shall be minus 29° plus or minus 2°C (minus 20° plus or minus 3.6°F).

4.5.9 Ozone resistance.

4.5.9.1 Specimens. The specimens shall consist of three strips. Each strip shall be 1/4 by 6 by 0.080 inch.

4.5.9.2 Procedure. The specimens shall be clamped at the ends and stretched to 20 percent elongation. The clamping device shall permit free circulation of air past each of the four longitudinal surfaces (front, back and two sides) of each specimen. A thin layer of melted paraffin wax shall be applied by brush to each of the four surfaces of the stretched specimen in the areas immediately adjacent to the clamps to prevent cracking of the specimen in the areas. At least 4 inches of each longitudinal surface shall be free of wax. The stretched specimens shall be conditioned for 16 hours plus or minus 1/4 hours at 38° plus or minus 1°C (100° plus or minus 1.8°F) in accordance with method 7221 of FED-STD-601. They shall then be exposed to air containing 1.0 plus or minus 0.05 parts of ozone per one million parts of air by volume for 168 hours plus or minus 2 hours at 38° plus or minus 1°C (100° plus or minus 1.8°F). Immediately after this exposure the stretched specimens shall be examined carefully for surface cracks using a hand glass with a magnification of at least 10X.

4.5.10 Oven aging. Test specimens for oven aging (tensile strength, ultimate elongation, sealing pressure, and compression set) shall be aged in accordance with method 7221 of FED-STD-601 except that the aging shall be conducted at 90° plus or minus 1°C (194° plus or minus 1.8°F) for 46 hours plus or minus 1/4 hours.

4.5.11 Liquid immersion. The test fluids for liquid immersions (volume change) shall be distilled water and medium method 6001 of FED-STD-601. The immersion time and temperature for the water shall be 166 hours plus or minus 2 hours at 100° plus or minus 1°C (212° plus or minus 1.8°F). The immersion time and temperature for the oils shall be 70 hours plus or minus 1/4 hours at 100° plus or minus 1°C (212° plus or minus 1.8°F).



Source: https://assist.dla.mil -- Downloaded: 2026-10-19T18:39Z
Check the source to verify that this is the current version before use.

4.6 Inspection of packaging. The inspection of preservation, packing and marking for shipment, stowage, and storage shall be in accordance with the requirements of section 5 and the documents specified therein.

5. PACKAGING

(The packaging requirements specified herein apply only for direct Government acquisition.)

5.1 General.

5.1.1 Navy fire-retardant requirements.

(a) Treated lumber and plywood. Unless otherwise specified (see 6.2) all lumber and plywood including laminated veneer material used in shipping container and pallet construction, members, blocking bracing, and reinforcing shall be fire-retardant treated material conforming to MIL-L-19140 as follows:

| | | |
|---|---|---|
| Levels A and B | - Type II | - weather resistant. |
| | Category 1 | - general use. |
| Level C | - Type I | - non-weather resistant. |
| | Category 1 | - general use. |

(b) Fiberboard. Unless otherwise specified (see 6.2), fiberboard used in the construction of class-domestic, non-weather resistant fiberboard and cleated fiberboard boxes including interior packing forms shall meet the flamespread index and the specific optic density requirements of PPP-F-320 and amendment thereto.

(c) Cushioning and wrapping materials. The use of excelsior, newspaper, shredded paper (all types), and similar hydroscopic or nonneutral materials and all types of loose fill materials for packaging applications such as cushioning, fill, stuffing, and dunnage is prohibited. Materials selected for cushioning and wrapping shall have properties (characteristics) for resistance to fire (see 6.4). Cushioning or wrapping materials, as applicable, shall be provided to prevent item and package damage and to prevent free movement of the container contents.

5.1.2 Asbestos.

5.1.2.1 Dusting material. Unless otherwise specified (see 6.2), dusting material such as talc, talcum and powdered soapstone shall be asbestos free (see 6.3).

5.2 Preservation. Preservation shall be level A, C or commercial as specified (see 6.2).

5.2.1 Level A. The rubber gasket material in the form specified (see 3.1), shall be dusted (see 5.1.2) and unit protected in accordance with MIL-P-116, method III, except as otherwise specified herein, and as follows:



Source: https://assist.dla.mil -- Downloaded: 2026-10-19T18:39Z
Check the source to verify that this is the current version before use.

(a) Sheets. Sheets, in dimensions specified (see 3.1), shall be interleaved with either a kraft paper or plastic film and rolled. Rolls shall be individually wrapped with waterproof, kraft paper or plastic and the wrapped secured by use of adhesive, ties, pressure sensitive tape or non-metallic banding.

(b) Strips. Strips, in dimensions specified (see 3.1), shall be interleaved, coiled, each coil wrapped and secured as specified for sheets. Coils shall be individually unit packed in a water resistant folding, set-up, or metal edged paperboard or fiberboard box meeting the unit container requirements of MIL-STD-2073-1, Appendix F, at the contractor's option. Box closure shall be in accordance with the applicable box specification.

(c) Gaskets. Gaskets, in quantity specified (see 6.2), interleaved as specified for sheets and protected against bending, crushing, and deformation shall be unit packed together without folding in containers as specified for strips.

(d) Extruded or molded items. Items, except for preformed packing (o-rings) (see 5.2.4), shall be wrapped as specified for sheets and individually unit packed in containers as specified for strips.

5.2.2 Level C. Gasket material in the form specified (see 3.1), shall be preserved as specified under level A except that the unit containers specified in 5.2.1 (b), shall be as follows:

(a) The paperboard containers shall be of the domestic or nonweather resistant type, class or variety as applicable and,

(b) The fiberboard box shall be of the class-domestic/fire-retardant material (see 5.1.1 (b)). The box closure shall be in accordance with method I using pressure sensitive adhesive tape.

5.2.3 Commercial. Commercial packaging (cleaning, preservation, cushioning, and unit pack) shall be in accordance with ASTM D 3951.

5.2.4 Preformed packing (o-ring). Preparation (preservation, unit and intermediate packaging) of preformed packing (see 3.2.1) shall be in accordance with MIL-P-4861 for the level specified (see 6.2) and 5.1 herein.

5.3 Packing. Packing shall be level A, B, C or commercial as specified (see 6.2).

5.3.1 General requirements for levels A, B and C. Containers selected (see 5.3.2), shall be of minimum weight and cube consistant with the protection required, and of uniform sized.

5.3.2 Levels A, B and C containers. Gasket material including preformed packing (see 5.2.4), preserved as specified (see 5.2), shall be packed in exterior shipping containers for the level of packing specified (see 5.3), in



Source: https://assist.dla.mil -- Downloaded: 2026-10-19T18:39Z
Check the source to verify that this is the current version before use.

accordance with table VII of MIL-STD-2073-1, Appendix C, and herein. Unless otherwise specified (see 6.2), container selection shall be at the contractor's option.

5.3.2.1 Caseliners, closure and gross weight.

5.3.2.1.1 Caseliners. When specified (see 6.2), level A shipping containers containing items preserved level C or commercial shall be provided with waterproof caseliners in accordance with MIL-STD-2073-1.

5.3.2.1.2 Closure. Container closure, reinforcing, or banding shall be in accordance with the applicable container specification or appendix thereto except that weather-resistant fiberboard boxes shall be closed in accordance with method V and reinforced with non-metallic or tape banding and domestic or fire-retardant fiberboard boxes shall be closed in accordance with method I using pressure sensitive tape.

5.3.2.1.3 Weight. Wood, plywood, and cleated type containers exceeding 200 pounds gross weight shall be modified by the addition of skid in accordance with MIL-STD-2073-1 and the applicable container specification or appendix thereto.

5.3.3 Commercial. Gasket material including preformed packing (see 5.2.4), preserved as specified (see 5.2) shall be packed for shipment in accordance with ASTM D 3951 and herein.

5.3.3.1 Container modification. Shipping containers exceeding 200 pounds gross weight shall have a minimum of two, 3-inch by 4-inch nominal wood skids laid flat, or a skid or sill type base which will support the material and facilitate handling by mechanical handling equipment during shipment, stowage and storage.

5.4 Marking, levels A, B, C and commercial. In addition to any special marking required (see 6.2), and herein, interior (unit) packs and shipping containers shall be marked including bar coding and the material cure date (quarter and year) for shipment, stowage, and storage in accordance with MIL-STD-2073-1, Appendix F. In addition, preformed packing material shall include the markings of MIL-P-4861.

6. NOTES

(This section contains information of a general or explanatory nature that may be helpful, but is not mandatory.)

6.1 Intended use. The synthetic rubber gasket material and packing material is intended for use on hatches, torpedo tube doors and other hull penetrations of underwater vehicles.



Source: https://assist.dla.mil -- Downloaded: 2026-10-19T18:39Z
Check the source to verify that this is the current version before use.

6.2 Acquisition requirements. Acquisition documents must specify the following:

(a) Title, number, and date of this specification.
(b) Issue of DoDISS to be cited in the solicitation, and if required, the specific issue of individual documents referenced (see 2.1.1 and 2.2).
(c) Form, dimensions and tolerances required (see 3.2).
(d) When fire-retardant packaging materials are not required (see 5.1.1 (a) and (b)).
(e) When a certificate of compliance is not required (see 5.1.2.1).
(f) Quantity of gaskets per unit pack (see 5.2.1 (c)).
(g) Level of preservation and level of packaging required (see 5.2, 5.2.4 and 5.3).
(h) Container selection if other than contractor's option (see 5.3.2).
(i) When caseliners are not required (see 5.3.2.1.1).
(j) Special marking required (see 5.4).

6.3 Consideration of data requirements. The following data requirements should be considered when this specification is applied on a contract. The applicable Data Item Descriptions (DIDs) should be reviewed in conjunction with the specific acquisition to ensure that only essential data are requested/ provided and that the DIDs are tailored to reflect the requirements of the specific acquisition. To ensure correct contractual application of the data requirements, a Contract Data Requirements List (DD Form 1423) must be prepared to obtain the data, except where DOD FAR Supplement 27.475-1 exempts the requirement for a DD Form 1423.

| Reference paragraph | DID number | DID title | Suggested tailoring |
|---|---|---|---|
| 5.1.2 | DI-T-2072 | Test report | ----- |

The above DIDs were those cleared as of the date of this specification. The current issue of DOD 5010.12-L, Acquisition Management Systems and Data Requirements Control List (AMSDL), must be researched to ensure that only current, cleared DIDs are cited on the DD Form 1423.

6.4 Cushioning and wrapping materials (see 5.1.1 (c)). Materials having properties for resistance to fire and acceptable for use within unit packs and shipping containers for Navy acquisitions are:

| Material | Specification |
|---|---|
| Paper, Kraft, Treated (Fire-Resistant) | A-A-1894 |
| Paper, Kraft, Wrapping | UU-P-268, Type II, Grade C or D |
| Fiberboard | PPP-F-320, Class-Domestic/ Fire Retardant |
| Plastic Film, Flexible, Cellular | PPP-C-795, Class 3, Fire |



Source: https://assist.dla.mil -- Downloaded: 2026-10-19T18:39Z
Check the source to verify that this is the current version before use.

| | |
|---|---|
| | Retardant |
| Polystyrene Expanded, Resilient Plastic, Open Cell, Cushioning | PPP-C-850, Grade SE<br>PPP-C-1842, Type I, Style B |
| Bound Fiber | PPP-C-1120, Type III or IV, Class C |
| Rubber, Latex Foam | MIL-R-5001, Grade A |
| Rubber, Cellular | MIL-R-6130, Grade A |
| Fibrous Glass | MIL-C-17435 |
| Polystyrene Foam | MIL-P-19644, Type II |
| Rubber, Cellular, Synthetic | MIL-R-20092, Class 5 |
| Polyurethane Foam | MIL-P-26514 |
| Polyurethane Foam, Flexible, Open Cell | MIL-F-81334 |
| Foam-In-Place Packaging Materials: General Specification For | MIL-F-83671 |
| Foam, Combustion, Retardant, for Cushioning Supply Items Aboard Navy Ships | MIL-F-87090(SA) |

6.5 Subject term (key word) listing.

Hatches
Molded items
O-ring
Torpedo tube doors
Underwater vehicles

6.6 Changes from previous issue. Marginal notations are not used in this revision to identify changes with respect to the previous issue due to the extensiveness of the changes.

Preparing activity:
Navy - SH
(Project 5330-N124)



Source: https://assist.dla.mil -- Downloaded: 2026-10-19T18:39Z
Check the source to verify that this is the current version before use.

# STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

## INSTRUCTIONS

1. The preparing activity must complete blocks 1, 2, 3, and 8. In block 1, both the document number and revision letter should be given.
2. The submitter of this form must complete blocks 4, 5, 6, and 7.
3. The preparing activity must provide a reply within 30 days from receipt of the form.

NOTE: This form may not be used to request copies of documents, nor to request waivers, or clarification of requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

| I RECOMMEND A CHANGE: | 1. DOCUMENT NUMBER<br>MIL-G-23983A(SH) | 2. DOCUMENT DATE (YYMMDD)<br>1992 09 17 |
|---|---|---|

**3. DOCUMENT TITLE**
Gasket and Packing Material, Oil Resistant Rubber, Access Hull Applications

**4. NATURE OF CHANGE** *(Identify paragraph number and include proposed rewrite, if possible. Attach extra sheets as needed.)*

**5. REASON FOR RECOMMENDATION**

**6. SUBMITTER**

| a. NAME (Last, First, Middle Initial) | b. ORGANIZATION | |
|---|---|---|
| c. ADDRESS (Include Zip Code) | d. TELEPHONE (Include Area Code)<br>(1) Commercial<br>(2) AUTOVON (If applicable) | 7. DATE SUBMITTED (YYMMDD) |

**8. PREPARING ACTIVITY** TECHNICAL POINT OF CONTACT:

| a. NAME | b. TELEPHONE (Include Area Code)<br>(1) Commercial | (2) AUTOVON |
|---|---|---|
| MR. Richard Dempsey (05M3.2) | (703)602-0146 | 8-332-0146 |

c. ADDRESS (Include Zip Code)
Commander, SEA 05Q42
Naval Sea Systems Command
2531 National Center Building 3
Washington, DC 20362-5160

**IF YOU DO NOT RECEIVE A REPLY WITHIN 45 DAYS, CONTACT:**
Defense Quality and Standardization Office
5203 Leesburg Pike, Suite 1403, Falls Church, VA 22041-3466
Telephone (703) 756-2340 AUTOVON 289-2340

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T18:39Z
Check the source to verify that this is the current version before use.