The documentation and process conversion measures necessary to comply with this revision shall be completed by 23 May 2006.

INCH-POUND
MIL-PRF-19500/260J
23 February 2006
SUPERSEDING
MIL-PRF-19500/260H
15 March 2005

PERFORMANCE SPECIFICATION SHEET

SEMICONDUCTOR DEVICE, DIODE, SILICON, POWER RECTIFIER,
TYPES 1N1202A, 1N1204A, 1N1206A, 1N3671A, 1N3673A, AND AR VERSIONS,
JAN, JANTX, JANTXV, JANS, JANHC, AND JANKC,
1N1124A, 1N1126A, 1N1128A, 1N3649, 1N3650, 1N1124RA,
1N1126RA, 1N1128RA , 1N3649R, AND 1N3650R, JAN ONLY

The 1N1124A, 1N1126A, 1N1128A, 1N3649, 1N3650 and reverse versions have been moved from MIL-S-19500/104, which has been canceled, are now inactive for new design.

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The requirements for acquiring the product described herein shall consist of this specification sheet and MIL-PRF-19500.

1. SCOPE

1.1 Scope. This specification covers the performance requirements for silicon semiconductor power rectifier diodes. Four levels of product assurance are provided for each encapsulated 1N1202A, 1N1204A, 1N1206A, 1N3671A, 1N3673A device type as specified in MIL-PRF-19500, and two levels of product assurance for each unencapsulated device type. One level of product assurance is provided for each device type as specified in MIL-PRF-19500, for the 1N1124A, 1N1126A, 1N1128A, 1N3649, 1N3650. For normal and reverse (A, R, RA, and AR suffix) type devices see 3.4.1.

1.2 Physical dimensions. See figure 1 (DO-203AA, formerly DO–4) and figure 2 (JANHC and JANKC).

1.3 Maximum ratings. Unless otherwise specified, T_C = +25°C.

Type	V_{RWM}	I_O (1) T_C = 150°C	$I_{f(surge)}$ T_C = 150°C T = 1/120 s	Barometric pressure (reduced)	T_J and T_{STG}	$R_{\theta JC}$
	V dc	A dc	A pk	mmHg	°C	°C/W max
1N1202A	200	12 (1)	240	N/A	-65 to +200	2.0
1N1204A	400	12 (1)	240	8	-65 to +200	2.0
1N1206A	600	12 (1)	240	16	-65 to +200	2.0
1N3671A	800	12 (1)	240	30	-65 to +200	2.0
1N3673A	1000	12 (1)	240	54	-65 to +200	2.0
1N1124A (2)	200	3.3 (3)	25	8	-65 to +175	2.0
1N1126A (2)	400	3.3 (3)	25	8	-65 to +175	2.0
1N1128A (2)	600	3.3 (3)	25	16	-65 to +175	2.0
1N3649 (2)	800	3.3 (3)	25	30	-65 to +175	2.0
1N3650 (2)	1,000	3.3 (3)	25	54	-65 to +175	2.0

See notes on next page.

Comments, suggestions, or questions on this document should be addressed to Defense Supply Center, Columbus, ATTN: DSCC-VAC, P.O. Box 3990, Columbus, OH 43218-3990, or emailed to Semiconductor@dscc.dla.mil. Since contact information can change, you may want to verify the currency of this address information using the ASSIST Online database at http://assist.daps.dla.mil .

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T13:57Z
Check the source to verify that this is the current version before use.

1.3 Maximum ratings. Unless otherwise specified, T_C = +25°C - Continued.

(1) Derate linearly 2 percent of I_O per degrees Celcius for T_C = 150°C to T_C = 200°C.
(2) The 1N1124A, 1N1126A, 1N1128A, 1N3649, 1N3650 and reverse versions have been moved from MIL-S-19500/104, which has been canceled, are now inactive for new design.
(3) Derate linearly 23 mA dc/°C for T_C = 50°C to T_C = 150°C.

2. APPLICABLE DOCUMENTS

2.1 General. The documents listed in this section are specified in sections 3, 4, or 5 of this specification. This section does not include documents cited in other sections of this specification or recommended for additional information or as examples. While every effort has been made to ensure the completeness of this list, document users are cautioned that they must meet all specified requirements of documents cited in sections 3, 4, or 5 of this specification, whether or not they are listed.

2.2 Government documents.

2.2.1 Specifications, standards, and handbooks. The following specifications, standards, and handbooks form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those cited in the solicitation or contract.

DEPARTMENT OF DEFENSE SPECIFICATIONS

MIL-PRF-19500 - Semiconductor Devices, General Specification for.

DEPARTMENT OF DEFENSE STANDARDS

MIL-STD-750 - Test Methods for Semiconductor Devices.

(Copies of these documents are available online at http://assist.daps.dla.mil/quicksearch/ or http://assist.daps.dla.mil. or from the Standardization Document Order Desk, 700 Robbins Avenue, Building 4D, Philadelphia, PA 19111-5094.)

2.3 Order of precedence. In the event of a conflict between the text of this document and the references cited herein, the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 General. The individual item requirements shall be as specified in MIL-PRF-19500 and as modified herein.


3.2 Qualification. Devices furnished under this specification shall be products that are manufactured by a manufacturer authorized by the qualifying activity for listing on the applicable qualified manufacturer's list (QML) before contract award (see 4.2 and 6.3).

3.3 Abbreviations, symbols, and definitions. Abbreviations, symbols, and definitions used herein shall be as specified in MIL-PRF-19500.

3.4 Interface and physical dimensions. The interface and physical dimensions shall be as specified in MIL-PRF-19500 and on figures 1 (DO-203AA, formerly DO–4) and figure 2 (JANHC and JANKC).

3.4.1 Normal and reverse (A, R, RA, and AR suffix) types. Reverse and normal types are identical except: The normal types have the cathode connected to the stud and the reverse types have the anode connected to the stud.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T13:57Z
Check the source to verify that this is the current version before use.




Ltr	Dimensions				Notes
	Inches		Millimeters		
	Min	Max	Min	Max	
CH		.405		10.29	
CD		.424		10.77	
HF	.424	.437	10.77	11.10	
HT	.075	.175	1.90	4.44	
OAH		.800		20.32	
C		.250		6.35	9
ϕT	.060		1.52		
SL	.422	.453	10.72	11.51	
K					3,5,7

NOTES:
1. Dimensions are in inches.
2. Millimeters are given for general information only.
3. Units must not be damaged by torque of 15 inch-pounds applied to 10-32NF-2B nut assembled on thread.
4. Diameter of unthreaded portion .189 inch (4.80 mm) max and .163 inch (4.14 mm) min.
5. Complete threads to extend to within 2.5 threads of seating plane.
6. Angular orientation of this terminal is undefined.
7. Max pitch diameter of plated threads shall be basic pitch diameter .169 inch (4.31 mm) reference FED-STD-H28 (Screw Thread Standards for Federal Services.)
8. The A.S.A. thread reference is 10-32UNF2A.
9. Terminal shape is unrestricted.
10. Reversed (anode to stud) units shall be marked with an R following the last digit in the type number
11. In accordance with ASME Y14.5M, diameters are equivalent to ϕx symbology.

FIGURE 1. Physical dimensions (DO-203AA, formerly DO-4), 1N1202A, 1N1204A, 1N1206A, 1N3671A, 1N3673A and AR versions, and 1N1124A, 1N1126A, 1N1128A, and RA versions 1N3649, 1N3650, and R versions.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T13:57Z
Check the source to verify that this is the current version before use.



A Version

Ltr	Dimensions			
	Inches		Millimeters	
	Min	Max	Min	Max
A	.116	.122	2.95	3.10
B	.147	.153	3.73	3.89
C	.009	.012	0.229	0.305

NOTES:
1. Dimensions are in inches.
2. Millimeters are given for general information only.
3. The physical characteristics of the die are: Metallization {front (anode)}, consists of: Ti thickness = 1,200 Å minimum, Ni thickness = 2,000 Å minimum, Ag thickness = 4,000 Å minimum. Metallization {back, (cathode)} consists of: Ti thickness = 1,200 Å minimum, NI thickness = 2,000 Å minimum, Ag thickness = 4,000 Å minimum.
4. In accordance with ASME Y14.5M, diameters are equivalent to ϕx symbology.

FIGURE 2. Physical dimensions JANHC and JANKC 1N1202A, 1N1204A, 1N1206A, 1N3671A, 1N3673A.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T13:57Z
Check the source to verify that this is the current version before use.

3.4.2 Lead finish. Lead finish shall be solderable in accordance with MIL-PRF-19500, MIL-STD-750 and herein. Where a choice of lead finish is desired, it shall be specified in the contract or purchase order (see 6.2).

3.4.3 Diode construction. All devices shall be in accordance with the requirements of MIL-PRF-19500 and herein.

3.5 Marking. Marking shall be in accordance with MIL-PRF-19500.

3.5.1 Polarity. The polarity shall be indicated by a graphic symbol with the arrow pointing toward the negative end for forward bias. The reversed units shall also be marked with an R, AR, or RA suffix in the part number.

3.6 Electrical performance characteristics. Unless otherwise specified herein, the electrical performance characteristics are as specified in 1.3, 1.4, and table I herein.

3.7 Electrical test requirements. The electrical test requirements shall be the subgroups specified in table I herein.

3.8 Workmanship. Semiconductor devices shall be processed in such a manner as to be uniform in quality and shall be free from other defects that will affect life, serviceability, or appearance.

4. VERIFICATION

4.1 Classification of inspections. The inspection requirements specified herein are classified as follows:

a. Qualification inspection (see 4.2).

b. Screening (see 4.3).

c. Conformance inspection (see 4.4).

4.1.1 Sampling and inspection. Sampling and inspection shall be in accordance with MIL-PRF-19500 and herein, except for accumulation period shall be 3 months in lieu of 6 weeks.

4.2 Qualification inspection. Qualification inspection shall be in accordance with MIL-PRF-19500 and herein. Tests in either polarity shall be sufficient to obtain approval of both polarities.

4.2.1 JANHC and JANKC devices. Qualification for JANHC and JANKC devices shall be in accordance with MIL-PRF-19500.

4.2.2 Group E qualification. Group E inspection shall be performed for qualification or re-qualification only. In case qualification was awarded to a prior revision of the specification sheet that did not request the performance of table II tests, the tests specified in table II herein that were not performed in the prior revision shall be performed on the first inspection lot of this revision to maintain qualification.

*4.2.1.1 Group E thermal impedance. Each supplier shall submit a thermal impedance ($Z_{\theta JX}$) histogram of the entire qualification lot. The histogram data shall be taken prior to the removal of devices that are atypical for thermal impedance. Thermal impedance curves (from $Z_{\theta JX}$ test pulse time to $R_{\theta JX}$ minimum steady-state time) of the best device in the qual lot and the worst device in the qual lot (that meets the supplier proposed screening limit), or from the thermal grouping, shall be submitted. The optimal test conditions and proposed initial thermal impedance screening limit shall be provided in the qualification report. Data indicating how the optimal test conditions were derived for $Z_{\theta JX}$ shall also be submitted. The proposed specification maximum thermal impedance curve shall be submitted. The qualifying activity may approve a different $Z_{\theta JX}$ limit not to exceed the specification's thermal curve for conformance inspection end-point measurements as applicable**.** Equivalent data, procedures, or statistical process control plans may be used for part, or all, of the above requirements. The approved thermal impedance conditions and limit for $Z_{\theta JX}$ shall be used by the supplier in screening and table I, subgroup 2. The approved thermal resistance conditions for $R_{\theta JX}$ shall be used by the supplier for conformance inspection. For product families with similar thermal characteristics based on the same physical and thermal die, package, and construction combination (thermal grouping), the supplier may use the same thermal impedance curves.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T13:57Z
Check the source to verify that this is the current version before use.

4.3 Screening. Screening shall be in accordance with table IV of MIL-PRF-19500, and as specified herein. The following measurements shall be made in accordance with table I herein. Devices that exceed the limits of table I herein shall not be acceptable.

Screen (see table IV of MIL-PRF-19500)	Measurement	
	JANS level	JANTX and JANTXV levels
1a 1b	Required Required	Not required Required (JANTXV only)
2	Optional	Not required
3a (1) 3b 3c	Required Surge (see 4.3.1) Thermal impedance (see 4.3.2)	Required Surge (see 4.3.1) Thermal impedance (see 4.3.2)
4	Not applicable	Not applicable
5	Applicable	Not applicable
6	Not applicable	Not applicable
7a 7b	Optional Optional	Optional Optional
8	Required	Not required
(2) 9	V_{F2} and I_{R1}	Not applicable
10	Method 1038 of MIL-STD-750, test condition A, t = 96 hours	Not applicable
11	V_{F2} and I_{R1}; Subgroup 2 of table I herein, $\Delta V_{F2} = \pm 0.1$ V(pk) from initial value; $\Delta I_{R1} = \pm 5$ μA dc or 100 percent from the initial value, whichever is greater.	V_{F2} and I_{R1}
12	Burn-in, see 4.3.3 and 4.5.2. method 1038 of MIL-STD-750, test condition B.	Method 1038 of MIL-STD-750 test condition A, t = 48 hours
13	Subgroups 2 and 3 of table I herein; $\Delta V_{F2} = \pm 0.1$ V (PK); $\Delta I_{R1} = \pm 5$ μA dc or 100 percent from the initial value, whichever is greater.	Subgroup 2 of table I herein, $\Delta V_{F2} = \pm 0.1$ V(pk) from initial value; $\Delta I_{R1} = \pm 5.0$ μA dc or 100 percent from the initial value, whichever is greater.
14a 14b	Required Required	Required Required
15	Required	Not required
16	Required	Not required

(1) Surge shall precede thermal impedance. These tests shall be performed anytime after screen 3a and before screen 9.
(2) I_{R1} measurement shall not be indicative of an open condition.

4.3.1 Surge current. Surge current, method 4066 of MIL-STD-750. IO = 0; VRM(W) = 0; IFSM = 275 A; six surges; T_A = 25°C; tp = 8.3 ms; one minute minimum time between surges.

NOTE: A shorter time between surges will be allowed as long as it can be demonstrated that $\Delta T_J \leq 10°C$, as measured immediately prior to the first current pulse and immediately after the final current pulse.

4.3.2 Thermal impedance The thermal impedance measurements shall be performed in accordance with method 3101 of MIL-STD-750. The thermal impedance conditions and maximum thermal impedance limit shall be derived by each vendor. The chosen thermal impedance measurement and conditions for each device in the qualification lot shall be submitted in the qualification report and a thermal impedance curve shall be plotted. The chosen thermal impedance values shall be considered final after the manufacturer has had the opportunity to test five consecutive lots. Heating current (I_H) ≥ rated I_O; t_H = 150 to 400 ms; t_{MD} = 50 to 300 μs; 50 mA ≤ I_M ≤` 250 mA.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T13:57Z
Check the source to verify that this is the current version before use.

4.3.3 Power burn-in. Power burn-in conditions are as follows: method 1038 of MIL-STD-750, test condition B. T_C = 150°C, f = 60 Hz, I_O = 12 A dc (see 4.5.2); V_R = rated V_{RWM} (pk) (see 1.3).

4.3.4 Screening (JANHC and JANKC). Screening of JANHC and JANKC die shall be in accordance with MIL-PRF-19500. As a minimum, die shall be 100-percent probed to ensure compliance with I_{R1} of table I, subgroup 2.

4.4 Conformance inspection. Conformance inspection shall be in accordance with MIL-PRF-19500, and as specified herein.

4.4.1 Group A inspection. Group A inspection shall be conducted in accordance with MIL-PRF-19500, and table I herein.

4.4.2 Group B inspection. Group B inspection shall be conducted in accordance with the conditions specified for subgroup testing in table VIa (JANS) and table VIb (JAN, JANTX, and JANTXV) of MIL-PRF-19500 and 4.4.2.1 and 4.4.2.2 herein. Electrical measurements (end-points) shall be in accordance with table I, subgroup 2 herein. Delta measurements shall be in accordance with table III herein.

4.4.2.1 Group B inspection, table VIa (JANS) of MIL-PRF-19500.

Subgroup	Method	Condition
B3	1051	-55°C to +175°C, 100 cycles.
B3	4066	Condition A, T_C = 150°C; V_R = (rated V_R) AC peak (see 1.3), I_{FSM} (surge) = 240 A; I_O = 12 A_{AVG}; six surges 1/120 s, t_P = 8.3 mS, one minute minimum time between surges.
B4	1037	0.25 rated $I_O \leq I_O$ applied $\leq$ rated I_O (see 4.5.3) 2,000 cycles.
B5	1027	I_F = 4 A dc; V_R = rated V_R (see 1.3), T_A = 125°C; or adjusted as required to achieve T_J = 275°C minimum (see 4.5.2), f = 60 Hz t = 1,000 hours.
		Option 1: T_A = + 30°C max. ; T_J = 225°C minimum; t = 216 hours; n = 45 c = 0.
	or	Option 2: T_A = + 100°C max. ; T_J = 275°C minimum; t = 96 hours, n = 22, c = 0.
B6	3101 or 4081	$R_{\theta JC}$ = 2.0°C/W maximum; I_M = 50 – 250 mA; $I_H \geq$ rated I_O; $t_H \geq$ 15s; t_{MD} = 50 to 300 µs.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T13:57Z
Check the source to verify that this is the current version before use.

4.4.2.2 Group B inspection, table VIb (JAN, JANTX and JANTXV) of MIL-PRF-19500.

Subgroup	Method	Condition
B2	1051	-55°C to +175°C, 25 cycles.
B2	4066	Condition A, T_C = 150°C; V_R = rated V_R (AC peak) (see 1.3), i_f (surge) = 240 A; I_O = 12 A dc average; six 1/120 s surges. 1 minute minimum time between surges. t_p = 8.3 ms.
	or	
		Test condition C; $T_A = T_C = T_J$ = 200°C; V_R = rated V_R (AC peak) (see 1.3), I_O = 0, I_{FSM} (surge) = 240 A, six 1/120 s surges. 1 minute minimum time between surges. t_p = 8.3 ms.
B3	1037	0.25 rated $I_O \leq I_O$ applied $\leq$ rated I_O (see 4.5.3) 2,000 cycles.
B3	1038 or 1049	Condition A; 340 hrs.
B5		Not required.

4.4.3 Group C inspection. Group C inspection shall be conducted in accordance with the conditions specified for subgroup testing in table VII of MIL-PRF-19500 and as follows. Electrical measurements (end-points) shall be in accordance with table I, subgroup 2 herein. Delta measurements shall be in accordance with table III herein.

4.4.3.1 Group C inspection, table VII of MIL-PRF-19500.

Subgroup	Method	Condition
C2	1056	Test condition B.
C2	2036	Test condition A, weight = 10 pounds, t = 15 s.
C2	2036	Test condition F, method B, weight = 5 pounds, t = 15 s.
C2	2036	Test condition D1, seal torque = 10 ounce-inches, t = 15 s.
C2	2036	Test condition D2, stud torque = 15 pound-inches, t = 15 s.
C5	3101	$R_{\theta JC}$ = 2.0°C/W maximum; I_M = 50 – 250 mA; $I_H \geq$ rated I_O; $t_H \geq$ 15s; t_{MD} = 50 to 300 μs.
C6	1037	0.25 rated $I_O \leq I_O$ applied $\leq$ rated I_O (see 4.5.3) 6,000 cycles.

4.4.4 Group E inspection. Group E inspection shall be conducted in accordance with the conditions specified for subgroup testing in table IX of MIL-PRF-19500. Electrical measurements (end-points) shall be in accordance with table I, subgroup 2 herein. Delta measurements shall be in accordance with table III herein.

4.5 Methods of inspection. Methods of inspection shall be as specified in the appropriate tables and as follows.

4.5.1 Pulse measurements. Conditions for pulse measurement shall be as specified in section 4 of MIL-STD-750.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T13:57Z
Check the source to verify that this is the current version before use.

4.5.2 Burn-in and steady-state operation life tests. These tests shall be conducted with a half-sine waveform of the specified peak voltage impressed across the diode in the reverse direction followed by a half-sine waveform of the specified average rectifier current. The forward conduction angle of the rectified current not be greater than 180 degrees nor less than 150 degrees.

4.5.3 DC intermittent operation life. A cycle shall consist of an on period, when power is applied suddenly, not gradually, to the device for the time necessary to achieve a delta case temperature of 85°C +15°C -5°C followed by an off period, when the power is suddenly removed, for cooling. Auxiliary (forced) cooling is permitted during the off period only. 30 s $\leq t_{Heating} \leq$ 60 s, $P = V_F \times I_F$ or $P = V_{FPK} \times I_{av}$ if using sine wave current. DC full wave current (or equivalent half sine wave current) shall be used for the power required during the on period. The test power, or current, shall be at least the free air rating. Within the time interval of 50 cycles before to 500 cycles after the termination of the test, the sample units shall be removed from the specified test conditions and allowed to reach room ambient conditions. Specified end-point measurements for qualification and quality conformance verification shall be completed within 96 hours after removal of sample units from the specified test conditions. Additional readings may be taken at the discretion of the manufacturer.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T13:57Z
Check the source to verify that this is the current version before use.

TABLE I. Group A inspection.

Inspection 1/	MIL-STD-750		Symbol	Limits		Unit
	Method	Conditions		Min	Max	
Subgroup 1						
Visual and mechanical inspection	2071					
Subgroup 2						
Forward voltage 1N1202A, 1N1204A, 1N1206A, 1N3671A, 1N3673A	4011	I_F = 38 A (pk) pulse; pulse width ≤ 8.5 ms, duty cycle ≤ 2 percent pulse	V_{F2}		1.35	V (pk)
Forward voltage 1N1124A, 1N1126A, 1N1128A, 1N3649, 1N3650	4011	I_F = 10 Adc (pulse): $t_p \leq$ 8.5 msec;	V_F		2.2	V (pk)
Reverse current	4016	DC method, V_R = rated $V_{R(pk)}$ (see 1.3)	I_{R1}		5	µA dc
Thermal impedance	3101	See 4.3.2	$Z_{\theta JX}$			°C/W
Subgroup 3						
High temperature operation:		T_C = 150°C				
Reverse current 1N1202A, 1N1204A, 1N1206A, 1N3671A, 1N3673A	4016	DC method, V_R = rated $V_{R(pk)}$ (see 1.3)	I_{R2}		1	mA dc
1N1124A, 1N1126A, 1N1128A, 1N3649, 1N3650	4016	DC method, V_R = rated $V_{R(pk)}$ (see 1.3)	I_{R2}		200	µA dc
Low temperature operation		T_C = -65°C				
Reverse current 1N1202A, 1N1204A, 1N1206A, 1N3671A, 1N3673A	4016	DC method, V_R = rated $V_{R\ (dc)}$ (see 1.3)	I_{R3}		1	mA dc
Subgroups 4 and 5						
Not applicable						
Subgroup 6 2/						
Forward voltage	4011	$I_F = I_{FSM}$, t_P = 800 µs	V_{F1}		2.5	V dc
Forward voltage	4011	$I_F = I_{FSM}$, $t_P \leq$ 8.3 ms	V_{F1}		2.3	V dc

1/ For sampling plan, see MIL-PRF-19500.
2/ V_{F1} shall be performed with either t_p = 800 µs or t_p = 8.3 ms. This subgroup does not apply to 1N1124A, RA; 1N1126A, RA; 1N1128A, RA; 1N3649, R; and 1N3650, R.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T13:57Z
Check the source to verify that this is the current version before use.

* TABLE II. Group E inspection (all quality levels) for qualification and requalification only.

Inspection	MIL-STD-750		Sampling plan
	Method	Conditions	
Subgroup 1			45 devices c = 0
Thermal shock	1056	100 cycles, 0°C to 100°C.	
Electrical measurements		See table I, subgroup 2 herein.	
Subgroup 2			22 devices c = 0
Steady-state dc blocking life	1038	1,000 hours, condition A.	
Electrical measurements		See table I, subgroup 2	
Subgroup 4			
Thermal impedance curves		See 4.2.1.1	
Subgroup 5			22 devices c = 0
Barometric pressure, reduced (altitude operation)	1001	Hg = rated Hg (see 1.3), t = 60 s, While the 22 devices, c = 0; test is being performed, I_R shall be monitored and shall not exceed table I limits.	
1N1202A, AR 1N1204A, AR 1N1206A, AR 1N3671A, AR 1N3673A, AR		N/A 400 V dc 600 V dc 800 V dc 1,000 V dc	
Subgroup 6			
Not applicable			
Subgroup 7			
Not applicable			

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T13:57Z
Check the source to verify that this is the current version before use.

* TABLE III. Groups B, C and E delta measurements. 1/ 2/ 3/ 4/

Step	Inspection	MIL-STD-750		Symbol	Limits		Unit
		Method	Conditions		Min	Max	
1.	Forward voltage	4011	IF = 38 A (pk) pulse; pulse width ≤ 8.5 ms, duty cycle ≤ 2 percent pulse	ΔVF2	±50 mV dc maximum change from previous measured value.		
2.	Reverse current	4016	DC method, VR = Rated VR(dc) (see 1.3)	ΔIR1 5/	±100 percent of initial value or ±5.0 μA, (whichever is greater) from previous measured value.		

1/ The delta electrical measurements for table Via (JANS) of MIL-PRF-19500 are as follows:
   a. Subgroup 3, see table III herein, steps 1 and 2.
   b. Subgroup 4, see table III herein, steps 1 and 2.
   c. Subgroup 5, see table III herein, step 2.

2/ The delta electrical measurements for table VIb (JAN, JANTX and JANTXV) of MIL-PRF-19500 are as follows:
   a. Subgroup 2, see table III herein, step 1.
   b. Subgroup 3, see table III herein steps1 and 2.

3/ The delta electrical measurements for table VII of MIL-PRF-19500 are as follows:
   a. Subgroup 2 see table III herein, step 1 (JAN, JANTX and JANTXV), steps 1 and 2 (JANS).
   b. Subgroup 6, see table III herein, steps 1 and 2 (JANS), and steps 1 and 2 (JAN, JANTX and JANTXV).

4/ The delta electrical measurements for table IX of MIL-PRF-19500 are as follows:
   a. Subgroup 1 see table III herein, step 1.
   b. Subgroup 2, see table III herein, steps 1 and 2.

5/ Devices which exceed the group A limits for this test shall be rejected.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T13:57Z
Check the source to verify that this is the current version before use.

5. PACKAGING

5.1 Packaging. For acquisition purposes, the packaging requirements shall be as specified in the contract or order (see 6.2). When packaging of materiel is to be performed by DoD or in-house contractor personnel, these personnel need to contact the responsible packaging activity to ascertain packaging requirements. Packaging requirements are maintained by the Inventory Control Point's packaging activities within the Military Service or Defense Agency, or within the Military Service's system commands. Packaging data retrieval is available from the managing Military Department's or Defense Agency's automated packaging files, CD-ROM products, or by contacting the responsible packaging activity.

6. NOTES

(This section contains information of a general or explanatory nature that may be helpful, but is not mandatory.)

6.1 Notes. The notes specified in MIL-PRF-19500 are applicable to this specification.

6.2 Acquisition requirements. Acquisition documents should specify the following:

a. Title, number, and date of this specification.

b. Packaging requirements (see 5.1).

c. Lead finish (see 3.4.2).

d. Product assurance level and type designator.

6.3 Qualification. With respect to products requiring qualification, awards will be made only for products which are, at the time of award of contract, qualified for inclusion in Qualified Manufacturers List (QML 19500) whether or not such products have actually been so listed by that date. The attention of the contractors is called to these requirements, and manufacturers are urged to arrange to have the products that they propose to offer to the Federal Government tested for qualification in order that they may be eligible to be awarded contracts or orders for the products covered by this specification. Information pertaining to qualification of products may be obtained from Defense Supply Center, Columbus, ATTN: DSCC/VQE, P.O. Box 3990, Columbus, OH 43218-3990 or e-mail vqe.chief@dla.mil.

6.4 Suppliers of JANHC and JANKC die. The qualified JANHC and JANKC suppliers with the applicable letter version (example, JANHCA1N1202A) will be identified on the QML.

JANHC and JANKC ordering information	
	Manufacturer
PIN	59377
1N1202A	JANHCA1N1202A, JANKCA1N1202A
1N1204A	JANHCA1N1204A, JANKCA1N1204A
1N1206A	JANHCA1N1206A, JANKCA1N1206A
1N3671A	JANHCA1N3671A, JANKCA1N3671A
1N3673A	JANHCA1N3673A, JANKCA1N3673A

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T13:57Z
Check the source to verify that this is the current version before use.

6.5 Changes from previous issue. The margins of this specification are marked with asterisks to indicate where changes from the previous issue were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous issue.

Custodians:
Army - CR
Navy - EC
Air Force - 11
NASA – NA
DLA - CC

Review activities:
Army - AR, MI
Navy – AS, MC
Air Force - 19, 71, 99

Preparing activity:
DLA - CC

(Project 5961-2005-004)

NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using the ASSIST Online database at http://assist.daps.dla.mil .

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T13:57Z
Check the source to verify that this is the current version before use.