RR-D-575B
December 2, 1971
SUPERSEDING
Fed. Spec. RR-D-575A
October 25, 1966

FEDERAL SPECIFICATION

DOOR, METAL, SLIDING AND SWINGING: DOOR FRAME, METAL (FLUSH AND SEMIFLUSH)

This specification was approved by the Commissioner, Federal Suppply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers steel doors and frames for interior and exterior use.

1.2 Classification.

1.2.1 Types, styles, and classes. Doors shall be of the following types, classes and styles, as specified (see 6.2):

Type I - Standard duty, 1-3/8 and 1-3/4 inch.

Style 1 - Flush panel, stile and panel construction.
2 - Full flush, hollow steel construction.
3 - Seamless, hollow steel construction.
4 - Seamless, composite metal face construction.

Type II - Heavy duty, 1-3/4 inch.

Style 1 - Flush panel, stile and panel construction.
2 - Full flush, hollow steel construction.
3 - Seamless, hollow steel construction.
4 - Seamless, composite metal face construction.

Type III - Extra heavy duty, 1-3/4 inch.

Style 2 - Full flush, hollow steel construction.
3 - Seamless, hollow steel construction.
4 - Seamless, composite metal face construction.
5 - Flush panel, stile and rail construction.
6 - Industrial tubular.

Class F - Full panel flush door.
L - Louver near bottom.
TL - Louver near top.
LL - Two louvers, at top, and bottom.
V - Glass, vision near top.
VL - Glass, vision near top, louver near bottom.
N - Narrow long glass one side.
NL - Narrow long glass one side, louver near bottom.
G - Large half glass.
GL - Large half glass, louver near bottom.
G2 - Large half glass, 2 lights of glass.
G2L - Large half glass, 2 lights of glass, louver near bottom.
G3 - Large half glass, 3 lights of glass.
G3L - Large half glass, 3 lights of glass, louver near bottom.
G4 - Large half glass, 4 lights of glass.
G6 - Large half glass, 6 lights of glass.
FG - Large glass nearly full length and width.
FG3 - Large glass nearly full length and width, 3 lights of glass.
FL - Louver nearly full length of door.
D - Dutch doors.
S - Special.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:10Z
Check the source to verify that this is the current version before use.

1.2.2 Sizes. Thickness of type I doors shall be 1-3/8 or 1-3/4 inches, as specified (see 6.2). Doors and frames shall be of the opening sizes in table I, as specified (see 6.2):

TABLE I. Opening sizes, feet and inches 1/

Width of opening	Type I, 1-3/8 inch thick doors, height of opening			Types I, II, and III, 1-3/4 inch thick doors, height of opening				
2, 0	6, 8	7, 0	7, 2	6, 8	7, 0	7, 2	7, 10	8, 0
2, 4	6, 8	7, 0	7, 2	6, 8	7, 0	7, 2	7, 10	8, 0
2, 6	6, 8	7, 0	7, 2	6, 8	7, 0	7, 2	7, 10	8, 0
2, 8	6, 8	7, 0	7, 2	6, 8	7, 0	7, 2	7, 10	8, 0
3, 0	6, 8	7, 0	7, 2	6, 8	7, 0	7, 2	7, 10	8, 0
3, 4	-	-	-	6, 8	7, 0	7, 2	7, 10	8, 0
3, 6	-	-	-	6, 8	7, 0	7, 2	7, 10	8, 0
3, 8	-	-	-	6, 8	7, 0	7, 2	7, 10	8, 0
4, 0	-	-	-	6, 8	7, 0	7, 2	7, 10	8, 0

1/ Sizes shown are for single doors. For pairs of doors use twice the indicated width

2. APPLICABLE DOCUMENTS

2.1 The following documents, of the issue in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein:

Federal Specifications:

QQ-S-698 - Steel, Sheet and Strip, Low-Carbon.
PPP-B-601 - Boxes, Wood, Cleated-Plywood.
PPP-B-636 - Box, Fiberboard.
PPP-C-650 - Crates, Wood, Open and Covered.

Federal Standard:

Fed. Std. No. 123 - Marking for Domestic Shipment (Civil Agencies).

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U.S. Government Printing Office, Washington, DC 20402.

(Single copies of this specification and other Federal Specifications required by activities outside the Federal Government for bidding purposes are available without charge from Business Service Center at the General Services Administration Regional Offices in Boston, New York, Washington, DC, Atlanta, Chicago, Kansas City, MO, Fort Worth, Denver, San Francisco, Los Angeles, and Seattle, WA.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

Military Standards:

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129 - Marking for Shipment and Storage.

(Copies of Military Specifications and Standards required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless a specific issue is identified, the issue in effect on date of invitation for bids or request for proposal shall apply.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:10Z
Check the source to verify that this is the current version before use.

American Society for Testing and Materials (ASTM) Standards:

A366 - Specification for Cold-Rolled Carbon Steel Sheets, Commercial Quality.
A569 - Specification for Hot-Rolled Carbon Steel Sheets and Strip, Commercial Quality.
D635 - Test for Flamability of Self-Supporting Plastics.
D1621 - Test for Compressive Strength of Rigid Cellular Plastics.
D1622 - Test for Apparent Density of Rigid Cellular Plastics.

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA. 19103.)

American National Standards Institute, Inc. (ANSI) Standard:

A151.1 - Performance Test for Standard Steel Doors, Frames, Anchors, Hinge Reinforcings and Exit Device Reinforcings.

(Application for copies should be addressed to the American National Standards Institute, 1430 Broadway, New York, NY. 10018, or to the Steel Door Institute, 2130 Keith Building, Cleveland, OH. 44115.)

Underwriters' Laboratories (UL), Inc. Publication:

UL10 - Fire Test of Door Assemblies.

(Application for copies should be addressed to the Underwriters' Laboratories, Inc., 207 East Ohio St., Chicago, IL. 60611; 2250 Dundee Road, Box 247, Northbrook, IL. 60062; Walt Whitman Road, Melville, Long Island NY. 11749; 1665 Scott Blvd., Santa Clara, CA. 95050.)

National Motor Freight Traffic Association, Inc., Agent:

National Motor Freight Classification.

(Application for copies should be addressed to the American Trucking Association, Inc., Tariff Order Section, 1616 P Street, N.W., Washington, DC 20036.)

Uniform Classification Committee, Agent:

Uniform Freight Classification.

(Application for copies should be addressed to the Uniform Classification Committee, Room 202 Union Station, 516 W. Jackson Blvd., Chicago, IL 60606.)

3. REQUIREMENTS

3.1 Types I, II and III.

3.1.1 Material. Doors and frames shall be fabricated from steel. The steel shall be cold rolled, or hot rolled pickled and oiled. Cold rolled steel shall be commercial quality in accordance with Fed. Spec. QQ-S-698 or ASTM A366. Hot rolled steel shall be commercial quality in accordance with Fed. Spec. QQ-S-698 or ASTM A569. Door panels shall be fabricated or formed from the above steels with a stretcher level degree of flatness. Concealed reinforcing members shall be finished structural steel shapes or formed steel strip sections.

3.1.2 Finish. Doors and frames shall be primed (under coat), or zinc-coated, as specified (see 6.2).

3.1.2.1 Uncoated doors and frames. Metal doors and frames shall be cleaned thoroughly, treated to assure maximum paint adhesion, and given a factory dip or spray coat of rust inhibitive metallic oxide or synthetic resin primer on all exposed surfaces. The type of primer shall be at the manufacturer's option. Exterior doors and frames shall be given a phosphate treatment prior to the application of the prime coat. When specified (see 6.2), light proof louvers shall be prime coated on exposed surfaces.

3.1.2.2 Zinc-coated doors and frames. Doors and frames shall be electrolytically zinc plated or hot dipped galvanized, followed by a phosphate treatment and a shop prime coat of rust inhibitive paint as above for uncoated doors and frames.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:10Z
Check the source to verify that this is the current version before use.

3.2 Doors.

3.2.1 Edges and clearances.

3.2.1.1 Edges. Meeting edges of single acting doors may be double beveled or rounded.

3.2.1.2 Clearances. Single swing doors shall have not more than 1/8 inch clearance at jambs and heads, 1/4 inch clearance at meeting edges of pairs or doors, and 3/4 inch clearance at bottom. All dimensions are nominal and subject to recognized manufacturing tolerance. The lock edges of door shall be so designed as to provide proper operating clearance. Maximum clearance at bottom of sound and light proof doors shall be 1/4 inch. Bottom of doors shall be undercut when required for ventilating purposes (see 6.2).

3.2.2 Metal thickness. Thickness of sheet steel used in panels, stiles, and rails of doors shall be in accordance with tables II and III (see 4.4.1.1).

TABLE II. Thickness of sheet steel for flush panel, full flush and seamless doors

Type	Style	Steel sheet gage number	Nominal thickness		Minimum thickness	
			Uncoated	Zinc coated	Uncoated 1/	Zinc coated 2/
			inch	inch	inch	inch
I	1	20	0.0359	0.0396	0.0329C	0.0346D, 0.0356P
	2	20	.0359	.0396	.0329C	.0346D, .0356P
	3	20	.0359	.0396	.0329C	.0346D, .0356P
	4	22	.0299	.0336	.0269C	.0296D, .0306P
II	1	18	.0478	.0516	.0476C, .0456H	.0456D, .0476P
	2	18	.0478	.0516	.0476C, .0456H	.0456D, .0476P
	3	18	.0478	.0516	.0476C, .0456H	.0456D, .0476P
	4	20	.0359	.0396	.0329C	.0346D, .0356P
III	2	16	.0598	.0635	.0548C, .0528H	.0565D, .0585P
	3	16	.0598	.0635	.0548C, .0528H	.0565D, .0585P
	4	18	.0478	.0516	.0438C, .0428H	.0456D, .0476P
	5	18	.0478	.0516	.0438C, .0428H	.0456D, .0476P
	6	18	.0478	.0516	.0438C, .0428H	.0456D, .0476P

1/ Letters C and H opposite thickness for uncoated sheet steel refer to cold rolled, and hot rolled respectively.
2/ Letters D and P opposite thickness for zinc-coated sheet steel refer to hot dipped, and electroplated respectively.

TABLE III. Thickness of rails and stiles

Type	Style	Steel sheet gage number	Nominal thickness		Minimum thickness	
			Uncoated	Zinc coated	Uncoated 1/	Zinc coated 2/
			inch	inch	inch	inch
I	1	20	0.0359	0.0396	0.0329C	0.0346D, 0.0356P
II	1	18	.0478	.0516	.0476C, .0456H	.0456D, .0476P
III	4	16	.0598	.0635	.0548C, .0528H	.0565D, .0585P
III	6	16	.0598	.0635	.0548C, .0528H	.0565D, .0585P

1/ See note 1/ under table II.
2/ See note 2/ under table II.

3.2.3 Interior and exterior doors. Doors shall be for interior or exterior mounting, as specified (see 6.2). Exterior doors shall have the top edge closed flush.

3.2.4 Dutch doors. Dutch doors shall have a service shelf of the size specified (see 6.2). The shelf shall be formed of minimum 18 gage steel with edges boxed and returned. The shelf shall be supported by two steel brackets.

3.2.5 Swing and sliding doors. Swing for doors shall be as specified (see 6.2 and 6.3). Dimensions and construction of sliding doors shall be as specified (see 6.2).

3.2.6 Type I, standard duty, 1-3/8 and 1-1/4 inch.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:10Z
Check the source to verify that this is the current version before use.

3.2.6.1 Style 1, flush panel, stile and panel construction. Minimum 20 gage stiles shall be butted against the 20 gage panels the full length of the door. Panels shall interlock with the stiles, or be joined to the stiles by welding. Edges and panels shall be closed at top and bottom of door with recessed spot welded end channel closures. Surfaces of panels and stiles shall lie in parallel planes, but panels may be recessed an amount no greater than the thickness of the stile metal.

3.2.6.2 Style 2, full flush hollow steel construction. Doors shall have face sheets formed from one steel sheet. No seams shall occur on the door face, but may be on the vertical door edge. The top and bottom of the door shall either be closed with a recessed channel end closure or shall receive a flush end closure treatment.

3.2.6.3 Style 3, seamless, hollow steel construction. Doors shall have face sheets formed from one steel sheet. No seams shall occur on the door face or vertical edge. The top and bottom of the door shall either be closed with a recessed channel end closure or shall receive a flush end closure treatment.

3.2.6.4 Style 4, seamless, composite metal face construction. Doors shall have face sheets formed from one steel sheet. No seams shall occur on the door face or perimeter edge. Cores shall be manufactured of a solid composite noncombustible material bonded to the face sheets with adhesive, under pressure.

3.2.7 Type II, heavy duty, 1-3/4 inch.

3.2.7.1 Style 1 flush panel, stile and panel construction. Minimum 18 gage stiles shall be butted against the 18 gage panels the full length of the door. Panels shall interlock with the stiles, or be joined to the stile by welding. Edges and panels shall be closed at top and bottom of door with recessed spot welded end channel closures. Surfaces of panels and stiles shall lie in parallel planes, but panels may be recessed an amount no greater than the thickness of the stile metal.

3.2.7.2 Style 2, full flush, hollow steel construction. Doors shall have face sheets formed from one sheet of steel, 18 gage. No seams shall occur on the door face, but maybe on the vertical door edge. The top and bottom of the door shall either be closed with a recessed channel end closure or shall receive a flush end closure treatment.

3.2.7.3 Style 3, seamless, hollow steel construction. Doors shall have face sheets each formed from one sheet of steel, 18 gage. No seams shall occur on the door face or vertical edge. The top and bottom of the door shall either be closed with a recessed channel end closure or shall receive a flush end closure treatment.

3.2.7.4 Style 4, seamless, composite construction. Doors shall have face sheets each formed from one sheet of steel, 20 gage. No seams shall occur on the door face or perimeter edge. Cores shall be manufactured of a solid composite noncombustible material bonded to the face sheets with adhesive, under pressure.

3.2.8 Types I and II, standard and heavy duty.

3.2.8.1 Styles 1, 2 and 3.

3.2.8.1,1 Panel reinforcement. Unless otherwise specified (see 6.2), panel reinforcement shall be any of the following methods:

(a) Not lighter than 22 gage steel vertical channels or Z forms spaced not more than 6, 8-1/2 or 12 inches apart, as specified (see 6.2). Horizontal channels and Z forms shall be not lighter than 18 or 22 gage steel, as specified (see 6.2). Spacing of horizontal reinforcement shall be not more than 14 inches apart. Channel and Z forms shall be spot welded to both face sheets (panels) at intervals not greater than 6 inches.

(b) Not lighter than 24 gage steel horizontal U forms spaced 8-1/2 inches or less on centers, and welded in alternating sequence to the inside face of the outer sheet so that horizontal stiffening occurs approximately 17 inches on each face sheet.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:10Z
Check the source to verify that this is the current version before use.

(c) Continuous vertical or horizontal stiffeners not lighter than 22 gage steel spaced not to exceed 17 inches on centers, or not lighter than 20 gage steel spaced not to exceed 15 inches, as specified (see 6.2). Stiffeners not lighter than 20 gage steel shall be spot welded to one face at intervals not greater than 6 inches alternating at front and rear so that stiffeners occur at not more than 8-1/2 inches on centers. Stiffeners not lighter than 20 gage steel shall be spaced not to exceed 15 inches on centers and spot welded to both sheets at intervals not greater than 6 inches.

(d) A continuous truss formed inner core not lighter than 28 gage steel spot welded to the face sheet every 2-3/4 inches horizontally and vertically over the entire surface of both sheets, or when specified (see 6.2), a continuous formed steel truss core full height and width spot welded to face sheets at intervals not greater than 9 inches in both directions.

(e) An inner gride system consisting of vertical and horizontal member of not lighter than 20 gage steel welded or interlocked for maximum strength and spaced not to exceed an average of 18 inches in both directions and spot welded to both face sheets at intervals not greater than 6 inches.

(f) A honeycomb core laminated to the inside of both face panels with a water resistant adhesive. The honeycomb material shall have a crushing strength of not less than 4000 pounds per foot (p.s.f) when tested in accordance with 4.4.2.2.1.

(g) Polyurethane foamed in place or laminated to each panel. Compressive strength of polyurethane shall be 20 p.s.i, minimum (see 4.4.2.2.1). Voids in foam shall not exceed 1/2-inch in any direction. Foam density shall be not less than 1.8 p.c.f. (see 4.4.2.2.1.2).

(h) A rigid core of polystyrene slab bonded to face sheets by a thermosetting adhesive. Compressive strength of the core shall be not less than 1,500 p.s.f. (see 4.4.2.2.1). The polystyrene core to steel bond strength shall be at least equal to that of the core. The core shall be rated as self extinguishing when tested in accordance with 4.4.2.2.3.

(i) Solid hydrous calcium silicate with fibrous reinforcement bonded to each face with waterproof resorcinal adhesive under pressure to produce smooth flat surfaces. Top and bottom of door shall be reinforced with minimum 18 gage continuous horizontal formed steel channels.

3.2.8.1.2 Sound deadening. Sound deadening material that is noncombustible shall be applied to hollow spaces in doors for the purpose of elimating metallic sound incident to normal door operation.

3.2.9 Type II, extra heavy duty, 1-3/4 inch.

3.2.9.1 Style 2, full flush, hollow steel construction. Door shall have face sheets, each formed from one steel sheet. No seams shall occur on the door face, but may be on the vertical door edge. The top and bottom of the door shall either be closed with a recessed channel end closure or shall receive a flush end closure treatment.

3.2.9.2 Style 3, seamless, hollow steel construction. Doors shall have face sheets, each formed from one steel sheet. No seams shall occur on the door face or vertical edge. The top and bottom of the door shall either be closed with a recessed channel end closure or shall receive a flush end closure treatment.

3.2.9.3 Style 4, seamless, composite construction. Door shall have face sheets, each formed from one steel sheet. No seams shall occur on the door face or perimeter edge. Cores shall be manufactured of a solid composite noncombustible material bonded to the face sheets with adhesive, under pressure.

3.2.9.4 Style 5, flush panel, stile and rail construction. The minimum 16 gage stiles and rails shall be either mitered or butted. When mitered, they shall be welded and ground smooth at the corners; when butted, they shall be horizontally stiffened with U shaped end closures. Unmitered joints may be left visible. Interlocking 18 gage panels shall join with the stiles and be stiffened or reinforced. Surface of panels and stiles shall lie in parallel planes, but panels may be recessed an amount equal to thickness of the stile metal.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:10Z
Check the source to verify that this is the current version before use.

3.2.9.5 Style 6, industrial tubular. Stiles and rails shall be constructed of minimum 16 gage tubular design with locked seam. Corners shall be of welded construction with all joints face welded and ground smooth. Panels shall consist of two sheets of 18 gage steel with a resilient separator, nominally 3/8 inch in total thickness, and interlocked into the stiles and rails. Single sheet panels of 16 gage steel which shall be bedded into mastic and secured to stiles and rails with continuous angles and screws may also be used. Glass panel muntins (molding) for inside glazing with steel strips and bed putty shall be securely fastened to rails or stiles.

3.2.9.6 Styles 2, 3, 5, and 6, panel reinforcement. Unless otherwise specified (see 6.2), panel reinforcement shall be at the manufacturers option.

3.2.9.7 Styles 2, 3, and 5, sound deadening. Sound deadening material that is noncombustible shall be applied to hollow spaces in doors.

3.2.10 Types I, II and III.

3.2.10.1 Louvered doors. Louvers shall be sight-proof and either pierced into the panels of the door or inserted into the panels, as specified (see 6.2). Inserted louvers shall be stationary or adjustible. Louver frames shall be formed of minimum 20 gage steel. Minimum 24 gage blades shall be welded or tenoned to frame and the entire assembly shall be fastened to the door with moldings shall be an integral part of the louver.

3.2.10.2 Glazing. Glazing stops on the outside of exterior doors and on the secure side of interior doors, shall be non-removable. Glazing beads on the inside of glass and louver panels shall be removable. When specified (see 6.2), muntins shall interlock at intersections and be securely fastened to the door.

3.2.10.3 Fire and casualty hazards, fire doors only.

3.2.10.3.1 Each contractor shall submit to the contracting agency proof that the doors he proposes to supply under this specification conform to the applicable requirement of UL10 (b) for the type, style and class of doors specified by the contracting authority. The label, or listing with re-examination, of the Underwriters' Laboratories, Inc. may be accepted as evidence that the doors conform to this requirement.

3.2.10.3.2 In lieu of the label, or listing with reexamination, the contractor may submit independent proof satisfactory to the contracting agency that the doors conform to the applicable requirements of the published standards, including Methods of Test of UL10 (b).

3.2.10.3.3 Oversized doors. When fire doors and frames exceed the size for which testing and label service is offered by the UL, a certificate of inspection from the UL shall be furnished. The certificate shall state that the door and frame conform to the requirements of the UL, Inc. for design, materials, and construction for the class of door furnished.

3.2.10.3.4 Steel astragal on fire doors. Pairs of fire doors shall have an overlapping metal astragal, except when the doors are equipped with approved rim type exit hardware and provided with a removable mullion.

3.3 Frames.

3.3.1 Welded, knockdown, and drywall frames. Pressed steel frames for doors, transoms, sidelights, mullions, interior glazed panels and other openings, where indicated, shall be combination buck, frame and trim type. Frames shall be knockdown field assembled type or welded unit type, as specified (see 6.2).

3.3.1.1 Knockdown frames. Knock down frames shall have joints that interlock rigidly to maintain alignment of parts and provide functionally satisfactory performance of completed frames when field assembled.

3.3.1.2 Welded frames. Headers and jambs shall be secured at the corners either by internal welding of faces or by welded splice plates. Joints at jambs and headers shall be further secured at the rabbet either by tack welding on the inside of the profile or by mechanical interlock. Faces of frames at junction of head and jamb shall precent neat line joints.

3.3.1.3 Drywall frames. Drywall frames are designed for installation after the wall is erected on the construction site. Accordingly, details of frame construction shall be as specified (see 6.2).

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:10Z
Check the source to verify that this is the current version before use.

3.3.2 Thickness of frames. Thickness of formed steel used in constructing or fabricating frames shall be in accordance with table IV, except where thicker steel or heavier gages are used for fire door frames.

TABLE IV. Thickness of steel frames

Door			Frame, minimum thickness		
Type	Style	Thickness inches	Gage 1/	Hot rolled inch	Cold rolled inch
I	1,2,3,4	1-3/8	18	0.0476	0.0456
I	1,2,3,4	1-3/8, 1-3/4	16	.0548	.0528
II	1,2,3,4	1-3/8, 1-3/4	16	.0548	.0528
III	2,3,4,5,6	1-3/8, 1-3/4	16	.0548	.0528

1/ See table II for uncoated nominal thickness, gages 16 and 18.

3.3.3 Frames with mullions and transom bars. Mullions and transom bars shall be tubular construction joined with heads and jambs and be either butt-welded thereto or knocked down for field assembly. Knockdown mullions and transom bars shall have joints that interlock rigidly so as to maintain alignment of parts. Bottom of door mullions shall have floor anchors.

3.3.4 Frame anchors for wall conditions. Frames shall be provided with 3 or more anchors for each jamb as required for the adjoining wall construction. Anchors shall be not less than 18 gage steel strip. Ceiling struts, when used, shall be not less than 18 gage steel strip. Frames for 2 inch solid plaster partitions with gypsum lath or steel lath cores shall be provided with four anchors for each jamb.

3.3.5 Floor anchors. All frames shall be provided with 18 gage steel strip anchors for attachment at the floor.

3.3.6 Glazing beads. Frame glazing beads shall be furnished in interior glazed openings and other locations where fixed glass is indicated in pressed steel frames. Frames shall be prepared for the type of glazing beads required to receive the glass and gaskets indicated. Beads shall be mitered or butt joined at corners and may be either the screw-on or snap-on type.

3.3.7 Terminated stops. When specified (see 6.2), interior door frames shall have stops terminated 6 inches above floor. Stops shall be cut at a 45 degree angle and bottom of stop covered with a metal filler plate welded in place. Stops shall not be terminated on frames for light-proof doors, sound-proof doors, or lead-lined doors.

3.4 Hardware. Type of hardware shall be as specified (see 6.2).

3.4.1 Preparation for hardware, doors and frames. Doors and frames shall be reinforced, drilled and tapped to receive mortise hinges, locks, latches, flush bolts, deadlock strikes, roller latches and other hardware as applicable. Drilling or tapping for surface hardware is done in the field.

3.4.2 Anchor or pivoted reinforced hinges. When specified (see 6.2 and 6.3), the doors shall be premortised and reinforced only. Drilling and tapping is not required as it is ordinarily field accomplished.

3.4.3 Reinforcement for hardware.

3.4.3.1 Steel strip. Steel shall be hot or cold rolled, and the temper of cold rolled strip shall be at the manufacturer's option.

3.4.3.2 Thickness. Thickness of reinforcement shall be in accordance with table V, except for reinforcement having punched and expanded holes permitting additional depth for threads formed by fasteners. Reinforcement strip having expanded holes may be lighter, providing an equal number of threads is achieved.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:10Z
Check the source to verify that this is the current version before use.

TABLE V. Thickness of hardware reinforcement

Hardware		Reinforcement		
		Nominal thickness	Minimum thickness	
			Hot rolled	Cold rolled
		inch	inch	inch
Hinges 1/	1-3/8 inch door	0.1046	0.100	0.102
	1-3/8 inch frame	.1046	.100	.102
	1-3/4 inch door	.1345	.129	.132
	1-3/4 inch frame	.1345	.129	.132
Mortise locksets and deadlocks	Door	.0747	.070	.072
	Frame	.0747	.070	.072
Bored or cylindrical locks	Door	.0747	.070	.072
	Frame	.0747	.070	.072
Flush bolts and chain and foot bolts		.0747	.070	.072
		.0747	.070	.072
Surface applied closers	Door	.1046	.100	.102
	Frame	.1046	.100	.102
Hold-open arms	Door	.1046	.100	.102
	Frame	.1046	.100	.102
Pull plates and bars	Door	.0598	.055	.057
Kick and push plates and bar	Door	-	-	-
Surface panic devices 2/	Door	.0747	.070	.072
Floor checking hinges	Door	-	-	-
	Frame	.1495	.144	.147

1/ When reinforcing channels are used nominal thickness shall be 0.1196 inch, and minimum thickness shall be 0.114 inch for hot rolled strip and 0.117 inch for cold rolled strip.

2/ Thickness of pull plates and bars shall be at the manufacturer's option when through bolts are used.

3.5 Performance, doors and frames.

3.5.1 Frame anchors. Frame anchors shall not fracture or pull out when tested in accordance with 4.4.2.3.

3.5.2 Twist. When tested in accordance with 4.4.2.3, doors shall not become twisted with a permanent set. Permanent set shall not exceed 1/8 inch for flush doors, and 1/4 inch for half glass doors.

3.5.3 Hinge reinforcement and exit device reinforcement. Neither type of reinforcement shall deform with a permanent set when tested in accordance with 4.4.2.3.

3.6 Workmanship. Doors and frames shall be free from warp and buckle. Door panels shall be free from oil canning. Formed members shall be straight and true with points coped or mitered and in alignment.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the supplier may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

4.2 Sampling. The sample size levels of inspection shall be in accordance with MIL-STD-105.

4.2.1 Lot. Unless otherwise specified (see 6.2), a lot shall consist of each type class, style and size of doors and frames submitted for inspection at the same time.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:10Z
Check the source to verify that this is the current version before use.

4.2.2 Sampling for dimensional and visual examination, and test. Sampling of doors and frames for dimensional and visual examination shall be in accordance with level S-3. Sample size for tests shall be in accordance with level S-1.

4.3 Examination.

4.3.1 Doors and frames. Doors and frames selected in 4.2.2, shall be examined in accordance with table VI. The acceptable quality level (AQL's) for defects listed in table VI shall be 2.5 percent defective for major defects and 4.0 percent defective for minor defects in accordance with MIL-STD-105.

TABLE VI. Classification of defects

Defects	Major	Minor
Type, class, style and size not as specified.	X	
Finish on doors and frames not as specified.	X	
Exposed metal surfaces of doors and frames not primed.		X
Clearance at jambs and heads greater than 1/8 inch.	X	
Clearance of meeting edges of pair of doors greater than 1/4 inch.	X	
Clearance at bottom of door greater than 3/4 inch.	X	
Thickness of sheet metal for door panels not in accordance with table II, and thickness of rails and styles not in accordance with table III.	X	
Top of exterior doors not sealed.		X
Size of shelf on dutch doors not as specified, and thickness less than 18 gage sheet steel.	X	
Swing for doors and slide door not as specified.	X	
Panels on doors not reinforced where required.	X	
Seams on face of doors.	X	
Holes in plastic cores greater than 1/2 inch in any direction.	X	
Sound deadening material missing from interior hollow spaces in doors.		X
Doors warped, buckled, or oil canning on panels.	X	
Thickness of frames not in accordance with table IV.	X	
Frame anchors missing.		X
Stops missing when required.	X	
Frames not square or straight.	X	
Joints in frames not in alignment.		X
Hardware not as specified.	X	
Thickness of hardware not in accordance with table V.	X	
Damage or defects affecting function or serviceability.	X	
Damage or defects not affecting function or serviceability.		X

4.3.2 Inspection of preparation for delivery requirements. An inspection shall be made to determine that packaging, packing, and marking requirements of section 5 are complied with. Defects shall be scored in accordance with table VII. For examination of contents, the sample unit shall be one shipping container fully prepared for delivery selected just prior to the closing operations. Defects of closure listed shall be examined on shipping containers fully prepared for delivery. The lot size shall be the number of shipping containers in the end item inspection lot. The inspection level shall be II and the AQL shall be 4.0 defects per hundred units.

TABLE VII. Classification of preparation for delivery defects

Examine	Defects
Markings (exterior and interior)	Omitted; incorrect; illegible; or improper size, location, sequence, or method of application.
Materials	Any component missing or damaged.
Workmanship	Inadequate application of components such as incomplete closure of container flaps, loose strapping, inadequate stapling.
	Bulging or distortion of container.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:10Z
Check the source to verify that this is the current version before use.

4.4 Test methods.

4.4.1 Thickness of sheet steel.

4.4.1.1 Doors. Determine thickness of panels, rails, and stiles using resonant or pulse ultrasonic equipment, or by micrometer measurement of the sheet steel used in fabrication of doors. Calibrate ultrasonic equipment by measuring sheet or strip of known thickness. Determine thickness of panel and hardware reinforcement ultrasonically or by micrometer measurement see (see 3.2.2 and tables II and III).

4.4.1.2 Frames. Determine thickness of frames by micrometer measurement (see 3.3.2 and table IV).

4.4.2 Doors, frames, and cores in doors.

4.4.2.1 Frequency of test. Unless otherwise specified (see 6.2), all tests under 4.4.2.2 and in 4.4.2.3 shall be performed on the initial inspection, and thereafter only when changes are made in the material.

4.4.2.2 Door cores.

4.4.2.2.1 Compressive strength, and crushing strength. Test honeycomb cores for crushing strength, and polyurethane and polystyrene cores for compressive strength, using either procedure A or B in ASTM D1621 (see 3.2.8.1.1 (f), (g) and (h)).

4.4.2.2.2 Density, polyurethane. Test solidified poured-in-place polyurethance and board polyurethane for apparent density in accordance with ASTM D1622 (see 3.2.8.1.1 (g)).

4.4.2.2.3 Flammability, polystyrene core. Test in accordance with ASTM D635 (see 3.2.8.1.1 (h)).

4.4.2.3 Endurance test for doors and frames. Test endurance in accordance with ANSI Std A151.1 for the following (see 3.5.1, 3.5.2 and 3.5.3):

(a) Frame anchors.
(b) Twist in doors.
(c) Hinge and exit reinforcement.

5. PREPARATION FOR DELIVERY

5.1 Packaging. Packaging shall be level A or C, as specified (see 6.2).

5.1.1 Level A.

5.1.1.1 Doors. Doors shall be individually packaged in fiberboard shipping container conforming to PPP-B-636, class-weather resistant, grade - V3c.

5.1.1.2 Frames of welded unit construction. Frames of welded unit construction shall have temporary steel spreaders securely fastened to bottom of frames.

5.1.1.3 Knockdown type frames. Knockdown type frames shall be shipped unassembled in bundles securely strapped.

5.1.2 Level C. Doors shall be packed in accordance with the supplier's standard practice.

5.2 Packing. Packing shall be level A, B, or C as specified (see 6.2).

5.2.1 Level A. Doors of like description shall be packed in a close-fitting box conforming to PPP-B-601, overseas type. The strapping shall be zinc-coated.

5.2.2 Level B. Doors of like description shall be packed in a crate conforming to PPP-C-650, type III, style B. Crate closure shall be in accordance with the appendix of the crate specification.

5.2.3 Level C. The doors and frames shall be packed in a manner which will insure arrival at destination in satisfactory condition and be acceptable to the carrier at lowest rates. Containers and packing shall comply with Uniform Freight Classification rules or National Motor Freight Classification rules.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:10Z
Check the source to verify that this is the current version before use.

5.3 Marking.

5.3.1 Civil agencies. In addition to markings required by the contract or order, the frame units, bundles, and shipping containers shall be marked in accordance with Fed. Std. No. 123.

5.2.2 Military acitivities. In addition to markings required by the contract or order, the frame units, bundles and shipping containers shall be marked in accordance with MIL-STD-129.

6. NOTES

6.1 Intended use. Steel doors and frames are intended for use in buildings and other structures.

6.2 Ordering data. Purchasers should select the preferred options permitted herein, and include the following information in procurement documents:

(a) Title, number and date of this specification.
(b) Type, class, and style (see 1.2.1).
(c) Opening size types I, II and III, and thickness type I (see 1.2.2).
(d) Finish, doors and frames (see 3.1.2 and 3.1.2.1).
(e) Bottom of doors undercut for ventilating purposes when required (see 3.2.1.2).
(f) Whether door is for interior or exterior mounting (see 3.2.3).
(g) Size of service shelf for dutch doors, class D (see 3.2.4).
(h) Swing for doors, and sliding doors (see 3.2.5 and 6.3).
(i) Panel reinforcement, types I and II, styles 1, 2 and 3, and if different (see 3.2.8.1.1).
(j) Spacing channels and Z forms, and thickness of horizontal members, types I and II, styles 1, 2 and 3, when required (see 3.2.8.1.1 (a)).
(k) Continuous vertical and horizontal stiffeners, types I and II, styles 1, 2 and 3, when required (see 3.2.8.1.1 (c)).
(l) Method for continuous truss, types I and II, styles 1, 2 and 3, when required (see 3.2.8.1.1 (d)).
(m) Panel reinforcement for type III doors (see 3.2.9.6).
(n) Louvers in doors (see 3.2.10.1).
(o) Whether muntins shall interlock at intersections and securely fastened to door (see 3.2.10.2).
(p) Whether frames shall be completely welded or knockdown (see 3.3.1).
(q) Frame construction for drywall frames (see 3.3.1.3).
(r) Whether stops are required (see 3.3.7).
(s) Type of hardware required (see 3.4).
(t) Whether doors should be premortised and reinforced for hardware (see 3.4.2).
(u) Size of lot, if different from 4.2.1.
(v) Frequency of tests (see 4.4.2.1).
(w) Selection of applicable level of packaging and packing required (see 5.1 and 5.2).

6.3 Nomenclature for doors and frames. Refer to ANSI Std A123.1 for definitions and illustrations of terms for doors and frames. Also included in A123.1 are illustrations of the various combinations for louvers, and glass inserts, and swing for doors.

6.4 Hardware. Locks and doors are covered by Federal Specification FF-H-106 Hardware, Builders'; Locks and Door-Trim. Door closing devices are covered by Federal Specification FF-H-121 Hardware, Builders' Door-closing Devices.

6.5 Glass. Flat glass used in doors is covered by Federal Specification DD-G-451 Glass, Flat and Corrugated, for Glazing, Mirrors, and Other Uses.

6.6 Cross reference data. Cross reference between types, classes and styles covered by this specification, and types and styles of the preceeding specification RR-D-575A are as follows:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:10Z
Check the source to verify that this is the current version before use.

RR-D-575A	RR-D-575B
Type I - Commercial.	Type I - Standard duty, 1-3/8 and 1-3/4 inch.
Style 1 - Flush - hollow steel construction.	Style 1 - Flush panel, stile and panel construction.
2 - Flush composite metal face construction.	2 - Full flush, howllow steel construction.
3 - Flush panel - stile and panel construction.	3 - Seamless, hollow steel construction.
4 - Flush panel - stile and rail construction.	4 - Seamless, composite metal face construction.
5 - Recess panel - stile and rail construction.	-----
Type II - Industrial tubular.	Type II - Heavy duty, 1-3/4 inch.
-----	Style 1 - Flush panel, stile and panel construction.
-----	2 - Full flush, hollow steel construction.
-----	3 - Seamless, hollow steel construction.
-----	4 - Seamless, composite metal face construction.
Type III - Light commercial and dewelling.	Type III - Extra heavy duty, 1-3/4 inch.
Style 1 - Flush - stile and panel construction.	-----
2 - Flush - hollow steel construction.	Style 2 - Full flush, hollow steel construction.
-----	3 - Seamless, hollow steel construction.
-----	4 - Seamless, composite metal face construction.
-----	5 - Flush panel, stile and rail construction.
-----	6 - Industrial tubular.
-----	Types I, II, and III
-----	Class F - Full panel flush door.
-----	L - Louver near bottom.
-----	TL - Louver near top.
-----	LL - Two louvers at top, and bottom.
-----	V - Glass, vision near top.
-----	VL - Glass, vision near top, louver near bottom.
-----	N - Narrow long glass one side.
-----	NL - Narrow long glass one side, louver near bottom.
-----	G - Large half glass.
-----	GL - Large half glass, louver near bottom.
-----	G2 - Large half glass, 2 lights of glass.
-----	G2L - Large half glass, 2 lights of glass, louver near bottom.
-----	G3 - Large half glass, 3 lights of glass.
-----	G3L - Large half glass, 3 lights of glass, louver near bottom.
-----	G4 - Large half glass, 4 lights of glass.
-----	G6 - Large half glass, 6 lights of glass.
-----	FG - Large glass nearly full length and width.
-----	FG3 - Large glass nearly full length and width, 3 lights of glass.
-----	FL - Louver nearly full length of door.
-----	D - Dutch doors.
-----	S - Special.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:10Z
Check the source to verify that this is the current version before use.

Military Coordinating Activity:

Navy - YD

Custodians:

Army - ME
Air Force - 84

Review activities:

Navy - YD
Army - ME
Air Force - 84

User activities:

Army - CE

Preparing activity:

GSA-FSS

Orders for this publication are to be placed with the General Services Administration, acting as an agent for the Superintendent of Documents. See section 2 of this specification to obtain extra copies and other documents referenced herein. Price 15 cents each.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:10Z
Check the source to verify that this is the current version before use.