
INCH-POUND
MIL-C-24640/10B
31 July 1989
SUPERSEDING
MIL-0024640/10A(SH)
23 October 1985
USED IN LIEU OF
MIL-C-24640/10
10 August 1984

MILITARY SPECIFICATION SHEET

CABLE, ELECTRICAL, 600 VOLTS, LIGHTWEIGHT, MULTI-CONDUCTOR, AWG 16, TYPE MXSO

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The requirements for acquiring the product described herein shall consist of this specification sheet and the issue of the following specification listed in that issue of the Department of Defense Index of Specifications and Standards (DoDISS) specified in the solicitation: MIL-C-24640.



SH 12757

FINISHED WIRE:

(B) White MIL-W-81044/12-16, except identification codes and methods shall be in accordance with MIL-C-24640. Standard identifiction code applied by method 1.

FIGURE 1. Construction (non-watertight).

(B) denotes changes.

AMSC N/A FSC 6145

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T23:43Z
Check the source to verify that this is the current version before use.

(B) TABLE I. Construction details.

PIN M24640/10	Type number	Number of conductors	Diameter over shield (inch) (nom)	Jacket thickness (inch) (minimum)	Cable diameter (inch) (min)	Cable diameter (inch) (max)	Cable weight (pounds per 1000 feet) (max)
-01U0	MXSO-2	2	0.175	0.034	0.282	0.304	76.4
-02U0	MXSO-9	9	.325	.041	.424	.458	176.0
-03U0	MXSO-21	21	.456	.044	.552	.596	329.0
-04U0	MXSO-37	37	.562	.044	.644	.694	473.0

REQUIREMENTS:

Qualification required.

Construction details: See table I.

(B) Overall shield shall be tin-coated copper braid with a coverage not less than 90 percent determined in accordance with MIL-C-27500.

EXAMINATION AND TESTS:

	Requirements
Basic electrical:	
(B) Conductor resistance - ohms/1000 feet, at 25°C, maximum	5.15
(B) Voltage withstand - volts, root mean square, minimum	
Conductor to conductor	2000
Conductor to shield	1000
Shield to shield	Not applicable
Insulation resistance - megohms/1000 feet, minimum	5000
Conductor and shield continuity	No failure
Jacket flaws	No failure
Group A:	
Visual and dimensional	No failure
Capacitance:	
Mutual capacitance - at 1 MHz, picofarads/foot (pF/ft), maximum	Not applicable
Capacitance unbalance - percent, maximum	Not applicable
Characteristic impedance - at 1 MHz, ohms	Not applicable
Watertightness (see table XI of MIL-C-24640 for limits of water leakage)	Not applicable
Weight	No failure

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T23:43Z
Check the source to verify that this is the current version before use.

EXAMINATION AND TESTS: - Continued

	Requirements
Group B:	
Cold bending	No failure
Drip	Zero
Tear - pounds per inch thickness, minimum	35
Physicals (unaged)	
Jacket	
Tensile strength - lb/in2, minimum	1300
Elongation - percent, minimum	160
Attenuation - at 3 MHz, dB/100 feet, maximum	Not applicable
Gas flame (1 hour)	Not applicable
Group C:	
Physicals (aged)	
Jacket	
Air oven	
Tensile strength - percent of unaged, minimum	60
Elongation - percent of unaged, minimum	60
Hot oil immersion	
Tensile strength - lb/in2, minimum	50
Elongation - percent, minimum	50
Permanence of printing (conductor) - cycles, minimum	50
Permanence of printing (jacket) - cycles, minimum	250
Armor - conformance to material, construction and coverage	Not applicable
Shield - conformance to material, construction and coverage	No failure
Heat distortion - percent unaged, maximum	30
Cable filler removability	No failure
Shrinkage	No failure
Mutual inductance - dB/1000 feet, maximum	Not applicable
Surface transfer impedance	
Milliohms per meter, maximum	700
EMP response, dB, minimum	60
Pulse response time - ms/500 feet	
Rise time, maximum	Not applicable
Decay time, maximum	Not applicable

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T23:43Z
Check the source to verify that this is the current version before use.

QUALIFICATION INSPECTION:

	Requirements
Qualification inspection shall include basic electrical, all of groups A, B, and C, plus the following:	
Aging and compatibility (cable)	No failure
Acid gas equivalent - percent, maximum	
Jacket	2
Fillers	2
Insulation	18
Halogen content - percent, maximum	
Jacket	0.2
Fillers	0.2
Flame propagation	No failure
Immersion	
Tensile strength - percent of unaged, minimum	50
Elongation - percent of unaged, minimum	50
Smoke index, maximum	
Jacket	25
Fillers	--
Insulation	10
Toxicity index, maximum	
Jacket	5
Fillers	5
Insulation	1.5
Durometer - (type A) hardness, minimum	80
Weathering	No failure
Fungus resistance	No failure
Abrasion resistance	No failure
Gas flame (3 hour)	Not applicable
Finished wire	Not applicable

Preparing activity:
Navy - SH
(Project 6145-1004-10)

Custodians:
Army - MI
Navy - SH
Air Force - 85

Review activities:
Navy - EC
Air Force - 99
DLA - IS

User activities:
Army - ME, AR
Navy - CG

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T23:43Z
Check the source to verify that this is the current version before use.