INCH-POUND
MIL-DTL-24640/10D
22 August 2002
SUPERSEDING
MIL-C-24640/10C
26 June 1995

DETAIL SPECIFICATION SHEET

CABLE, ELECTRIC, 600 VOLTS, LIGHT-WEIGHT, MULTI-CONDUCTOR, AWG 16, TYPE MXSO

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The requirements for acquiring the product described herein shall consist of this specification sheet and the issue of MIL-DTL-24640 listed in that issue of the Department of Defense Index of Specifications and Standards (DoDISS) specified in the solicitation.

Construction (Non-Watertight)

First - 19-strand, tin-coated copper conductor, AWG size 16.
Second - Component wires shall be MIL-W-81044/12, except identification shall be in accordance with the codes and methods of MIL-DTL-24640. Testing shall be done in accordance with the component wire ratings and requirements listed on this slash sheet. Quality conformance testing shall be in accordance with MIL-W-81044, prior to cabling. If Method 1 is used, component wire shall be white.
Third - The required number of singles shall be cabled together. Cabling sequence shall be consecutive, starting with number 1 from center outward. Fillers may be used as necessary, to form a round cable.
Fourth - Binder tape applied helically with overlap.
Fifth - Braided shield, tin coated copper strands. Braid must be constructed to meet Surface Transfer Impedance requirements as listed herein.
Sixth - Binder tape applied helically with overlap, at manufacturer's option.
Seventh - Crosslinked polyolefin jacket. (See Table I for thickness).

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.
Source: https://assist.dla.mil -- Downloaded: 2026-10-19T23:43Z
Check the source to verify that this is the current version before use.

TABLE I. Construction details.

PIN M24640/10	Type number	Number of component wires	Diameter over shield (inch) (nom)	Jacket thickness (inch) (min)	Cable diameter (inch) (min)	(max)	Cable weight (pounds per 1000 feet) (max)
-01UO	MXSO-2	2	0.175	0.034	0.282	0.304	76.4
-02UO	MXSO-9	9	.325	.041	.424	.458	180.0
-03UO	MXSO-21	21	.456	.044	.552	.596	329.0
-04UO	MXSO-37	37	.562	.044	.644	.694	497.0

REQUIREMENTS:

Qualification required.
Construction details: See Table I.

Component wire: The component wire shall be per MIL-W-81044 and shall be tested in accordance with the following wire ratings and additional requirements.

Temperature rating: 150°C (302°F) maximum conductor temperature
Voltage rating: 600 volts (rms) at sea level.
Accelerated aging: Oven temperature, 300 ± 2°C (572 ± 3.6°F) for 6 hours
Blocking: 150 ± 2°C (302 ± 3.6°F)
Flammability: 30 seconds (max); 3.0 inches (max); no flaming of tissue paper.
Humidity resistance: 5000 megohms for 1000 feet, minimum insulation resistance after humidity exposure.
Impulse dielectric test:
    Primary insulation (when tested in lieu of spark test):
        6.0 kilovolts (peak) 100 percent test.
    Finished wire: 8.0 kilovolts (peak), or 3 kHz spark test
    5.5 kV, 100 percent test.
Insulation resistance: 5000 megohms for 1000 feet (min).
Life cycle: Oven temperature, 200 ± 2°C (392 ± 3.6°F) for 168 hours.
Physical properties of primary insulation:
    Tensile strength, 2500 lb/in^2 (min).
    Elongation, 150 percent (min).
Shrinkage: 0.125 inch maximum at 300 ± 2°C (572 ± 3.6°F).
Spark test primary insulation: 1500 volts (rms), 60 Hz or 3 kHz, 100 percent test.
Surface resistance: 500 megohms inches (min), initial and final readings.
Thermal shock: Oven temperature, 150 ± 2°C (302 ± 3.6°F).
    Maximum change in measurement: 0.060 inch.
Wet dielectric test: 2500 volts (rms).
Wrap test: Mandrel wrap test required.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T23:43Z
Check the source to verify that this is the current version before use.

EXAMINATION AND TESTS:

Basic electrical:	Requirements:
Conductor Resistance - ohms/1000 feet at 25°C, maximum	5.15
Voltage withstand - volts, root mean square, minimum	
Conductor to conductor	2000
Conductor to shield	1000
Shield to shield	Not applicable
Insulation resistance - megohms-1000 feet, minimum	2500
Conductor and shield continuity	No failure
Jacket flaws	No failure
Group A:	
Visual and dimensional	No failure
Capacitance:	
Mutual capacitance - at 1 MHz, picofarads/foot (pF/ft), maximum	Not applicable
Capacitance unbalance - percent, maximum	Not applicable
Characteristic impedance - at 1 MHz, ohms	Not applicable
Watertightness (see Table IX of MIL-DTL-24640 for limits of water leakage)	Not applicable
Weight	No failure
Group B:	
Cold bending	No failure
Drip	Not applicable
Cross link proof test (percent maximum)	
Jacket	50
Tear - pounds per inch thickness, minimum	35
Physicals (unaged)	
Jacket	
Tensile strength - lb/in^2, minimum	1300
Elongation - percent, minimum	160
Attenuation - at 3 MHz, dB/100 feet, maximum	Not applicable
Gas flame (1 hour)	Not applicable
Group C:	
Physicals (aged)	
Jacket	
Air oven	
Tensile strength - percent of unaged, minimum	60
Elongation - percent of unaged, minimum	60
Permanence of printing ((conductor) (Method 1 only)) cycles, minimum	25
Permanence of printing (jacket) - cycles, minimum	125
Shield - conformance to material, construction and coverage	No failure
Heat distortion - percent of unaged, maximum	30
Cable sealant removability	Not applicable

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T23:43Z
Check the source to verify that this is the current version before use.

Shrinkage ..... No failure
Mutual inductance - dB/1000 feet, maximum ..... Not applicable
Surface transfer impedance
    Milliohms per meter, maximum 700
    EMP response, dB, minimum 60
Pulse response time - ms/500 feet
    Rise time, maximum ..... Not applicable
Decay time, maximum ..... Not applicable

QUALIFICATION INSPECTION:

Qualification inspection shall include basic electrical, all of groups A, B, C and D, plus the following:

Flame propagation ..... No failure
Aging and compatibility (cable) ..... No failure
Acid gas equivalent - percent, maximum
    Jacket 2
    Fillers 2
    Insulation 18
Halogen content - percent, maximum
    Jacket 0.2
    Fillers 0.2
Hot oil immersion
    Tensile strength - percent of unaged, minimum 50
    Elongation - percent of unaged minimum 50
Smoke index, maximum
    Jacket 25
    Fillers 45
    Insulation 10
Toxicity index, maximum
    Jacket 5
    Fillers 5
    Insulation 1.5
Durometer (jacket) - (type A) hardness, minimum 80
Weathering (jacket) ..... No failure
Fungus Resistance ..... No failure
Abrasion resistance ..... No failure
Gas Flame (3 hour) ..... Not applicable
Component wire ..... No failure

Unit ordering length: 2 & 9 500 feet nominal
21 & 37 250 feet nominal

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T23:43Z
Check the source to verify that this is the current version before use.

Custodians:
Army - MI
Navy - SH

Preparing Activity:
Navy - SH
(Project 6145-2307-010)

Review Activities:
Army - AR, AV, CR, CR4
Navy - CG, EC
DLA - IS

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T23:43Z
Check the source to verify that this is the current version before use.