INCH-POUND
MIL-DTL-24640/6E
8 November 2011
SUPERSEDING
MIL-DTL-24640/6D
22 August 2002

DETAIL SPECIFICATION SHEET

CABLE, ELECTRIC, -20 TO +105 °C, 600 VOLTS, LIGHTWEIGHT, MULTI-PAIR, 22 AWG, TYPES 2XAO AND 2XAOW

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The requirements for acquiring the product described herein shall consist of this specification sheet and MIL-DTL-24640.

Construction, Non-Watertight (2XAO) or Watertight (2XAOW)

First	-	19-strand, tin-coated copper conductor, 22 AWG. Watertight constructions shall be constructed with 7 strands.
Second	-	Component wires shall be SAE-AS81044/12, except identification shall be in accordance with the codes and methods of MIL-DTL-24640. Testing shall be in accordance with the component wire ratings and requirements listed on this specification sheet. Conformance testing shall be in accordance with SAE-AS81044 prior to cabling.
Third	-	The insulated component wires, one black and one white, shall be twisted together to form the required number of pairs. The pitch shall be 1½±¼ inch. Twisted pair identification codes applied using Method 6.
Fourth	-	The required number of pairs shall be cabled together.
Fifth	-	Optional binder tape.
Sixth	-	Braided shield, tin-coated copper strands. Braid must be constructed to meet surface transfer impedance requirements as listed herein.
Seventh	-	Optional binder tape.
Eighth	-	Cross-linked polyolefin jacket (see table I for thickness). NOTE: Manufacturer's identification tape or thread is required (see 3.7.3).

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T23:41Z
Check the source to verify that this is the current version before use.

TABLE I. Construction details.

PIN M24640/6	Type number	Number of pairs	Jacket thickness (inch) (min.)	Cable diameter (inch)		Cable weight (pounds per 1000 feet) (max.)
				(min.)	(max.)	
-01UO	2XAO-2	2	0.038	0.307	0.331	79.4
-02UO	2XAO-7	7	0.041	0.392	0.422	131.0
-03UO	2XAO-10	10	0.041	0.475	0.511	175.0
-04UO	2XAO-18	18	0.044	0.567	0.611	263.0
-05UO	2XAO-40	40	0.047	0.796	0.858	513.0
-06UO	2XAOW-2	2	0.038	0.310	0.335	115.1
-07UO	2XAOW-7	7	0.041	0.395	0.425	134.6
-08UO	2XAOW-10	10	0.041	0.475	0.515	184.2
-09UO	2XAOW-18	18	0.044	0.570	0.615	263.0
-10UO	2XAOW-40	40	0.047	0.800	0.860	494.6

REQUIREMENTS:

Qualification required.

Construction details: See table I.

Component wire: The component wire shall be in accordance with SAE-AS81044 and shall be tested in accordance with the following wire ratings and additional requirements.

Temperature rating	150 °C (302 °F) (max.) conductor temperature
Voltage rating	600 volts (root mean square) at sea level
Accelerated aging	
Non-blocked	Oven temperature, 300±2 °C (572±3.6 °F) for 6 hours
Water-blocked	Oven temperature, 250±2 °C (482±3.6 °F) for 6 hours
Blocking	150±2 °C (302±3.6 °F)
Flammability	30 seconds (max.)
	3.0 inches (max.)
	No flaming of tissue paper
Humidity resistance	5000 megohms for 1000 feet (min.) insulation resistance after humidity exposure
Dielectric test	
Primary insulation (when tested in lieu of spark test)	6.0 kilovolts (peak), 100 percent impulse test
Finished wire	8.0 kilovolts (peak), or 3 kHz spark test, 5.5 kV, 100 percent test
Insulation resistance	5000 megohms for 1000 feet (min.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T23:41Z
Check the source to verify that this is the current version before use.

Life cycle	
Non-blocked	Oven temperature, 200±2 °C (392±3.6 °F) for 168 hours
Water-blocked	Oven temperature, 200±2 °C (392±3.6 °F) for 120 hours
Physical properties of primary insulation	
Tensile strength	2500 lb/in^2 (min.)
Elongation	150 percent (min.)
Shrinkage	
Non-blocked	0.125 inch (max.) at 300±2 °C (572±3.6 °F)
Water-blocked	0.125 inch (max.) at 250±2 °C (482±3.6 °F)
Spark test primary insulation	1500 volts (root mean square), 3 kHz, 100 percent test
Surface resistance	500 megohms inches (min.), initial and final readings
Thermal shock	Oven temperature, 150±2 °C (302±3.6 °F)
Maximum change in measurement	0.060 inch
Wet dielectric test	2500 volts (root mean square)
Wrap test	Mandrel wrap test required

INSPECTION:

Basic Electricals:

Conductor resistance (ohms/1000 feet at 25 °C, max.)	17.39
Voltage withstand (volts, root mean square, min.)	
Conductor to conductor	2000
Conductor to shield	1000
Shield to shield	Not applicable
Insulation resistance (megohms/1000 feet, min.)	2500
Conductor and shield continuity	No failure
Jacket flaws	No failure

Group A:

Visual and dimensional	No failure
Capacitance:	
Mutual capacitance (at 1 MHz, picofarads/foot (pF/ft), max.)	40
Capacitance unbalance (percent, max.)	15
Characteristic impedance (at 1 MHz, ohms)	Not applicable
Watertightness (Type 2XAOW only) (see table IX of MIL-DTL-24640 for limits of water leakage)	No failure

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T23:41Z
Check the source to verify that this is the current version before use.

Weight	No failure
Group B:	
Cold bending	No failure
Cross-link proof test (percent, max.)	
Jacket	50
Drip (Type 2XAOW only)	No failure
Tear (lb/in thickness, min.)	35
Physicals (unaged)	
Jacket	
Tensile strength (lb/in^2, min.)	1300
Elongation (percent, min.)	160
Attenuation (at 3 MHz, dB/100 feet, max.)	Not applicable
Gas flame (1 hour)	Not applicable
Group C:	
Physicals (aged), air oven	
Jacket	
Tensile strength (percent of unaged, min.)	60
Elongation (percent of unaged, min.)	60
Permanence of printing (conductor insulation, cycles, Method 1 only, min.)	25
Permanence of printing (jacket, cycles, min.)	125
Heat distortion (percent of unaged, max.)	30
Cable sealant removability (Type 2XAOW only)	No failure
Shrinkage	No failure
Surface transfer impedance	
Milliohms per meter (max.)	700
EMP response (dB, min.)	60
Group D:	
Flame propagation	No failure

Qualification Inspection:

Qualification inspection shall include basic electricals; groups A, B, C, and D; plus the following:

Aging and compatibility cable	No failure
Acid gas equivalent (percent, max.)	

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T23:41Z
Check the source to verify that this is the current version before use.

Jacket	2
Fillers	2
Insulation	18
Halogen content (percent, max.)	
Jacket	0.2
Fillers	0.2
Immersion (jacket)	
Tensile strength (percent of unaged, min.)	50
Elongation (percent of unaged, min.)	50
Smoke index (max.)	
Jacket	25
Fillers	45
Insulation	10
Toxicity index (max.)	
Jacket	5
Fillers	5
Insulation	1.5
Durometer (jacket) - Type A (hardness, min.)	80
Weathering (jacket)	No failure
Fungus resistance	No failure
Abrasion resistance	No failure
Gas flame (3 hour)	Not applicable
Component wire	No failure

UNIT ORDERING LENGTHS:

Type and size	Feet (nominal)
All types and sizes 2 - 10	500
All types and sizes 18 - 40	250

CHANGES FROM PREVIOUS ISSUE: Marginal notations are not used in this revision to identify changes with respect to the previous issue due to the extent of the changes.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T23:41Z
Check the source to verify that this is the current version before use.

Custodians:
Army – MI
Navy – SH

Preparing Activity:
Navy – SH
(Project 6145-2009-074)

Review Activities:
Army – AR, AV, CR, CR4
Navy – CG, EC
DLA – CC

NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using the ASSIST Online database at https://assist.daps.dla.mil.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T23:41Z
Check the source to verify that this is the current version before use.