
MIL-C-0024640/9A(SH)
23 October 1985
USED IN LIEU OF
MIL-C-24640/9
10 August 1984

MILITARY SPECIFICATION SHEET

CABLE, ELECTRICAL, 600 VOLTS, LIGHTWEIGHT, MULTI-PAIR, AWG 22, TYPE 2XS (INCLUDING VARIATION TYPES 2XSA AND 2XSO)

This military specification has been prepared by the Naval Sea Systems Command based upon currently available technical information but it has not been approved for promulgation as a coordinated revision of MIL-C-24640. It is subject to modification. However, pending its promulgation as a coordinated military specification, it may be used in acquisition.

The requirements for acquiring the cable described herein shall consist of this specification and the latest issue of MIL-C-24640.



SH 12756

COMPONENT SHIELDED PAIR: One black MIL-W-81044/12-22 wire twisted with one white MIL-W-81044/12-22 wire, except identification codes and methods shall be in accordance with MIL-C-24640. The shield shall be tin-coated copper braid with a coverage not less than 85 percent determined in accordance with MIL-C-27500.

FIGURE 1. Construction (non-watertight).

(A) denotes changes.

FSC 6145

DISTRIBUTION STATEMENT A Approved for public release; distribution unlimited

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T23:43Z
Check the source to verify that this is the current version before use.

(A) TABLE I. Construction details - unarmored.

Type number	Number of pairs	Jacket thickness (inch) (minimum)	Cable diameter (inch) (min)	Cable diameter (inch) (max)	Cable weight (pounds per 1000 feet) (max)
2XS-2	2	0.038	0.308	0.332	61.4
2XS-3	3	.038	.325	.350	74.2
2XS-7	7	.041	.423	.455	132.0
2XS-10	10	.044	.537	.579	193.0
2XS-14	14	.044	.582	.627	240.0
2XS-19	19	.044	.644	.694	308.0
2XS-24	24	.047	.758	.818	390.0
2XS-30	30	.047	.804	.866	468.0

(A) TABLE II. Construction details - armored.

Type number	Number of pairs	Jacket thickness (inch) (minimum)	Cable diameter (inch) (min)	Cable diameter (inch) (max)	Cable weight (pounds per 1000 feet) (max)
2XSA-2	2	0.038	0.358	0.382	81.4
2XSA-3	3	.038	.375	.400	101.7
2XSA-7	7	.041	.473	.505	176.1
2XSA-10	10	.044	.587	.629	228.5
2XSA-14	14	.044	.632	.677	280.0
2XSA-19	19	.044	.694	.744	359.5
2XSA-24	24	.047	.808	.868	442.8
2XSA-30	30	.047	.854	.916	531.3

(A) TABLE III. Construction details - overall shield.

Type number	Number of pairs	Diameter over shield (inch) (nom)	Jacket thickness (inch) (minimum)	Cable diameter (inch) (min)	Cable diameter (inch) (max)	Cable weight (pounds per 1000 feet) (max)
2XSO-3	3	0.271	0.038	0.380	0.410	117.0
2XSO-7	7	.373	.041	.474	.510	184.0
2XSO-10	10	.487	.044	.594	.640	262.0
2XSO-14	14	.541	.044	.636	.686	301.0
2XSO-19	19	.607	.044	.709	.765	383.0
2XSO-30	30	.777	.047	.869	.937	554.0

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T23:43Z
Check the source to verify that this is the current version before use.

REQUIREMENTS:

Qualification required.
Construction details: See tables I, II and III.

When this cable is manufactured with armor, the following additional requirements shall apply:

(a) Braided metal armor and paint shall be added.
(b) Cable surface marking will not be required.

When this cable is manufactured with an overall shield, the following additional requirements shall apply:

(a) An overall tin-coated copper braid shall be added.
(b) Braid coverage shall be not less than 85 percent determined in accordance with MIL-C-27500.

EXAMINATION AND TESTS:

	Requirements
Basic electrical:	
Conductor resistance - ohms/1000 feet, at 25°C, maximum	16.52
Voltage withstand - volts, root mean square, minimum	
Conductor to conductor	2500
Conductor to shield	1000
Shield to shield (type 2XSO only)	500
Insulation resistance - megohms/1000 feet, minimum	5000
Conductor and shield continuity (type 2XSO only)	No failure
Jacket flaws (type 2XSO only)	No failure
Group A:	
Visual and dimensional	No failure
Capacitance:	
Mutual capacitance - at 1 MHz, picofarads/foot (pF/ft), maximum	40
Capacitance unbalance - percent, maximum	15
Characteristic impedance - at 1 MHz, ohms	55 ± 5
Watertightness (see table XI of MIL-C-24640 for limits of water leakage)	Not applicable
Weight	No failure
Group B:	
Cold bending	No failure
Drip	Zero
Tear - pounds per inch thickness, minimum	35
Physicals (unaged)	
Jacket	
Tensile strength - lb/in^2, minimum	1300
Elongation - percent, minimum	160
Attenuation - at 3 MHz, dB/100 feet, maximum	3
Gas flame (1 hour)	Not applicable

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T23:43Z
Check the source to verify that this is the current version before use.

EXAMINATION AND TESTS: (Continued)

	Requirements
Group C:	
Physicals (aged)	
Jacket	
Air oven	
Tensile strength - percent of unaged, minimum	60
Elongation - percent of unaged, minimum	60
Hot oil immersion	
Tensile strength - lb/in^2, minimum	50
Elongation - percent, minimum	50
Permanence of printing (conductor) - cycles, minimum	50
Permanence of printing (jacket) - cycles, minimum	250
Armor (type 2XSA only) - conformance to material, construction and coverage	No failure
Shield - conformance to material, construction and coverage	No failure
Heat distortion - percent unaged, maximum	30
Cable filler removability	No failure
Shrinkage	No failure
Mutual inductance - dB/1000 feet, maximum	—
Surface transfer impedance (type 2XS0 only)	
Milliohms per meter, maximum	700
EMP response, dB, minimum	60
Pulse response time - ms/500 feet	
Rise time, maximum	—
Decay time, maximum	--

QUALIFICATION INSPECTION:

Qualification inspection shall include basic electrical, all of groups A, B and C, plus the following:

Aging and compatibility (cable)	No failure
Acid gas equivalent - percent, maximum	
Jacket	2
Fillers	2
Insulation	18
Halogen content - percent, maximum	
Jacket	0.2
Fillers	0.2
Flame propagation	No failure
Immersion	
Tensile strength - percent of unaged, minimum	50
Elongation - percent of unaged, minimum	50
Smoke index, maximum	
Jacket	25
Fillers	—
Insulation	10

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T23:43Z
Check the source to verify that this is the current version before use.

QUALIFICATION INSPECTION: (Continued)

	Requirements
Toxicity index, maximum	
Jacket	5
Fillers	5
Insulation	1.5
Durometer - (type A) hardness, minimum	80
Weathering	No failure
Fungus resistance	No failure
Abrasion resistance	No failure
Gas flame (3 hour)	Not applicable
Finished wire	Not applicable

Preparing activity:
Navy - SH
(Project 6145-N322-09)

Source: https://assist.dla.mil - Downloaded: 2026-10-19T23:43Z
Check the source to verify that this is the current version before use.