METRIC
DOD-E-24635(SH)
AMENDMENT 1
7 April 1987

MILITARY SPECIFICATION

ENAMEL, GRAY, SILICONE ALKYD COPOLYMER
SEMIGLOSS (FOR EXTERIOR USE) (METRIC)

This amendment forms a part of DOD-E-24635(SH), dated 13 September 1984, and is approved for use within the Naval Sea Systems Command, Department of the Navy and is available for use by all Departments and Agencies of the Department of Defense.

PAGE 3

3.3.1: Delete and substitute:

"3.3.1 Pigment. The basic hiding pigment shall be titanium dioxide in accordance with type IV of ASTM D 476. Small amounts of shading pigments (as necessary to match color no. 26270) and extender pigments may be used provided the finished product complies with the requirements specified herein."

PAGE 5

3.4.14, line 4: Delete "1.0" and substitute "4.0".

PAGE 6

Table II:

| | | Requirements | |
|---|---|---|---|
| | Characteristics | Minimum | Maximum |
| Under: | "Characteristics | | Requirements<br>Minimum Maximum" |
| Add: | "Lead | -- | 0.06" |

AMSC N/A FSC 8010
DISTRIBUTION STATEMENT A Approved for public release; distribution unlimited



Source: https://assist.dla.mil -- Downloaded: 2026-10-19T23:37Z
Check the source to verify that this is the current version before use.

Table III: Delete and subsitute:

"TABLE III. Specific quantitative requirements for gray color 26270.

| | |
|---|---|
| Color (number) - FED-STD-595 | 26270 |
| Color (name-designation) | Gray (Navy-Haze) |
| Total solids - minimum | 63 percent by weight of enamel |
| Hiding pigment - minimum | 14 } percent by weight of enamel |
| - maximum | 18 } |
| Extender pigment - maximum | 24 percent by weight of enamel |
| Vehicle solids - minimum | 26 percent by weight of total enamel |

Preparing activity:
Navy - SH
(Project 8010-N317)



Source: https://assist.dla.mil -- Downloaded: 2026-10-19T23:37Z
Check the source to verify that this is the current version before use.