A-A-1925
May 2, 1983

COMMERCIAL ITEM DESCRIPTION

SHIELD, EXPANSION (NAIL ANCHORS)

The General Services Administration has authorized the use of this commercial item description in preference to Federal Specification FF-S-325.

This description covers nail anchor type expansion shields for attaching equipment and fixtures to an existing solid manonry.

Salient characteristics:

General

Shall consist of a nail and of an anchor of a hollow rivet shape.

Dimensions and head styles shall be as specified according to table I.

Shall withstand proof test loads specified in table I when tested in accordance with ANSI/ASTM E 488.

TABLE I [1]

Anchor Body Size (inches)				Tensile Proof Test Loads (pounds)	
Diameter [2]	Length	Head Style [3]	Head Diameter (inches)	Solid material installation	Hollow material installation
3/16	3/4	F.H.	5/16	180	178
	1	F.H.	3/8	180	178
		R.H.			
		T.H.	1/2		
	1-1/2	F.H.	3/8	200	193
		R.H.			
1/4	3/4	F.H.	7/16	200	130
		T.H.	9/16		
	1	F.H.	7/16	235	155
		R.H.			
		T.H.	9/16		
	1-1/2	F.H.	7/16	265	188
		R.H.			

[1] All dimensions and loads specified are "minimum".

[2] The "diameter" is also the size of drill to be used in the installation of the anchor in hollow material. In solid material (concrete and masonry), an applicable size carbide tipped masonry drill in accordance with ANSI B 94.12 shall be used.

[3] Under "Head Style", "F.H. indicates flat head", "R.H. indicates round head", "T.H. indicates truss head".

Anchor body

Shall have a bore through the head into the stem until it reaches the slit or slits in the drive-in end of the stem.

Shall be of nylon.

Nail

Shall be a threaded steel type and shall have a slotted pan head, threads with rounded crests, and pinch tapered points. It shall be of low carbon steel composition 1039 and shall have a hardness of 44-50 HRC in accordance with ASTM E 18.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:18Z
Check the source to verify that this is the current version before use.

When set in the bore and hammered home, it shall expand the slitted end of the anchor stem and thus embed the anchor in the prepared hole in the masonry.

Shall withstand a 200 hour salt spray fog test in accordance with ASTM B 117.

Workmanship. The expansion shields shall be free from defects such as rust, scale, fins or any other defects which affect their use and serviceability.

The issues of ANSI B 94.12, ANSI/ASTM E 488, ASTM B 117, and ASTM E 18 in effect on the date of the solicitation shall be used to determine compliance with these requirements.

Regulatory requirements. The offeror/contractor is encouraged to use recovered materials in accordance with Public Law 94-580 to the maximum extent practicable.

Preservation, packaging, packing, labeling, and marking. The preservation, packaging, packing, labeling, and marking shall be as specified in the contract or order.

Note. Purchaser should specify dimensions and head styles.

ASTM standards are available from the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ANSI standards are available from the American National Standards Institute, Inc., 1430 Broadway, New York, NY 10018.

MILITARY INTERESTS:

Coordinating Activity

Army - AR

Custodians

Army - AR
Navy - YD
Air Force - 99

PREPARING ACTIVITY:

GSA - FSS

Source: https://assist.dla.mil -- Downloaded: 202610-26T08:18Z
Check the source to verify that this is the current version before use.