INCH-POUND

MIL-S-19500/628
18 November 1994

MILITARY SPECIFICATION

SEMICONDUCTOR DEVICE, DIODE, SILICON, POWER RECTIFIER, ULTRAFAST, TYPES 1N6690 THROUGH 1N6693, 1N6690US THROUGH 1N6693US, JANTX, JANTXV, AND JANS

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers the detail requirements for silicon, ultrafast power rectifier diodes. Three levels of product assurance are provided for each device type as specified in MIL-S-19500.

1.2 Physical dimensions. See figures 1 and 2.

1.3 Maximum ratings.

Types	V_{RWM}	I_O 1/ T_A = +25°C	t_{rr}	I_{FSM} t_p = 8.3 ms, T_A = +25°C	$R_{\theta JL}$ at L = 0.35	$R_{\theta JE}$ 2/	T_{STG} and T_J
	V dc	A dc	ns	A (pk)	°C/W	°C/W	°C
1N6690,1N6690US	600	20	75	375	4	3.5	-65 to +175
1N6691,1N6691US	800	20	75	375	4	3.5	-65 to +175
1N6692,1N6692US	1,000	20	75	375	4	3.5	-65 to +175
1N6693,1N6693US	1,200	20	75	375	4	3.5	-65 to +175

1/ Derate linearly at 267 mA/°C from +100°C to +175°C.
2/ -US suffix devices only.

2. APPLICABLE DOCUMENTS

2.1 Government documents.

2.1.1 Specifications, standards, and handbooks. The following specifications, standards, and handbooks form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those listed in the issue of the Department of Defense Index of Specifications and Standards (DODISS) and supplement thereto, cited in the solicitation (see 6.2).

SPECIFICATION

MILITARY

MIL-S-19500 - Semiconductor Devices, General Specification for.

STANDARDS

MILITARY

MIL-STD-750 - Test Methods for Semiconductor Devices.


(Unless otherwise indicated, copies of federal and military specifications, standards, and handbooks are available from the Defense Printing Services Detachment Office, Building 4D (Customer Service), 700 Robbins Avenue, Philadelphia, PA 19111-5094.)

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Defense Electronics Supply Center, ATTN: DESC-ELD, 1507 Wilmington Pike, Dayton, OH 45444-5765, by using the Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

AMSC N/A FSC 5961

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:20Z
Check the source to verify that this is the current version before use.



TOLERANCES: .XX ±.03
.XXX ±.010
(UNLESS OTHERWISE SPECIFIED)

FIGURE 1. Dimensions and configuration for 1N6690 through 1N6693.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:20Z
Check the source to verify that this is the current version before use.




FIGURE 2. Physical dimensions for surface mount devices (1N6690US through 1N6693US).

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:20Z
Check the source to verify that this is the current version before use.

2.2 Order of precedence. In the event of a conflict between the text of this document and the references cited herein, the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 Associated detail specification. The individual item requirements shall be in accordance with MIL-S-19500 and as specified herein.

3.2 Abbreviations, symbols, and definitions. Abbreviations, symbols, and definitions used herein shall be as specified in MIL-S-19500.

3.3 Design, construction, and physical dimensions. The design, construction, and physical dimensions shall be as specified in MIL-S-19500, and on figures 1 and 2 herein. The US government's preferred system of measurement is the metric SI system. However, since this item was originally designed using inch-pound units of measurement, in the event of conflict between the metric and inch-pound units, the inch-pound units shall take precedence.

3.3.1 Diode construction. These devices shall be constructed utilizing non-cavity double plug construction with metallurgical bonding between both sides of the silicon die and terminal pins (see MIL-S-19500). Metallurgical bond shall be in accordance with the requirements of category I in MIL-S-19500. -US version devices shall be structurally identical to the non-surface mount devices except for lead terminations.

3.3.2 Lead formation and finish. Lead finish shall be solderable as defined in MIL-S-19500, MIL-STD-750, and herein. Where a choice of lead finish or formation is desired, it shall be specified in the acquisition document (see 6.2).

3.3.3 Polarity. Polarity shall be marked with a contrasting band or dot on the cathode side of the diode body.

3.4 Marking. Marking shall be in accordance with MIL-S-19500.

3.4.1 Marking for the -US devices. For -US devices only, all marking may be omitted from the device except for the cathode marking. All marking which is omitted from the body of the device shall appear on the label of the initial container.

4. QUALITY ASSURANCE PROVISIONS

4.1 Sampling and inspection. Sampling and inspection shall be in accordance with MIL-S-19500, and as specified herein.

4.2 Qualification inspection. Qualification inspection shall be in accordance with MIL-S-19500.

4.2.1 Construction verification. Cross sectional photos from three devices shall be submitted in the qualification report.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:20Z
Check the source to verify that this is the current version before use.

INSTRUCTIONS: The purpose of this form is to solicit beneficial comments

4.3 Screening (JANS, JANTX, and JANTXV levels only). Screening shall be in accordance with table II of MIL-S-19500, and as specified herein. The following measurements shall be made in accordance with table I herein. Devices that exceed the limits of table I herein shall not be acceptable.

Screen (see table II of MIL-S-19500)	Measurement	
	JANS level	JANTX and JANTXV levels
3c 1/	Thermal impedance (see 4.3.2)	Thermal impedance (see 4.3.2)
9	Not applicable	Not applicable
10	Not applicable	Not applicable
11	V_{F1} and I_{R1}	V_{F1} and I_{R1}
12	MIL-STD-750, method 1038; test condition A; t = 240 hours V_R = 80 percent of rated V_R; T_A = +125°C	MIL-STD-750, method 1038; test condition A; t = 48 hours V_R = 80 percent of rated V_R; T_A = +125°C
13	Subgroup 2 of table I herein; V_{F1} and I_{R1}; ΔV_{F1} = ±100 mV (pk); ΔI_{R1} = ±5 µA dc or 100 percent from the initial value, whichever is greater.	Subgroup 2 of table I herein; V_{F1} and I_{R1}; ΔV_{F1} = ±100 mV (pk); ΔI_{R1} = ±5 µA dc or 100 percent from the initial value, whichever is greater.

1/ Thermal impedance shall be performed any time after screen 3.

4.3.1 Burn-in conditions. Burn-in conditions are as follows: T_A = +125°C; V_R = 0.8 to 0.85 rated V_R dc (see 1.3)

4.4 Quality conformance inspection. Quality conformance inspection shall be in accordance with MIL-S-19500.

4.4.1 Group A inspection. Group A inspection shall be conducted in accordance with MIL-S-19500 and tables I and III herein. The following test conditions shall be used for $Z_{\theta JX}$, group A inspection:

a. I_M measure current - - - - - - - - - - - - - - - 10 mA

b. I_H forward heating current - - - - - - - - - - - 5 - 50 A

c. t_H heating time - - - - - - - - - - - - - - - - - 50 ms

d. t_{MS} measurement delay time - - - - - - - - - - - 100 µs minimum

The maximum limit for $Z_{\theta JX}$ under these test conditions are $Z_{\theta JX}$(max) = 3.8°C/W. For -US devices, $Z_{\theta JX}$(max) = 3.3°C/W.

Source: https://assist.dla.mil -- Downloaded: 2026l0-19T04:20Z
Check the source to verify that this is the current version before use.

4.4.2 Group B inspection. Group B inspection shall be conducted in accordance with the conditions specified for subgroup testing in table IVa (JANS) and table IVb (JANTX and JANTXV) of MIL-S-19500. Electrical measurements (end-points) and delta requirements shall be in accordance with the applicable steps of table I, group A, subgroup 2 and 4.4.5 herein.

4.4.2.1 Group B inspection, table IVa (JANS) of MIL-S-19500.

Subgroup	Method	Condition
3	4066	I_{FSM} = rated (see 1.3); 10 surges of 8.3 ms each at 1 minute intervals. Condition B, T_A = +25°C.
4	1037	T_A = room ambient as defined in the general requirements of MIL-STD-750 (see 4.5). I_F or I_O = 2 A minimum for 2,000 cycles.
5	1027	I_O = 2 A minimum, adjust T_A or I_O to achieve an average $T_J \geq +250°C$.

4.4.2.2 Group B inspection, table IVb (JANTX and JANTXV) of MIL-S-19500.

Subgroup	Method	Condition
3	4066	I_{FSM} = rated (see 1.3); 10 surges of 8.3 ms each at 1 minute intervals. Condition B, T_A = +25°C.
4	1037	T_A = room ambient as defined in the general requirements of MIL-STD-750 (see 4.5). I_F or I_O = 2A minimum for 2,000 cycles.
5	3101	Not applicable.

4.4.3 Group C inspection. Group C inspection shall be conducted in accordance with the conditions specified for subgroup testing in table V of MIL-S-19500. Electrical measurements (end-points) and delta requirements shall be in accordance with the applicable steps of table I, group A, subgroup 2 and 4.4.5 herein.

4.4.3.1 Group C inspection, table V of MIL-S-19500.

Subgroup	Method	Condition
2	2036	Test condition A, weight = 10 pounds, t = 15 seconds.
3		Not applicable.
6	1037	T_A = room ambient as defined in the general requirements of MIL-STD-750 (see 4.5). I_F or I_O = 2 A minimum for 6,000 cycles.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:20Z
Check the source to verify that this is the current version before use.

4.4.4 Group E inspection. Group E inspection shall be conducted in accordance with the conditions specified for subgroup testing in table VII of MIL-S-19500. Electrical measurements (end-points) and delta requirements shall be in accordance with the applicable steps and footnotes of table I, group A, subgroup 2 herein and 4.4.5.

4.4.4.1 Group E inspection, table VII of MIL-S-19500.

Subgroup	Method	Condition	Sampling plan
1	1051	500 cycles.	22 devices, c = 0
2	1038	Condition A, t = 1,000 hours V_R = 80 percent V_{rated}	22 devices, c = 0
3		Not applicable	
4	3101	T_A = +25°C; $R_{\theta JL}$ (or $R_{\theta JE}$) = rated $R_{\theta JL}$ (or $R_{\theta JE}$) (see 1.3).	5 devices, c = 0
5	1016	V_R = rated V_R (see 1.3); pressure = 33 mmHg; t = 1 minute (minimum), R_{ISO} = 2.0 x 10^6 Ω maximum	5 devices, c = 0

4.4.5 Group B, C, and E electrical measurements (delta requirements).

Test	Method	Condition	Symbol	Maximum	Unit
V_F	4011	I_F = 5 A (pk); pulsed (see 4.5.1)	V_{F1}	0.78	V dc
ΔV_F	4011		ΔV_{F1}	±100	mV dc
I_R	4016	DC method, V_R = rated V_R (see 1.3); pulsed (see 4.5.1)	I_{R1}	50	µA dc
ΔI_R	4016		ΔI_{R1}	±5 or 100 percent, whichever is greater.	µA dc

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:20Z
Check the source to verify that this is the current version before use.

TABLE I. Group A inspection.

Inspection 1/	MIL-STD-750		Symbol	Limits		Unit
	Method	Conditions		Min	Max	
Subgroup 1						
Visual and mechanical examination	2071					
Subgroup 2						
Thermal impedance	3101	See 4.4.1 1N6690 through 1N6693 1N6690US through 1N6693US	$Z_{\theta JX}$		 3.8 3.3	°C/W
Breakdown voltage	4022	I_R = 100 µA dc pulsed (see 4.5.1) 1N6690, 1N6690US 1N6691, 1N6691US 1N6692, 1N6692US 1N6693, 1N6693US	V_{BR}	 600 800 1,000 1,200		V dc
Forward voltage	4011	I_F = 5 A (pk); pulsed (see 4.5.1) I_F = 20 A (pk); pulsed (see 4.5.1) I_F = 70 A (pk); pulsed (see 4.5.1)	V_{F1} V_{F2} V_{F3}		1.25 1.9 2.4	V dc V dc V dc
Reverse current leakage	4016	DC method; V_R = rated V_R (see 1.3); pulsed (see 4.5.1)	I_{R1}		10	µA dc
Subgroup 3						
High temperature operation:		T_C = +100°C				
Reverse current leakage	4016	DC method; V_R = rated V_R (see 1.3); pulsed (see 4.5.1)	I_{R2}		250	mA dc
Low temperature operation:		T_A = -65°C				
Forward voltage	4011	I_F = 5 A (pk); pulsed (see 4.5.1)	V_{F4}		1.5	V dc
Subgroup 4						
Scope display evaluation	2/					
Reverse recovery time	4031	Condition B; I_F = .5 A, I_R = 1 A I_{RR} = .25 A	t_{rr}		75	ns
Junction capacitance	4001	V_R = 10 V dc, f = 1 MHz V_{SIG} = 50 mV (p-p) (max)	C_J		250	
Subgroups 5, 6, and 7						
Not applicable						

1/ For sampling plan, see MIL-S-19500.

2/ The reverse breakdown characteristics shall be viewed on an oscilloscope with display calibration factors of 20 to 50 µA/division and 20 to 200V/division. Reverse current over the knee shall be at least 100 µA. Each device may exhibit a slightly rounded characteristic and any discontinuity or dynamic instability of the trace shall be cause for rejection.

Source: https://assist.dla.mil -- Downloaded: 2026l0-19T04:20Z
Check the source to verify that this is the current version before use.

4.5 Methods of inspection. Methods of inspection shall be as specified in the appropriate tables as follows.

4.5.1 Pulse measurements. Conditions for pulse measurement shall be as specified in 4.3.2.1 of MIL-STD-750.

4.5.2 Thermal impedance $Z_{\theta JX}$ measurements for screening. The $Z_{\theta JX}$ measurements shall be performed in accordance with MIL-STD-750, method 3101. The maximum limit (not to exceed the group A, subgroup 2 limit) for $Z_{\theta JX}$ in screening (table II of MIL-S-19500) shall be derived by each vendor by means of statistical process control. When the process has exhibited control and capability, the capability data shall be used to establish the fixed screening limit. In addition to screening, once a fixed limit has been established, monitor all future sealing lots using a random five piece sample from each lot to be plotted on the applicable X, R chart. If a lot exhibits an out of control condition, the entire lot shall be removed from the line and held for engineering evaluation and disposition.

4.5.2.1 Thermal impedance ($Z_{\theta JX}$ measurements) for initial qualification or requalification. The $Z_{\theta JX}$ measurements shall be performed in accordance with MIL-STD-750, method 3101 (read and record date $Z_{\theta JX}$). $Z_{\theta JX}$ shall be supplied on one lot (500 pieces minimum) and a thermal response curve shall be submitted. Twenty two of these samples shall be serialized and provided to the qualifying activity for correlation prior to shipment of parts. Measurements conditions shall be in accordance with 4.4.1.

5. PACKAGING

5.1 Packaging requirements. The requirements for packaging shall be in accordance with MIL-S-19500.

6. NOTES

(This section contains information of a general or explanatory nature that may be helpful, but is not mandatory.)

6.1 Notes. The notes specified in MIL-S-19500 are applicable to this specification.

6.2 Acquisition requirements. Acquisition documents should specify the following:

a. Issue of DODISS to be cited in the solicitation.

b. Lead formation and finish as specified (see 3.3.1).

c. Product assurance level and type designation.

CONCLUDING MATERIAL

Custodians:
Army - ER
Navy - EC
Air Force - 17
NASA - NA

Review activities:
Army - AR, MI, SM
Navy - AS, CG, MC
Air Force - 19, 85, 99

Preparing activity:
DLA - ES

(Project 5961-1721-03)

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:20Z
Check the source to verify that this is the current version before use.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:20Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS

1. The preparing activity must complete blocks 1, 2, 3, and 8. In block 1, both the document number and revision letter should be given.

2. The submitter of this form must complete blocks 4, 5, 6, and 7.

3. The preparing activity must provide a reply within 30 days from receipt of the form.

NOTE: This form may not be used to request copies of documents, nor to request waivers, or clarification of requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

I RECOMMEND A CHANGE:	1. DOCUMENT NUMBER MIL-S-19500/628	2. DOCUMENT DATE (YYMMDD) 94/11/18

3. DOCUMENT TITLE
SEMICONDUCTOR DEVICE, DIODE, SILICON, POWER RECTIFIER, ULTRAFAST, TYPES 1N6690 THROUGH 1N6693, 1N6690US THROUGH 1N6693US, JANTX, JANTXV, AND JANS

4. NATURE OF CHANGE (Identify paragraph number and include proposed rewrite, if possible. Attach extra sheets as needed.)

5. REASON FOR RECOMMENDATION

6. SUBMITTER

a. NAME (Last, First, Middle initial)	b. ORGANIZATION	
c. ADDRESS (Include Zip Code)	d. TELEPHONE (Include Area Code) (1) Commercial (2) AUTOVON (If applicable)	7. DATE SUBMITTED (YYMMDD)

8. PREPARING ACTIVITY

a. NAME Alan Barone	b. TELEPHONE (Include Area Code) (1) Commercial 513-296-6048 (2) AUTOVON 986-6048
c. ADDRESS (Include Zip Code) Defense Electronics Supply Center Attn: DESC-ELDT Dayton, Ohio 45444-5765	**IF YOU DO NOT RECEIVE A REPLY WITHIN 45 DAYS, CONTACT:** Defense Quality and Standardization Office 5203 Leesburg Pike, Suite 1403, Falls Church, VA 22041-3466 Telephone (703) 756-2340 AUTOVON 289-2340

DD Form 1426, OCT 89 Previous editions are obsolete 198/290

Source: https://assist.dla.mil -- Downloaded: 202610-19T04:20Z
Check the source to verify that this is the current version before use.

procured with ar [redacted] lification in procurement of products for [illegible]