MIL-S-11476D
10 June 1980
SUPERSEDING
MIL-S-11476C
3 July 1969

MILITARY SPECIFICATION

STONES, CORRECTION, LITHOGRAPHIC

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers lithographic correction stones suitable for cleaning zinc and aluminum lithographic plates.

1.2 Classification. Correction stones shall be of the following types, and sizes, specified (see 6.2):

Type I - Scotch hone.
Size - 1/8 inch square
3/16 inch square
1/4 inch square
3/8 inch square
1/2 inch square
1 inch square

Type II - Etching slip.
Size - Rectangular - 1/4 inch thick, plus or minus 1/16 inch, by 3/8 inch wide, plus or minus 1/8 inch.
- Round - Diameter not less than 1/4 inch and not more than 1/2 inch.

2. APPLICABLE DOCUMENTS

2.1 Issues of documents. The following documents of the issue in effect on date of invitation for bids or request for proposal form a part of this specification to the extent specified herein:

FSC 3610

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: US Army Mobility Equipment Research and Development Command, ATTN: DRDME-DS, Fort Belvoir, VA 22060 by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T16:04Z
Check the source to verify that this is the current version before use.

SPECIFICATIONS

FEDERAL

P-P-105	- Paper, Abrasive, (Flint).
PPP-B-566	- Boxes, Folding, Paperboard.
PPP-B-601	- Boxes, Wood, Cleated-Plywood.
PPP-B-636	- Boxes, Shipping, Fiberboard.
PPP-B-640	- Boxes, Fiberboard, Corrugated, Triple-Wall.

MILITARY

MIL-P-116	- Preservation - Packaging, Methods of.

STANDARDS

MILITARY

MIL-STD-105	- Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129	- Marking for Shipment and Storage.
MIL-STD-1188	- Commercial Packaging of Supplies and Equipment.

(Copies of specifications and standards required by contractor in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

3. REQUIREMENTS

3.1 Description. The correction stones shall be of an abrasive nature capable of smoothing out nicks or scratches, or of removing unwanted material, either part of the image, or foreign matter, from lithographic press plates.

3.2 Material. Material shall be as specified herein. The use of recycled material is encouraged and may be used when approved by the Contracting Officer, provided it meets the requirements of the specification (see 6.2 and 6.3).

3.3 Performance. The correction stones shall withstand the normal pressure required to remove the image from the surface of a zinc or aluminum lithographic plate without breaking, chipping, or disintegrating. There shall be no change in the composition or form of the stone other than normal wear at the surface encountering the plate. The area of the plate from which the image is removed shall be grease repellent and shall show no evidence of accepting rub-up ink after the area has been etched, washed, gummed, and rubbed-up. The stones shall be free of coarse grit, grease, oil, or any other substance that might be detrimental to the surface of the plate.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T16:04Z
Check the source to verify that this is the current version before use.

3.4 Brittleness. The correction stones shall undergo reduction in size and render a new surface without chipping or splitting.

3.5 Type I (scotch hone). Correction stones shall be of a natural stone of uniform texture and hardness.

3.5.1 Size. The stones shall be 5 inches long, plus or minus 1/8 inch, the square dimensions shall have a tolerance of plus or minus 1/32 inch.

3.6 Type II (etching slip). Correction stones shall consist of a mixture of fine pumice abrasive and glue, or other adhesive, molded to size and form, and dried.

3.6.1 Size. The stones shall be 6 inches long plus or minus 1/4 inch .

3.7 Workmanship. Workmanship shall be in accordance with high grade manufacturing practice for lithographic correction stones.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.2 Classification of inspection. Inspection shall be classified as follows:

(a) Quality conformance inspection (see 4.3).
(b) Inspection of packaging (see 4.5).

4.3 Quality conformance inspection.

4.3.1 Sampling. Sampling for examination and tests shall be in accordance with MIL-STD-105.

4.3.1.1 Lot. A lot shall consist of all the correction stones of one type offered for delivery at one time.

4.3.2 Examination. Samples selected in accordance with 4.3.1 shall be examined as specified in 4.4.1. AQL shall be 2.5 percent defective.

4.3.3 Tests. Samples selected in accordance with 4.3.1 shall be tested as specified in 4.4.2. AQL shall be 2.5 percent defective.

4.4 Inspection procedure.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T16:04Z
Check the source to verify that this is the current version before use.

4.4.1 Examination. The correction stones shall be examined for the following defects:

101. Material not as specified.
102. Dimensions not as specified.
103. Contains coarse grit.
104. Contains grease, oil, or other substance detrimental to plates.

4.4.2 Tests

4.4.2.1 Performance. Using the stone in the manner of a pencil when making erasures, remove a small area of a surface image on a zinc or aluminum lithographic plate. Then wash and etch the area and apply a thin coating of gum arabic solution (14° Be). While the gum is still wet, apply rub-up ink to the area. The plates shall be prepared according to standard lithographic practice. Nonconformance to 3.3 shall constitute failure of this test.

4.4.2.2 Brittleness. With normal pressure, rub one end of the stone over the surface of abrasive flint paper conforming to P-P-105, grit size fine. Nonconformance to 3.4 shall constitute failure of this test.

4.5 Inspection of packaging.

4.5.1 Quality conformance inspection of pack.

4.5.1.1 Unit of product. For the purpose of inspection, a completed pack prepared for shipment shall be considered a unit of product.

4.5.1.2 Sampling. Sampling for examination shall be in accordance with MIL-STD-105.

4.5.1.3 Examination. Samples selected in accordance with 4.5.1.2 shall be examined for the following defects. AQL shall be 2.5 percent defective.

103. Materials, methods, and containers not as specified for Level A or B. Each incorrect material, method, or container shall be considered one defect.
104. Quantities preserved together not as specified.
105. Intermediate pack not as specified.
106. Gross weight exceeds 200 pounds for level A.
107. Gross weight or size exceeds box limitations for level B.
108. Marking missing, illegible, incorrect, or incomplete.

5. PACKAGING

5.1 Preservation. Preservation shall be level A, or Commercial, as specified (see 6.2).

5.1.1 Level A. Stones of like description shall be preserved together in quantities of 12 each in accordance with MIL-P-116, method IC-2, using the contractor's commercial box or container, or a close-fitting box conforming to PPP-B-566, variety 1, style, type, and class optional.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T16:04Z
Check the source to verify that this is the current version before use.

5.1.2 Commercial. Commercial preservation shall be in accordance with MIL-STD-1188.

5.2 Intermediate pack. Stones of like description, preserved as specified in 5.1.1, shall be placed together in a close fitting box conforming to PPP-B-636, W6c, in quantities not to exceed the weight limitations of the box specification.

5.3 Packing. Packing shall be level A, level B, or Commercial, as specified (see 6.2).

5.3.1 Level A. The stones, preserved and intermediate packed as specified in 5.1 and 5.2, shall be packed in quantities not to exceed 200 pounds in close fitting boxes conforming to PPP-B-601, overseas type, style optional. Box closure and strapping shall be in accordance with the appendix to the box specification.

5.3.2 Level B. The stones, preserved and intermediate packed as specified in 5.1 and 5.2, shall be packed in close fitting fiberboard boxes conforming to PPP-B-636, V3c, style optional, or PPP-B-640, class 2, style optional. The gross weight or size of each box shall not exceed the limitations of the applicable box specification. Box closure and strapping shall be in accordance with the appendix to the applicable box specification.

5.3.3 Commercial. Commercial packing shall be in accordance with MIL-STD-1188.

5.4 Marking. In addition to any special marking required by the contract or order, marking for military levels of protection shall be in accordance with MIL-STD-129. Commercial marking shall be in accordance with MIL-STD-1188.

6. NOTES

6.1 Intended use. The stones are intended for cleaning and repairing minor damage to zinc and aluminum lithographic plates.

6.2 Ordering data. Procurement documents should specify the following:

(a) Title, number, and date of this specification.
(b) Type, size, and shape of stones required (see 1.2, 3.5.1 and 3.6.1).
(c) Degree of preservation and degree of packing required (see 5.1 and 5.3).

6.3 Recycled Material. It is encouraged that recycled material be used, when practical, as long as it meets the requirements of this specification (see 3.2).

Custodians:
Army - ME
Air Force - 99

Review activity:
DLA - GS

User activity:
Navy - MC

Preparing activity:
Army - ME

Project 3610-0308

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T16:04Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

OMB Approval
No. 22-R255

INSTRUCTIONS: The purpose of this form is to solicit beneficial comments which will help achieve procurement of suitable products at reasonable cost and minimum delay, or will otherwise enhance use of the document. DoD contractors, government activities, or manufacturers/ vendors who are prospective suppliers of the product are invited to submit comments to the government. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements. Attach any pertinent data which may be of use in improving this document. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity.

DOCUMENT IDENTIFIER AND TITLE
MIL-S-11476D Stones, Correction, Lithographic

NAME OF ORGANIZATION AND ADDRESS

CONTRACT NUMBER

MATERIAL PROCURED UNDER A
☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE DOCUMENT CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?
   A. GIVE PARAGRAPH NUMBER AND WORDING.

   B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY DOCUMENT REQUIREMENT CONSIDERED TOO RIGID

3. IS THE DOCUMENT RESTRICTIVE?
   ☐ YES ☐ NO *(If "Yes", in what way?)*

4. REMARKS

SUBMITTED BY *(Printed or typed name and address - Optional)*

TELEPHONE NO.

DATE

DD FORM 1 JAN 72 1426 REPLACES EDITION OF 1 JAN 66 WHICH MAY BE USED

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T16:04Z
Check the source to verify that this is the current version before use.