MILITARY SPECIFICATION

FORCEPS, DRESSING, 3 1/2 INCH

This specification is mandatory for use by all the Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers a tweezer type dressing forceps suitable for use in first aid and field kits.

2. APPLICABLE DOCUMENTS

2.1 The following documents of the issue in effect on date of invitation for bids or request for proposals, form a part of the specification to the extent specified herein:

SPECIFICATIONS

Federal

GG-I-526	Instruments, Dental and Surgical, General Specifications.
MMM-A-250	Adhesive, Water Resistant (for Sealing Fiberboard Boxes).
PPP-B-585	Boxes, Wood, Wirebound.
PPP-B-601	Boxes, Wood, Cleated-Plywood.
PPP-B-621	Boxes, Wood, Nailed and Lock-Corner.
PPP-B-636	Box, Fiberboard.
PPP-T-76	Tape, Pressure-Sensitive Adhesive Paper, (for Carton Sealing).

Military

MIL-P-116	Preservation, Methods of.

Source: https://assist.dla.mil -- Downloaded: 202610-21T09:16Z
Check the source to verify that this is the currentversion before use.

STANDARDS

Federal

FED-STD-151	Metal, Test Methods.

Military

MIL-STD-105	Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129	Marking for Shipment and Storage.

DRAWING

DEFENSE PERSONNEL SUPPORT CENTER

Drawing No. 1973	Forceps, Dressing, 3-1/2 Inch.

(Copies of specifications, standards, and drawing required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposals shall apply:

AMERICAN SOCIETY FOR TESTING AND MATERIALS

E 18	Rockwell Hardness and Rockwell Superficial Hardness of Metallic Materials, Test for.
B 117	Salt Spray (Fog) Testing.

(Application for copies should be addressed to ASTM, 1916 Race Street, Philadelphia, Pa. 19103).

3. REQUIREMENTS

3.1 Materials. The forceps shall be fabricated from properly forged martensitic stainless steel or plain carbon steel. The plain carbon steel forceps shall be protected by electrodeposited chromium over nickel. The martensitic stainless steel shall conform to the requirements of Class 4 and the plain carbon steel of Class 1 steels of GG-I-526.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T09:16Z
Check the source to verify that this is the current version before use.

3.2 Style, design, and dimensions. The dressing forceps shall be suitable for use in the application and removal of surgical dressings. The style, design, and dimensions of the forceps shall be in accordance with DPSC Drawing No. 1973. The forceps shall be of the tweezer type with the proximal ends of the two members permanently secured. The dressing forceps shall have the necessary spring action and shall have the proper alignment to be used repeatedly with the tips maintaining coincidence.

3.3 Hardness. The plain carbon steel forceps shall have a minimum hardness of Rockwell B 80. If made from martensitic stainless steel the forceps shall be properly hardened for maximum corrosion resistance.

3.4 Finish. The finished forceps shall have a polished mirror or mirror and satin surface. The plain carbon steel forceps shall be in accordance with Class 8 nickel and chromium plating of GG-I-526. Forceps shall meet the corrosion resistance requirements for the martensitic stainless steel and chromium over nickel plated plain carbon steel as specified in GG-I-526.

3.5 Workmanship. Workmanship shall be first class throughout. The forceps shall be free from defects which detract from their appearance or may impair their serviceability.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the supplier may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

4.1.1 Records. Records of examinations and tests performed by or for the contractor shall be maintained by the contractor and made available to the Government, upon the Government's request, at any time, or from time to time, during the performance of the contract and for a period of two years after delivery of the supplies to which such records relate.

4.1.2 Inspection. Inspection, as used in this specification, is defined as both examination (such as visual or auditory investigation without the use of special laboratory appliances or procedures) and testing (determination by technical means of physical and chemical properties) of the item.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T09:16Z
Check the source to verify that this is the current version before use.

4.1.3 Certificates of quality. Certificates of quality, supplied by the manufacturer of the steels, may be furnished in lieu of actual performance of such testing by the contractor, provided lot identity has been maintained and can be demonstrated to the Government. The certificate shall include the name of the contractor, the contract number, the name of the manufacturer or supplier, the FSN, the item identification, the name of the material, the lot number, the lot size, the sample size, the date of testing, the test method, individual test results, and the specification requirements.

4.2 Sampling.

4.2.1 Sampling for examination. Sampling for examination shall be conducted in accordance with MIL-STD-105 and as indicated in Table I.

Table I. Sampling Criteria for Examination

Type of defect	Inspection level	AQL (% defective)
Major	S-3	1.0*
Minor	S-1	1.5

* If acceptance number is not exceeded, lot shall be accepted. If rejection number is equalled or exceeded, then the inspection at Level II may be performed to determine the final rejection or acceptance.

4.2.2 For tests. Sampling for tests shall be conducted in accordance with MIL-STD-105 and as indicated in Table II.

Table II. Sampling Criteria for Tests

Component	Characteristic	Requirement	Test procedure	Inspection level	AQL
Steel	Composition	3.1	4.2.3, 4.4.1	S-2	2.5
Forceps	Hardness	3.3	4.4.2	S-1	4.0
	Corrosion resistance:				
Plated steel	Salt Spray	3.4 and GG-I-526	4.4.3	S-3	1.5
Stainless steel	Copper Sulfate	3.4 and GG-I-526	4.4.3	S-2	1.5
Stainless steel	Boil test	3.4 and GG-I-526	4.4.3	S-2	1.5

Source: https://assist.dla.mil -- Downloaded: 202640-21T09:16Z
Check the source to verify that this is the current version before use.

4.2.3 Raw material. Four ounces of each lot of each metal used in the fabrication of the forceps shall be selected for chemical analysis.

4.2.4 Sample unit usage. Where possible, the same sample unit shall be used for the determination of two or more test characteristics.

4.3 Examination. The forceps shall be examined for defects including, but not limited to, those listed in Table III.

Table III. Classification of Defects

Categories	Defects
Major	
101	Halves of forceps not permanently secured.
102	Forceps not properly aligned.
103	Forceps lacks spring action.
104	Edges of forceps not smooth, free from burrs, cracks, or pits.
Minor	
201	Dimensions, other than those of tips, not as specified.
202	Marking of interior packages and exterior containers not as specified.
203	Packaging and packing not as specified.

4.4 Test procedures.

4.4.1 Chemical analysis. In the absence of certificates of quality (see 4.1.3), the chemical composition of the steel used in the manufacture of the forceps shall be determined, using Method 111.2 or 112.2 of FED-STD-151.

4.4.2 Hardness. The hardness of the steel used in the fabrication of the forceps shall be determined in accordance with ASTM Method E 18.

4.4.3 Corrosion resistance. The 24-hour salt spray resistance shall be determined for plated forceps by ASTM Method B-117. The boil test and copper sulphate tests shall be conducted as specified in GG-I-526.

5. PREPARATION FOR DELIVERY

5.1 Packaging. Packaging shall be level A or C as specified (see 6.2).

5.1.1 Unit of issue. One forceps, as specified, constitutes one unit of issue.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T09:16Z
Check the source to verify that this is the current version before use.

5.1.2 Packaging quantities. The number of units of issue indicated in Table IV shall be packaged in each unit, intermediate, and exterior container, as applicable, for the required level of protection specified in the procurement document.

Table IV. Packaging Quantities

Unit package	Intermediate package	Exterior container
1 unit	12 units	576 units

5.1.2.1 Packing variation permitted. If the required number of units in the entire shipment is less than the number of units specified to be overpacked in an exterior container, such units may be packed in an exterior container of suitable size and design, acceptable to a common carrier, which shall insure safe delivery to destination.

5.1.3 Level A.

5.1.3.1 Cleaning and drying. Each unit shall be thoroughly cleaned and dried in accordance with the applicable method as outlined in MIL-P-116.

5.1.3.2 Preservative. Not required.

5.1.3.3 Intimate wrap. Each unit shall be wrapped in neutral tissue or other suitable anticorrosive material.

5.1.3.4 Unit package. Each unit shall be packaged in accordance with MIL-P-116, method IA-8.

5.1.3.5 Intermediate package. Intermediate package shall be a box of appropriate size and design constructed in accordance with PPP-B-636, type CF, class weather-resistant. Boxes shall be closed by taping the top and bottom flaps with 2 inch wide tape conforming to PPP-T-76. Closing of bottom flaps with adhesive conforming to MMM-A-250 or metal stitches is permitted.

5.1.4 Level C. Units shall be packaged in standard commercial containers of the size and kind commonly used, which will afford the degree of protection required for shipment and use of the product for its intended purpose.

5.2 Packing. Packing shall be level A, B or C as specified (see 6.2).

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T09:16Z
Check the source to verify that this is the current version before use.

5.2.1 Level A.

5.2.1.1 Exterior container. Exterior container shall be designed for a type 2 load and constructed in accordance with PPP- B-585, class 3, style 3; PPP-B-601, overseas type; PPP-B-621, class 2; or PPP-B-636, class weather-resistant, grade V3c. Closure and strapping shall be as specified in the appendix of the applicable box specification.

5.2.2 Level B.

5.2.2.1 Exterior container. Exterior container shall be designed for a type 2 load and constructed in accordance with PPP-B-585, class 1, style 3; PPP-B-601, domestic type; PPP-B-621, class 1; or PPP-B-636, class domestic. Closure shall be as specified in the appendix of the applicable box specification. Fiberboard box shall be closed by method II of PPP-B-636.

5.2.3 Level C. The subject commodity shall be packed in substantial commercial containers of the type, size, and kind commonly used for the purpose, so constructed as to insure acceptance and safe delivery by common or other carriers, at the lowest rate, to point of delivery called for in the contract or purchase order.

5.3 Marking.

5.3.1 Interior packages. Each unit package and each intermediate package shall be marked in accordance with MIL-STD-129. When labels are utilized, waterproofing shall be required only when applicable carton is fabricated of water-resistant material. Contract or purchase order number and name of contractor shall be shown.

5.3.2 Exterior container. Exterior container shall be marked in accordance with MIL-STD-129.

6. NOTES

6.1 Intended use. This specification covers a dressing forceps intended for use in the field and in first aid kits for applying and removing dressings.

6.2 Ordering data. Procurement documents should specify the following:

(a) Title, number and date of this specification.
(b) Applicable levels of packaging and packing (See 5.1 and 5.2).
(c) Federal stock number.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T09:16Z
Check the source to verify that this is the current version before use.

6.3 This specification covers the following item appearing in the Federal Stock Catalog:

Stock No.	Item Identification
6515-333-2200	Forceps, Dressing, 3 1/2 Inch

Custodians:
Army - MD
Navy - MS
Air Force - 03

Review activities:
Army - MD
Navy - MS
Air Force - 03

Preparing activity:
Defense Supply Agency - DM

Project No. 6515-1566

Review information is current as of the date of this document. For future coordination of changes to this document, draft circulation should be based on the information in the current DODISS.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T09:16Z
Check the source to verify that this is the current version before use.

SPECIFICATION ANALYSIS SHEET

Form Approved
Budget Bureau No. 22-R255

INSTRUCTIONS: This sheet is to be filled out by personnel, either Government or contractor, involved in the use of the specification in procurement of products for ultimate use by the Department of Defense. This sheet is provided for obtaining information on the use of this specification which will insure that suitable products can be procured with a minimum amount of delay and at the least cost. Comments and the return of this form will be appreciated. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments and suggestions submitted on this form do not constitute or imply authorization to waive any portion of the referenced document (s) or serve to amend contractual requirements.

SPECIFICATION

MIL-F-36759 FSN:

ORGANIZATION

CITY AND STATE

CONTRACT NUMBER

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE SPECIFICATION CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A. GIVE PARAGRAPH NUMBER AND WORDING.

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY SPECIFICATION REQUIREMENT CONSIDERED TOO RIGID

3. IS THE SPECIFICATION RESTRICTIVE?

☐ YES ☐ NO *(If "yes", in what way?)*

4. REMARKS *(Attach any pertinent data which may be of use in improving this specification. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity)*

SUBMITTED BY *(Printed or typed name and activity - Optional)*

DATE

DD FORM 1 JAN 65 1426 REPLACES EDITION OF 1 OCT 64, WHICH MAY BE USED.

Source: https://assist.dla.mil -- Downloaded: 202640-21T09:16Z
Check the source to verify that this is the current version before use.

CAUTION

NOTICE TO BIDDERS/OFFERORS

DO NOT CONDITION OR BASE YOUR BID/OFFER ON ANY CURRENT PROCUREMENT ON THE INFORMATION SUBMITTED ON THIS FORM SINCE ANY CHANGES OR DELETIONS IN THE SPECIFICATIONS MAY RENDER YOUR BID/OFFER NON-RESPONSIVE IN WHICH CASE IT CANNOT BE CONSIDERED FOR AWARD.

Fold

DEFENSE PERSONNEL SUPPORT CENTER
2800 SOUTH 20TH STREET
PHILADELPHIA, PA. 19101

DEFENSE SUPPLY AGENCY
OFFICIAL BUSINESS

POSTAGE AND FEES PAID
DEFENSE SUPPLY AGENCY

HEADQUARTERS, DEFENSE PERSONNEL SUPPORT CENTER
ATTN: DIRECTORATE OF MEDICAL MATERIEL, CODE ATT
2800 SOUTH 20TH STREET
PHILADELPHIA, PA. 19101

Fold

DPSC FORM 2418
MAR 68

EDITION AUG 66, WILL BE USED UNTIL EXHAUSTED

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T09:16Z
Check the source to verify that this is the current version before use.