A-A-0053756(DM)
31 October 1988

INTERIM COMMERCIAL ITEM DESCRIPTION

GAUZE, OINTMENT IMPREGNATED

The General Services Administration has authorized the use of this Interim Commercial Item Description which was developed by the Defense Personnel Support Center, Directorate of Medical Materiel, DPSC-RST, 2800 South 20th Street, Philadelphia, PA 19101, based upon the currently available technical information.

This interim commercial item description covers dressings impregnated with an anhydrous petrolatum based ointment.

Salient characteristics.

Shall be sterile, one ply, non-adhering, acetate gauze dressings impregnated with anhydrous petrolatum based ointment for use in dressing partial thickness burns and split thickness skin grafts. The dressing shall be sterile when tested in accordance with the USP. The dressings shall be of the following sizes:

SIZE	INCHES (+/- 1/8 INCH)
1	3 BY 8
2	3 BY 3

The gauze shall be warp knit having 23±1 top ends per inch, 22±1 bottom ends per inch and 27 to 30 courses per inch. The dry gauze shall be 52 to 56 yards per pound for the three inch width. Both edges of the gauze shall be selvage.

The gauze shall be thoroughly and evenly coated with anhydrous petrolatum based ointment on both sides of the gauze and still leave the interstices between the gauze knit open and porous.

AMSC/NA FSC 6510

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:24Z
Check the source to verify that this is the current version before use.

The ointment shall be comprised of the following:

White Petrolatum, USP
Mineral Oil, USP
Lanolin Alcohols, NF (Wool Wax Alcohol) that is odor free
Ceresin Wax (Mineral Wax)

The ointment shall have a pH of 6.50 to 7.50 when tested in accordance with the USP and shall have a specific gravity of 0.865 to 0.872 when tested at 25°C using the Mettler DMA specific gravity testing instrument (or an equivalent method giving the same results). The ointment shall have a melting range of 42 to 45°C (temperature where the ointment softens and where it is melted) when tested by placing a small amount of the ointment on a slip cover and using the Fisher Melting Point Apparatus (or and equivalent method giving the same results). The ointment shall be unscented and shall be washable. The bandage shall be non-irritating and nontoxic; free of loose threads; and the top and bottom ends and the courses shall be evenly spaced.

Workmanship. The dressings shall be free from defects which detract from their appearance or impair their serviceability.

Unit. Package (PG). Each sterile impregnated gauze dressing shall be individually packaged in a sealed peel-open foil package capable of maintaining sterility of contents unless package is damaged or opened. One package containing 50 individually sealed dressings of one size only, as specified, constitutes one unit.

Quality Assurance Provisions.

Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

Source: https://assist.dla.mil -- Downloaded: 202610-26T09:24Z
Check the source to verify that this is the currentversion before use.

Records. Records of examinations and tests performed by or for the contractor shall be maintained by the contractor and made available to the Government upon the Government's request, at any time, or from time to time, during the performance of the contract and for a period of three years after delivery of the supplies to which such records relate.

Inspection. Inspection, as used herein, is defined as both examination (such as visual or auditory investigation without the use of special laboratory appliances or procedures) and testing (determination by technical means of physical and chemical properties) of the item. Testing and examination shall be conducted to determine compliance with all specification requirements. Test methods shall be suitable, accurate and reproducible.

Sampling for examination. Sampling for examination shall be conducted in accordance with MIL-STD-105 and as specified herein. The unit of product for examination shall be one dressing. Unless otherwise specified, sampling for examination shall be conducted at inspection level II, AQL 2.5 maximum percent defective.

Contractor certification. The contractor shall certify that the product offered meets the salient characteristics of this description and conforms to the producers' own drawings, specifications, standards, and quality assurance practices. The Government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

Metric products. Products manufactured to metric dimensions will be considered on an equal basis with those manufactured using inch-pound units, providing they fall within the tolerances specified using conversion tables contained in the latest revision of Federal Standard No. 376, and all other requirements of this document are met.

If a product is manufactured to metric dimensions and those dimensions exceed the tolerances specified in the inch/pound units, a request should be made to the contracting officer to determine if the product is acceptable.

The contracting officer has the option of accepting or rejecting the product.

Source: https://assist.dla.mil -- Downloaded: 202610-26T09:24Z
Check the source to verify that this is the current version before use.

Regulatory requirements.

Federal Food, Drug and Cosmetic Act. If the product covered by this document has been determined by the U.S. Food and Drug Administration to be under its jurisdiction, the offeror/contractor shall comply, and be responsible for compliance by its subcontractors/suppliers, with the requirements of the Federal Food, Drug and Cosmetic Act, as amended, and regulations promulgated thereunder. In addition, the offeror/contractor shall comply, and be responsible for compliance by its subcontractors/suppliers, with the requirements of all other applicable Federal, State, and local statutes, ordinances, and regulations.

Recovered materials. The offeror/contractor is encouraged to use recovered material in accordance with Public Law 94-580, as amended, and as implemented by Federal Acquisition Regulation Subpart 23.4 to the maximum extent practical.

Preservation, packaging, packing, labeling, and marking. Unless otherwise specified, preservation, packaging, and packing shall be to a degree of protection to preclude damage to containers and/or contents thereof under normal shipping conditions, handling, etc., involving shipment from the supply source to the receiving activity, plus reshipment from receiving activity, and shall conform to applicable carrier's rules and regulations. Intermediate and exterior package quantities and labeling and marking shall be as specified in the contract and/or order.

NOTE: The following National Stock Numbers are covered by this document:

NSN	ITEM IDENTIFICATION	SIZE
6510-01-228-6000	GAUZE, OINTMENT IMPREGNATED, 3 By 8 Inches, 50s	1
6510-01-281-1239	GAUZE, OINTMENT IMPREGNATED, 3 By 3 Inches, 50s	2

Ordering data. Expiration dating required, intermediate/exterior package quantities and labeling and marking must be specified in the contract and/or order.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:24Z
Check the source to verify that this is the current version before use.

MILITARY INTERESTS:

Custodians:

Army - MD
Navy - MS
Air Force - 03

PREPARING ACTIVITY:

DoD - MB

Agent:

DLA-DM

CIVIL AGENCY COORDINATING ACTIVITY:

VA-OSS
PHS
FDA-MPQAS

PGC 71129

Project No. 6510-0766

☆U.S. GOVERNMENT PRINTING OFFICE: 1989 - 604-033/11551

Source: https://assist.dla.mil -- Downloaded: 202610-26T09:24Z
Check the source to verify that this is the current version before use.