# COMMERCIAL ITEM DESCRIPTION

## SPONGE, SCLERAL, SILICONE (Lincaff)

The General Services Administration has authorized the use of this commercial item description.

This commercial item description covers a silicone scleral sponge used in scleral buckling procedures to reattach the retina to the choroid in retinal detachment and ophthalmic surgery.

Salient characteristics:

General. The sponge shall be a sterile, permanent, non-pyrogenic, nonantigenic and nontoxigenic silicone scleral sponge of the Lincaff design for retinal detachment and opthalmic surgery.

Material. The scleral sponge shall be fabricated from heat cured silicone sponge elastomer. This material shall comply with the property requirements listed in Table I. Sample of the material shall be subjected to the test specified for each property.

TABLE I. Property Requirements.

| Property | | Test Method |
|---|---|---|
| Density Durometer Hardness | 0.605 g/cm$^3$ | ASTM D792 * |
| Shore 00 | 40 ± 5 | ASTM D2240 |
| Cell Size | 0.4 mm | |
| Tensile Strength | 37 ± 5 psi | ASTM D412 |
| Ultimate Elongation | 80 ± 5% | ASTM D412 |
| Pyrogenicity | Non-pyrogenic | USP ** |

AMSC N/A FSC 6515

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:24Z
Check the source to verify that this is the current version before use.

TABLE I. Property Requirements. (cont).

| Property | | Test Method |
|---|---|---|
| Toxicity | Nontoxic | USP ** |
| Cytotoxicity | Noncytotoxic | ASTM F895 |
| Arsenic | 5 ppm maximum | USP ** |
| Barium | 5 ppm maximum | USP ** |
| Bismuth | 5 ppm maximum | USP ** |
| Cadmium | 5 ppm maximum | USP ** |
| Lead | 5 ppm maximum | USP ** |
| Mercury | 5 ppm maximum | USP ** |

* American Society for Testing and Materials
** United States Pharmacopeia, latest revision

Style, design and dimensions. The sponge shall be in accordance with Defense Personnel Support Center (DPSC) Drawing No. 23424.

Biocompatibility. The silicone scleral sponge shall be biocompatible when tested in accordance with USP Class V for plastics.

Sterility. The sterility assurance level shall be 0.000001 when tested in accordance with the latest edition of USP.

Finish. The silicone scleral sponge shall have a smooth, uniform finish.

Workmanship. The silicone scleral sponge shall be free from blooming, blisters, dish-eyes, frosting, pits, pimples, shorts, warpage, wrinkles, and any other defects which detract from its appearance or impairs its serviceability. Definitions of defects listed above shall be in accordance with ASTM Designation D883, "Standard Definitions of Terms Relating to Plastics".



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:24Z
Check the source to verify that this is the current version before use.

Unit. Package (PG). One package containing five individually packaged sterile silicone scleral sponges, as specified, constitutes one unit. The individual package shall be a sealed peel-open type container capable of maintaining sterility of contents unless the package is damaged or opened.

Quality Assurance Provisions.

Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

Records. Records of examinations and tests performed by or for the contractor shall be maintained by the contractor and made available to the Government upon the Government's request, at any time, or from time to time, during the performance of the contract and for a period of three years after delivery of the supplies to which such records relate.

Inspection. Inspection, as used herein, is defined as both examination (such as visual or auditory investigation without the use of special laboratory appliances or procedures) and testing (determination by technical means of physical and chemical properties) of the item.

Tests. Tests shall be conducted to determine compliance with specification requirements. Where feasible, the same sample shall be used for the determination of two or more test characteristics.

Sampling for inspection. Sampling for inspection of all materials shall be conducted in accordance with MIL-STD-105 at Level S-2 and AQL 1.0%. Acquisition of samples from raw material lots shall be conducted in accordance with Section 12.2 of ASTM Designation D1899.



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:24Z
Check the source to verify that this is the current version before use.

Sampling for inspection of end items shall be conducted in accordance with MIL-STD-105 at Level S-2, AQL 1.5%. For this inspection, the unit of product for inspection purposes shall be one silicone scleral sponge as specified herein.

Contractor certification. The contractor shall certify that the product offered meets the salient characteristics of this description and conforms to the producer's own drawings, specifications, standards, and quality assurance practices. The Government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

Metric products. Products manufactured to metric dimensions will be considered on an equal basis with those manufactured using inch-pound units, providing they fall within the tolerances specified using conversion tables contained in the latest revision of Federal Standard No. 376, and all other requirements of this document are met.

If a product is manufactured to metric dimensions and those dimensions exceed the tolerances specified in the inch/pound units, a request should be made to the contracting officer to determine if the product is acceptable.

The contracting officer has the option of accepting or rejecting the product.

Regulatory requirements.

Federal Food, Drug and Cosmetic Act. If the product covered by this document has been determined by the U.S. Food and Drug Administration to be under its jurisdiction, the offeror/contractor shall comply, and be responsible for compliance by its subcontractors/suppliers, with the requirements of the Federal Food, Drug and Cosmetic Act, as amended, and regulations promulgated thereunder. In addition, the offeror/contractor shall comply, and be responsible for compliance by its subcontractors/suppliers, with the requirements of all other applicable Federal, State, and local statutes, ordinances, and regulations.

Recovered materials. The offeror/contractor is encouraged to use recovered material in accordance with Public Law 94-580, as amended, and as implemented by Federal Acquisition Regulation Subpart 23.4 to the maximum extent practical.



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:24Z
Check the source to verify that this is the current version before use.

Preservation, packaging, packing, labeling, and marking. Unless otherwise specified, preservation, packaging, and packing shall be to a degree of protection to preclude damage to containers and/or contents thereof under normal shipping conditions, handling, etc., involving shipment from the supply source to the receiving activity, plus reshipment from receiving activity, and shall conform to applicable carrier's rules and regulations. Intermediate and exterior package quantities and labeling and marking shall be as specified in the contract and/or order.

NOTE 1: The following National Stock Number is covered by this document:

| NSN | ITEM IDENTIFICATION |
|---|---|
| 6515-01-248-2600 | SPONGE, SCLERAL, Lincaff, 5.5mm x 7.5 mm x 80 mm Long, 5s: Sterile, Nontoxic, Nonantigenic and Non-pyrogenic |

NOTE 2: The following tests shall be in accordance with the United States Pharmacopeia Revision XXI:

| | | |
|---|---|---|
| #71 | - | Sterility |
| #151 | - | Toxicity |
| #231 | - | Pyrogenicity |
| #851 | - | Spectrophotometry |

Ordering data (Intermediate/exterior package quantities and labeling and marking must be specified in the contract and/or order).

MILITARY INTERESTS:

Custodians:

Army - MD
Navy - MS
Air Force - 03

Preparing Activity:

DoD-MB

Agent:

DLA-DM

CIVIL AGENCY COORDINATING ACTIVITIES:

VA-OSS
PHS
FDA-MPQAS

Project No. 6515-4213



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:24Z
Check the source to verify that this is the current version before use.

# STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

*(See Instructions – Reverse Side)*

| 1. DOCUMENT NUMBER | 2 DOCUMENT TITLE |
|---|---|
| A-A-53773 | SPONGE, SCLERAL, SILICONE (Lincaff) |

| 3a. NAME OF SUBMITTING ORGANIZATION | 4 TYPE OF ORGANIZATION *(Mark one)* |
|---|---|
| | ☐ VENDOR |
| | ☐ USER |
| b ADDRESS *(Street, City, State, ZIP Code)* | ☐ MANUFACTURER |
| | ☐ OTHER *(Specify)* _____ |

5 PROBLEM AREAS

a. Paragraph Number and Wording

b. Recommended Wording

c Reason/Rationale for Recommendation

6 REMARKS

| 7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional | b WORK TELEPHONE NUMBER *(Include Area Code)* – Optional |
|---|---|
| c MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional | 8 DATE OF SUBMISSION *(YYMMDD)* |

*(TO DETACH THIS FORM, CUT ALONG THIS LINE.)*

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:24Z
Check the source to verify that this is the current version before use.

INSTRUCTIONS: In an effort to make our standardization documents better, the DoD provides this form for use in submitting comments and suggestions for improvements. All users of military standardization documents are invited to provide suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge *(DO NOT STAPLE)*, and mailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, was too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

*NOTE* This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document*(s)* or to amend contractual requirements.

*(Fold along this line)*

*(Fold along this line)*

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO 4966 Alexandria, VA

POSTAGE WILL BE PAID BY

Commander
Defense Personnel Support Center
ATTN: DPSC-RST E
2800 South 20th Street
Philadelphia, Pennsylvania 19101-8419

NO POSTAGE NECESSARY IF MAILED IN THE UNITED STATES

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:24Z
Check the source to verify that this is the current version before use.