[INCH-POUND]
A-A-59122
29 June 1998
SUPERSEDING
MIL-C-13600A
14 May 1962

COMMERCIAL ITEM DESCRIPTION

CUPRIC OXIDE, TECHNICAL

The General Services Administration has authorized the use of this commercial item description as a replacement for MIL-C-13600A for all federal agencies.

1. SCOPE. This commercial item description (CID) covers technical grade cupric oxide for use in ordnance applications. Cupric oxide is typically used as a pyrotechnic component in marine location markers.

2. SALIENT CHARACTERISTICS

2.1 General. Cupric oxide shall be furnished in powdered form.

2.2 Chemical properties. When tested using the methods and procedures described in ASTM Standard D 280 and in the American Chemical Society (ACS) Specification for "Reagent Chemicals", the cupric oxide produced shall meet the chemical requirements of table I.

TABLE I. Chemical requirements.

Chemical Properties	% by Weight	Limit	Test Method
Assay (CuO)	95.0	Minimum	ACS (Cupric Oxide, Powdered)
Moisture	0.2	Maximum	ASTM D 280, Method A
Acid insoluble matter	0.5	Maximum	ACS (Cupric Oxide, Powdered)

2.3 Sieve analysis. When sieve analysis is performed in accordance with ASTM Standard B 214, at least 95% by weight of any selected cupric oxide test specimen shall pass through Sieve No. 200.

Beneficial comments, recommendations, additions, deletions, clarifications, etc., and any other data which may improve this document should be sent to: Defense Supply Center Richmond (DSCR), ATTN: DSCR-VBD, 8000 Jefferson Davis Highway, Richmond, VA 23297-5678.

AMSC N/A FSC 6810

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T10:02Z
Check the source to verify that this is the current version before use.

3. REGULATORY REQUIREMENTS

3.1 Material Safety data sheet. Manufacturers shall prepare and submit a material safety data sheet (MSDS) in accordance with FED-STD-313 and meeting the Code of Federal Regulations requirements of 29CFR 1910.1200.

4. QUALITY ASSURANCE PROVISIONS

4.1 Product conformance. The products provided shall meet the salient characteristics of this commercial item description, shall conform to the producer's own drawings, specifications, standards, and quality assurance practices, and shall be the same product offered for sale in the commercial market. The government reserves the right to require proof of such conformance.

5. PACKAGING

5.1 Preservation, packing, and marking. For acquisition purposes, cupric oxide shall be preserved, packed, and marked as specified in the contract or order.

6. NOTES

6.1 Source of documents.

6.1.1 Copies of American Chemical Society (ACS) Specifications for Reagent Chemicals may be obtained from the American Chemical Society, 1155 16th Street NW, Washington, DC 20036.

6.1.2 Copies of ASTM standards may be obtained from the American Society for Testing and Materials, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959.

6.1.3 For bidding purposes, copies of Federal Standard No. 313 may be obtained from the General Services Administration, Federal Supply Service Bureau, Specification Section, Suite 8100, 479 L'Enfant Plaza SW, Washington, DC 20407.

6.2 National stock number (NSN). This CID is associated with NSN 6810-01-376-5842. Other NSNs may also correspond with this CID.

Custodian:
Army - AR

Preparing activity:
DLA - GS

(Project 6810-1416)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T10:02Z
Check the source to verify that this is the current version before use.