MIL-C-17566D
4 October 1976
SUPERSEDING
MIL-C-17566C
6 April 1973

MILITARY SPECIFICATION

CLOTH, BILLIARD

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers the requirements for a wool billiard cloth in one type only.

2. APPLICABLE DOCUMENTS

* 2.1 Issue of documents. The following documents of the issue in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein.

SPECIFICATIONS

FEDERAL

PPP-P-1132 - Packaging and Packing of Woolen, Worsted and Wool Blend (Synthetic Fiber; Cotton) Fabrics

MILITARY

MIL-C-43665 - Cloth, Wool: Mothproofing Treatment of

STANDARDS

FEDERAL

FED-STD-191 - Textile Test Methods

MILITARY

MIL-STD-655 - Provisions for Evaluating Quality of Cloth, Wool, and Wool Blends

(Copies of specifications, standards, drawings and publications required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

FSC 8305

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T10:18Z
Check the source to verify that this is the current version before use.

LAWS AND REGULATIONS

RULES AND REGULATIONS UNDER THE WOOL PRODUCTS LABELING ACT OF 1939

(Application for copies should be addressed to the Superintendent of Documents, Government Printing Office, Washington, DC 20402.)

2.2 Other publications. The following document forms a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal shall apply.

U. S. DEPARTMENT OF AGRICULTURE

Methods of Test for Grades of Wool

(Application for copies should be addressed to the U. S. Department of Agriculture, Agricultural Marketing Service, Washington, DC 20402.)

3. REQUIREMENTS

3.1 Standard sample. When a standard sample is available, the finished cloth shall match the standard sample for shade and shall be equal to or better than the standard sample with respect to all characteristics for which the standard sample is referenced (see 6.3).

* 3.2 First article. When specified, the contractor shall furnish a sample of cloth for first article inspection and approval (see 4.2 and 6.2).

3.3 Material.

3.3.1 Wool stock. The wool stock shall be of fleece or pulled wool, or a combination of both, not lower in grade than 56's U.S. Standard (see 4.3.1.1). The use of noils, laps or any other wool manufacturing by-products is prohibited.

3.3.1.1 Wool content. The wool content of the finished cloth shall be not less than 95 percent based on the dry weight of the specimen when tested as specified in 4.4.

* 3.3.2 Yarn. The wool shall be carded and spun on the woolen system into single yarn for both the warp and filling.

NOTE: Selvage yarns - To prevent edges of the cloth from building up when rolled, the single yarn used in the selvage may be made of a finer count than those used in the body of the cloth. The selvage yarns shall contain the same fibers as those used in the body of the cloth.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T10:18Z
Check the source to verify that this is the current version before use.

3.4 Physical requirements. The finished cloth shall conform to the requirements listed in Table I when tested as specified in 4.4.

Table I. Physical requirements

Weight, ounce (Kg) per linear yard (min.)	Yarns per inch (cm) (min.)		Breaking strength pounds (Newtons) (min.)	
	Warp	Filling	Warp	Filling
(based on 60 inches) (1.52 m)				
17.2 (0.48)	50 (19.8)	40 (15.8)	50 (222.50)	45 (200.25)

3.4.1 Weave. The weave shall be 2 up, 1 down - right hand twill.

3.4.2 Width. The width of the finished cloth shall be a minimum of 60 inches (1.52 m) exclusive of selvages.

3.5 Length and put-up. Unless otherwise specified (see 6.2), the cloth shall be furnished in continuous lengths, each not less than 50 yards (45.7 m). Each length shall be put up on full width rolls face side inward as specified in PPP-P-1132.

3.6 Color. The color of the finished cloth shall be Green 3402 and shall be obtained by stock or piece dyeing.

3.6.1 Colorfastness. The dyed fabric shall show fastness to crocking equal to or better than the standard sample when tested as specified in 4.4. When no standard sample is established or referenced for colorfastness to crocking, the dyed fabric shall show a Munsell value for crocking not lower than 8.5. Test shall be performed as specified in 4.4.

* 3.6.2 Matching. The color of the finished cloth shall match the standard shade under artificial daylight having a color temperature of 7500° Kelvin and shall be a good approximation to the standard shade under incandescent lamplight at 2800° Kelvin.

3.7 Finish. The fabric shall have a finish and hand equal to or better than the standard sample. The fabric shall be thoroughly scoured, properly fulled, free from vegetable matter (carbonized if necessary) and face evenly sheared.

3.8 Wool content label. Cloth manufactured under this specification shall be labeled in accordance with the Wool Products Labeling Act of 1939.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T10:18Z
Check the source to verify that this is the current version before use.

3.9 Mothproofing. The cloth shall be given a mothproofing treatment in accordance with MIL-C-43665 (see 4.4).

3.10 pH. The pH of the water extract of the finished cloth shall be no less than 4.0 nor more than 8.0 when tested as specified in 4.4.

3.11 Marking. The back of the cloth shall be marked "Back" at both ends of each roll with letters not less than 1/2 inch (12.7 mm) in height. The marking shall be clearly legible in any indelible marking used commercially and shall not show through on the face of the cloth.

* 3.12 Workmanship. The finished cloth shall conform to the quality established by this specification. The demerit points per 100 square yards (83.61 m^2) when calculated as specified in Section 4, shall not exceed the established maximum point value. Each defect shall be marked with a 1 to 1-1/2 inch (2.54 to 3.81 cm) long string. The string shall be sewn into the selvage near the defect. A red string shall represent a three or four point defect and a white string shall represent a one or two point defect (see 4.4.2.5).

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Certificate of compliance. Where certificates of compliance are submitted, the Government reserves the right to check test such items to determine the validity of the certification.

4.2 First article inspection. When required, the first article of the finished cloth submitted in accordance with 3.2 shall be visually inspected for appearance, color and finish. The sample shall be tested for physical and chemical properties in accordance with the methods specified in 4.4.

4.3 Inspection. Inspection shall be performed in accordance with MIL-STD-655, except where otherwise indicated.

4.3.1 Component and material inspection. In accordance with 4.1 above, components and materials shall be inspected and tested in accordance with all requirements of referenced specifications, drawings, and standards unless otherwise excluded, amended, modified or qualified in this specification or applicable purchase document.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T10:18Z
Check the source to verify that this is the current version before use.

4.3.1.1 Wool. The wool shall be visually examined for grade in scoured form, prior to dyeing, picking or carding by comparison with the applicable U. S. Standard (see 2.2). The examination for grade shall be performed on a composite sample of 1 pound (0.45 Kg) of scoured wool for each 10,000 pounds (4500 Kg) or fraction thereof in the lot. The composite sample shall be selected from not less than 10 percent of the bags/bales in the lot. In the event of dispute resulting from above comparisons, the grade shall be determined by a width method (wedge). The lot shall be unacceptable if one or more composite sample fails to meet the requirements of 3.3.1. Each lot shall consist of one grade of wool only.

4.3.1.2 In-process inspection. Inspection shall be made at any point during any phase of the manufacturing process to assure that no laps, noils, or any other wool manufacturing by-products are used (see 3.3.1). The Government reserves the right to exclude from consideration for acceptance any material for which in-process inspection has indicated non-conformance.

* 4.3.2 Examination of the end item. Examination of the end item for yard-by-yard, length, back marking, compliance with the Wool Products Labeling Act, and for defect marking (stringing of defects) shall be as specified in MIL-STD-655. The fabric quality for the finished cloth shall be quality level 15.

* 4.3.2.1 Limits of slubs and knots. Only slubs and knots which exceed "F" for slubs and "E" for knots on the Sears Fabric Defect Scale (see 6.4) shall be scored.

* 4.3.2.2 Examination for shade and finish, individual rolls. Each roll in the lot shall be examined visually for shade match (see 3.6), and finish (see 3.7). A roll shall be unacceptable if it fails to meet the requirements for shade match or finish as applicable. The sample unit shall be a 4-inch by 20-inch (10.1 by 50.8 cm) swatch of the cloth. A sample unit shall be drawn from each roll in the lot.

4.3.3 Examination of preparation for delivery requirements. An examination shall be made in accordance with the provisions of PPP-P-1132 to determine that packaging, packing and marking comply with the Section 5 requirements of this specification.

4.4 Testing of the end item. The methods of testing specified in FED-STD-191 wherever applicable and as listed in Table II, shall be followed. The physical and chemical values specified in Section 3, except where otherwise indicated, apply to the results of the determinations made on a sample unit for test purposes as specified in the applicable test methods. All test reports shall contain the individual values utilized in expressing the final result. The sample unit shall be 2 yards (1.82 m), full width of the finished cloth. The lot size shall be expressed in units of one yard (0.914 m). The sample size shall be as follows and the lot shall be unacceptable if one or more sample units fail to meet any requirements specified.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T10:18Z
Check the source to verify that this is the current version before use.

Lot size (yards)	Sample size (units)
800 or less	2
801 up to and including 22,000	3
22,001 and over	5

Table II. Test methods

Characteristic	Requirement paragraph	Test method
Wool content	3.3.1.1	2101
Weight	Table I	5041
Yarns per inch	Table I	5050
Breaking strength	Table I	5100
Weave	3.4.1	Visual 1/
Colorfastness to:		
Crocking	3.6.1	5651
Mothproofing content	3.9	2/
pH	3.10	2811

1/ One determination shall be made and the results reported as "Pass" or "Fail."

2/ As specified in MIL-C-43665.

5. PACKAGING

5.1 Preservation-Packaging. Packaging shall be level A or C as specified (see 6.2).

5.1.1 Levels A and C. The cloth shall be packaged in accordance with the applicable requirements of PPP-P-1132.

5.2 Packing. Packing shall be level A, B or C as specified (see 6.2).

5.2.1 Levels A, B, and C. The cloth shall be packed in accordance with the applicable requirements of PPP-P-1132.

5.3 Marking. In addition to any special marking required in the contract or order, shipments shall be marked in accordance with the requirements of PPP-P-1132.

6. NOTES

6.1 Intended use. The cloth covered by this specification is intended for use as table covers.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T10:18Z
Check the source to verify that this is the current version before use.

6.2 Ordering data. Procurement documents should specify the following:

a. Title, number and date of this specification.
b. Requirements for first article approval (see 3.2 and 4.2).
c. Width of cloth required (if other than specified).
d. When length is other than specified (see 3.5).
e. Selection of applicable levels of packaging and packing (see 5.1 and 5.2).

6.3 Standard sample. For access to standard sample, address the procuring office issuing the invitation for bids (see 3.1).

* 6.4 Sears Fabric Defect Scales are available from Sears, Roebuck and Co., Department 733Q. "Sears Defect Replica Kit," Sears Tower, Chicago, IL 60684.

6.5 Changes from previous issue. The margins of this specification are marked with an asterisk to indicate where (additions, modifications, corrections, deletions) from the previous issue were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and suppliers are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous issue.

Custodians:
Navy - SA
Air Force - 99

Preparing activity:
Navy - SA

Project No. 8305-N331

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T10:18Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

OMB Approval
No. 22-R255

INSTRUCTIONS: The purpose of this form is to solicit beneficial comments which will help achieve procurement of suitable products at reasonable cost and minimum delay, or will otherwise enhance use of the document. DoD contractors, government activities, or manufacturers/ vendors who are prospective suppliers of the product are invited to submit comments to the government. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements. Attach any pertinent data which may be of use in improving this document. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity.

DOCUMENT IDENTIFIER AND TITLE

MIL-C-17566D; Cloth, Billiard

NAME OF ORGANIZATION AND ADDRESS

CONTRACT NUMBER

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE DOCUMENT CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?
   A. GIVE PARAGRAPH NUMBER AND WORDING.

   B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY DOCUMENT REQUIREMENT CONSIDERED TOO RIGID

3. IS THE DOCUMENT RESTRICTIVE?

   ☐ YES ☐ NO *(If "Yes", in what way?)*

4. REMARKS

SUBMITTED BY *(Printed or typed name and address - Optional)*

TELEPHONE NO.

DATE

DD FORM 1 JAN 72 1426 REPLACES EDITION OF 1 JAN 66 WHICH MAY BE USED

S/N 0102-014-1802

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T10:18Z
Check the source to verify that this is the current version before use.

FOLD

Officer in Charge
Navy Clothing and Textile Research Facility
21 Strathmore Road
Natick, MA 01760

POSTAGE AND FEES PAID



OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

Officer in Charge
Navy Clothing and Textile Research Facility
21 Strathmore Road
Natick, MA 01760

FOLD

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T10:18Z
Check the source to verify that this is the current version before use.