O-C-650B
December 8, 1975
SUPERSEDING
Fed. Spec. O-C-650A
October 5, 1972

FEDERAL SPECIFICATION

CORRECTION FLUID, WHITE OPAQUE; AND THINNER

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers requirements for a white opaque correction fluid, primarily for correcting and concealing typing errors, changes or block out, in copy preparation for offset and other photographic reproduction. A solvent for thinning of correction fluid where required, is also covered herein. (See 6.1).

1.2 Classification.

1.2.1 Types. The correction fluid shall be of the following types as specified (see 6.2).

Type I - Solvent base.
Type II - Water base.

1.2.2 Thinner shall be of but one grade (see 3.2).

1.2.3 Correction fluid (Type I) and thinner. Correction fluid (Type I) and thinner shall be furnished in kit form or in individual containers as hereinafter specified and as required in the invitation for bids, contract, or order (see 6.2).

1.2.3.1 Kits. Each kit shall contain one (1) ounce (29.57 ml) bottle of Type I correction fluid and one (1) ounce (29.57 ml) bottle of thinner together with instructions for use (see 3.5 and 5.1.1.1.1). A brush, of materials and construction in accordance with good commercial practice, with dimensions as specified in paragraph 3.3, shall be attached to the cap of each bottle of correction fluid, as specified in 5.1.1.1.1. A thinner applicator, such as an eye-dropper or equivalent, shall be furnished in accordance with the manufacturer's normal commercial practice.

1.2.3.2 Individual containers (sizes). One ounce (29.57 ml) or one pint (473.18 ml) containers of either fluid or thinner, together with instructions for use (see 3.5), shall be furnished individually or together (see 3.2, 5.1.1.1.2, and 5.1.1.2.2), as specified. Brushes with dimensions as specified in 3.3 and eye droppers or equivalent for use with thinner, unless otherwise specified, shall be furnished in accordance with normal commercial practice. (See 6.2).

1.2.4 Correction fluid (Type II). Correction fluid (Type II) shall be furnished in 1/2-ounce (14.79 ml) or one ounce (29.57 ml) bottles, or one pint (473.18 ml) containers, together with instructions for use (see 3.5) as specified. A brush, of materials and construction in accordance with good commercial practice, with dimensions as specified in paragraph 3.3, shall be attached to the cap of each bottle of correction fluid as specified in 5.1.1.1.1.

2. APPLICABLE DOCUMENTS

2.1 The following documents, of the issues in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein.

Federal Specifications:

L-R-350 - Ribbons, Typewriter and Composing Machine, Changeable Type-Plate Style Polyethylene.
UU-P-121 - Paper, Bond and Writing; White and Colored.
DDD-R-311 - Ribbons, Typewriter.
PPP-B-566 - Boxes, Folding, Paperboard.
PPP-B-636 - Boxes, Shipping, Fiberboard.

FSC 7510

Source: https://assist.dla.mil -- Downloaded: 202640-26T11:15Z
Check the source to verify that this is the currentversion before use.

PPP-B-665 - Boxes, Paperboard, Metal Edged and Components.
PPP-B-676 - Boxes, Set-Up.
PPP-C-96 - Cans, Metal, 28-Gage and Lighter.

Federal Standards:

Fed. Std. No. 123 - Marking for Shipment (Civil Agencies).
Fed. Std. No. 595 - Colors.
Fed. Test Method Std. No. 141 - Paint, Varnish, Lacquer, and Related Materials; Methods of Inspection, Sampling, and Testing.
Fed. Test Method Std. No. 791 - Lubricants, Liquid Fuels, and Related Products; Methods of Testing.

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U.S. Government Printing Office, Washington, DC 20402.

(Single copies of this specification and other Federal Specifications required by activities outside the Federal Government for bidding purposes are available without charge from Business Service Centers at the General Services Administration Regional Offices in Boston, New York, Washington, DC, Atlanta, Chicago, Kansas City, MO, Fort Worth, Denver, San Francisco, Los Angeles, and Seattle, WA.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

Military Standards:

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129 - Marking for Shipment and Storage.

(Copies of Military Specifications and Standards required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

Laws and Regulations:

16 CFR 1500 - Food and Drug Administration Regulations under the Federal Hazardous Substances Act.

(The Code of Federal Regulations (CFR) and the Federal Register (FR) are for sale on a subscription basis by the Superintendent of Documents, U.S. Government Printing Office, Washington, DC 20402. When indicated, reprints of certain regulations may be obtained from the Federal agency responsible for issuance thereof.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless a specific issue is identified, the issue in effect on date of invitation for bids or request for proposal shall apply.

American Society for Testing and Materials (ASTM) Standard:

D 476 - Titanium Dioxide Pigments.

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.)

National Motor Freight Traffic Association, Inc., Agent:

National Motor Freight Classification.

(Application for copies should be addressed to the American Trucking Associations, Inc., Tariff Order Section, 1616 P Street, N.W., Washington, DC 20036.)

Source: https://assist.dla.mil -- Downloaded: 202610-26T11:15Z
Check the source to verify that this is the current version before use.

Uniform Classification Committee, Agent:

Uniform Freight Classification.

(Application for copies should be addressed to the Uniform Classification Committee, Room 1106, 222 South Riverside Plaza., Chicago, IL 60606.)

3. REQUIREMENTS

3.1 Correction fluid.

3.1.1 Composition (Type I).

3.1.1.1 Pigment. The pigment in the correction fluid shall be rutile titanium dioxide conforming to ASTM D 476, Titanium Dioxide Pigments.

3.1.1.2 Nonvolatile vehicle. The nonvolatile vehicle may consist of cellulose nitrate, cellulose acetate, acrylate copolymers, plasticizers and resins, or other suitable plastic film-forming material.

3.1.1.3 Volatile. The volatile portion may consist of a suitable blend of esters, ketones, alcohols, glycols, ethers, and hydrocarbons, or other suitable solvents. The correction fluid shall not produce obnoxious vapors in such concentrations as to become an annoyance or a health hazard to personnel. The volatile portion shall not contain benzene or carbon tetrachloride solvents. (See 3.1.4.4.)

3.1.2 Composition (Type II).

3.1.2.1 Pigment. The pigment in the correction fluid shall be rutile titanium dioxide conforming to ASTM D 476, Titanium Dioxide Pigments, Type III.

3.1.2.2 Nonvolatile vehicle. The nonvolatile vehicle may consist of acrylic resins, polyvinyl esters, acrylic emulsions, polyvinyl acetate emulsion or other suitable plastic film-forming material.

3.1.2.3 Volatile. The volatile portion shall consist for the most part of water and may contain alcohols, glycols, and other types of suitable solvents.

3.1.3 Quantitative requirements. The correction fluid shall conform to the quantitative requirements specified in table I (see table III and 4.3, as applicable).

TABLE I. Quantitative requirements

Characteristics	Requirements			
	Type I		Type II	
	Min.	Max.	Min.	Max.
Pigment % by wt. of correction fluid.	40	60	40	60
Drying time (airdrying) secs. (1/)	--	30	--	40
Viscosity No. 4 Ford cup secs.	15	75	15	75
Fineness of grind, Hegman gauge.	5	--	5	--
Nonvolatile vehicle content, % by wt. of vehicle.	5	20	5	20

1/ On specified paper preconditioned for 24 hours at temperature of 23 ± 1°C (73 ± 2°F) and humidity of 50 ± 2%. The applied coating shall have a dry film thickness of 1.5 mils (0.004 cm).

3.1.3.1 Dry opacity. The correction fluid shall show a minimum dry-film contrast ratio of 0.99 when applied at a wet-film thickness of 3.0 mils (0.008 cm).

3.1.4 Qualitative requirements.

3.1.4.1 Color and appearance. The color of the correction fluid shall be a practical match of bond paper, white, conforming to Type III of UU-P-121. The correction fluid shall be homogeneous and free from undissolved and foreign matter when tested as specified in 4.3.1.

3.1.4.2 Flash point (Type I only). Flash point shall be not less than 40°F(4.4°C), when tested as specified in table III.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:15Z
Check the source to verify that this is the current version before use.

3.1.4.3 Odor. The odor of the correction fluid in the container, in application of the film, or as an applied film shall not be obnoxious (see 4.3.1).

3.1.4.4 Toxicity. The correction fluid shall not contain any substance which is toxic under normal conditions of usage.

3.1.4.5 Condition in container. The correction fluid, as received in a freshly opened full container, shall be capable of being redispersed, if there is any evidence of settling, to a smooth, free-flowing, homogeneous state when shaken by hand. The correction fluid shall show no curdling, livering, or caking, and shall be free from lumps and skins when tested as specified in 4.3.1.

3.1.4.6 Storage stability (filled container). After storage for 1 year, the correction fluid shall show no skimming, livering, curdling, hard settling, or caking, and shall readily re-mix to a satisfactory, usable condition as indicated in 3.1.4.5, when tested as specified in 4.3.1.

3.1.4.7 Brushing properties and appearance of dry film (coating). The correction fluid shall be of a good brushing consistency in the packaged condition. When tested as specified in 4.3.1, the fluid shall dry to a smooth, uniform film free from streaking, blushing, peeling, blistering, and any other defects which affect the appearance or which might affect the satisfactory performance of the product. Evidence of "Mudcracking" should not be visible to the naked eye in dry film thicknesses up to 0.003 inch (0.008 cm).

3.1.4.8 Flexibility. When tested as described in 4.3.1 and 4.3.2, the film (coating) of correction fluid shall not crack, flake, or show any blemishes.

3.1.4.9 Additional performance requirements. The correction fluid shall satisfactorily meet the specified test requirements, as applicable, and shall provide an adherent, opaque coated surface suitable for retyping and for reproduction when tested as specified in 4.3.1. When the correction fluid is applied over original copy as specified in the test procedure of 4.3.1, it shall not run and disturb the surrounding letters or character of the typed copy. Neither shall it cause the paper to wrinkle in adjacent areas. If alcohol or other component is used to reduce the drying time, no bleeding or raising of the ink shall occur.

3.2 Thinner. Solvent supplied for thinning of type I correction fluid shall be the product of the manufacturer of the correction fluid. The thinner shall be compatible with the correction fluid and shall be of a quality as established in the specification for the correction fluid. Unless otherwise specified (see 6.2 and 6.2.1), thinner shall be furnished separately or in equal quantities with packages or units of packages of correction fluid (See 5.1.1.1.2 and 5.1.1.2.2).

3.2.1 Quantitive requirements.

3.2.1.1 Flash point. The flash point of the thinner shall be not less than 40°F(4.4°C) (see 4.3.4).

3.3 Brush dimensions. The brush, attached to the cap, shall be 3/8 ± 1/16 inch (0.95 ± 0.16 cm) long and 1/16 ± 1/64 inch (0.159 ± 0.040 cm) wide at its widest point.

3.4 Workmanship. Workmanship shall be in accordance with normal commercial practice. Labels, when used, shall be legibly printed, neatly and securely affixed to containers, and containers shall show no evidence of spillage or leakage of contents.

3.5 Instructions for use. Instructions for use of correction fluid and thinner shall be furnished with each kit as specified in 1.2.3.1; and with containers as specified in 1.2.3.2 and 1.2.4 in a manner in accordance with manufacturer's normal commercial practice. Instructions, so furnished, may be in sheet form or appear on labels of individual containers in accordance with the manufacturer's normal commercial practice. Instructions shall be comprehensive and complete and legibly printed, and unless otherwise specified in the invitation for bids (see 6.2), shall identify the surfaces on which the product can be used.

Source: https://assist.dla.mil -- Downloaded: 202640-26T11:15Z
Check the source to verify that this is the current version before use.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the supplier may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements. (See 6.2.)

4.2 Sampling and inspection.

4.2.1 Sampling for examination. Sampling for examination of the end item shall be in accordance with methods 1011, 1021, or 1031 of Fed. Test Method Std. No. 141, as applicable, except where otherwise indicated hereinafter. (See 4.2.2.)

4.2.2 Sampling for tests. Sampling for tests shall be in accordance with the applicable provisions of test methods specified in table III, or as specified hereinafter. The sample unit for examination and tests described in 4.3.1 and 4.3.2 for kits, shall be one complete kit, except for container of the component items (see 4.2.3.2), for each 50 or less kits contained in the inspection lot, batch, or delivery. For individual filled containers (not furnished in kits), the sample unit shall be one 1-pint unit of correction fluid or thinner, as applicable.

4.2.3 Examinations.

4.2.3.1 End item. Examination of each item shall be in accordance with the applicable requirements of methods specified in 4.2.1 and as specified hereinafter, as applicable. Examinations for appearance and other visual defects, as applicable, shall be conducted in accordance with MIL-STD-105. Unless otherwise specified, the inspection level and acceptable quality level (AQL) for examination (4.3.1, 4.3.2 and 4.3.3) shall be S-4 and 4.0, percent defective respectively.

4.2.3.2 Preparation for delivery. Examination shall be made to determine compliance with the packaging, packing, and marking requirements of Section 5 and the contract or order. Defects shall be scored in accordance with table II. For examination of contents, the sample unit shall be one shipping container prepared for delivery and selected just prior to the closing operations. Defects of closure specified shall be examined on shipping containers fully prepared for delivery. The lot size shall be the number of shipping containers in the end-item inspection lot. Inspection shall be in accordance with MIL-STD-105; inspection level S-4, with an AQL of 4.0 percent defective.

TABLE II. Examination of preparation for delivery

Examine	Defects
Markings	Incorrect; omitted, illegible, improper size, location, sequence, or method of application.
Materials	Wrong type, class, or other category of required specification; materials missing, damaged, or defective affecting serviceability.
Workmanship	Wrong or careless means in placement and use of labeling, packaging, and packing materials such as loose or partially attached labels; flaps of containers incompletely closed; loose or overtight straps, dangerous strap ends, protruding nails, and smeared adhesive; spillage and leakage of contents.
Contents	Quantities not as specified. Wrong arrangement; cans on side or upside down.
Closure of shipping containers	Not as specified.
Gross weight of shipping containers	In excess of specified weight. In excess of box limitation shown on boxmaker's certificate.

Source: https://assist.dla.mil -- Downloaded: 202610-26T11:15Z
Check the source to verify that this is the current version before use.

4.3 Test procedures. Correction fluid shall be tested in accordance with the applicable test methods of Fed. Test Method Std. No. 141 indicated in table III and as specified hereinafter. Thinner shall be tested as specified in 4.3.4. Failure of any sample to pass any of the tests required shall be cause for rejection of the lot, or batch, as applicable, represented by the sample.

TABLE III. Test methods (correction fluid)

Characteristics	Fed. Test Method Std. No. 141 (Method No.)	Requirements reference paragraph	Test procedure paragraph
Drying time	----	3.1.3	4.3.1
Viscosity (pigmented materials)	4282	3.1.3	-----
Fineness of grind	4411	3.1.3	-----
Dry opacity	1/ 4121	3.1.3.1	-----
Flash point (Pensky-Martens closed cup tester)	4293	3.1.4.2	-----
Odor	----	3.1.4.3	4.3.1
Condition in container	----	3.1.4.5	4.3.1
Storage stability	----	3.1.4.6	4.3.1
Brushing properties and appearance of dry-film (coating)	----	3.1.4.7	4.3.1
Flexibility	----	3.1.4.8	4.3.2
Film-forming content of vehicle	4021	3.1.3	-----
Pigment content, percent	4021	3.1.3	-----
Pigment analysis	----	3.1.1.1 and 3.1.2.1	4.3.3

1/ Apply the film with a Bird film applicator or other doctor blade suitable for applying a 3.0 mil (0.008 cm) coating of correction fluid.

4.3.1 Performance and brushing, drying and hiding properties, and appearance of dry film (coating).

4.3.1.1 Copy preparation. Typed copy shall be made on bond paper, white, basis weight 40 pounds (18.14 kg), conforming to UU-P-121, Type III (JCPG40) to conduct the tests specified herein. The copy shall be made on an electric typewriter with freshly cleaned pica type. The typewriter impression indicator and the copy control device shall be set so that type impressions will be clear and distinct without any cutout of the letters or characters. Other machines may be used, provided they can be adapted to provide the test conditions specified. A fabric typewriter ribbon shall be used to conduct the tests specified hereinafter, and then the tests shall be repeated under the same specified conditions using a polyethylene type ribbon. The ribbons shall conform to specifications DDD-R-311 and L-R-350, respectively.

4.3.1.2 Procedure. Insert paper in typewriter and then type three lines, approximately 4 inches (10.16 cm) in length, of capital B's, K's, and R's. Push carriage, bearing the ribbon with it, back to starting point, shift the paper a single-spaced line, and again type the same letters for the same distance. Prepare a third line as specified. Following the above, shift paper as required, single spacing, and type two additional lines of lower case letters and characters such as the comma, figures 6 and 8, parens, and other characters. With the paper still in the typewriter, roll copy up in a manner that corrections can be made on the second and fourth lines as hereinafter described, with the copy in the machine and resting on the platen or removed from the machine and resting on a flat surface, as desired. Shake a previously unopened sample container of correction fluid, remove cap and brush, stroking any excess fluid from the brush on the inside of container top. Paint a coat of correction fluid 1.5 mils (0.004 cm) thick to hide the original copy and still provide a suitable surface for retyping.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:15Z
Check the source to verify that this is the current version before use.

and reproduction, over the third character on second line of copy prepared as described above. Repeat in the same manner over the sixth, seventh, eighth, and ninth capital letters of the same line, and then over the last eight letters of the line. Repeat all of the foregoing procedure on the fourth line. Care shall be taken to apply the fluid to only the areas specified to be coated without disturbing adjacent letters or characters of prepared copy. Allow up to 30 seconds for Type I and 40 seconds for Type II correction fluid to dry and then retype over the painted areas under conditions as specified above, using different capital letters on the second line and different lower case letters and other characters on the fourth line. (Application of the correction fluid may be made in accordance with the manufacturer's instructions, if different.) During the above procedures and after removal of prepared copy from the typewriter, examine for conformance with the requirements of 3.1.3, 3.1.4.1 (as applicable), 3.1.4.3, 3.1.4.5, 3.1.4.7, and 3.1.4.9.

4.3.2 Flexibility. When test and examination have been completed as specified in 4.3.1, fold the entire sheet lengthwise in a manner that the fold falls through a corrected portion of more than one letter or character of copy, pressing sufficiently to cause a slight but perceptible crease or bend through the copy; repeat, folding the paper crosswise. Examine copy where folds or creases meet to determine compliance with the requirements of 3.1.4.7 and 3.1.4.8, as applicable.

4.3.3 Pigment analysis. Analysis of pigment content shall be made by X-Ray diffraction spectrometry, or other suitable instrumentation.

4.3.4 Flash point (thinner). The flash point of the thinner shall be determined in accordance with method 4291 of Fed. Test Method Std. 141.

5. PREPARATION FOR DELIVERY

5.1 Packaging. Packaging shall be level A or C as specified (see 6.2).

5.1.1 Level A.

5.1.1.1 Unit packages.

5.1.1.1.1 Kits. Type I correction fluid and thinner shall be furnished in 1 ounce (29.57 ml) quantities in glass or plastic bottles as specified (see 6.2). The bottles shall be closed with a metal, plastic or composition screw-cap with liner. The specified materials shall be of good commercial quality for the purpose intended. An applicator brush (see 3.3) shall be furnished with each bottle of correction fluid, fastened to the cap in a secure manner. One bottle of correction fluid, one bottle of thinner, applicator and instructions for use (see 1.2.3.1 and 3.5) shall be packaged together in a close-fitting box conforming to PPP-B-566, variety 1, style II, or PPP-B-676, type I, variety 1, with thumb notches. Closure of boxes shall be in accordance with the appendix to the applicable box specification.

5.1.1.1.2 Individual containers.

5.1.1.1.2.1 Bottles. Type I correction fluid or thinner and Type II correction fluid shall be furnished in glass or plastic bottles in 1/2 ounce (14.79 ml) and 1 ounce (29.57 ml) quantities as specified (see 6.2). The bottles shall be closed with a metal, plastic or composition screw-cap with liner. The specified materials shall be of good commercial quality for the purpose intended. An applicator brush (see 3.3) shall be furnished with each bottle of correction fluid, fastened to the cap in a secure manner. The bottles shall be further packaged individually with instructions for use (see 1.2.3.1 and 3.6) in close fitting boxes conforming to PPP-B-566, variety 1, style II, or PPP-B-676, type I, with thumb notches. Closure of boxes shall be in accordance with the appendix to the applicable box specification.

5.1.1.1.2.2 Cans. One pint (473.18 ml) of the correction fluid or thinner shall be packaged in a metal can conforming to PPP-C-96, type V, class 4 or 6. (See 1.2.3.2, 3.2 and 3.5.)

5.1.1.2 Intermediate packages.

5.1.1.2.1 Kits. Twelve kits, unit packaged as specified in 5.1.1.1.1, shall be intermediate packaged in a box conforming to PPP-B-566, style II, type A; PPP-B-665, style optional; or PPP-B-676, type optional. The boxes shall be closed in accordance with the appendix to the applicable box specification.

Source: https://assist.dla.mil -- Downloaded: 202640-26T11:15Z
Check the source to verify that this is the current version before use.

5.1.1.2.2 Individual containers.

5.1.1.2.2.1 Bottles. Unless otherwise specified (see 6.2), twenty four bottles of correction fluid or thinner, packaged as specified in 5.1.1.1.2.1, shall be intermediate packaged in a close-fitting box conforming to PPP-B-566, PPP-B-665, PPP-B-636, class domestic or PPP-B-676. Close boxes in accordance with the applicable box specification.

5.1.1.2.2.2 Cans. Unless otherwise specified (see 6.2), 12 cans of correction fluid or thinner, packaged as specified in 5.1.1.1.2.2, shall be intermediate packaged in a close-fitting box conforming to PPP-B-636, type CF, class-domestic. Each box shall be closed in accordance with method I of the appendix to the box specification.

5.1.1.2.3 Multiple pack (cans). Unless otherwise specified (see 6.2), six cans of type I correction fluid and six cans of thinner, (total, 12 cans), shall be intermediate packaged together in a box as specified in 5.1.1.2.2. Each box shall be closed in accordance with method I of the appendix to the box specification.

5.1.2 Level C.

5.1.2.1 Unit packages.

5.1.2.1.1 Kits. Kits, as specified in 1.2.3.1 and 5.1.1.1.1, shall be unit packaged in accordance with the supplier's normal commercial practice, providing that this insures protection for the fluid during shipment and provides for safe delivery to its destination.

5.1.2.1.2 Individual containers.

5.1.2.1.2.1 Bottles. Bottles, packaged as specified in 5.1.1.1.2.1 shall be unit packaged in accordance with the supplier's normal commercial practice, providing that this insures protection for the fluid during shipment and provides for safe delivery to its destination.

5.1.2.1.2.2 Cans. One pint (473.18 ml) of correction fluid or one pint (473.18) of thinner shall be packaged in a metal can in accordance with the supplier's commercial practice, providing that this insures protection for the fluid during shipment and provides for safe delivery to its destination (see 1.2.3.2, 3.2, and 3.5).

5.1.2.2 Intermediate packages.

5.1.2.2.1 Kits. Twelve kits, unit packaged as specified in 5.1.2.1.1, shall be intermediate packaged in a box in accordance with the supplier's normal commercial practice, providing that this insures protection for the fluid during shipment and provides for safe delivery to its destination.

5.1.2.2.2 Individual containers.

5.1.2.2.2.1 Bottles. Unless otherwise specified (see 6.2), 24 bottles of correction fluid or thinner, packaged as specified in 5.1.2.1.2.1, shall be intermediate packaged in a box in accordance with the supplier's normal commercial practice, providing that this insures protection for the fluid during shipment and provides for safe delivery to its destination.

5.1.2.2.2.2 Cans. Unless otherwise specified, twelve cans of correction fluid or thinner shall be intermediate packaged together in a box in accordance with the supplier's normal commercial practice, providing that this insures protection for the fluid during shipment and provides for safe delivery to its destination.

5.1.2.2.2.3 Multiple pack (cans). Unless otherwise specified, six cans of Type I correction fluid and six cans of thinner (total, 12 cans) shall be intermediate packaged together in a box in accordance with the supplier's normal commercial practice, providing that this insures protection for the fluid during shipment and provides for safe delivery to its destination.

5.2 Packing. Packing shall be level A, B, or C, as specified (see 6.2).

5.2.1 Level A.

5.2.1.1 Kits. Intermediate packages, as specified in 5.1.1.2.1, shall be packed in a box conforming to PPP-B-636, V3c. Each box shall be closed, and waterproof sealed in accordance with the appendix to the box specification.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:15Z
Check the source to verify that this is the current version before use.

5.2.1.2 Individual containers.

5.2.1.2.1 Bottles. 1/2-Ounce (14.79 ml) and 1-ounce (29.57 ml) bottles of Type I correction fluid or thinner and Type II correction fluid, packaged as specified in 5.1.1.2.2.1, shall be packed in a close-fitting box conforming to PPP-B-636, V3c. Each box shall be closed and waterproof sealed in accordance with the appendix to the box specification.

5.2.1.2.2 Cans. Pint (473.18 ml) cans of Type I correction fluid and thinner or Type II correction fluid, intermediate packaged as specified in 5.1.1.2.2.2 or 5.1.1.2.3, shall be packed in a box conforming to PPP-B-636, V3c. Each box shall be closed and waterproof sealed in accordance with the appendix to the box specification.

5.2.2 Level B.

5.2.2.1 Kits. Twelve intermediate packages, as specified in 5.1.1.2.1, shall be packed in a box conforming to PPP-B-636, class-domestic. Closure of boxes shall be in accordance with the appendix to the box specification.

5.2.2.2 Individual containers.

5.2.2.2.1 Bottles. Four intermediate packages of 1/2-ounce (14.79 ml) or 1-ounce (29.57 ml) bottles of correction fluid or thinner, packaged as specified in 5.1.1.2.2.1, shall be packed in a close-fitting box conforming to PPP-B-636, class-domestic. Closure of boxes shall be in accordance with the appendix to the box specification.

5.2.2.2.2 Cans. Four intermediate packages of correction fluid or thinner (see 5.1.2.2.2.2), or four intermediate packages of Type I correction fluid and thinner (see 5.1.1.2.3), shall be packed in a box conforming to PPP-B-636, class-domestic. Closure of boxes shall be in accordance with the appendix to the box specification.

5.2.3 Level C. Correction fluid and thinner, packaged as specified in 5.1.2 through 5.1.2.2.2.3, shall be packed to insure carrier acceptance and safe delivery at destination in shipping containers complying with the rules of the National Motor Freight Classification and the Uniform Freight Classification.

5.3 Marking. In addition to the special marking required by 5.3.3, all marking shall comply with 5.3.1 or 5.3.2 as specified (see 6.2).

5.3.1 Civil agencies. In addition to any special marking required by the contract or order, interior packages and exterior shipping containers shall be marked in accordance with Fed. Std. No. 123.

5.3.2 Military agencies. In addition to any special marking required by the contract or order, interior packages and exterior shipping containers shall be marked in accordance with MIL-STD-129.

5.3.3 Hazardous substance marking. Containers, individual and shipping, shall bear appropriate cautionary markings in compliance with the applicable standards specified herein and the rules and regulations applicable to the mode of transportation, including that in accordance with the Food and Drug Administration Regulations under the Federal Hazardous Substances Labeling Act, as applicable.

6. NOTES

6.1 Intended use.

6.1.1 Correction fluid. This commodity is intended primarily for use as specified in 1.1; however, it can also be used by engineers, architects, draftsmen, and commercial artists. It is used for making alterations in drawings, as a touch-up solution for art work, and as an opaquing medium for work preparation for reproduction, overlays, and charts. It can also be used for blocking out copy on spirit duplicator masters.

6.1.2 Thinner. (See 1.1.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:15Z
Check the source to verify that this is the current version before use.

6.2 Ordering data. Purchasers should select the preferred options permitted herein, (see 1.2.1, 1.2.3.2, 3.2, 3.5, 5.1.1.1.1, 5.1.1.1.2, and 5.1.1.2.2.1), and include the following information in procurement documents:

(a) Title, number, and date of this specification.
(b) Type I or Type II.
(c) Whether correction fluid and thinner is to be furnished in kits or in individual containers (see 1.2.3); if individual containers, whether commodity is to be furnished as specified in 5.1.1.2.2.1, 5.1.1.2.2.2, or 5.1.1.2.3.
(d) Arrangement for inspection and inspection facilities, if different than as indicated in 4.1.
(e) Levels of packaging and packing and any special marking for shipment required (see 5.1, 5.2, and 5.3).

6.2.1 Thinner (when ordered separately). In requirements for thinner to be furnished in 1-pint (473.18 ml) cans, without correction fluid, purchasing officers should identify the correction fluid with which the thinner is to be used (see 3.2).

6.3 This specification covers only the end items required by the Federal Government. It is not intended to include all of the types, etc., which are commercially available.

COORDINATION WAIVED BY DOD

Preparing activity

GSA-FSS

User Interest:

Army - GL

Orders for this publication are to be placed with General Services Administration, acting as an agent for the Superintendent of Documents. See Section 2 of this specification to obtain extra copies and other documents referenced herein. Price 35 cents each.

Source: https://assist.dla.mil -- Downloaded: 202640-26T11:15Z
Check the source to verify that this is the currentversion before use.