MILITARY SPECIFICATION

SHELTER AND ENTRANCE ASSEMBLY - CHEMICAL-BIOLOGICAL SHELTER SYSTEM: INFLATABLE

This amendment forms a part of MIL-S-51422B(EA), dated 24 September 1987, and is approved for use within the Chemical Research, Development and Engineering Center, Department of the Army and is available for use by all Departments and Agencies of the Department of Defense.

PAGE 1

2.1.1: Under FEDERAL SPECIFICATIONS add the following:

"L-P-1040 - Plastic Sheets and Strips (Polyvinylfluoride)."

PAGE 4

3.1.3:

Lines 1 to 6 (inclusive): Delete these lines in their entirety and substitute the following:

"3.1.3 Window material. The material used in the windows shall be a homogeneous polyvinylfluoride laminate sheet 0.008 ± 0.001 inches thick formed by heat and pressure from a minimum of two sheets of material conforming to the requirements of type I, transparent, grade C, class I of L-P-1040 except for the following:

(1) The haze requirement for the single sheet is eliminated.

(2) The material is not limited to the 0.001 inch thickness.

In addition, the polyvinylfluoride laminate shall conform to the following requirements:"

AMSC N/A FSC 4240

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T21:00Z
Check the source to verify that this is the current version before use.

Item (b): Delete in its entirety and substitute the following:

"(b) The window material shall maintain flexibility and there shall be no indication of cracking or delamination at either -25°F or -60°F when tested as specified in 4.4.10.2."

PAGE 5

3.1.8, line 2: Delete "(see 6.5)".

PAGE 8

3.3.5.4: Change from "Scratch or abrastions" to "Scratch or abrasions".

PAGE 10

4.2: Delete in its entirety and substitute the following:

"4.2 Preproduction inspection. A preproduction sample of four shelter and entrance assemblies submitted in accordance with 3.4 shall be examined and tested for all requirements of the applicable drawings and this specification (see 6.2)."

PAGE 22

4.4.10.2:

Line 4: Insert the following sentence after the words "...shall not be determined.":

"A second 4 inches by 4 inches specimen shall be exposed for 60 ± 10 minutes at a temperature of -25°F ± 1.8°F and tested as specified in Method 5874 of Fed. Test Method Std. 191 except that the hydrostatic resistance shall not be determined."

Lines 4 and 5:

Delete "Samples" and substitute "Both samples".

Delete "(if laminated)".

4.4.10.3, line 3: Delete "test" and substitute "tests".

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T21:00Z
Check the source to verify that this is the current version before use.

6.2(d): Delete in its entirety and substitute the following:

"(d) When and for what purpose any of the following will be provided as Government furnished equipment (GFE):

Inflatable shelter	-	NSN 4240-00-152-1304
Inflatable entrance	-	NSN 4240-00-152-1306
Filter and utilities unit M68	-	NSN 4240-00-152-1305
Shelter system M51	-	NSN 4240-00-854-4144".

Custodian:

Army - EA

Preparing activity:

Army - EA

Project No. 4240-A981

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T21:00Z
Check the source to verify that this is the current version before use.