INCH POUND

MIL-R-46846R
AMENDMENT 1
18 November 1994

MILITARY SPECIFICATION

RUBBER, SYNTHETIC, HEAT - SHRINKABLE

This amendment forms a part of MIL-R-46846B, dated 30 April 1992, and is approved for use by all Departments and Agencies of the Department of Defense.

PAGE 2

1.2.3: Delete and substitute:

"1.2.3 Type III. Cross-linked, fluoroelastomer, modified polymer of hexafluoropropylene and vinylidene fluoride dipolymer, molded parts and extended periods of high temperature and solvent attack.

a. Class 1 - Tubing, expansion ratio 2, service temperature range -55 to 200°C.

b. Class II - Molded parts and extruded shapes, expansion ratio 3.5, service temperature range of -55 to 200°C."

1.2.5: Delete.

PAGE 3

1.2.6: Renumber to read "1.2.5".

PAGES 5 AND 6

3.2: Delete and substitute:

"3.2 Materials. Type I synthetic rubber specified herein shall be fabricated from a cross-linked, stabilized, modified polychloroprene (Neoprene) composition. Type II synthetic rubber shall be fabricated from a cross-linked, stabilized, flame-retardant, modified silicone rubber composition. Type III synthetic rubber shall be fabricated from a cross-linked, stabilized, flame-resistant, fluorelastomer, modified polymer of hexafluoropropylene and vinylidene fluoride diploymer. Type IV

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T07:04Z
Check the source to verify that this is the current version before use.

synthetic rubber shall be fabricated from a cross-linked stabilized, propellant-resistant, modified butyl rubber composition. Type VI synthetic rubber shall be fabricated from a cross-linked, stabilized, flame-resistant, modified ethylene-proplylene rubber composition. These expanded synthetic rubbers shall shrink to predetermined dimensions upon the application of heat as follows:

a. Types I, IV, and VI - Heat in excess of 135°C

b. Types II, III - Heat in excess of 175°"

PAGE 7

Table I: Delete Type V from Table.

PAGE 8

Table II: Delete Type V from Table.

PAGE 9

Para 3.5, line 3: Delete "type V,"

PAGE 14

Para 4.7.2, line 9: Delete "V and" and change word "Types" to read "Type."

PAGE 15

Para 4.7.3, line 5: Delete "and 100±3°C for Type V,"

PAGE 20

Add the following new paragraph:

"6.4 Type V synthetic rubber has been deleted from this specification because it duplicates the synthetic rubber specified by MIL-I-23053/5."

Para 6.4.1, line 10: Delete: "V, Class I -55 to 135±°C"

Source: https://assist.dla.mil -- Downloaded: 202610-22T07:04Z
Check the source to verify that this is the current version before use.

PAGES 20 AND 21

Renumber the current paragraphs 6.4 through 6.8 to read "6.5 through 6.9."

Custodian:
Army - MI

Review Interest:
Army - EA, ME- MR,
OLA - GS

Preparing Activity
Army - MI

(Project No. 5970-1128)

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T07:04Z
Check the source to verify that this is the current version before use.