FED. SUP CLASS
3110

USER ACTIVITIES:
ME, PA, WV, SA,
84, 17, MC

REVIEWI TIES:
AV, M.

...ndard is approved for use by all Departments and Agencies of the Department of Defense.
...new engineering and design applications and for repetitive use shall be made from this
...document





TABLE I.
BASIC DIAMETER
NON-FERROUS BRASS BALLS

| NOMINAL BALL DIAMETER | BASIC DIAMETER A | GRADE 200 DASH NO. |
|---|---|---|
| 1/16 | .062500 | -20001 |
| 3/32 | .093750 | -20002 |
| 1/8 | .125000 | -20003 |
| 5/32 | .156250 | -20004 |
| 3/16 | .187500 | -20005 |
| 7/32 | .218750 | -20006 |
| 1/4 | .250000 | -20007 |
| 9/32 | .281250 | -20008 |
| 5/16 | .312500 | -20009 |
| 11/32 | .343750 | -20010 |
| 3/8 | .375000 | -20011 |
| 13/32 | .406250 | -20012 |
| 7/16 | .437500 | -20013 |
| 15/32 | .468750 | -20014 |
| 1/2 | .500000 | -20015 |
| 9/16 | .562500 | -20016 |
| 5/8 | .625000 | -20017 |
| 11/16 | .687500 | -20018 |
| 3/4 | .750000 | -20019 |

For NOTES see SHEET 2.

TABLE II.
TOLERANCE BY GRADE FOR INDIVIDUAL BALLS
NON-FERROUS BRASS BALLS
(Tolerance in millionths of an inch)

| GRADE | ALLOWABLE BALL DIAMETER VARIATION VD | ALLOWABLE DEVIATION FROM SPHERICAL FORM W |
|---|---|---|
| 200 | 200 | 200 |

TABLE III.
TOLERANCE BY GRADE FOR LOTS OF BALLS
NON-FERROUS BRASS BALLS
(Tolerance in millionths of an inch)

| GRADE | ALLOWABLE LOT DIAMETER VARIATION | BASIC DIAMETER TOLERANCE |
|---|---|---|
| 200 | 400 | ±1000 |

APPROVED 3 November 1959 REVISED (A) 17 November 1965 (B) 3 August 1976

(B) ENTIRE STANDARD REVISED

| P. A. OS | INTERNATIONAL INTEREST | TITLE | MILITARY STANDARD |
|---|---|---|---|
| Other Cust AT 11 | | BALLS, BEARING, NON-FERROUS BRASS | MS 19062 |
| PROCUREMENT SPECIFICATION MIL-B-1083 | SUPERSEDES: | | SHEET 1 OF 2 |



Source: https://assist.dla.mil -- Downloaded: 2026-10-23T14:20Z
Check the source to verify that this is the current version before use.

NOTES:

1. MATERIAL: Non-ferrous brass conforming to chemical composition of SAE CA 260. Balls shall be manufactured from selected brass free from alloy segregation, and shall be free from cracks when examined visually without magnification.

2. HARDNESS: Surface hardness of Rockwell Rb 75-87 or equivalent measured on parallel flats.

3. SURFACE ROUGHNESS: Not to exceed maximum roughness height value (AA) of 8 microinches, interpreted in accordance with ANSI B46.1.

4. MATERIAL DENSITY: .306 pound per cubic inch.

5. PART NUMBER:

   (a) The MS part number consists of the MS number, plus the dash number.

   Example: MS 19062-20001 is the part number for a Grade 200 non-ferrous brass bearing ball with basic diameter of .062500 inch.

   (b) Dash numbers, formerly designated -1 thru -19, have been redesignated -20001 thru -20019.

6. DIMENSIONS: All dimensions are in inches, unless otherwise specified. Column headings in tolerance tables are defined in AFBMA Standard 10.

7. OTHER NOTES:

   (a) Referenced documents shall be of the issue in effect on date of invitation for bids.

   (b) For design feature purposes, this standard takes precedence over procurement documents referenced herein.

APPROVED 3 November 1959 REVISED (B) For changes see Sheets 1 a

(B) ENTIRE STANDARD REVISED

| P. A. | OS | INTERNATIONAL INTEREST | TITLE | MILITARY STANDARD |
|---|---|---|---|---|
| Other Cust | AT | | BALLS, BEARING, NON-FERROUS BRASS | MS 19062 |
| | 11 | | | |
| PROCUREMENT SPECIFICATION: MIL-B-1083 | | SUPERSEDES: | | SHEET 2 OF |

DD FORM 672-1 COORDINATED

This military standard is approved for use by all Departments and Agencies of the Department of Defense. Selection for all new engineering and design applications and for repetitive use shall be made from this document

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T14:20Z
Check the source to verify that this is the current version before use.