
MS9448 (ASG)

FED SUP CLASS 5306



PART NUMBER	L	K	APPROX WEIGHT LB/100
MS9448-06	1 250	.129- .149	25.08
MS9448-07	1.312	.129- .149	25 77
MS9448-08	1.375	.129- .149	26.46
MS9448-09	1.437	129- .149	27.15
MS9448-10	1.500	.129- .149	27.84
MS9448-11	1.562	129- .149	28.53
MS9448-12	1.625	.129- .149	29.23
MS9448-13	1.688	.129- .149	29.92
MS9448-14	1.750	.129- .149	30.62
MS9448-15	1.812	.129- .149	31.31
MS9448-16	1.875	.129- .149	32.01
MS9448-17	1.938	.168- .188	32.70
MS9448-18	2.000	.190- .250	33.40
MS9448-19	2.125	315- .375	34.79
MS9448-20	2.250	.440- .500	36.18
MS9448-21	2.375	.565- .625	37.57
MS9448-22	2.500	.690- .750	38.96
MS9448-23	2.625	.815- .875	40.35
MS9448-24	2.750	.940-1.000	41.74
MS9448-25	2.875	1.065-1.125	43.13
MS9448-26	3.000	1 190-1.250	44.52
MS9448-27	3.125	1.315-1.375	45 91
MS9448-28	3.250	1.440-1 500	47.31
MS9448-29	3.375	1.565-1.625	48.70
MS9448-30	3.500	1.690-1.750	50.09
MS9448-31	3 625	1.815-1.875	51.48
MS9448-32	3.750	1.940-2.000	52.87
MS9448-33	3.875	2.065-2.125	54.26
MS9448-34	4 000	2.190-2.250	55.65
MS9448-35	4.125	2.315-2.375	57.04
MS9448-36	4 250	2.440-2.500	58.43
MS9448-37	4 375	2.565-2.625	59.82
MS9448-38	4 500	2.690-2.750	61.21
MS9448-39	4 625	2.815-2.875	62.60
MS9448-40	4.750	2.940-3.000	63.99
MS9448-41	4 875	3.065-3.125	65 38
MS9448-42	5.000	3.190-3.250	66.77
MS9448-43	5 125	3.315-3.375	68.17
MS9448-44	5 250	3.440-3.500	69 56
MS9448-45	5.375	3.565-3.625	70.98
MS9448-46	5.500	3.690-3.750	72.34
MS9448-47	5 625	3.815-3.875	73 73
MS9448-48	5.750	3.940-4.000	75.12
MS9448-49	5.875	4.065-4.125	76.51
MS9448-50	6.000	4.190-4.250	77.90

1. SHANK SHALL BE STRAIGHT WITHIN .002 FIR PER INCH OF BOLT LENGTH.
2. THE CONCENTRICITY OF THREAD PD IN RELATION TO THE SHANK SHALL BE WITHIN .006 FIR.
3. THE CONCENTRICITY OF THE SHANK IN RELATION TO THE WASHER FACE DIAMETER AND HEXAGON SHALL BE WITHIN .032 FIR.
4. INCOMPLETE THREADS NOT TO ENTER FILLET AREA
5. MATERIAL STEEL AMS 6304
6. HARDNESS. ROCKWELL C42-46
7. FINISH DIFFUSED NICKEL-CADMIUM PLATE AMS 2416. DIMENSIONS SPECIFIED ARE AFTER PLATING CONTACT POINTS PERMISSIBLE PD MAY BE REDUCED .0012 MAXIMUM BEFORE PLATING
8. MANUFACTURING SPECIFICATION AMS 7455. PARTS SUBJECT TO MAGNETIC PARTICLE INSPECTION PER AMS 2640 BEFORE PLATING
9. SURFACE ROUGHNESS AS 291, UNLESS OTHERWISE SPECIFIED SURFACES TO BE 125 MICROINCHES EXCEPT HEXAGON
10. BREAK SHARP EDGES .003 - .015 UNLESS OTHERWISE SPECIFIED
11. DIMENSIONS IN INCHES UNLESS OTHERWISE SPECIFIED TOLERANCES; LINEAR DIMENSIONS ± .010, ANGULAR DIMENSIONS ± 5°
12. TRUE POSITION TOLERANCES SPECIFIED ARE FOR MAXIMUM MATERIAL CONDITION.
13. DO NOT USE UNASSIGNED PART NUMBERS

AS & AMS ARE SAE PUBLICATIONS

THIS STANDARD WAS DEVELOPED COOPERATIVELY WITH THE ENGINE AND PROPELLER UTILITY PARTS COMMITTEE OF THE SAE

APPROVED 21 DEC 62 REVISED

P.A USAF - AFSC Other Cust NAVY - WEP	TITLE BOLT, MACHINE - STEEL AMS 6304, DIFFUSED NICKEL-CADMIUM PLATED, HEXAGON HEAD, DRILLED, .750-16 UNJF-3A	MILITARY STANDARD MS9448 (ASG)
PROCUREMENT SPECIFICATION NONE	SUPERSEDES:	SHEET 1 OF 1

DD FORM 672-1 (Limited coordination) PREVIOUS EDITIONS OF THIS FORM ARE OBSOLETE

NOTICE—When Government drawings, specifications, or other data are used for any purpose other than in connection with a definitely related Government procurement operation, the United States Government thereby incurs no responsibility nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use or sell any patented invention that may in any way be related thereto

This standard has been approved by the Department of the and is mandatory for use by that activity. All other military activities are required to employ this standard where suitable

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T13:17Z
Check the source to verify that this is the current version before use.