INCH-POUND

MIL-R-82828(OS)
5 February 1990
SUPERSEDING
WS 21054
8 November 1983

MILITARY SPECIFICATION

REINFORCEMENT, SILICA

This specification is approved for use by the Naval Sea Systems Command, Department of the Navy and is available for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers the requirements for one type of silica reinforcement, referred to herein as the reinforcement.

2. APPLICABLE DOCUMENTS

2.1 Government documents.

2.1.1 Specifications, standards and handbooks. The following specifications, standards and handbooks form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those listed in the issue of the Department of Defense Index of Specifications and Standards (DODISS) and supplement thereto, cited in the solicitation (see 6.2).

STANDARDS

MILITARY

MIL-STD-129 Marking for Shipment and Storage

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Commanding Officer, Naval Ordnance Station, Standardization Branch (3730), Indian Head, MD 20640-5000, by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

AMSC N/A FSC 9340

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:28Z
Check the source to verify that this is the current version before use.

(Unless otherwise indicated, copies of federal and military specifications, standards and handbooks are available from: Military Specifications and Standards, Bldg. 4D, 700 Robbins Avenue, Philadelphia, PA 19111-5094.)

2.1.2 **Other Government documents, drawings, and publications.** The following other Government documents, drawings, and publications form a part of this document to the extent specified herein. Unless otherwise specified, the issues are those cited in the solicitation.

CODE OF FEDERAL REGULATIONS (CFR)

49 CFR 100-199 Transportation

(Application for copies of CFRs should be addressed to the Superintendent of Documents, U.S. Government Printing Office, Washington, D.C. 20402-0001.)

2.2 **Non-Government publications.** The following documents form a part of this document to the extent specified herein. Unless otherwise specified, the issues of the documents which are DoD adopted are those listed in the issue of the DODISS cited in the solicitation. Unless otherwise specified, the issues of documents not listed in the DODISS are the issues of the documents cited in the solicitation (see 6.2).

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

ASTM C 135 True Specific Gravity of Refractory Materials by Water Immersion

ASTM D 1682 Breaking Load and Elongation of Textile Fabrics

ASTM D 1777 Measuring Thickness of Textile Materials

ASTM D 3775 Fabric Count of Woven Fabric

ASTM D 3776 Mass Per Unit Area Weight of Woven Fabric

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103-1187.)

AMERICAN TRUCKING ASSOCIATION, INC.

National Motor Freight Classification

(Application for copies should be addressed to the American Trucking Association, Inc., Attn: Traffic Dept., 2200 Mill Road, Alexandria, VA 22314-4677.)

NATIONAL RAILROAD FREIGHT COMMITTEE

Uniform Freight Classification (UFC) 6000

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:28Z
Check the source to verify that this is the current version before use.

(Application for copies should be addressed to the National Railroad Freight Committee, 222 South Riverside Plaza, Suite 1120, Chicago, IL 60606-5945.)

(Non-Government standards and other publications are normally available from the organizations that prepare or distribute the documents. These documents also may be available in or through libraries or other informational services.)

2.3 **Order of precedence.** In the event of a conflict between the text of this document and the references cited herein, the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 **Material.** The material used to produce the reinforcement shall be Type E glass that has been final processed for heat stabilization at a temperature range of 1400 to 2000°F and supplied in an 8-harness satin weave with properties as defined in table I.

TABLE I. Properties.

Property	Limits	
	Minimum	Maximum
Silica, percent	98.5	---
Weight, ounces per square yard	17.5	19.5
Breaking strength, pound per inch of width		
Warp direction	35	---
Fill direction	30	---
Thread count, yarns per inch		
Warp direction	40	57
Fill direction	30	45
Specific gravity at 25°	2.00	2.25
Thickness, inch	0.022	0.030
Moisture content, at high temperature, percent	---	5.0

3.2 **Workmanship.** The reinforcement shall be free from tears, holes, impurities, non-uniform width and thickness, and other defects which could render it unsuitable for its intended use.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:28Z
Check the source to verify that this is the current version before use.

4. QUALITY ASSURANCE PROVISIONS

4.1 **Responsibility for inspection.** Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements (examinations and tests) specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to ensure supplies and services conform to prescribed requirements.

4.1.1 **Responsibility for compliance.** All items shall meet all requirements of sections 3 and 5. The inspection set forth in this specification shall become a part of the contractor's overall inspection system or quality program. The absence of any inspection requirements in the specification shall not relieve the contractor of the responsibility of ensuring that all products or supplies submitted to the Government for acceptance comply with all requirements of the contract. Sampling inspection, as part of manufacturing operations, is an acceptable practice to ascertain conformance to requirements, however, this does not authorize submission of known defective material, either indicated or actual, nor does it commit the Government to accept defective material.

4.2 **Quality conformance inspection.** Quality conformance inspection shall consist of the tests specified in table II.

TABLE II. Quality conformance inspection.

Examination and Tests	Requirement	Test Method
Visual examination	3.2 and Section 5	4.3.1
Silica and moisture content	3.1	4.3.2
Weight	3.1	4.3.3
Breaking strength	3.1	4.3.4
Thread count	3.1	4.3.5
Thickness	3.1	4.3.6
Specific gravity	3.1	4.3.7

4.2.1 **Lot.** A lot shall consist of all the silica reinforcement rolls subjected to inspection at one time from one of the following:

a. A single batch (see 6.3.1).

Source: https://assist.dla.mil -- Downloaded: 202610-23T07:28Z
Check the source to verify that this is the current version before use.

b. A continuous process (see 6.3.2).

4.2.2 **Sampling.** Except where 100 percent sampling is indicated, the number of rolls to be selected shall be in accordance with table III. Material shall be selected from the exposed end of each sampled roll in sufficient quantity to perform all the tests specified herein. Except as otherwise specified, three specimens shall be tested from each sample for each of the properties requiring test specimens. The average test results of three test specimens shall be recorded in addition to the recording of individual test specimen values.

TABLE III. Sampling.

Number of rolls in lot	Number of sample rolls selected for testing
1 to 3	All
4 to 40	3
41 to 65	4

4.3 **Inspection methods.** The following inspection methods shall be used. Unless otherwise specified in the applicable method, all weights, volumes, temperatures, and times shall be measured to the nearest specified unit or decimal.

NOTE: Reagent grade chemicals shall be used for chemical reactions in the conduct of all tests defined herein. Solvents and indicators may be commercial nonreagent grade materials.

4.3.1 **Visual examination.** Visual examination shall be made to verify conformance to the requirements of 3.2 and section 5.

4.3.2 **Silica and moisture content.** A silica and moisture content determination shall be performed as follows:

a. Weigh a specimen of 3.0 ± 0.6 grams to the nearest 0.001 g and record weight as (A).

b. Place specimen into a preweighed crucible, heat crucible with a burner under a full flame for a minimum of 10 minutes, cool in a desiccator to ambient temperature, determine weight of dried specimen to the nearest 0.001 g, and record dried specimen weight as (B).

c. Calculate percent moisture content to the nearest 0.1 percent as follows:

$$\frac{(A - B)}{A} \times 100$$

Source: https://assist.dla.mil -- Downloaded: 202640-23T07:28Z
Check the source to verify that this is the current version before use.

d. Weigh 0.60 ± 0.12 g of the dried specimen to the nearest 0.001 g into a preweighed platinum crucible with cover. Record weight of crucible and cover as (W). Record weight of specimen, crucible, and cover as (W1).

e. Add 5 drops of a 1:1 sulfuric acid-water solution. Carefully add enough 49 percent reagent grade hydrofluoric acid to fill the crucible to about 50 percent capacity.

f. Place the crucible on a hot plate at 275 ± 25°F and evaporate slowly under a fume hood until fuming ceases. Do not allow splattering.

g. Repeat steps e and f.

h. Heat the crucible for 10 minutes minimum under full flame of the burner after the second evaporation.

i. Cool in a desiccator and weigh crucible with cover to the nearest 0.001 g (W2).

j. Calculate silica content as follows:

$$\text{Percent silica content} = \frac{(W1 - W2)}{W1 - W} \times 100$$

Where:

W = tare weight of crucible with cover, g

W1 = initial weight of specimen and crucible with cover, g

W2 = final weight of specimen and crucible with cover, g

k. Record the moisture and silica content to the nearest 0.1 percent.

4.3.3 **Weight.** The weight of the material shall be determined in accordance with ASTM D 3776.

4.3.4 **Breaking strength.** The breaking strength test shall be conducted in accordance with ASTM D 1682.

4.3.5 **Thread count.** The thread count of the material shall be determined in accordance with ASTM D 3775.

4.3.6 **Thickness.** Thickness shall be determined in accordance with ASTM D 1777, using a pressure of 5 pounds per square inch (psi).

4.3.7 **Specific gravity.** Specific gravity shall be determined in accordance with ASTM C 135.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:28Z
Check the source to verify that this is the current version before use.

4.4 **Inspection of packaging.** The reinforcement containers and container markings shall be visually examined to verify compliance with section 5.

5. **PACKAGING**

5.1 **Packaging.** Unless otherwise specified in the contract or order (see 6.2), packaging shall be level C as specified herein.

5.1.1 **Level C.** The reinforcement shall be packaged to afford adequate protection against loss, contamination, deterioration, and damage during shipment from the supply source to the first receiving activity. Containers in the same shipment shall be of the same size. The packaging shall conform to UFC 6000, National Motor Freight Classification, 49 CFR 171-178, or to other carrier rules and regulations as applicable to the mode of transportation.

5.2 **Marking.**

5.2.1 **Standard marking.** In addition to any special marking required by the contract or order (see 6.2), interior and exterior containers shall be marked in accordance with MIL-STD-129.

5.2.2 **Special marking.** In addition to the marking requirements of 5.2.1, each container marking shall include the following:

a. Title, number, and date of this specification.

b. Manufacturer's name and address.

c. Net weight of contents and number of rolls.

d. Container identification number.

e. Purchase document number.

f. Contractor's name, lot number, and material name on inside of each spool.

g. Date of manufacture.

6. **NOTES**

(This section contains information of a general or explanatory nature that may be helpful, but is not mandatory.)

6.1 **Intended use.** The reinforcement is intended for use in silica cloth phenolic for reinforced plastic nozzle components.

6.2 **Acquisition requirements.** Acquisition documents must specify the following:

Source: https://assist.dla.mil -- Downloaded: 202640-23T07:28Z
Check the source to verify that this is the currentversion before use.

a. Title, number and date of this specification.

b. Issue of DODISS to be cited in the solicitation, and if required, the specific issue of individual documents referenced (see 2.1.1 and 2.1.2).

c. Special marking, if other than as specified in 5.2.2

6.3 **Definitions.**

6.3.1 **Batch.** A batch is that amount of reinforcement silica made as one unit in the manufacturing process.

6.3.2 **Continuous process.** A continuous process is an uninterrupted process of manufacture from which, in one unbroken flow, the reinforcement silica is accumulated for a lot.

6.3.3 **Roll.** A single roll of continuous or joined cloth delivered to the impregnator.

6.3.4 **Sample.** A roll of cloth selected in accordance with the requirements of this specification for performance of inspections.

6.3.5 **Specimen.** A portion of material taken from a sample roll for performance of inspections.

6.4 **Subject term (key word) listing.**

Rocket Motor, Dual Thrust, Mk 104
Standard Missile

Preparing Activity:
NAVY-OS
(Project 9340-N069)

Source: https://assist.dla.mil -- Downloaded: 202610-23T07:28Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS

1. The preparing activity must complete blocks 1, 2, 3, and 8. In block 1, both the document number and revision letter should be given.
2. The submitter of this form must complete blocks 4, 5, 6, and 7.
3. The preparing activity must provide a reply within 30 days from receipt of the form.

NOTE: This form may not be used to request copies of documents, nor to request waivers, or clarification of requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

I RECOMMEND A CHANGE:	1. DOCUMENT NUMBER MIL-R-82828	2. DOCUMENT DATE (YYMMDD) 5 February 1990

3. DOCUMENT TITLE
REINFORCEMENT, SILICA

4. NATURE OF CHANGE (*Identify paragraph number and include proposed rewrite, if possible. Attach extra sheets as needed.*)

5. REASON FOR RECOMMENDATION

6. SUBMITTER

a. NAME (Last, First, Middle Initial)	b. ORGANIZATION
c. ADDRESS (Include Zip Code)	d. TELEPHONE (Include Area Code) (1) Commercial (2) AUTOVON (If applicable)
	7. DATE SUBMITTED (YYMMDD)

8. PREPARING ACTIVITY NAVAL ORDNANCE STATION (CODE 3730) INDIAN HEAD, MD 20640-5000

a. NAME	b. TELEPHONE (Include Area Code) (1) Commercial (2) AUTOVON
c. ADDRESS (Include Zip Code)	IF YOU DO NOT RECEIVE A REPLY WITHIN 45 DAYS, CONTACT: Defense Quality and Standardization Office 5203 Leesburg Pike, Suite 1403, Falls Church, VA 22041-3466 Telephone (703) 756-2340 AUTOVON 289-2340

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:28Z
Check the source to verify that this is the current version before use.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:28Z
Check the source to verify that this is the current version before use.