MILITARY SPECIFICATION
CLOTH, KNITTED, ACRYLIC FIBER

1. SCOPE

1.1 This specification covers one type of olive drab jersey knit acrylic cloth.

2. APPLICABLE DOCUMENTS

2.1 Government documents. The following documents of the issue in effect on date of invitation for bids or request for proposal form a part of this specification to the extent specified herein:

SPECIFICATIONS

FEDERAL

CCC-T-191	-	Textile Test Methods.

STANDARDS

MILITARY

MIL-STD-105	-	Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129	-	Marking for Shipment and Storage.

(Copies of specifications, standards, drawings, and publications required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following document forms a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal, shall apply.

UNIFORM CLASSIFICATION COMMITTEE

Uniform Freight Classification Ratings, Rules and Regulations.

Source: https://assist.dla.mil -- Downloaded: 20261O-22T20:54Z
Check the source to verify that this is the current version before use.

(Application for copies of these freight classification rules and regulations should be addressed to Uniform Classification Committee, 202 Union Station, Chicago, Illinois 60606.)

3. REQUIREMENTS

3.1 Material. The cloth shall be a jersey knit manufactured from yarn composed of acrylic fibers, 2/30 natural bulk, 3 denier.

3.2 Physical requirements.

3.2.1 Weight. The cloth shall weigh 7.0 ± 1.0 ounces per square yard when tested in accordance with 4.3.4.1.

3.2.2 Count. After dyeing (see 3.3), the cloth shall have 17 ± 1 wales per inch and 24 ± 2 courses per inch when tested in accordance with 4.3.4.1.

3.2.3 Dimensions.

3.2.3.1 Thickness. The cloth shall be 0.047 ± 0.005 inch thick when tested in accordance with 4.3.4.1.

3.2.3.2 Width. The width shall be as specified in the contract or purchase order (see 6.2) when tested in accordance with 4.3.4.1.

3.2.3.3 Length of roll. Unless otherwise specified, the cloth shall be furnished in rolls of no less than 90 nor more than 110 yards. No roll shall contain more than 2 pieces and no piece shall be less than 20 yards in length.

3.2.4 Elongation. The elongation of the cloth in the direction of the wales shall be 65 ± 10 percent under a tension load of 50 pounds and in the direction of the courses shall be 120 ± 15 percent under a tension load of 25 pounds when tested in accordance with 4.3.4.1.

3.2.5 Ball burst strength. The ball burst strength of the cloth shall be a minimum of 80 pounds tension load for each determination when tested in accordance with 4.3.4.1.

3.3 Color. The color of the cloth shall be olive drab (see 6.3).

3.3.1 Color fastness. There shall be no marked change in color when the color is immersed for 24 hours in 5.25 percent aqueous sodium hypochlorite solution and 1:1 aqueous hydrochloric acid when tested in accordance with 4.3.4.2.

Source: https://assist.dla.mil -- Downloaded: 20261O-22T20:54Z
Check the source to verify that this is the currentversion before use.

3.4 Preproduction. Prior to the start of regular production, a preproduction sample of cloth shall be produced in accordance with this specification for examination and test (see 4.2).

3.5 Workmanship. The finished cloth shall be free from foreign matter (dirt, grease and oil) and damage (holes, cuts, tears, abrasion marks, runs) in excess of the applicable acceptable quality level. The cloth shall be finished in such a manner as to make it relaxed for ease of cutting and sewing.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection.

4.1.1 Supplier's responsibility. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own facilities or any commercial laboratory acceptable to the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to specified requirements.

4.1.2 Objective evidence. The supplier shall provide objective evidence acceptable to the contracting officer that the requirements of 3.1 and section 5 for which specific inspection has not been provided in this specification have been satisfied.

4.2 Preproduction.

4.2.1 Sample. A preproduction sample of 50 yards of cloth shall be manufactured using the same methods, materials, equipment and processes as will be used during regular production.

4.2.2 Examination and test. The preproduction sample shall be examined and tested for all the requirements of this specification. A 1-1/2 yard specimen, full width, cut from each 10 yards of the sample shall be used for testing as specified in 4.3.4.

4.2.3 Acceptance/rejection criteria. The preproduction sample shall meet all the requirements of this specification to be acceptable. The supplier shall obtain written approval from the contracting officer prior to starting with regular production.

Source: https://assist.dla.mil -- Downloaded: 20261O-22T20:54Z
Check the source to verify that this is the currentversion before use.

4.3 Regular production.

4.3.1 Lotting. A lot shall consist of the acrylic cloth produced by one manufacturer, at one plant, from the same materials, under essentially the same manufacturing conditions.

4.3.2 Sampling.

4.3.2.1 For examination. Sampling shall be conducted in accordance with MIL-STD-105 and table I.

Table I. Sample size (in rolls)

Lot size in yards	Sample size in rolls
Up to 1300[1]	3
1301 to 8000	5
8001 to 35,000	8
35,001 and over	13

[1] If the lot contains less than 3 rolls, each roll in the lot shall be selected.

4.3.2.2 For test. A sample of 1-1/2 continuous yards, full width of the finished cloth shall be taken from each sample roll selected in accordance with table I.

4.3.3 Inspection.

4.3.3.1 Examination of the end item.

(a) Yard by yard examination. The required yardage of each roll shall be examined on one side only; however, the side examined shall be alternated on each successive piece examined and visual defects classified as listed in table II. All defects found shall be counted regardless of their proximity to each other, except where two or more defects represent a single local condition of the cloth, in which case only the more serious defect shall be counted as one defect for each wale-wise yard or fraction thereof in which it occurs. The unit of product for this examination shall be one linear yard. The acceptable quality level (AQL) shall be 10.0 defects per hundred units. The number of rolls from which the sample is to be selected shall be in accordance with table I. An approximately equal number of yards shall be examined in each roll of the sample.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:54Z
Check the source to verify that this is the current version before use.

Table II. Yard by yard examination

Defects
Any hole, cut or tear
Abrasion mark resulting in a weak area
Shade bar or streak, stains, or spots; clearly visible*, caused by yarn of different weight, twist, thickness, or other physical difference from adjacent yarns
Oversized knot extending above surface of cloth
Any run or dropped stitch
Any mend clearly visible* which may affect serviceability
Slubs or heavy yarns, more than twice the normal thickness
Heavy or light areas
Cut or frayed ends
Embedded crease or wrinkle

*Clearly visible at normal inspection distance (three to six feet).

(b) Overall examination. Each defect listed in table III shall be counted no more than once in each roll examined. The unit of product shall be one roll. The number of rolls to be examined (sample size) shall be in accordance with table I; the acceptance number shall be 0 for up to 5 rolls, 1 for 6 to 8 rolls, 2 for all over 8 rolls.

Table III. Overall examination

Defects
Any gross length found to be more than 2 yards below the gross length marked on the roll ticket.
Any piece less than 20 yards in length
Number of pieces in roll not stencilled on last 6 inches of roll on outer surface
Uneven knitting throughout the roll
Uneven knapping

4.3.3.2 For tests. The sample cloth shall be tested in accordance with 4.3.4. The lot shall be rejected if one or more samples fail to meet any of the specified tests.

Source: https://assist.dla.mil -- Downloaded: 20261O-22T20:54Z
Check the source to verify that this is the currentversion before use.

4.3.4 Tests.

4.3.4.1 Physical tests. Tests shall be conducted in accordance with the applicable test method of CCC-T-191 and table IV.

Table IV. Physical tests

Characteristic	Test method
Weight	5041
Count (wales and courses)	5071
Thickness	5030
Width	5020
Elongation	5100
Ball burst strength	5120

4.3.4.2 Color fastness. A specimen 27 inches by 12 inches shall be taken no closer than 4 inches from the edge of the sample (4.3.2.2). The center section shall be retained for color comparison. One end section shall be tested in each of the following tests.

(a) Sodium hypochlorite solution. One end section shall be weighed to the nearest 0.1 gram and completely immersed for 24 hours in 5.25 percent aqueous sodium hypochlorite solution. The quantity of sodium hypochlorite solution shall be 30 times the weight of the end section of the cloth specimen to be immersed. The end section shall be rinsed free of the sodium hypochlorite solution with water, dried, and compared to the center section (4.3.4.2) for visible change in color.

(b) Hydrochloric acid. The second end section shall be weighed to the nearest 0.1 gram and completely immersed for 24 hours in 1:1 aqueous hydrochloric acid. The quantity of hydrochloric acid shall be 30 times the weight of the end section of the cloth specimen to be immersed. The end section shall be rinsed free of the hydrochloric acid with water, dried, and compared to the center section (4.3.4.2) for visible change in color.

Source: https://assist.dla.mil -- Downloaded: 202610-22T20:54Z
Check the source to verify that this is the currentversion before use.

5. PREPARATION FOR DELIVERY

5.1 Packing, level C. The cloth shall be packed to afford protection against damage during direct shipment from the supply source to the first receiving activity for immediate use. Containers used shall comply with the Uniform Freight Classification rules or other carrier regulations applicable to the mode of transportation.

5.2 Marking. In addition to any marking required by the contract or order, shipments shall be marked in accordance with MIL-STD-129.

6. NOTES

6.1 Intended use. The cloth covered by this specification is intended to be used in the manufacture of bags to contain re-impregnating and decontaminating powder for use in the M13 kit.

6.2 Ordering data. Procurement documents should specify the following:

(a) Title, number, and date of this specification.
(b) Width of cloth required.
(c) Preproduction.

(1) Time allowed for supplier submission of samples for Government test and evaluation after award of contract.

(2) Name and address of test facility and shipping instructions when testing is performed by the Government.

(3) Time required for the Government to notify the supplier whether or not to proceed with production.

6.3 Color. The following dye has been found to give the desired color with the desired color fastness properties: A Dupont formulation containing 1.7 percent "Sevron" Brown YL, 0.1 percent "Sevron" Yellow R, 1.0 percent "Sevron" Blue B, and 0.33 percent "Sevron" Blue 5G.

6.4 Supersession. This specification supersedes Edgewood Arsenal Purchase Description 197-54-751, dated 8 June 1965.

Custodian:

Army - MU

Preparing activity:

Army - MU(EA)

Project No. 8305-A341

Source: https://assist.dla.mil -- Downloaded: 20261O-22T20:54Z
Check the source to verify that this is the current version before use.

TO DETACH FORM ON THIS LINE

SPECIFICATION ANALYSIS SHEET

Form Approved Budget Bureau No. 119 R004

INSTRUCTIONS

This sheet is to be filled out by personnel either Government or contractor, involved in the use of the specification in procurement of products for ultimate use by the Department of Defense. This sheet is provided for obtaining information on the use of this specification which will insure that suitable products can be procured with a minimum amount of delay and at the least cost. Comments and the return of this form will be appreciated. Fold on lines on reverse side, staple in corner, and send to preparing activity.

SPECIFICATION

ORGANIZATION	CITY AND STATE

CONTRACT NO.	QUANTITY OF ITEMS PROCURED	DOLLAR AMOUNT
		$

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE SPECIFICATION CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A. GIVE PARAGRAPH NUMBER AND WORDING

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY SPECIFICATION REQUIREMENT CONSIDERED TOO RIGID

3. IS THE SPECIFICATION RESTRICTIVE?

☐ YES ☐ NO IF "YES", IN WHAT WAY?

4. REMARKS *(Attach any pertinent data which may be of use in improving this specification. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity)*

SUBMITTED BY *(Printed or typed name and activity)*	DATE

DD FORM 1 APR 63 1426

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:54Z
Check the source to verify that this is the current version before use.