MIL-C-83314A
7 October 1983
SUPERSEDING
MIL-C-83314(USAF)
22 March 1971

MILITARY SPECIFICATION

CLOTH, BROADCLOTH, POLYESTER/COTTON (DURABLE PRESS)

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers the requirements for polyester and cotton blended broadcloth, chemically treated with a durable press finish and cured.

1.2 Classification. The cloth shall be of the following classes as specified (see 6.2):

Class 1 - 3.5 - 4 oz - Blue 1550
Class 2 - 3.5 - 4 oz - White 3060
Class 3 - 3.8 - 4.3 oz - Blue 1550
Class 4 - 3.8 - 4.3 oz - Blue 1550

2. APPLICABLE DOCUMENTS

2.1 Government documents

2.1.1 Specifications, standards, and handbooks. Unless otherwise specified, the following specifications, standards, and handbooks of the issue listed in that issue of the Department of Defense Index of Specifications and Standards (DoDISS) specified in the solicitation form a part of this specification to the extent specified herein.

SPECIFICATIONS

Federal

V-T-285	Thread, Polyester
PPP-P-1134	Packaging and Packing of Cotton and Cotton-Synthetic Fiber Blend Fabrics (Excluding Duck Fabrics)

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: ASD/ENES, Wright-Patterson AFB, OH 45433 by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

FSC 8305

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:48Z
Check the source to verify that this is the current version before use.

STANDARDS

Federal

FED-STD-4 Glossary of Fabric Imperfections
FED-STD-191 Textile Test Methods

Military

MIL-STD-105 Sampling Procedures and Tables for Inspection by Attributes

(Copies of specifications, standards, drawings, and publications required by manufacturers in connection with specific acquisition functions should be obtained from the contracting activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. The issues of the documents which are indicated as DoD adopted shall be the issue listed in the current DoDISS and the supplement thereto, if applicable.

LAWS AND REGULATIONS

Rules and Regulations Under the Textile Fiber Products Identification Act, effective 3 March 1960

(Application for copies should be addressed to the Federal Trade Commission, Washington DC 20580.)

THE AMERICAN ASSOCIATION OF TEXTILE CHEMISTS AND COLORISTS

Technical Manual of the American Association of Textile Chemists and Colorists

AATCC Chromatic Transference Scale

(Application for copies should be addressed to The American Association of Textile Chemists and Colorists, Research Triangle Park, P.O. Box 12215, Durham NC 27709.)

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

ASTM D 1424 Tear Resistance of Woven Fabrics by Falling-Pendulum (Elmendorf) Apparatus

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race St., Philadelphia PA 19103.)

(Industry association specifications and standards are generally available for reference from libraries. They are also distributed among technical groups and using Federal agencies.)

2.3 Order of precedence. In the event of a conflict between the text of this specification and the references cited herein, the text of this specification shall take precedence.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:48Z
Check the source to verify that this is the current version before use.

3. REQUIREMENTS

3.1 Standard sample. The dyed, treated, and cured (finished) cloth shall match the standard sample for shade and finish appearance and shall be equal to or better than the standard sample with respect to all characteristics for which the standard sample is referenced (see 6.4).

3.2 First article. When specified, a sample of cloth shall be subjected to first article inspection and approval (see 4.3, 6.2 and 6.3).

3.3 Materials (see 6.7)

3.3.1 Fibers

3.3.1.1 Polyester fiber. The fiber shall be polyethylene glycol teraphthalate (see 4.4.1).

3.3.1.2 Cotton. The cotton shall be carded and combed (see 4.4.1).

3.3.2 Yarns. The yarns shall be a blend of polyester and cotton, drawn and spun into single yarns for both warp and filling. The finished cloth shall contain 65 $\pm$ 3 percent polyester fiber and not less than 32 percent cotton based on the dry weight of the desized specimen before treatment and finishing. Tests shall be made as specified in 4.5.

3.4 Color. Unless otherwise specified, the color of the Class 1, 3, and 4 cured (finished) cloth shall be Air Force Blue 1550 to match the standard sample and the color of the Class 2 cured (finished) cloth shall be White 3060 and shall match the standard sample (see 3.5.1).

3.4.1 Matching. The treated and cured (finished) cloth shall match the standard sample under artificial daylight having a correlated color temperature of 7000 $\pm$ 500 kelvins and shall be a good approximation to the standard sample under incandescent lamplight at 2850 $\pm$ 100 kelvins.

3.4.2 Colorfastness. The dyed, treated, and cured (finished) cloth shall show fastness to laundering (after 3 cycles) crocking, perspiration, and light equal to or better than the standard samples. When no standard sample has been established or designated as applicable to colorfastness, the dyed, treated, and cured (finished) cloth shall show "good" fastness to laundering (after 3 cycles) perspiration and light, and shall show an AATCC Chromatic Transference Scale rating for crocking not lower than 3.5 when tested as specified in 4.5.

3.4.3 Sulfur content. The use of dyes and compounds containing elementary sulfur capable of oxidation to sulfuric acid is prohibited. The dyestuff shall be chosen and so applied that the dyed and cured (finished) cloth shall contain no more labile sulfur than shown by the standard sample when tested as specified in 4.5. When a standard sample is not available, the dyed and cured (finished) cloth shall show no more than a slight trace of labile sulfur as defined in the test method specified in 4.5.

3.5 Physical requirements. The treated and cured (finished) cloth shall conform to the requirements in table I, when tested as specified in 4.5.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:48Z
Check the source to verify that this is the current version before use.

TABLE I. Physical requirements.

Classes	Weight per sq yd		Yarns per inch		Breaking strength pounds		Weave	Tearing strength pounds	
	Ounces		Minimum		Minimum			Minimum	
	Min	Max	Warp	Filling	Warp	Filling		Warp	Filling
1	3.5	4	100	64	70	52	Plain	4	3
2	3.5	4	100	64	70	52	Plain	3	3
3	3.8	4.3	101	65	72	90	Plain	4	5
4	3.8	4.3	100	62	85	55	Plain	5	3

3.5.1 Construction. Classes 1, 3, and 4 cloth shall be of an end-and-end construction with alternating warp ends in blue and white. The blue warp ends shall be solid color and white warp ends and all filling shall be white in the body and selvage of the cloth. The Class 2 cloth shall be all white.

3.5.2 Width. The width of the cloth shall be as specified (see 6.2) and shall be the minimum acceptable width inclusive of selvages when fly shuttle looms are used, and exclusive of selvages and fringe when shuttleless weaving machines are used.

3.6 Cloth preparation. The dyed and untreated cloth shall be scoured, singed, stabilized, and mercerized, when required, to result in a smooth and lustrous finish equal in character to that of the standard sample and to meet the requirements of this specification.

3.6.1 Nonfibrous material. The starch and protein content, including chloroform-soluble and water-soluble material, of the dyed and untreated cloth shall not exceed 2.0 percent when tested as specified in 4.5.

3.7 Shrinkage. The cloth shall be preshunk and shall not shrink more than 2.0 percent in either the direction of the warp or the filling when tested as specified in 4.5. The preshrinking process used shall not be identified by name or trademark either on the cloth, ticket, or package.

3.8 pH. The pH value of the water extract of the dyed, treated and cured (finished) cloth shall be no less than 5.0 nor more than 8.5 when tested as specified in 4.5.

3.9 Seam efficiency. The treated and cured (finished) cloth shall have a seam efficiency of not less than 85 percent when tested as specified in 4.5.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:48Z
Check the source to verify that this is the current version before use.

3.10 Treatment. The cloth shall be given an approved durable press treatment (see 6.6) consisting of a suitable catalyzed resin system in combination with hand modifiers. A wetting agent may be used to facilitate processing. The cloth shall be so processed that the dyed, treated, and cured (finished) cloth shall meet the applicable requirements of this specification when tested as specified in 4.5.

3.10.1 Appearance. The cured (finished) cloth shall have a minimum average rating of 3.5 per sample unit when tested after 5 launderings as specified in 4.5.

3.11 Length and put-up. Unless otherwise specified (see 6.2), the cloth shall be furnished in continuous lengths, each not less than 40 yards. Each length shall be put up on full width rolls as specified in PPP-P-1134.

3.12 Fiber identification. Each roll of cloth shall be labeled, ticketed, or invoiced for fiber content in accordance with the Rules and Regulations under the Textile Fiber Products Identifiction Act. The face side of the cloth shall be identified by applying a stamping on that side of the cloth with the word "FACE" at each end of the piece.

3.13 Workmanship. The cured (finished) cloth shall conform to the quality established by this specification. The demerit points per 100 square yards when calculated as specified in section 4 shall not exceed the established maximum point value.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the supplier may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapporved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Certificate of compliance. Where certificates of compliance are submitted, the Government reserves the right to check test such items to determine the validity of the certification.

4.2 Classification of inspections. The inspection requirements specified herein are classified as follows:

a. First article inspection (see 4.3)

b. Quality conformance inspection (see 4.4)

4.3 First article inspection. When required, the first article sample of the treated and finished cloth, submitted in accordance with 3.2, shall be visually inspected for appearance, color, and finish. The sample shall be tested for physical and chemical characteristics in accordance with table II, FED-STD-191, and 4.5, as applicable.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:48Z
Check the source to verify that this is the current version before use.

TABLE II. Component test method.

Characteristic	Requirement Paragraph	Test Method
Polyester identification	3.3.1.1	4.5.1 1/
Cotton identification	3.3.1.2	1200 1/
Cotton combed	3.3.1.2	1/

1/ Unless otherwise specified, a certificate of compliance shall be submitted and will be acceptable for the stated requirement.

4.4 Quality conformance inspection. Unless otherwise specified, sampling for inspection shall be performed in accordance with MIL-STD-105.

4.4.1 Component and material inspection. In accordance with 4.1, components and materials shall be inspected in accordance with all the requirements of referenced specifications, drawings, and standards unless otherwise excluded, amended, modified, or qualified in this specification or applicable purchase documents.

4.4.2 Examination of the end item. Examination of the end item shall be in accordance with 4.4.2.1 through 4.4.2.4.

4.4.2.1 Yard-by-yard examination. Each roll in the sample shall be examined on the face side only. When the total yardage in the roll does not exceed 100 yards, the entire yardage of the roll shall be examined. When the total yardage in the roll exceeds 100 yards, only 100 yards shall be examined. All defects as defined in section I of FED-STD-4, which are clearly noticeable at normal inspection distance (3 feet) shall be scored and assigned demerit points as listed in 4.4.2.1.1, except that only those slubs and knots which exceed the limits shown on figure 3 of FED-STD-4 and those slubs and knots which exceed the limits shown on Sears Fabric Defect Scales (see 6.5), "E" for slubs and "B" for knots shall be scored. No linear yard (increments of 1 yard on the measuring device of the inspection machine) from any one roll within the sample shall be penalized more than 4 points. The sample size shall be in accordance with the following:

Lot size (yards)	Sample size (rolls) 1/
3200 or less	8
3201 up to and including 10,000	13
10,001 and over	20

1/ No more than one roll shall be taken from any shipping container unless the number of shipping containers in the lot is less than the required number of rolls, in which case all shipping containers shall be present in the sample.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:48Z
Check the source to verify that this is the current version before use.

The lot shall be unacceptable if the points per 100 square yards of the total yardage examined exceeds 30.0 points. The lot shall be unacceptable if the points per 100 square yards of two or more individual rolls exceeds 45.0 points. If no individual roll exceeds the point level, the lot shall be acceptable with respect to this characteristic. If one roll exceeds the point level, a second sample equal in size to the first, shall be examined only for individual roll quality examination. The lot shall be unacceptable if one or more rolls in the second sample exceeds the point level. Point computation for lot quality and individual roll quality shall be as follows:

$$\frac{\text{Total points scored in sample} \times 3600}{\text{Contracted width of cloth (inches)} \times \text{total yards inspected}} = \text{Points per 100 sq yds}$$

4.4.2.1.1 Demerit points. Demerit points shall be assigned as follows:

For defects 3 inches or less in any dimension	- one point
For defects exceeding 3 inches, but not exceeding 6 inches in any dimension	- two points
For defects exceeding 6 inches, but not exceeding 9 inches in any dimension	- three points
For defects exceeding 9 inches in any dimension	- four points

NOTE: The following defects, when present, shall be scored four points for each yard in which they occur:

Holes, cuts, and tears
Baggy, ridgy, or wavy cloth
Objectionable odor
Width less than specified
Poor dye penetration, mottled, streaky, or cloudy color
Excessive neppiness
Character of finish not equal to standard sample.

4.4.2.2 Examination for length

4.4.2.2.1 Individual rolls. During the yard-by-yard examination, each roll in the sample shall be examined for length. Any length found to be less than the minimum specified or more than 2 yards less than the length marked on the ticket shall be considered a defect with respect to length. The lot shall be unacceptable if two or more rolls in the sample are defective in respect to length.

4.4.2.2.2 Total yardage in sample. The lot shall be unacceptable if the total of the actual lengths of rolls in the sample is less than the total of the lengths marked on the roll tickets. The rolls examined shall be those selected for the examination of individual rolls.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:48Z
Check the source to verify that this is the current version before use.

4.4.2.3 Examination for shade. During the yard-by-yard examination, each roll in the sample shall be examined for shade and finish appearance. Any roll in the sample off shade, shaded side to side, side to center, or end to end shall be cause for rejection of the entire lot represented by the sample.

4.4.2.4 Examination for face identification, non-identification of preshrinking process, and compliance with Textile Fiber Products Identification Act. During the yard-by-yard examination, each roll in the sample shall be examined for defects listed below. The lot shall be unacceptable if two or more of the following defects are present in the sample:

"FACE" identification missing from either or both ends
"FACE" identification on wrong side
Preshrinkage process identified by name or trademark on cloth or ticket
Not labeled or ticketed in accordance with the Rules
and Regulations under the Textile Fiber Products Identification Act.

4.5 End item testing. The methods of testing specified in FED-STD-191, wherever applicable, and as listed in tables III and IV shall be followed. The physical and chemical values specified in section 3 apply to the average result of the determinations made on a sample unit for test purposes as specified in the applicable test methods. The sample unit shall be 4 continuous yards full width of the finished cloth, and 1/2 yard full width of the dyed untreated cloth. The lot size shall be expressed in units of 1 yard each. The lot shall be unacceptable if one or more sample units fail to meet any test requirements specified. All test reports shall contain the individual values utilized in expressing the final results. The sample size shall be in accordance with the following:

Lot size (yards)	Sample size (units)
800 or less	2
801 up to and including 22,000	3
22,001 and over	5

TABLE III. End item tests (applicable to dyed untreated cloth).

Characteristic	Requirement Paragraph	Test Method
Fiber content		
Polyester (percent)	3.3.2	2100, 4.5.2
Cotton (percent)	3.3.2	2100, 4.5.2
Yarn (single)		
Warp	3.3.2	Visual 1/
Filling	3.3.2	Visual 1/
Weave	3.5	Visual 1/
Mercerization	3.6	2/
Nonfibrous materials	3.6.1	2611

1/ One determination for each sample unit and the result reported as "pass" or "fail".

2/ Microscopic examination for swelling of the cloth fibers. One determination per sample unit and the result reported as "pass" or "fail".

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:48Z
Check the source to verify that this is the current version before use.

4.5.1 Fiber. The polyester filament shall be insoluble in each of the following solvents: Acetone (boiling), 70 percent sulfuric acid, 5.0 percent sodium hydroxide (boiling), and methylene chloride (boiling). The methylene chloride shall be prepared by mixing 9 parts methylene chloride with 1 part U.S.P. (95 percent) ethyl alcohol. The methylene chloride solution is extremely toxic and adequate ventilation or use of fume hood is recommended. Unless otherwise specified, the above solvents shall be used at room temperature, using 100 times as much solvent as fiber. The fiber shall remain in the solvent for 10 minutes with intermittent stirring. This is a visual qualitative test.

4.5.2 Test for polyester fiber and cotton content. The general procedures of method 2100, FED-STD-191 shall be followed and the fiber content percentages shall be calculated as follows:

$$\frac{\text{Weight of dry residual fiber X 100}}{\text{Weight of dry desized specimen}} = \text{percent polyester}$$

100 - percent polyester = percent cotton

TABLE IV. End item tests (applicable to treated and finished cloth).

Characteristic	Requirement Paragraph	Test Method
Colorfastness to:		
Laundering (after 3 cycles)	3.4.2	5610
Crocking	3.4.2	5651
Perspiration	3.4.2	5680
Light	3.4.2	5660 1/
Sulfur content	3.4.3	2020
Weight	3.5	5041
Yarns per inch		
Warp	3.5	5050
Filling	3.5	5050
Breaking strength		
Warp	3.5	5100
Filling	3.5	5100
Tearing strength		
Warp	3.5	ASTM D 1424
Filling	3.5	ASTM D 1424
Dimensional stability	3.7	4.5.3
pH	3.8	2811
Seam efficiency	3.9	5110 2/
Appearance after 5 launderings	3.10.1	4.5.3

1/ Method 5660 shall be used, except that exposure of the specimen and standard sample shall be for 20 standard fading hours. Any specimen showing discoloration less than or equal to that of the standard sample shall be rated "pass". Any specimen showing discoloration greater than that of the standard sample shall be rated "fail". One determination shall be made for each sample unit and the result reported as "pass" or "fail".

2/ The needle shall measure 0.036 ± 0.001 inch across the blade at the eye. The polyester thread shall be type I, class I of V-T-285. The needle thread shall be size AA and the looper thread shall be size A.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:48Z
Check the source to verify that this is the current version before use.

4.5.2.1 Report. Two specimens shall be tested from each sample unit and the average percent polyester and the average percent cotton of the two specimens shall be reported to the nearest 1.0 percent.

4.5.3 Test for appearance and dimensional stability after laundering

4.5.3.1 Apparatus and material. Apparatus and material shall be as specified in AATCC Technical Manual, method 124 - 1982.

4.5.3.2 Preparation of specimens. Three specimens 22 X 22 inches measured parallel to the warp and filling shall be cut from a portion of the cloth sample. One specimen shall be cut from each side of the sample unit to within three inches of the selvages and the third specimen shall be taken from the center. No two specimens shall contain the same filling yarns. The specimen shall be conditioned to equilibrium under Standard Conditions in accordance with FED-STD-191. The conditioned specimens shall be laid without tension on a flat surface, care being taken that the cloth is free from wrinkles or creases. Three distances, each a minimum of 18 inches, shall be measured and marked off parallel to each of the warp and filling directions of the specimen. Each pair of markings shall be a minimum of 6 inches from each other and not closer than one inch to the edges of the specimen. The distance may be marked with indelible ink and a fine pointed pen, or by sewing fine threads into the cloth, or by stamping. The samples shall then be laundered in accordance with 4.5.3.2.1.

4.5.3.2.1 Laundering. Place the three 22 X 22 inch specimens in the washer. The washing load shall be 4 $\pm$ 1/4 pounds. Dummy pieces shall be added to the machine, along with the specimens to make up the 4 $\pm$ 1/4-pounds load. Fill to the full water level of the washer with water of a hardness not to exceed 50 parts per million and at a temperature of 120° $\pm$ 5°F (48.9° $\pm$ 15°C) and the rinse temperature shall be 80°$\pm$ 5°F (26°$\pm$ 3°C). Add 140 $\pm$ 1 grams of detergent. Set the washer for a 12 minute cycle on the "Permanent Press" setting. Allow the washing to proceed automatically through the final spin cycle. Remove the specimens immediately at the completion of the final spin and separate from the dummy pieces and each other, if tangled. Place the complete washed load (4 $\pm$ 1/4 pounds) in the dryer and dry at the "Permanent Press" setting with a ten minute cool down cycle. Operate the dryer until the load is dry and continue tumbling 5 minutes with the heat turned off (cool down cycle). Remove the load immediately after the machine stops. Repeat the wash and dry cycles for 5 complete cycles. All the specimens are removed and shall be conditioned to equilibrium under standard conditions in accordance with FED-STD-191.

4.5.3.3 Evaluation. Three trained observers shall evaluate each sample unit for appearance characteristics. The observers shall make their observations independently. Each observer, while standing in front of the viewing board and 4 feet back from it, shall evaluate each specimen for appearance as it hangs on the viewing board.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:48Z
Check the source to verify that this is the current version before use.

4.5.3.3.1 Evaluation of the appearance of the cloth. The overhead lighting shall be used (see 4.5.3.1). Mount the specimen on the viewing board with the center of the specimen 5 feet from the floor. Place three-dimensional plastic replicas on each side of the specimen with the centers 5 feet from the floor, to facilitate comparative rating. The specimen shall be rated according to the appearance on the plastic replica that most nearly matches the appearance of the cloth. The average of the rating values assigned for appearance of the cloth by the observers rounded off to the nearest 0.5 rating shall be the rating of the specimen. Each rating value given by the observers for appearance of the cloth shall also be reported.

4.5.3.3.2 Dimensional stability. After evaluation or appearance is made, the three 22 X 22 inch specimens shall be laid out without tension on a flat surface in the standard atmosphere. Care shall be taken that the specimens are free from wrinkles and creases. The previously measured distance marked on the specimens shall be measured in both the warp and filling directions. The dimensional stability of the specimens shall be calculated as follows:

$$\text{Dimensional change, percent} = \frac{A-B}{A} \times 100$$

Where A = Average of initial measurements (3 specimens)
B = Average measurements after laundering (3 specimens)

The dimensional change of the sample unit in the warp and filling directions shall be the average of the specimens tested in each direction respectively and shall be reported separately to the nearest 0.1 percent. The individual values used to calculate the average shall also be reported.

4.6 Packaging inspection. The inspection shall be in accordance with the quality assurance provisions of PPP-P-1134.

5. PACKAGING

5.1 Preservation. Preservation shall be level A or Commercial as specified (see 6.2).

5.1.1 Levels A or Commercial. The cloth shall be put-up and preserved in accordance with the applicable requirements of PPP-P-1134.

5.2 Packing. Packing shall be level A, B, or Commercial as specified (see 6.2).

5.2.1 Levels A, B, or Commercial. The cloth shall be packed in accordance with the applicable requirements of PPP-P-1134.

5.3 Marking. In addition to any special marking required by the contract or purchase order, shipments shall be marked in accordance with the requirements of PPP-P-1134.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:48Z
Check the source to verify that this is the current version before use.

6. NOTES

6.1 Intended use. The cloth covered by this specification is intended for use in the manufacture of men's and women's shirts worn by personnel of the Department of Defense.

6.2 Ordering data. Acquisition documents should specify the following:

a. Title, number, and date of this specification

b. When a first article sample is required (see 3.2, 4.3, and 6.3)

c. Class of cloth required (see 1.2)

d. Width of cloth required (see 3.5.2)

e. Length required when other than specified (see 3.11)

f. Selection of applicable levels of preservation and packing (see 5.1 and 5.2).

6.3 First article. When a first article sample is required, it shall be inspected and approved. The contracting officer should include specific instructions in acquisition documents regarding arrangements for examinations, quantity, and testing and approval of the first article.

6.4 Standard sample. For access to standard sample, address the contracting activity issuing the invitation for bids.

6.5 Fabric defect scales. Fabric Defect Replica Kits are available from Sears, Roebuck and Company, Department 817 (ATTN: BSC 23-29), Sears Tower, Chicago IL 60684.

6.6 Durable press resin treatment. Only those durable press resin treatments approved and so listed in the invitation for bids or request for proposals shall be considered acceptable for the related acquisition.

6.7 Recycled material. It is encouraged that recycled material be used when practical as long as it meets the requirements of the specification (see 3.3).

6.8 Changes from previous issue. Asterisks are not used in this revision to identify changes with respect to the previous issue due to the extensiveness of the changes.

Custodians:
Army - GL
Navy - NU
Air Force - 11

Review activity:
Army - MD
Navy - CG
Air Force - 82, 99

Preparing activity:
Air Force - 11

Project No. 8305-0886

☆U.S. GOVERNMENT PRINTING OFFICE: 1983 — 706-040/5443

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:48Z
Check the source to verify that this is the current version before use.

INSTRUCTIONS: In a continuing effort to make our standardization documents better, the DoD provides this form for use in submitting comments and suggestions for improvements. All users of military standardization documents are invited to provide suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge *(DO NOT STAPLE)*, and mailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, was too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

NOTE: This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document*(s)* or to amend contractual requirements.

(Fold along this line)

(Fold along this line)

DEPARTMENT OF THE AIR FORCE
ASD/ENESS
Wright-Patterson AFB OH 45433

NO POSTAGE NECESSARY IF MAILED IN THE UNITED STATES

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO. 73236 WASHINGTON D. C.
POSTAGE WILL BE PAID BY THE DEPARTMENT OF THE AIR FORCE

ASD/ENESS
Wright-Patterson AFB OH 45433

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:48Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions – Reverse Side)

1. DOCUMENT NUMBER	2. DOCUMENT TITLE
MIL-C-83314A	

3a. NAME OF SUBMITTING ORGANIZATION	4. TYPE OF ORGANIZATION *(Mark one)*
	☐ VENDOR ☐ USER ☐ MANUFACTURER ☐ OTHER *(Specify)*:
b. ADDRESS *(Street, City, State, ZIP Code)*	

5. PROBLEM AREAS

a. Paragraph Number and Wording:

b. Recommended Wording:

c. Reason/Rationale for Recommendation:

6. REMARKS

7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional	b. WORK TELEPHONE NUMBER *(Include Area Code)* – Optional
c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional	8. DATE OF SUBMISSION *(YYMMDD)*

DD FORM 82 MAR 1426 PREVIOUS EDITION IS OBSOLETE.

(TO DETACH THIS FORM, CUT ALONG THIS LINE.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:48Z
Check the source to verify that this is the current version before use.