FED. SUP CLASS
6640

PART NUMBER	SIZE ± 5mm	CLASS	PART NUMBER	SIZE ± 5mm	CLASS	PART NUMBER	SIZE ± 5mm	CLASS
MS36508-1	76x127	1	MS36508-16	178x279	2	MS36508-31	108x127	4
MS36508-2	76x178	1	MS36508-17	191x279	2	MS36508-32	127x146	4
MS36508-3	102x152	1	MS36508-18	508x762	2	MS36508-33	127x171	4
MS36508-4	108x127	1	MS36508-19	76x127	3	MS36508-34	178x279	4
MS36508-5	127x146	1	MS36508-20	76x178	3	MS36508-35	191x279	4
MS36508-6	127x171	1	MS36508-21	102x152	3	MS36508-36	508x762	4
MS36508-7	178x279	1	MS36508-22	108x127	3	MS36508-37	76x127	5
MS36508-8	191x279	1	MS36508-23	127x146	3	MS36508-38	76x178	5
MS36508-9	508x762	1	MS36508-24	127x171	3	MS36508-39	102x152	5
MS36508-10	76x127	2	MS36508-25	178x279	3	MS36508-40	108x127	5
MS36508-11	76x178	2	MS36508-26	191x279	3	MS36508-41	127x146	5
MS36508-12	102x152	2	MS36508-27	508x762	3	MS36508-42	127x171	5
MS36508-13	108x127	2	MS36508-28	76x127	4	MS36508-43	178x279	5
MS36508-14	127x146	2	MS36508-29	76x178	4	MS36508-44	191x279	5
MS36508-15	127x171	2	MS36508-30	102x152	4	MS36508-45	508x762	5
						MS36508-46	*	6

*As specified at invitations for bid.

MATERIAL AND CLASSES: Class 1 - Lightweight and Class 4 - Heavyweight, wet-strength paper shall be made from bleached chemical wood pulp, cotton or linen fibers or mixtures of these, and shall not be contaminated with any unbleached or mechanical wood pulp.

Class 2 - Heavyweight, paper shall be made from 100 percent cotton or linen fibers.

Class 3 - Heavyweight, silicone treated paper shall be made from 100 percent bleached chemical wood pulp.

Class 5 - Lightweight, wet-strength paper shall be made from 1.5 denier viscose rayon at least .635 mm long with cellulosic or cellulose derivative binding agents, and shall be free from wood fiber.

Class 6 - Wrapping paper shall be made from either white or unbleached wood pulp, free of ground wood particles.

COLOR: Classes 1, 2, 4, and 5 paper shall be white, Class 3 paper shall be lavender. Class 6 paper shall be white or of natural unbleached pulp.

DESIGN: The lens paper shall be furnished in individual sheets or book form or envelopes. When furnished in book form, the sheets shall be securely fastened together along one edge and perforated in such manner that they can be easily and cleanly torn from the book.

INTENDED USE: Classes 1, 2, and 3 lens paper are used for wrapping and dry cleaning applications of lenses and other glass and highly polished surfaces; Classes 4 and 5, for wet cleaning. Class 6 lens paper is used for wrapping or covering of all coated optics.

NOTES:

1. Items differing from this Military Standard by minor variations in design or dimensions are considered standard under this document, provided such variations do not affect performance and are not in conflict with the material requirements specified herein.
2. For design feature purposes, this standard takes precedence over procurement document referenced herein.
3. Referenced documents shall be of the issue in effect on date of invitation for bid.

USER ACTIVITIES: ARMY - MD, DM
NAVY - MS

REVIEWER ACTIVITIES: ARMY - ME
NAVY - OS
AIR FORCE - 03

This military standard is approved for use by all Departments and Agencies of the Department of Defense. Selection for all new engineering and design applications and for repetitive use shall be made from this document.

APPROVED 30 APR 1982 REVISED

P.A. EA	INTERNATIONAL INTEREST	TITLE	MILITARY STANDARD
Other Cust MS 99		PAPER, LENS	MS36508
Procurement Specifications NNN-P-40	SUPERSEDES:		SHEET 1 OF 1

DD FORM 1 MAY 73 672 (COORDINATED) PREVIOUS EDITIONS OF THIS FORM ARE OBSOLETE PROJECT NUMBER 6640-0715 STANDARD DATE

Source: https://assist.dla.mil -- Downloaded: 2020-10-28T17:40Z
Check the source to verify that this is the current version before use.