MILITARY SPECIFICATION

FUZE CLOTH

1. SCOPE

1.1 Scope. This specification covers one type of fuze cloth.

1.2 Classification. The fuze cloth shall be of the following sizes:

Size I - 1/8 inch wide.
Size II - 1/4 inch wide.
Size III - 3/8 inch wide.

2. APPLICABLE DOCUMENTS

2.1 Government documents. The following documents of the issue in effect on date of invitation for bids or request for proposal form a part of this specification to the extent specified herein:

STANDARDS

MILITARY

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129 - Marking for Shipment and Storage.
MIL-STD-1168 - Lot Numbering of Ammunition.

DRAWINGS

US ARMY MUNITIONS COMMAND

EDGEWOOD ARSENAL

C146-1-169 - Fuze Cloth.
B146-1-144 - Fuze Strip.

(Copies of specifications, standards, drawings and publications required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:57Z
Check the source to verify that this is the current version before use.

2.2 Other publications. The following document forms a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal shall apply.

UNIFORM CLASSIFICATION COMMITTEE

Uniform Freight Classification Ratings, Rules and Regulations.

(Application for copies of these ratings, rules and regulations should be addressed to Uniform Classification Committee, 202 Union Station, 516 West Jackson Boulevard, Chicago, Illinois 60606.)

3. REQUIREMENTS

3.1 Materials.

3.1.1 Base fabric. The base fabric shall be as specified on Drawing C146-1-169.

3.1.2 Coating compound. The base fabric shall be coated on one side in accordance with Drawing C146-1-169 (see 6.3).

3.2 Size. The coated cloth shall be cut to sheet size as specified on Drawing C146-1-169.

3.3 Thickness. The thickness of the coated cloth shall be as specified on Drawing C146-1-169 when tested as specified in 4.4.4.1.

3.4 Burning rate.

3.4.1 Size I. The burning rate for size I cloth shall be 0.3 to 0.8 second per 3 inches when tested as specified in 4.4.4.2.

3.4.2 Size II. The burning rate for size II cloth shall be 0.4 to 0.9 second per 3 inches when tested as specified in 4.4.4.2.

3.4.3 Size III. The burning rate for size III cloth shall be 0.4 to 0.9 second per 3 inches when tested as specified in 4.4.4.2.

3.5 Low temperature. Dry strips of size I, II and III fuze cloth shall burn completely after storage at minus 65° ± 5°F for a minimum of 15 minutes when tested as specified in 4.3.3.

3.6 Preproduction. Prior to the start of regular production a preproduction sample of fuze cloth shall be produced in accordance with this specification for examination and test (see 4.3).

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:57Z
Check the source to verify that this is the current version before use.

3.7 Workmanship. The fuze cloth shall be free from foreign matter (lint or dirt) and damage such as cracks, chips or bare spots which could affect its intended use.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection.

4.1.1 Supplier's responsibility. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the supplier may utilize his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.2 Objective evidence. The supplier shall provide objective evidence acceptable to the contracting officer that the requirements of 3.1 and section 5 for which specific inspection has not been provided in this specification have been satisfied.

4.2 Classification of inspections.

(a) Preproduction inspection (see 4.3).
(b) Quality conformance inspection (see 4.4).

4.3 Preproduction inspection.

4.3.1 Sample. A preproduction sample of nine fuze cloth sheets, three of each size, shall be manufactured using the same methods, materials, equipment and processes as will be used during regular production.

4.3.2 Inspection procedure.

4.3.2.1 For examination and nondestructive test. The sample fuze cloth shall be examined and tested in accordance with the classification of defects (4.4.3.3). The AQL's do not apply.

4.3.2.2 For destructive tests. Two sheets of fuze cloth shall be cut into size I (minimum of 90 full-length strips), three sheets shall be cut into size II (minimum of 65 full length strips), and four sheets shall be cut into size III (minimum of 52 full length strips). Subject three strips of each size to the burning rate test in accordance with 4.4.4.2. Subject 40 strips of each size to the low temperature test in accordance with 4.3.3.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:57Z
Check the source to verify that this is the current version before use.

4.3.3 Low temperature test. The sample strips of fuze cloth shall be stored at the specified temperature for the required period of time. Ignite individual strips in cold chamber and observe burning process.

4.3.4 Acceptance/rejection criteria. The preproduction sample shall comply with the examinations and tests specified in 4.3.2 to be acceptable. The acceptance number is zero. The supplier shall obtain written approval from the contracting officer prior to proceeding with regular production.

4.4 Quality conformance inspection.

4.4.1 Lotting. Each lot shall be identified and controlled in accordance with MIL-STD-1168. Contained in any one interfix number of fuze cloth, no more than one batch (see 6.4) of coating compound from one manufacturer is permitted.

4.4.2 Sampling.

4.4.2.1 For examination and nondestructive test. Sampling shall be conducted in accordance with MIL-STD-105.

4.4.2.2 For destructive test. Sampling shall be conducted in accordance with MIL-STD-105, inspection level S-2.

4.4.3 Inspection procedure.

4.4.3.1 For examination and nondestructive test. The sample sheets of fuze cloth shall be examined and tested in accordance with the classification of defects and MIL-STD-105.

4.4.3.2 For destructive test. The sample sheets of fuze cloth shall be cut into full-length strips. A minimum of one sheet of fuze cloth of each size (I, II and III) shall be used to obtain strips. Four strips shall be randomly selected from each fuze cloth sheet and subjected to test in accordance with 4.4.4.2, using an AQL of 1.5 percent defective for duds and an AQL of 10.0 percent defective for burning rate. A dud is defined as a failure to ignite or burn for the entire strip length.

4.4.3.3 Classification of defects.

(a) Fuze cloth (Drawing C146-1-169).

Categories	Defects	Acceptance standards
Critical:	None defined	
Major:	AQL 1.0 percent defective	
101	Thickness incorrect	4.4.4.1
102	Workmanship (3.7)	

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:57Z
Check the source to verify that this is the current version before use.

4.4.3.3 Classification of defects (continued).

Categories	Defects	Acceptance standards
Minor:	AQL 4.0 percent defective	
201	Width incorrect	
202	Length incorrect	

4.4.4 Tests. Test shall be conducted as follows:

4.4.4.1 Thickness. Determine thickness of the coated cloth with a No. 2 Amex comparator gage or equivalent. The measurements shall be taken at six equally spaced points approximately 2 inches from each edge of the sheet.

4.4.4.2 Burning rate. Cut sheets of the coated cloth to the specified widths and full length of sheet, and dry in oven at 160° ± 5°F for 2 ± 1/2 hours, maintaining strips in relative sheet position. Determine burning rate of 3-inch span with burning rate tester in conjunction with electronic counter-timer (see 6.5).

5. PREPARATION FOR DELIVERY

5.1 Packaging, level C. The fuze cloth shall be packaged to provide adequate protection against deterioration and damage from the supply source to the first receiving activity for immediate use or for controlled humidity storage.

5.2 Packing, level C. The fuze cloth, packaged as specified in 5.1, shall be packed to insure carrier acceptance and safe delivery to the first domestic destination. Containers shall be in compliance with Uniform Freight Classification rules or the regulations of other common carriers applicable to the mode of transportation.

5.3 Marking. In addition to any special marking required by the contract or order, unit packages, intermediate packages, and shipping containers shall be marked in accordance with MIL-STD-129.

6. NOTES

6.1 Intended use. The fuze cloth is intended for use in the E8 launcher to ignite the E23 cartridges.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:57Z
Check the source to verify that this is the current version before use.

6.2 Ordering data. Procurement document should specify the following:

(a) Title, number and date of this specification.
(b) Type of fuze cloth required.
(c) Preproduction.

(1) Time allowed for supplier submission of samples for Government test and evaluation after award of contract.
(2) Name and address of test facility and shipping instructions when testing is performed by the Government.
(3) Time required for the Government to notify the supplier whether or not to proceed with production.

6.3 Caution. Due to the hazards inherent in pyrotechnic mixes suppliers are advised to take all necessary precautions to protect personnel while handling and manufacturing fuze cloth.

6.4 Batch. A batch is defined as that quantity of material which has been subjected to some chemical or physical mixing process intended to yield a substantially uniform product.

6.5 Tester. The tester may be procured from Brush Instruments, Division of Clevite Corporation, Cleveland, Ohio. Type BL-202, 115 volt, 60 cycle, millisecond timer with recording chart.

6.6 Supersession data. This specification supersedes Edgewood Arsenal Purchase Description 196-131-896, 13 May 1968.

Custodian:

Army - MU

Preparing activity:

Army - MU(EA)

Project No. 1310-A128

☆ U. S. GOVERNMENT PRINTING OFFICE: 1970-433-692/2606

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:57Z
Check the source to verify that this is the current version before use.

FOLD

POSTAGE AND FEES PAID

OFFICIAL BUSINESS

Commanding Officer
Edgewood Arsenal
ATTN: SMUEA-QAES
Edgewood Arsenal, Maryland 21010

FOLD

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:57Z
Check the source to verify that this is the current version before use.

SPECIFICATION ANALYSIS SHEET

Form Approved
Budget Bureau No. 22-R255

INSTRUCTIONS: This sheet is to be filled out by personnel, either Government or contractor, involved in the use of the specification in procurement of products for ultimate use by the Department of Defense. This sheet is provided for obtaining information on the use of this specification which will insure that suitable products can be procured with a minimum amount of delay and at the least cost. Comments and the return of this form will be appreciated. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments and suggestions submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or serve to amend contractual requirements.

SPECIFICATION

ORGANIZATION

CITY AND STATE | CONTRACT NUMBER

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE SPECIFICATION CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A. GIVE PARAGRAPH NUMBER AND WORDING.

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY SPECIFICATION REQUIREMENT CONSIDERED TOO RIGID

3. IS THE SPECIFICATION RESTRICTIVE?

☐ YES ☐ NO *(If "yes", in what way?)*

4. REMARKS *(Attach any pertinent data which may be of use in improving this specification. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity)*

SUBMITTED BY *(Printed or typed name and activity - Optional)* | DATE

DD FORM 1 JAN 66 1426 REPLACES EDITION OF 1 OCT 64 WHICH MAY BE USED.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:57Z
Check the source to verify that this is the current version before use.