INCH-POUND

A-A-55225
August 17, 1993

COMMERCIAL ITEM DESCRIPTION

SCARF, NECKWEAR, WOMAN'S ACRYLIC

The General Services Administration has authorized the use of this Commercial Item Description in preference to MIL-S-43317.

Abstract. This Commercial Item Description covers the requirements for a women's acrylic neckwear scarf. The scarf is intended for wear by female personnel of the Department of the Navy.

Salient Characteristics. The scarf shall be made of one piece single thickness material with fringed ends and overedge stitched side edges. The length direction of the scarf shall be in the warp direction of the material, with even 3/4 (+1/4,-1/8) inch fringing on the ends. The overedge stitch on the sides of the scarf shall be 3/16 inch wide, 16 - 18 stitches per inch, with the chain at each end of stitching the same length as the fringe (-1/4 inch tolerance). The finished dimensions of the scarf shall be 46-1/2 to 48 inches long (including fringe), and 10-1/2 to 11-1/4 inches wide (including overedge stitching).

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Defense Personnel Support Center, Clothing and Textiles Directorate, Attn: DPSC-FSSD, 2800 South 20th Street, Philadelphia, PA 19101-8419, by using the Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

AMSC N/A


FSC 8445

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:45Z
Check the source to verify that this is the current version before use.

Materials.

Basic cloth. The fiber for the basic cloth shall be acrylic, semi-dull, 2 ply warp and filling yarns of a suitable staple length, twisted with 6-9 turns per inch, Z twist. The ply yarn consists of two single yarns, each with 5-9 turns per inch, S twist. The weave shall be a crowfoot satin, repeating on 4 ends and 4 picks, as shown in the diagram below:



The Finished cloth shall be chemically bleached white and may be supplemented with optional brighteners which fluoresce to the blue region, matching the Navy shade White 3032, and shall conform to the requirements specified in Table I when tested as specified.

Table I. Requirements and test methods

Characteristics	Requirements	Test method
Fiber identification	As stated above	1/
Weight oz./sq. yd.	3.8 (min)	ASTM-D 3776-85 Option C
Yarns per inch:		
Warp	28 ends/inch (min)	ASTM-D 3775-85
Filling	20 picks/inch (min)	
Breaking strength:		
Warp	40 lbs. (min)	ASTM-D 5034-90
Filling	25 lbs. (min)	
Nonfibrous material	2.0% Max.	ASTM-D 629-88
pH	5.0 - 8.5	ASTM-D 2165-90

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:45Z
Check the source to verify that this is the current version before use.

1/ Unless otherwise specified, a certificate of compliance shall be submitted and will be acceptable for the stated requirements.

Thread, cotton. The cotton thread for seaming the edges of the scarf shall be ticket number 00, 3 ply, conforming to type III (mercerized machine thread) of A-A-52094 except that the colorfastness requirements do not apply. The color of the thread shall be white A.H. C.A. 66050 in accordance with the Department of Defense Standard Shades for Sewing Threads.

Label/tag. Each scarf shall be individually coded with a type VIII, class 17 of DDD-L-20 label/tag bar code for personal clothing items. The scarf shall be folded so that the label/tag bar code is completely visible in the packaging.

Workmanship. The finished scarves shall conform to the quality of product established by this document. The occurrence of defects shall not exceed the applicable acceptable quality levels.

Product Demonstration Model. When required, offerers shall submit samples of their intended production. The product demonstration model will consist of units independently developed. Product demonstration models will be analyzed and evaluated by the government. Evaluation criteria and basis for award are contained in the solicitation. Product demonstration models will be retained by the government. One (1) product demonstration model approved by DPSC under the resultant contract will serve as a manufacturing standard for the corresponding production items delivered under this contract. Offerers are advised that the product demonstration model does not relieve the successful offerer of his responsibility to perform in accordance with the Commercial Item Description specified above.

Quality Assurance

Certification. The contractor shall certify that the product offered meets the salient characteristics of this description and that the product conforms to the producer's own drawings, specifications, standards and quality assurance practices. The government reserves the right to require proof of such conformance prior to the first delivery and thereafter as may be otherwise provided for, under the provisions of the contract. Reliance on contractor QA systems shall not relieve the contractor of the responsibility of ensuring that all products or supplies submitted to the government for acceptance comply with all requirements of the contract.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:45Z
Check the source to verify that this is the current version before use.

Examination

Visual Examination. The scarf shall be examined for the defects listed below. The lot size shall be expressed in units of scarfs. The sample unit is one scarf.

Defects. The scarfs shall be examined for the following defects:

Any hole, cut, tear, smash, floats, slubs, needle chew, shade bar, streak or wrong color.
Width of overedge stitching less than 1/8 inch or more than 3/16 inch; overedge stitching missing.
Fringe missing on one or both ends, ragged or uneven.
Thread wrong color, not size or type specified.
Break in overedge stitching, runoff, loose tension, exposed loops or tight tension, resulting in puckering.
Spot, stain clearly visible or thread ends not trimmed.
Bar code label/tag omitted or not scannable, human-readable interpretation (HRI) omitted or illegible.

Dimensional Examination. The finished scarf shall conform to the dimensions specified. Any dimension that is not within the established tolerance shall be classified as a defect. The sample unit shall be one scarf.

Packaging Examination. The fully packaged shipping containers shall be examined in accordance with defects listed below. The lot size shall be the number of shipping containers in the inspection lot.

EXAMINE	DEFECT
Marking (exterior and interior)	Omitted; incorrect; illegible; of improper size, location, or method of application
Materials	Any component missing, damaged, or not as specified
Workmanship	Inadequate application of components, such as: incomplete closure of container flaps, loose strapping, improper taping, or inadequate stapling
Content	Number of items in container is more or less than required
	NSN shown on one or more items is not as specified on shipping container

Source: https://assist.dla.mil -- Downloaded: 202610-26T09:45Z
Check the source to verify that this is the current version before use.

EXAMINE	DEFECT - cont.
Palletization	Length, width, or height exceeds specified maximum requirements Pallet type not as specified Load not bonded as specified

Regulatory Requirements. The offeror/contractor is encouraged to use recovered materials in accordance with Public Law 94-580 to the maximum extent practicable.

Preservation, Packing, and Marking. The preservation, packing, and marking shall be as specified in the contract or order.

Source of Government Documents. Copies of Military and Federal documents are available from:

Standardization Documents Order Desk
Bldg. 4D
700 Robbins Avenue
Philadelphia, PA 19111-5094

Sources of Nongovernment Documents.

THE COLOR ASSOCIATION OF THE UNITED STATES

Department of Defense Standard Shades for Sewing Thread

(Application for copies may be obtained from the Color association of the United States, 343 Lexington Ave., New York, NY 10016).

ASTM-D 629 - Nonfibrous materials
ASTM-D 2165 - pH
ASTM-D 3775 - Yarns per inch
ASTM-D 3776 - Weight
ASTM-D 5034 - Breaking strength

(Applications for copies should be addressed to American Society For Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.)

Custodian:
Navy - NU

Civil Agency Coordinating Activity:
GSA - FSS

Preparing Activity:
DLA - CT

Project No. 8445-0122

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:45Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS

1. The preparing activity must complete blocks 1, 2, 3, and 8. In block 1, both the document number and revision letter should be given.
2. The submitter of this form must complete blocks 4, 5, 6, and 7.
3. The preparing activity must provide a reply within 30 days from receipt of the form.

NOTE: This form may not be used to request copies of documents, nor to request waivers, or clarification of requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

I RECOMMEND A CHANGE:	1. DOCUMENT NUMBER	2. DOCUMENT DATE (YYMMDD)
	A-A-55225	930817

3. DOCUMENT TITLE
SCARF, NECKWEAR, WOMAN'S ACRYLIC

4. NATURE OF CHANGE *(Identify paragraph number and include proposed rewrite, if possible. Attach extra sheets as needed.)*

5. REASON FOR RECOMMENDATION

6. SUBMITTER

a. NAME (Last, First, Middle Initial)	b. ORGANIZATION	
c. ADDRESS (Include Zip Code)	d. TELEPHONE (Include Area Code) (1) Commercial (2) AUTOVON (If applicable)	7. DATE SUBMITTED (YYMMDD)

8. PREPARING ACTIVITY

a. NAME Defense Personnel Support Center ATTN: DPSC-FSSD (12-3-D)	b. TELEPHONE (Include Area Code) (1) Commercial (2) AUTOVON
c. ADDRESS (Include Zip Code) 2800 South 20th Street P. O. Box 8419 Philadelphia, Pennsylvania 19101-8419	IF YOU DO NOT RECEIVE A REPLY WITHIN 45 DAYS, CONTACT: Defense Quality and Standardization Office 5203 Leesburg Pike, Suite 1403, Falls Church, VA 22041-3466 Telephone (703) 756-2340 AUTOVON 289-2340

Source: https://assist.dla.mil -- Downloaded: 20261026109:457
Check the source to verify that this is the current version before use.