INCH-POUND
A-A-55226A
October 23, 1996
SUPERSEDING
(see Section 7)

COMMERCIAL ITEM DESCRIPTION

SCARF, NECKWEAR, WOOL AND SCARF, HEADOVER, WOOL

The General Services Administration has authorized the use of this commercial item description for all Federal agencies.

1. SCOPE. This commercial item description covers the requirements for knitted wool scarfs intended for use by personnel of the Department of Defense.

2. CLASSIFICATION. The scarfs shall be of the following types and classes:

Type I -	Neckwear	
Type II	-	Headover
Class 1	-	Olive Green 208
Class 2	-	Gray 1155
Class 4	-	Blue 3346

3. SALIENT CHARACTERISTICS.

3.1 Description. The Type I scarf shall be a tubular seamless type, with open ends. The ends shall be reinforced with a single layer of tape around both ends of the scarf, and overlock stitched (12-16 stitches per inch). The tape ends shall overlap no less than 1/2 inch, and shall be bartacked to the scarf.

The Type II scarf shall be a tubular knit type, with hemmed ends. The ends shall be finished with a double chain stitch (402 or 406) (10-14 stitches per inch). Type I scarfs shall have a label sewn to the inside, with the top of the label positioned 1/2 $\pm$ 1/8 inch below and parallel to the edge. Type II scarfs shall have a label sewn to the inside of the hem and attached in the hem stitches. The finished scarfs shall be pressed flat with the label centered $\pm$ 1 inch (see Figure 1).

Beneficial comments, recommendations, additions, deletions, clarifications, etc. and any data which may improve this document should be sent to: Defense Personnel Support Center, Clothing and Textiles Directorate, Attn: DPSC-FNS, 2800 South 20th Street, Philadelphia, PA 19145-5099.

AMSC N/A ***FSC 8440***

DISTRIBUTION STATEMENT A. ***Approved for public release; distribution is unlimited.***

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:45Z
Check the source to verify that this is the current version before use.

3.2 Material.

3.2.1 Basic material. The basic material for the scarf shall be a flat jersey knit tube made on a circular machine using two ends of 2-ply worsted yarn in each feed. The wool yarn for knitting and for overedging the ends of the scarfs shall be mothproofed, 2-ply worsted yarn made of fleece or pulled sheep's wool, or a combination of both, not lower in grade than 56's US Standard. The face (wale side) of the fabric shall have a lightly brushed finish on both sides of the scarf. The basic material shall conform to the requirements specified in Table I.

3.2.1.1 Color. The color of the finished cloth shall match the standard sample when viewed under tungsten lamps that approximate artificial daylight and that have a correlated color temperature of 7500 ± 200 K (both types), with illumination of 100 ± 20 foot candles, and shall be a good match to the standard sample under incandescent lamplight at 2300 ± 200 K (Type I) and 2800 ± 200 K (Type II).

3.2.2 Thread. The thread for seaming and stitching shall be machine thread, soft finish cotton, 40 Tex, 3 ply. The color of the thread shall match the basic material color. Colorfastness tests and requirements are the same as specified in Table I.

3.2.3 Tape. The cotton tape for reinforcing the scarf ends shall be a 1/4 ± 1/32 inch wide, two up and two down single, or multiple herringbone twill with one or more reversals of the twill across the width of the tape, and woven edges on both sides. The color of the tape shall match the basic material color. Colorfastness tests and requirements are the same as specified in Table I. The finished tape shall conform to the requirements when tested as specified in Table II.

TABLE I. Basic material requirements

Characteristic	Minimum Requirements	Test Methods
Colorfastness to:		
Crocking	3.5 on AATCC Chromatic Transference Scale 2/	AATCC 8
Laundering	"good" 1/ 2/	AATCC 61, 1A 3/
Light	"good" 2/ 4/	AATCC 16, Opt. A
Perspiration	"good" 1/ 2/ 4/	AATCC 15
Courses per inch	10	ASTM-D-3887
Wales per inch	8	ASTM-D-3887
Bursting strength	60 lbs.	ASTM-D-3787
Shrinkage (after 1 laundering cycle)	13 percent	AATCC 96 5/
Wool content (Based on dry weight)	95 percent	AATCC 20
Mothproofing compounds (Percent by weight to be applied to wool fiber)	0.65 min. 1.45 max.	Test Method No. 2015.1 6/

1/ Color transfer equivalent to Step 4 on the Gray Scale for Staining
2/ When a standard sample is available, the scarf shall show colorfastness equal or better than the standard sample.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:45Z
Check the source to verify that this is the current version before use.

3/ The laundering cycle of the launderometer or similar machine shall be 30 minutes, and the temperature of the container shall be maintained at 100°F (38° ± 2°C).
4/ A change in color equivalent to Gray Scale Step 4
5/ The wool laundering procedure shall be used, except the specimens shall be air dried (not tumble dried) and shall not be pressed prior to measuring.
6/ Federal Test Method Standard 191
7/ Mothproofing compounds - Sodium 5-chloro-2-(4-chloro-2-[3-(3,4 dicholorphenyl)-ureido]phenoxyl]benzensulfonate

TABLE II. Tape requirements

Characteristic	Minimum requirements	Test methods
Yarn count and ply		
Warp	40/2 or 20/1	1/ 2/
Filling	60/2 or 30/1	1/ 2/
Yarns per inch	28 ends/inch	2/
	38 picks/inch	2/
Breaking strength (warp)	25 lbs.	ASTM-D-5034
Shrinkage	4.0 percent (max.)	2/ 3/

1/ Cotton count ± 5.0 percent.
2/ Unless otherwise specified, a certificate of compliance shall be submitted and will be acceptable for the stated requirement.
3/ The tape may be preshrunk.

3.3 Labels. A commercial-type label is acceptable, provided that an additional printed cloth label containing the contractor's name, contract number, size and National Stock Number (NSN) is caught on the stitching of the commercial label. The commercial label shall include fiber and laundering information. The laundering instructions shall be as follows:

DRY CLEAN OR HANDWASH GENTLY, IN LUKEWARM SUDS. DO NOT TWIST OR WRING. DRY ON FLAT SURFACE AWAY FROM HEAT. DO NOT TUMBLE DRY.

3.3.1 Label/tag. Each item shall be individually bar-coded with a paper tag for personal clothing items. The paper tag shall be standard bleached sulfate having a basis weight of 100 pounds. The paper used for the tags shall have a smooth finish to accept thermal transfer and direct printing. The tags shall have a hole and shall be attached to each item by a fastener, clearly legible and readable by a scanner. The bar coding element shall be a 13 digit national stock number (NSN). The bar code type shall be a medium to high code density and shall be located so that it is completely visible on the item when it is folded and/or packaged as specified and so that it causes no damage to the item.

3.4 Sizes and measurements. The finished scarfs shall conform to the measurements in Table III.

TABLE III. Finished measurements and weights

Characteristic	Measurement		Tolerance	
	Type I	Type II	Type I	Type II
Width	9 inches	9 inches	± 1/2 inch	± 1 inch

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:45Z
Check the source to verify that this is the current version before use.

Length	54 inches	24 inches	± 1-1/2 inches	± 1 inch
Weight (each)	6.0 ounces	2.8 ounces	Minimum 1/	Minimum 1/

1/ Weight shall be tested in accordance with ASTM-D-3776, option C. Samples shall be conditioned as directed in ASTM-D-1776 prior to testing.

4. REGULATORY REQUIREMENTS. The offeror/contractor is encouraged to use recovered materials to the maximum extent practicable, in accordance with paragraph 23.403 of the Federal Acquisition Regulation (FAR).

5. QUALITY ASSURANCE PROVISIONS

5.1 Product conformance. The products provided shall meet the salient characteristics of this commercial item description, conform to the producer's own drawings, specifications, standards, and quality assurance practices, and be a similar product that is offered for sale in the commercial market. The Government reserves the right to require proof of such conformance.

5.2 Market acceptance criteria. The item offered, or a generic equivalent, must have been sold to the commercial market or to the Government for at least two years.

5.3 Visual examination. Each scarf shall be examined for the defects listed below.

5.3.1 Defects. Any hole, cut, tear, or mend; shade bar; color not as specified; any spot or stain (outside); raw edges; open seams; thread ends not removed; reinforcing tape omitted or improperly applied; rolled puckered, or ragged scarf ends; overedge stitching omitted, broken, or skipped; face of fabric not lightly brushed; scarf not types specified; any operation not as specified; label missing, incorrect, or illegible; measurement of item not as specified; bar code omitted or not readable by scanner; human-readable interpretation (HRI) omitted or illegible; bar code not visible on folded, packaged item; bar code causes damage to the item; any items not packaged in accordance with the contract or purchase order.

5.4 Acceptance criteria. Acceptance criteria shall be as specified in the contract or purchase order.

6. PACKAGING

6.1 Preservation, packing, and marking. The preservation, packing, and marking shall be as specified in the contract or purchase order.

7. NOTES

7.1 Source of Government documents. Copies of military and Federal documents are available from:

Standardization Documents Order Desk
Bldg. 4D
700 Robbins Avenue
Philadelphia, PA 19111-5094

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:45Z
Check the source to verify that this is the current version before use.

7.2 Source of non-Government documents

ASTM Test Methods

(Applications for copies should be addressed to American Society For Testing and Materials (ASTM), 100 Barr Harbor Drive, West Consohocken, PA 19428-2959.)

AATCC Test Method

(Applications for copies should be addressed to American Association of Textile Chemists and Colorists (AATCC), P.O. Box 12215, Triangle Park, NC 27709-2215.)

7.3 Supersession data. This commercial item description supersedes A-A-55226, dated August 27, 1993 and MIL-S-29428A(MC), dated 6 May 1991.

MILITARY INTERESTS:

Custodians:
Army - GL
Navy - NU
Air Force - 99

Review Activities:
Air Force - 82, 45
Navy - MC

CIVIL AGENCY COORDINATING ACTIVITY:
GSA - FSS

PREPARING ACTIVITY:
DLA - CT

Project 8440-0228

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:45Z
Check the source to verify that this is the current version before use.



	Type I	Type II
Width (W)	9 inches	9 inches
Length (L)	54 inches	24 inches

FIGURE 1. Scarf, Neckwear, Wool, and Scarf, Headover, Wool

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:45Z
Check the source to verify that this is the current version before use.