MIL-P-60019A (AR)
AMENDMENT 3
18 March 1982
SUPERSEDING
AMENDMENT 2
30 March 1971

MILITARY SPECIFICATION

PROPELLANT M9
FOR USE WITH CHARGE PROPELLING, M36A1
FOR 4.2 INCH MORTAR

This amendment forms a part of Military Specification MIL-P-60019A (MU), dated 15 January 1969, and is approved for use by the US Army Armament Research and Development Command, and is available for use by all Departments and Agencies of Defense.

3.1, Material; Delete in its entirety and substitute the following:

"3.1, Material. - The propellant shall be M9 flake propellant with an advisory diameter of 0.059 inches and a nominal thickness of 0.008 inches, with a maximum thickness of .009 inches and shall conform to the requirements of Standard MIL-STD-652 (see 4.2.5)."

3.3, Graphite (glaze): Delete "0.20 percent" and substitute "0.40 percent".

PAGE 6

* 4.3.1, Acceptance tests: Add new sentence as follows:

"The test vehicle for all testing shall be the 4.2 Inch H.E. M329A1 cartridge (dwg 8863685), or the 4.2 Inch ~~M335A2 illuminating cartridge (dwg 8886595)~~ inert loaded to the weight of 26.00+ 0.01 pounds, with the M2A2 ignition cartridge (dwg 9252205)."

PAGE 7

4.3.3.2: Delete in its entirety and substitute the following:

FSC 1376

Source: https://assist.dla.mil -- Downloaded: 202610-23T00:04Z
Check the source to verify that this is the current version before use.

"4.3.3.2, Low temperature firings. - For the first ten lots of propellant produced by a manufacturer in accordance with this document, a low temperature uniformity series shall be conducted in addition to the 70°F firings. This series shall consist of 10 rounds assembled in the same manner as 4.3.3.1, but conditioned at a temperature of -50°F prior to firing. Velocity and pressure readiness shall be taken and reported for information only."

PAGE 8

* 6.9, Proving ground test summary: Delete in its entirety and substitute the following:

"6.9.1 Charge assessment. - Each lot of M9 propellant shall be assessed to a muzzle velocity of 355 fps at charge 5 with M329A1 projectile, or with the M335A2 projectile and the M2A2 ignition cartridge.

"6.9.2, Uniformity series

Temperature	Charge	No of Samples	Std dev of MV (max)	Pressure (individual) psi
70°F	5	10	5.0 fps (factored)	2900-4300
-50°F**	5	10	N/A	N/A

**Information only - Discontinued after 10 lots of a producer have been tested."

The margins of this amendment are marked with an asterisk or vertical lines to indicate where changes (additions, modifications, corrections, deletions) from the previous amendment were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous amendment.

Custodians:
Army-AR

Preparing activity:
Army-AR

(project 1376-A199)

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T00:04Z
Check the source to verify that this is the current version before use.