MILITARY SPECIFICATION

ELECTRODES, WELDING, BARE, SOLID, NICKEL-MANGANESE-CHROMIUM-MOLYBDENUM ALLOY STEEL FOR PRODUCING HY-130 WELDMENTS FOR AS-WELDED APPLICATIONS

This amendment forms a part of MIL-E-24355B(SH), dated 16 April 1982, and is approved for use by all Departments and Agencies of the Department of Defense.

PAGE 14

Table X: Delete and substitute:

"TABLE X. Cooling rate parameters.

Type	Nominal weldment plate thickness (inch)	Cooling rate	Figure number	Preheat and interpass temperature (°F)	Heat input (joules per inch)
MIL-140S-1	1	Low	2	275 to 300	40,000 to 45,000
		High	3	150 to 175	25,000 to 30,000

"

Preparing activity:
Navy - SH
(Project 3439-N645)

DISTRIBUTION STATEMENT A Approved for public release; distribution unlimited

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T21:30Z
Check the source to verify that this is the current version before use.