This document has been approved for public release and sale; its distribution is unlimited.

MIL-P-24333(SHIPS)
AMENDMENT-2
17 June 1970
Superseding 1/
AMENDMENT-1
5 May 1969

MILITARY SPECIFICATION

PLASTIC MATERIAL, UNICELLULAR, SHEET, ELASTOMERIC

This amendment forms a part of Military Specification MIL-P-24333(SHIPS), dated 17 June 1968.

Pages 2 and 3

Table II: Delete and substitute:

"Table II - Physical requirements.

Property	Test reference	Type	Requirement
Density, pounds per cubic foot	4.3.4	I	6.0 max.
		IA	8.5 max.
		II	5.5 - 9.0
Compression resistance at 25 percent deflection (p.s.i.)	4.3.5	I	3.0 max.
		IA	7.0 min.
		II	3.0 - 8.0
Water absorption pounds per square foot cut surface (max.)	4.3.6	I	0.1
		IA	0.06
		II	0.1
Compression set, percent, maximum	4.3.7	I	24
		IA	20
		II	24
Dimensional change, length percent maximum	4.3.8		7
Fire resistance			
Burning time-seconds, maximum	4.3.9		8
Char length-inches maximum	4.3.9		3
Oil resistance	4.3.10		No softening or visible swelling
Tensile strength p.s.i., minimum	4.3.12	I	20
		IA	60
		II	60
Ultimate elongation, percent minimum	4.3.12	I	75
		IA	--
		II	100
Tensile, strength of cemented joints, minimum	4.3.13.1		No bond failure
Flexibility at 28°F.	4.3.14.1		No cracking
Shock absorption - Percent rebound (max.) at 70°F. and 0°F.	4.3.15	I	--
		IA	--
		II	15

"

1/ CHANGES FROM PREVIOUS ISSUE. THE OUTSIDE MARGINS OF THIS DOCUMENT HAVE BEEN MARKED "#" TO INDICATE WHERE CHANGES (DELETIONS, ADDITIONS, ETC.) FROM THE PREVIOUS ISSUE HAVE BEEN MADE. THIS HAS BEEN DONE AS A CONVENIENCE ONLY AND THE GOVERNMENT ASSUMES NO LIABILITY WHATSOEVER FOR ANY INACCURACIES IN THESE NOTATIONS. BIDDERS AND CONTRACTORS ARE CAUTIONED TO EVALUATE THE REQUIREMENTS OF THIS DOCUMENT BASED ON THE ENTIRE CONTENT AS WRITTEN IRRESPECTIVE OF THE MARGINAL NOTATIONS AND RELATIONSHIP TO THE LAST PREVIOUS ISSUE.

FSC 9330

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T21:25Z
Check the source to verify that this is the current version before use.