MIL-P-24333(SHIPS)
17 June 1968
SUPERSEDING
MIL-P-15280D(In Part)
3 April 1962
(See 6.3)

MILITARY SPECIFICATION

PLASTIC MATERIAL, UNICELLULAR, SHEET, ELASTOMERIC

1. SCOPE

1.1 Scope. This specification covers chemically expanded unicellular elastomeric plastic foam material for buoyancy and shock absorption applications.

1.2 Classification. Plastic foam shall be of the following types, as specified (see 6.2):

Type I - Buoyant.
Type IA - Buoyant and strength.
Type II - Shock absorbent.

2. APPLICABLE DOCUMENTS

2.1 The following documents of the issue in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein.

SPECIFICATIONS

FEDERAL
C-C-91 - Candles, Illuminating.
PPP-B-576 - Box, Wood, Cleated, Veneer, Paper Overlaid.
PPP-B-591 - Boxes, Fiberboard, Wood-Cleated.
PPP-B-601 - Boxes, Wood, Cleated-Plywood.
PPP-B-621 - Boxes, Wood, Nailed and Lock-Corner.
PPP-B-636 - Box, Fiberboard.
PPP-B-640 - Boxes, Fiberboard, Corrugated, Triple-Wall.

MILITARY
MIL-P-116 - Preservation, Methods of.

STANDARDS

FEDERAL
FED-STD-601 - Rubber: Sampling and Testing.

MILITARY
MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129 - Marking for Shipment and Storage.
MIL-STD-414 - Sampling Procedures and Tables for Inspection by Variable for Percent Defective.

(Copies of specifications, standards, drawings and publications required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal shall apply.

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)
D 471 - Change in Properties of Elastomeric Vulcanizates Resulting from Immersion in Liquids.
D 1667 - Specification and Method of Test for Sponge Made from Closed Cell Poly (Vinyl Chloride) or Copolymers Thereof.

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, Pennsylvania 19103.)

Source: https://assist.dla.mil -- Downloaded: 202610-19T21:25Z
Check the source to verify that this is the current version before use.

UNIFORM CLASSIFICATION COMMITTEE
Uniform Freight Classification Rules.

(Application for copies should be addressed to the Uniform Classification Committee, 202 Union Station, 516 West Jackson Boulevard, Chicago, Illinois 60606.)

(Technical society and technical association specifications and standards are generally available for reference from libraries. They are also distributed among technical groups and using Federal agencies.)

3. REQUIREMENTS

3.1 Material. The material shall be a flexible foam composed of a multitude of individual closed cells of uniform size, free of extraneous and degrading matter, and of seams.

3.2 Type, dimension, and tolerance. The dimensions and type of plastic foam material shall be as specified (see 6.2). Unless otherwise specified (see 6.2), tolerances shall be as specified in table I.

Table I - Dimensional tolerances of sheets.

Thickness (Inches)		Length and width (Inches)	
Dimension	Tolerance	Dimension	Tolerance
Sheets			
Up to 1/4,	± 1/32	Up to 6, inclusive	± 1/4 inch
Over 1/4 to 1/2,	± 1/16	Over 6 to 12, inclusive	± 3/8 inch
Over 1/2 to 1,	± 3/32	Over 12	± 3 percent
Over 1	± 1/8		

3.3 Finish. Unless otherwise specified (see 6.2), sheets shall have at least one surface skin. The material, when furnished, shall not contain tears and shall not have been repaired.

3.4 Color. The color of the plastic foam material shall be at the option of the contractor unless otherwise specified (see 6.2).

3.5 Physical requirements. The material shall conform to the additional requirements shown in table II when tested as specified in 4.3.

Table II - Physical requirements.

Property	Test reference	Type	Requirement
Density, pounds per cubic foot	4.3.4	I	6.0 max.
		IA	8.5 max.
		II	5.5 - 9.0
Compression resistance at 25 percent deflection, (p.s.i.)	4.3.5	I	3.0 max.
		IA	7.0 max.
		II	3.8
Water absorption (percent by weight) maximum	4.3.6	I	.01
		IA	.06
		II	.01
Compression set, percent, maximum	4.3.7	I	24
		IA	20
		II	24
Dimensional change, length percent maximum	4.3.8		7
Fire resistance			
Burning time-seconds, maximum	4.3.9		8
Char length-inches maximum	4.3.9		3
Oil resistance	4.3.10		No softening or visible swelling
Tensile strength p.s.i., minimum	4.3.12	I	20
		IA	60
		II	60
Ultimate elongation, percent minimum	4.3.12	I	75
		IA	—
		II	100

Source: https://assist.dla.mil -- Downloaded: 202610-19T21:25Z
Check the source to verify that this is the current version before use.

Table II - Physical requirements. (Continued)

Property	Test reference	Type	Requirement
Tensile, strength of cemented joints, minimum	4.3.13.1		No bond failure
Flexibility at 28°F.	4.3.14.1		No cracking
Shock absorption - Percent rebound (max.) at 70°F. and 0°F.	4.3.15	I	—
		IA	—
		II	15

3.6 Odor. The material shall be free from objectionable odor when tested as specified in 4.4.11.

3.7 Adhesive cement. When specified (see 6.2), the manufacturer shall recommend an adhesive which shall be suitable for permanently securing the plastic foam material to itself and to applied structures under the stated conditions. Recommended adhesive shall not adversely affect, initially or in service, the plastic foam materials (see 3.1, 3.2, 3.3 and 3.5), or the surfaces on which it may be applied.

3.7.1 Instruction sheet for adhesive cement. When specified (see 6.2), the manufacturer of the plastic foam material shall also provide instruction sheets for adhesive cement recommended (see 3.7). The instruction sheet shall contain the following information:

(a) Names and addresses of adhesive manufacturers.
(b) Adhesive manufacturer's commercial designation and code number.
(c) Installation instructions including application to a substrate when specified and described (see 6.2).
(d) Handling precautions (if any).

3.8 Protective covering or coating. Plastic foam material which is subject in use to adverse conditions, (severe abrasion, puncture, outdoor weathering, ozone or ultra-violet radiation and others) may require a coating or covering. The covering shall not adversely affect or be affected by the plastic foam material, or the adhesive. If the purchasing activity specifies conditions of exposure (see 6.2), the plastic foam supplier shall furnish recommendations for an appropriate protective covering and methods of application. The instruction sheet shall contain the same type of information as required in 3.7.1.

3.9 Workmanship. Workmanship shall be in accordance with the requirements of this specification.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the supplier may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.2 Sampling for inspection. Sampling for inspection shall be performed in accordance with the provisions set forth in MIL-STD-105, except where otherwise indicated. For purposes of sampling an inspection lot for examination shall consist of all material of the same type and thickness, produced in one plant under essentially the same conditions and offered for delivery at one time. The unit of product shall consist of one sheet of type I, IA, or II material as applicable.

4.2.1 Inspection of materials. In accordance with 4.1 above, the supplier is responsible for insuring that materials used were manufactured, tested, and inspected in accordance with the requirements of referenced subsidiary specifications and standards to the extent specified, or, if none, in accordance with this specification. In the event of conflict, this specification shall govern.

4.2.2 Quality conformance inspection.

4.2.2.1 Examination. An examination shall be made in accordance with the classification of defects, inspection levels, and acceptable quality levels (AQLs) as specified herein. The lot size, for the purpose of determining the sample size in accordance with MIL-STD-105, shall be expressed in units of sheets as specified, for examination in 4.2.2.1.1, 4.2.2.1.2, and in units of shipping containers for examination in 4.2.2.1.3.

4.2.2.1.1 Examination for defects in appearance and workmanship. The sample unit for this examination shall be one sheet or tube, as applicable.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T21:25Z
Check the source to verify that this is the current version before use.

Examine	Defect
Appearance	Any cut, tear, seam, or repaired section. Surface skin missing or not as specified. Presence of dirt, foreign material, embedded particles, large voids.
Workmanship	Cell size not uniform. Color not uniform throughout material.

4.2.2.1.2 Examination for dimensional defects. The sample unit for this examination shall be one sheet.

Examine	Defect
Type	Type not as specified.
Length and width	Varies by more than the applicable tolerance specified in table I.
Thickness	Varies by more than the applicable tolerance specified in table I.

4.2.2.1.3 Examination of preparation for delivery. An examination shall be made to determine that packaging, packing, and markings comply with the requirements of section 5 of this specification. The sample unit for this examination shall be one shipping container, fully packed, selected just prior to the closing operation. Shipping containers fully prepared for delivery shall be examined for closure defects.

Examine	Defect
Packaging	Unit container not packaged as specified. Packaging material not as required. Interleaving of sheets omitted not as specified.
Packing	Not in accordance with contract requirements. Not level specified. Container not as specified, closure not accomplished by specified methods or materials. Inadequate application of components.
Instruction sheets	Instruction sheet for adhesive cement missing or not as specified (see 3.7), when required. Instruction sheet for protective covering or coating missing or not as specified, when required.
Count	Less than specified or indicated quantity.
Weight	Gross weight exceeds contract requirements.
Markings	Interior or exterior markings (as applicable) omitted, illegible, incorrect, or not in accordance with contract requirements.

4.2.2.1.4 Inspection levels and acceptable quality levels for examination. The inspection levels for determining the sample size and the AQL expressed in defects per 100 units, shall be as follows:

Examination paragraph	Inspection level	AQL
4.2.2.1.1	I	2.5
4.2.2.1.2	I	2.5
4.2.2.1.3	I	2.5

4.2.3 Sampling for quality conformance tests. A random sample of material shall be selected from each lot for shipment in accordance with Inspection Level II of MIL-STD-414. A lot for quality conformance tests shall be as described in 4.2.

4.2.4 Quality conformance tests. Samples selected in accordance with 4.2.3 shall be subjected to all of the tests of 4.3 and table II as applicable. If the samples are of such size or shape that test specimens cannot be prepared from them, a substitute sample shall be provided in the form of a piece or pieces of plastic foam having dimensions appropriate for the test required. The substitute samples shall be certified to be of the same material and to be representative of the lot of finished items offered for delivery. The AQL shall be 2.5 percent for each of these tests. Computations shall be accomplished as shown in section B of MIL-STD-414. However, if the result of any test can only be expressed as pass or fail, sampling shall be in accordance with Inspection Level I of MIL-STD-105 with an AQL of 2.5 percent.

Source: https://assist.dla.mil -- Downloaded: 20260-19T21:25Z
Check the source to verify that this is the current version before use.

4.3 Method of tests.

4.3.1 Conditioning procedures. Unless otherwise specified, all tests shall be conducted at a temperature of 70° ± 5°F., on specimens conditioned for at least 5 hours in the same atmosphere prior to testing. In case of dispute, specimens shall be conditioned at an atmosphere of 73.5° ± 2°F., and 50 plus or minus 2 percent relative humidity for at least 24 hours and tested at the same atmospheric conditions.

4.3.2 Dimensional measurements of test specimens.

4.3.2.1 Results. Results reported shall be the average of a minimum of three measurements.

4.3.2.2 Sheet. Unless otherwise specified, the length and width shall be measured with a suitable measuring device graduated in 1/16 inch. Care shall be taken not to distort the flexible unicellular material. Thickness shall be determined in accordance with method 12031 of FED-STD-601. Three measurements equally spaced over the specimen shall be made.

4.3.3 Weight measurement. Unless otherwise specified, all test specimens shall be weighed to the nearest 0.1 gram.

4.3.4 Density. The density of the material shall be determined by the procedure specified in ASTM D 1667.

4.3.5 Compression resistance. Compression resistance shall be determined in accordance with method 12151 of FED-STD-601, except that the deflection shall be maintained at 25 percent with automatic or manual control, and the load observed and recorded 60 seconds after the 25 percent deflection is reached.

4.3.6 Water absorption.

4.3.6.1 Specimens. Test specimens shall be 4 by 4 inches square in the thickness furnished. The specimen may have the natural skin on top and bottom, outer and inner surfaces, or on only one or none of these surfaces, as specified in 6.2.

4.3.6.2 Procedure. Three specimens shall be submerged in distilled water at room temperature (65° to 95°F.) 2 inches below the surface of the water and subjected to a vacuum of 25 inches of mercury for 3 minutes. Release the vacuum and allow the specimen to remain submerged for 3 minutes at an atmospheric pressure. Remove the specimen, allow to stand on end to drain for 10 minutes and blot lightly with paper towels. Values of each of the three specimens shall be calculated and reported in terms of pounds of water gain per square foot of skinless surface.

4.3.7 Compression set.

4.3.7.1 Specimens. The specimens shall have parallel top and bottom surfaces which shall be at right angles to the side surfaces. The specimen may be rectangular. The minimum dimension across the top shall be at least equal to the thickness. The top shall be not less than one square inch in area and not more than 16 square inches in area.

4.3.7.2 Procedure. The compression set of the material shall be determined in accordance with ASTM D 1667 except that the maximum dimension across the top of the specimen shall be not more than 16 square inches in area.

4.3.8 Dimensional change.

4.3.8.1 Specimens. Test specimens shall consist of pieces 12 inches by 3 inches by the thickness of the sheet supplied.

4.3.8.2 Procedure. Bench marks, approximately 10 inches apart, shall be placed on the center line of the specimens about one inch from the ends and the distance measured to the nearest 0.01 inch. The specimens shall be placed lengthwise on a piece of wooden board in an oven equipped with air circulation at 200° ± 3°F. for seven days. The specimen shall be removed from the oven, conditioned for a minimum of 2 hours at 70° ± 5°F. and the distance between the bench marks measured. The dimensional change shall be expressed in percent of the original length.

4.3.9 Fire resistance.

4.3.9.1 Specimens. The test specimens shall be 1/4 inch in thickness, 1/2 inch in width and approximately 6 inches in length.

4.3.9.2 Procedure. The specimens shall be clamped at one end in a position such that the long dimension forms a 45 degree angle down from the horizontal plane of the clamp and with the width in a vertical position. A candle flame shall be applied to the lower or free end of the specimen for 15 seconds. The candle shall

Source: https://assist.dla.mil -- Downloaded: 202610-19T21:25Z
Check the source to verify that this is the currentversion before use.

then be removed and the time that the specimen continues to burn after removal of the candle shall be recorded as burning time. The length of char shall also be recorded. The candle shall conform to class B of C-C-91, and the test shall be performed in a location free from drafts.

4.3.10 Oil resistance.

4.3.10.1 Specimens. The test specimens shall be not less than 1 inch by 1 inch by the thickness of the material.

4.3.10.2 Procedure. The specimen shall be immersed in ASTM No. 3 oil of ASTM D 471 for 70 hours. The specimen shall then be removed, blotted with filter paper, and compared to an untreated specimen of similar size for apparent softness and visible swelling.

4.3.11 Odor. The odor of sheets at room temperature shall be determined by sniffing.

4.3.12 Tensile strength and ultimate elongation.

4.3.12.1 Specimens. The test specimens shall be 1/2 plus or minus 1/16 inch thick. Die I of method 4111 of FED-STD-601 shall be used. The specimens shall have the number of skins specified in 6.2.

4.3.12.2 Procedure. The tensile strength and ultimate elongation shall be determined by methods 4111 and 4121, respectively, of FED-STD-601, with the following exceptions:

(a) A 0.5 ounce weight shall be used on the presser foot for measurement of thickness.
(b) The number of test specimens and test values shall conform to the requirements of MIL-STD-414.
(c) All values shall be reported.
(d) Median values shall not apply.

4.3.13 Strength of cemented joints.

4.3.13.1 Procedure. Test specimens conforming to 4.3.12.1 shall be cut in half at the center of the constricted portion and cemented together in accordance with manufacturer's recommendations (see 3.7.1). Allow to air dry for at least 24 hours. The strength of the cemented joint shall be determined as specified in 4.3.12. The number of specimens shall be that given in 4.3.12.2. The values reported shall be stated as either pass or fail.

4.3.14 Flexibility at 28°F.

4.3.14.1 Procedure. Test specimens shall have skin on one side, or no skin, as specified in 6.2. The size of the specimen shall be approximately 1 inch by 8 inches with a thickness of 1/4 plus or minus 1/16 inch. The test specimens and equipment shall be conditioned for at least 4 hours at 28° ± 2°F. and bent 180 degrees around a 1/2 inch diameter steel mandrel within 5 seconds at the test temperature. Care shall be taken to avoid warming the test specimens, particularly at or near the bend point, in performing the test.

4.3.15 Shock absorption (type II only). Specimens, 4 by 4 inch in cross section by thickness of the specimen furnished shall be conditioned for 24 hours at 70 ± 2°F. and at 0 ± 2°F. respectively. The specimen shall be tested on a Bashore Resiliometer at 70 ± 2°F. and 0 ± 2°F. respectively and the percent rebound read directly from the instrument.

4.4 Examination of preparation for delivery. The packaging, packing, and marking shall be examined to determine compliance with the requirements of section 5 of this specification.

4.5 Three copies of Government inspection reports shall be forwarded to the procuring activity via the inspector, who shall certify that the examination and tests were conducted under his supervision and in accordance with the requirements of this specification.

5. PREPARATION FOR DELIVERY

(The preparation for delivery requirements specified herein apply only for direct Government procurements. Preparation for delivery requirements of referenced documents listed in section 2 do not apply unless specifically stated in the contract or order. Preparation for delivery requirements for products procured by contractors shall be specified in the individual order.)

5.1 Domestic shipment and early material use.

5.1.1 Packaging. Packaging shall be sufficient to afford adequate protection against deterioration and physical damage during shipment from the supply source to the using activity and until early installation and may conform to the supplier's commercial practice when such meets these requirements.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T21:25Z
Check the source to verify that this is the current version before use.

5.1.2 Packing. Packing shall be accomplished in a manner which will insure acceptance by common carrier at the lowest rate and will afford protection against physical and mechanical damage during direct shipment from the supply source to the using activity for early installation. The shipping containers or method of packing shall conform to the Uniform Freight Classification Rules or other carrier regulations as applicable to the mode of transportation and may conform to the supplier's commercial practice when such meets these requirements.

5.1.3 Marking. Shipment marking information shall be provided on interior packages and exterior shipping containers in accordance with the supplier's commercial practice. The information shall include nomenclature, Federal stock number or manufacturer's part number, contract or order number, type, size, thickness, supplier's name, and destination.

5.2 Domestic shipment and storage or overseas shipment. The requirements and levels of packaging, packing, and marking for shipment shall be specified by the procuring activity (see 6.2).

(5.2.1 The following provides various levels of protection during domestic shipment and storage or overseas shipment, which may be required when procurement is made (see 6.2).

5.2.1.1 Packaging. Packaging shall be level A or C as specified (see 6.2).

5.2.1.1.1 Level A. Sheets shall be packaged in accordance with method III of MIL-P-116 as specified herein. Sheets shall be packaged flat and interleaved with paper or other suitable material to prevent adhesion of sheets during shipment and storage. Sheets shall then be packed to the level and quantity specified (see 6.2).

5.2.1.1.2 Level C. Packaging shall be sufficient to afford adequate protection against deterioration and physical damage during shipment from the supply source to the using activity and until early installation and may be in accordance with the manufacturer's commercial practice.

5.2.1.2 Packing. Packing shall be level A or B as specified (see 6.2).

5.2.1.2.1 Level A. Sheets, packaged as specified (see 6.2), shall be packed in snug containers conforming to any one of the following specifications at the option of the supplier:

Specification	Type or class
PPP-B-576	Class 2
PPP-B-591	Overseas type
PPP-B-601	Overseas type
PPP-B-621	Class 2
PPP-B-636	Class weather resistant
PPP-B-640	Class 2

All corner and edge seams and manufacturer's joints of fiberboard boxes shall be sealed with tape in accordance with the appendix to the applicable fiberboard box specification. Box closure, strapping or banding shall be in accordance with the applicable box specification or appendix thereto. The gross weight of wood or wood-cleated boxes shall not exceed 200 pounds; fiberboard boxes shall not exceed the weight limitations of the applicable fiberboard box specifications.

5.2.1.2.2 Level C. Sheets, packaged as specified (see 6.2), shall be packed as specified in 5.2.1.2.1, except containers shall be class 1 or domestic type.

5.2.1.3 Marking. In addition to any special marking required by the contract or order (see 6.2) interior packages and exterior shipping containers shall be marked in accordance with MIL-STD-129.

6. NOTES

6.1 Intended use. The materials covered by this specification are intended for buoyancy and shock absorption applications.

6.1.1 Type I. Type I material is intended primarily for buoyancy application; making sealed cell construction and very low water absorption characteristics mandatory. This material is applicable to life preservers.

6.1.1.1 Type IA material is intended for buoyancy application where strength is also required. This material must have the buoyant characteristics of type I material and in addition high compressive and tensile strength. This material is used for ring buoys.

Source: https://assist.dla.mil -- Downloaded: 202610-19T21:25Z
Check the source to verify that this is the currentversion before use.

6.1.2 Type II. This material is intended for shock absorbing applications. The outstanding characteristic for this material is high impact energy absorbing properties. This material is suitable for aircraft carrier ramp pads and padding.

6.2 Ordering data. Procurement documents should specify the following:

(a) Title, number, and date of this specification.
(b) Type required (see 1.2 and 3.2).
(c) Dimensions required and tolerance, if other than as specified (see 3.2).
(d) Location of skin or whether skin is unacceptable (see 3.3).
(e) Whether color is required (see 3.4).
(f) Adhesive requied (see 3.7 and 3.7.1).
(g) Number of sheets and quantity of adhesive required.
(h) Whether a protective covering or other coating is required (see 3.8).
(i) Packaging, packing, or marking requirements other than required by 5.1 and 5.2.

6.3 Supersession data. This specification includes the requirements of types I, IA, and III of MIL-P-15280D which are now types I, IA, and II of MIL-P-24333(SHIPS).

Preparing activity:
Navy - SH
(Project 9330-N409)

Source: https://assist.dla.mil -- Downloaded: 202610-19T21:25Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

OMB Approval
No. 22-R255

INSTRUCTIONS: *The purpose* of this form is to solicit beneficial comments which will help achieve procurement of suitable products at reasonable cost and minimum delay, or will *otherwise enhance use of* the document. DoD contractors, government activities, or manufacturers/vendors who are prospective suppliers of the product are invited to submit comments to the government. *Fold on lines on reverse* side, staple in corner, and send to preparing activity. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to *amend* contractual requirements. Attach any pertinent data which may be of use in improving this document. If there are additional papers, attach to form and place both in an envelope addressed *to preparing* activity.

DOCUMENT IDENTIFIER AND TITLE

NAME OF ORGANIZATION AND ADDRESS

CONTRACT NUMBER

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE DOCUMENT CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A. GIVE PARAGRAPH NUMBER AND WORDING.

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY DOCUMENT REQUIREMENT CONSIDERED TOO RIGID

3. IS THE DOCUMENT RESTRICTIVE?

☐ YES ☐ NO *(If "Yes", in what way?)*

4. REMARKS

SUBMITTED BY *(Printed or typed name and address - Optional)*

TELEPHONE NO.

DATE

DD FORM 1 JAN 72 1426 REPLACES EDITION OF 1 JAN 66 WHICH MAY BE USED

S/N 0102-014-1802

Source: https://assist.dla.mil -- Downloaded: 20261O-19T21:25Z
Check the source to verify that this is the current version before use.

FOLD

POSTAGE AND FEES PAID

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

Commander, Naval Ship EngineeringCenter
(Code 6124) Center Building
Prince George's Center
Hyattsville MD 20782

FOLD

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T21:25Z
Check the source to verify that this is the current version before use.