MIL-P-24364/1(SHIPS)
AMENDMENT 3
16 April 1984
SUPERSEDING
AMENDMENT 2
5 January 1973

MILITARY SPECIFICATION SHEET

PLASTIC SHEETS, LAMINATED, THERMOSETTING ELECTRICAL-INSULATING SHEET, POLYESTER GLASS-MAT GRADE GPO N-1 (CLASSES 130, 155, AND 180)

This amendment forms a part of Military Specification Sheet MIL-P-24364/1(SHIPS), dated 11 July 1969, and is approved for use by the Naval Sea Systems Command, Department of the Navy and is available for use by all Departments and Agencies of the Department of Defense.

PAGE 2

Table I, column 5, line 10: Delete "P.S.T." and substitute "P.S.I.".

PAGES 2, 3 and 4

* Tables I, II and III, title: Delete "Qualification tests" and substitute "First article inspection".

Tables I, II and III: Dielectric breakdown parallel to laminations, conditioning "336/50 water", 1/8 inch thickness delete "25" and substitute "15" and 1/2 inch thickness delete "30" and substitute "15".

Tables I, II and III: Dielectric Constant, Values required for each thickness 1/8 inch: Delete "5.0, 6.0, 4.5 and 5.5" and substitute "6.0, 6.5, 5.0 and 6.0" respectively.

Tables I, II and III: Dissipation Factor, Value required for each thickness 1/8 inch, delete "0.05" and substitute "0.10".

Tables I, II and III: Water absorption, under 1/16 inch thickness delete "0.8" and substitute "0.9", under 1/8 inch thickness delete "0.5" and substitute "0.6", under 1/2 inch thickness delete "0.3" and substitute "0.35".

PAGES 2 and 4

Tables I and III: Delete "Wet tracking" requirements in its entirety. Delete footnote "1/".

FSC 9330

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T21:32Z
Check the source to verify that this is the current version before use.

PAGE 5

Table IV, column 2, line 2: Delete "4.7.10" and substitute "4.7.5" and on line 3, delete "4.7.1" and substitute "4.7.10".

Table IV, Dielectric breakdown parallel to laminations, under values required for each thickness range, delete "25" and substitute "15", delete "30" and substitute "15", delete "35" and substitute "15".

Table IV, Flexural strength, under values required for each thickness range delete "16,000" in columns 6, 7 and 9 and substitute "18,000", delete "14,000" in column 10 and substitute "18,000".

NOTE: The margins of this amendment are marked with an asterisk to indicate where changes (additions, modifications, corrections, deletions) from the previous amendment were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous amendment.

Preparing activity:
Navy - SH
(Project 9330-NB08)

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T21:32Z
Check the source to verify that this is the current version before use.