INCH-POUND

MIL-C-823K
21 September 1990
SUPERSEDING
MIL-C-823J
21 December 1983

MILITARY SPECIFICATION

# CLOTH, SERGE, WOOL, WOOL AND NYLON, POLYESTER AND WOOL

This specification is approved for use by all Departments and Agencies of the Department of Defense.

## 1. SCOPE

1.1 Scope. This specification covers wool, wool and nylon, and polyester and wool serge cloth.

1.2 Classification. The cloth shall be of the following types and classes as specified (see 6.2 and 6.5):

| | | |
|---|---|---|
| Type I | - | Wool |
| Class 1 | - | 18 ounce |
| Class 2 | - | 16 ounce |
| Class 3 | - | 16 ounce |
| Class 5 | - | 15 ounce |
| Class 7 | - | 12 ounce |
| Class 8 | - | 12 ounce |

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be used in improving this document should be addressed to: U.S. Army Natick Research, Development, and Engineering Center, Natick, MA 01760-5014 by using the Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

AMSC N/A FSC 8305

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T11:32Z
Check the source to verify that this is the current version before use.

| | | |
|---|---|---|
| Type II | - | Wool and nylon |
| Class 1 | - | 18 ounce |
| Class 2 | - | 16 ounce |
| Type III | - | Polyester and wool |
| Class 1 | - | 14 ounce |
| Class 2 | - | 12 ounce |
| Class 3 | - | 11.3 ounce |

2. APPLICABLE DOCUMENTS

2.1 Government documents.

2.1.1 Specifications, standards, and handbooks. The following specifications, standards, and handbooks form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those listed in the issue of the Department of Defense Index of Specifications and Standards (DODISS) and supplement thereto, cited in the solicitation (see 6.2).

SPECIFICATIONS

FEDERAL

PPP-P-1132 - Packaging of Woolen, Worsted and Wool Blend (Synthetic Fiber; Cotton) Fabrics

MILITARY

MIL-C-43665 - Cloth Wool: Mothproofing Treatment of

STANDARDS

FEDERAL

FED-STD-191 - Textile Test Methods

MILITARY

MIL-STD-655 - Provisions for Evaluating Quality of Cloth, Wool, Worsted and Wool Blends

(Unless otherwise indicated, copies of federal and military specifications, standards, and handbooks are available from the Standardization Documents Order Desk, Building 4D, 700 Robbins Avenue, Philadelphia, PA 19111-5094.)



Source: https://assist.dla.mil -- Downloaded: 2026-10-16T11:32Z
Check the source to verify that this is the current version before use.

2.1 2 Other Government documents, drawings, and publications. The following other Government documents, drawings, and publications form a part of this specification to the extent specified herein. Unless otherwise specified, the issues are those cited in the solicitation.

FEDERAL TRADE COMMISSION

Rules and Regulations Under the Wool Products Labeling Act of 1939

(Copies may be obtained from the Federal Trade Commission, Pennsylvania Avenue at Sixth Street, N.W., Washington, DC 20580.)

U S DEPARTMENT OF AGRICULTURE (USDA)

Methods of Test for Grades of Wool Top

(Copies may be obtained from the U.S. Department of Agriculture, Agricultural Marketing Service, Washington, DC 20402.)

2.2 Non-Government publications. The following documents form a part of this document to the extent specified herein Unless otherwise specified, the issues of the documents which are DOD adopted are those listed in the issue of the DODISS cited in the solicitation. Unless otherwise specified, the issues of documents not listed in the DODISS are the issues of the documents cited in the solicitation (see 6.2).

AMERICAN ASSOCIATION OF TEXTILE CHEMISTS AND COLORISTS (AATCC)

Chromatic Transference Scale

(Application for copies should be addressed to the American Association of Textile Chemists and Colorists, P.O. Box 12215, Research Triangle Park, NC 27709-2215.)

(Non-Government standards and other publications are normally available from the organizations that prepare or distribute the documents. These documents also may be available in or through libraries or other informational services.)

2.3 Order of precedence. In the event of a conflict between the text of this document and the references cited herein, the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.



Source: https://assist.dla.mil -- Downloaded: 2026-10-16T11:32Z
Check the source to verify that this is the current version before use.

3. REQUIREMENTS

3.1 First article. When specified (see 6.2), a sample shall be subjected to first article inspection (see 6.3), in accordance with 4.3.

3.2 Standard sample. The finished cloth shall match the standard sample for shade, finish and appearance and shall be equal to or better than the standard sample with respect to all characteristics for which the standard sample is referenced (see 6.4).

3.3 Material. It is encouraged that recycled material be used when practical as long as it meets the requirements of this specification.

3.3.1 Wool. The wool component of the cloth shall be not lower than the grades specified below:

Types I and II

Class 1 (18 oz.) - 60's U.S. Standard
Class 2 (16 oz.) - 60's U.S. Standard
Class 3 (16 oz.) - 64's U.S. Standard
Class 5 (15 oz.) - 62's U.S. Standard
Class 7 (12 oz.) - 64's U.S. Standard
Class 8 (12 oz.) - 64's U.S. Standard

Type III

Class 1 (14 oz.) - 64's U.S. Standard
Class 2 (12 oz.) - 64's U.S. Standard
Class 3 (11.3 oz.) - 64's U.S. Standard

3.3.1.1 Type I. The wool top for type I shall be fleece wool, pulled wool, or any combination thereof not lower in grade than specified in 3.3.1 and shall be of suitable staple length to meet the requirements of this document. The use of laps, noils, or any other wool manufacturing by-products is prohibited (see 4.4.2).

3.3.1.2 Type II. The blend for type II shall consist of fleece wool, pulled wool, or any combination thereof not lower in grade than specified in 3.3.1 and nylon top or cut tow (see 6.2). Unless otherwise specified (see 6.2), the blend shall be in such proportion that the finished cloth shall contain between 80 to 85 percent wool with the remaining percentage of nylon fiber, based on the oven-dry weight when tested as specified in 4.4.4. The nylon fibers shall be of suitable denier and the wool and nylon fibers of suitable length to meet the requirements of this document. The use of laps, noils, or any other wool manufacturing by-products and nylon fiber waste is prohibited (see 4.4.2).

3.3.1.3 Type III. The blend for type III shall consist of fleece wool, pulled wool, or any combination thereof not lower in grade than specified in 3.3.1 and polyester top or cut tow (see 6.2). The polyester stock shall be semi-dull,



Source: https://assist.dla.mil -- Downloaded: 2026-10-16T11:32Z
Check the source to verify that this is the current version before use.

and the minimum average fiber length shall be 3 inches. The denier shall be suitable to blend adequately with the specified wool grade and meet the requirements of this document. The use of laps, noils, or any other wool manufacturing by-products and polyester fiber waste is prohibited (see 4.4.2). The finished cloth shall consist of the following fiber percentages based on the oven dry weight when tested as specified in 4.4.4:

| | Percentage | |
|---|---|---|
| | Minimum | Maximum |
| Polyester fiber | 55 | 60 |
| Wool fiber | 40 | -- |

3.3.2 Yarn. The yarn for the warp and the filling shall be spun from combed top. The yarn ply shall be as specified in table I.

NOTE: Selvage yarns. To prevent edges of all types of cloth from building up when rolled, 2-ply yarns used in the selvage may be made of a finer count than those used in the body of the cloth.

3.4 Color. The color shall be as specified (see 6.2). The color of the finished cloth shall match the standard sample (see 6.4 and 6.6.1). The color shall be applied in stock or top form. Speck dyeing is prohibited. When Army Green 44 is specified, the color shall be produced by blending dyed wool top (see 6.6). When Army Green 489 is specified, the color shall be produced by blending dyed wool top and dyed polyester fiber (see 6.5).

3.4.1 Mothproofing. Mothproofing of the wool material in accordance with MIL-C-43665, shall be accomplished during stock or top dyeing and tested as specified in 4.4.4.

3.4.2 Matching. The color of the finished cloth shall match the standard sample when viewed under filtered tungsten lamps that approximate artificial daylight and that have a correlated color temperature of 7500 $\pm$ 200K, with illumination of 100 $\pm$ 20 foot candles, and shall be a good match to the standard sample under incandescent lamplight at 2300 $\pm$ 200K.

3.4.3 Colorfastness. The finished cloth shall show fastness to wet drycleaning, perspiration and light (after 80 standard fading hours) equal to or better than the standard sample or equal to or better than a rating of "good". In addition, the type III, polyester and wool, shall show "good" fastness to dry heat (sublimation). The finished cloth shall show fastness to crocking equal to or better than the standard sample or shall have an AATCC Chromatic Transference Scale rating of not lower than 3.5. Testing shall be as specified in 4.4.4.



Source: https://assist.dla.mil -- Downloaded: 2026-10-16T11:32Z
Check the source to verify that this is the current version before use.

3.5 Physical requirements The finished cloth shall conform to the requirements specified in table I when tested as specified in 4.4.4.

TABLE I. Physical requirements

| Type | Class | Weight per linear yard on a 56 inch width basis (minimum) | Yarn ply | | Yarns per inch (minimum) | | Breaking strength (minimum) | | Shrinkage (maximum) | |
|---|---|---|---|---|---|---|---|---|---|---|
| | | | Warp | Filling | Warp | Filling | Warp | Filling | Warp | Filling |
| | | Ounces | | | | | Lbs. | Lbs. | Pct. | Pct. |
| I | 1 | 18.0 | 2 | 2 | 68 | 54 | 110 | 100 | 4.0 | 2.5 |
| I | 2 | 16.0 | 2 | 1 | 70 | 54 | 100 | 80 | 4.0 | 2.5 |
| I | 3 | 16.0 | 2 | 2 | 68 | 64 | 100 | 90 | 4.0 | 3.0 |
| I | 5 | 15.0 | 2 | 2 | 70 | 58 | 100 | 80 | 5.0 | 3.0 |
| I | 7 | 12.0 | 2 | 2 | 74 | 70 | 80 | 70 | 5.0 | 3.0 |
| I | 8 | 12.0 | 2 | 2 | 70 | 62 | 80 | 70 | 5.0 | 3.0 |
| II | 1 | 18.0 | 2 | 1 | 66 | 52 | 135 | 120 | 4.0 | 2.5 |
| II | 2 | 16.0 | 2 | 1 | 70 | 54 | 120 | 110 | 4.0 | 2.5 |
| III | 1 | 14.0 | 2 | 1 | 78 | 55 | 175 | 130 | 4.0 | 3.0 |
| III | 2 | 12.0 | 2 | 2 | 74 | 68 | 150 | 125 | 4.0 | 3.0 |
| III | 3 | 11.3 | 2 | 2 | 78 | 68 | 140 | 125 | 2.0 | 2.0 |
| | | 12,3 (max.) | | | | | | | | |

3.5.1 Width. The width of all types and classes of finished cloth shall be a minimum of 60 inches exclusive of selvage or exclusive of tuck-in, when woven on Sulzer-type looms.

3.5.2 Weave. The weave for all types and classes of finished cloth shall be a 2 up and 2 down, 4 harness right twill (see 4.4.4).

3.6 Finish. The cloth shall be fulled and sheared and shall be otherwise finished so as to provide stability of both color and finish (see 6.7). The type and character of finish shall conform to that shown by the standard sample.

3.6.1 Pilling. The type III cloth shall be finished to show no more pilling than the standard sample when tested as specified in 4.4.4.

3.6.2 pH. The pH value of the water extract of the finished cloth shall be no less than 5.5 nor more than 8.5 when tested as specified in 4.4.4.

3.7 Length and put-up. Unless otherwise specified (see 6.2), the cloth shall be furnished in continuous lengths, each not less than 50 yards. Each length shall be put-up on full width rolls as specified in 5.1.



Source: https://assist.dla.mil -- Downloaded: 2026-10-16T11:32Z
Check the source to verify that this is the current version before use.

3.8 Wool content. The finished type I cloth shall contain no less than 95 percent wool based on the dry weight of the specimen when tested as specified in 4.4.4.

3.9 Wool content label. The cloth shall be labeled in accordance with the Wool Products Labeling Act (see 2.1).

3.10 Marking. The back of the cloth shall be marked "BACK" at both ends of each roll with letters not less than 1/2 inch in height (see 4.4.3.3). The marking shall be clearly legible in any indelible marking medium used commercially.

3.11 Workmanship. The finished cloth shall conform to the quality of product established by this document. The demerit points per 100 square yards, when calculated as specified in section 4, shall not exceed the established maximum acceptable point value. Each defect shall be marked with a 1 to 1-1/2 inch long string. The string shall be sewn into the selvage near the defect. A red string shall represent a three or four-point defect and a white string shall represent a one or two-point defect (see 4.4.3.5).

4. QUALITY ASSURANCE PROVISION

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements (examinations and tests) as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in this specification where such inspections are deemed necessary to ensure supplies and services conform to prescribed requirements.

4.1.1 Responsibility for compliance. All items shall meet all requirements of sections 3 and 5. The inspection set forth in this specification shall become a part of the contractor's overall inspection system or quality program. The absence of any inspection requirements in the specification shall not relieve the contractor of the responsibility of ensuring that all products or supplies submitted to the Government for acceptance comply with all requirements of the contract. Sampling inspection, as part of manufacturing operations, is an acceptable practice to ascertain conformance to requirements, however, this does not authorize submission of known defective material, either indicated or actual, nor does it commit the Government to accept defective material.

4.1.2 Certificates of compliance. When certificates of compliance are submitted, the Government reserves the right to inspect such items to determine the validity of the certification.



Source: https://assist.dla.mil -- Downloaded: 2026-10-16T11:32Z
Check the source to verify that this is the current version before use.

4.2 Classification of inspections. The inspection requirements specified herein are classified as follows:

a. First article inspection (see 4.3)
b. Quality conformance inspection (see 4.4)

4.3 First article inspection. When a first article is required (see 3.1 and 6.2), it shall be examined for the defects specified in 4.4.3 through 4.4.3.5 and tested for the characteristics specified in 4.4.4.

4.4 Quality conformance inspection.

4.4.1 Component and material inspection. In accordance with 4.1, components and materials shall be inspected in accordance with all the requirements of referenced documents unless otherwise excluded, amended, modified, or qualified in this specification or applicable purchase document.

4.4.1.1 Wool grade examination. The wool shall be visually examined for grade (see 3.3.1) in undyed top form by comparison with the applicable U.S. Standard (see 2.1). In the event of a dispute, the wool grade shall be determined by the width method (wedge). The sample unit shall be 1 yard of undyed top prior to blending with nylon or polyester fibers. The sample size (number of sample units) shall be as shown below. The result from each sample unit shall be reported separately. The lot shall be unacceptable if one or more sample units fail to meet the required grade.

| Lot size (pounds) | Sample size (sample units) |
|---|---|
| 800 or less | 2 |
| 801 up to and including 22,000 | 3 |
| 22,001 and over | 5 |

4.4.1.2 Polyester fiber certification. Polyester fiber shall be accepted on the basis of a contractor's certification of compliance with the requirements specified in 3.3.1.3.

4.4.2 In-process inspection. Inspection shall be made at any point or during any phase of the manufacturing process to assure that no laps, noils or any other wool manufacturing by-products are used (see 3.3.1.1, 3.3.1.2 and 3.3.1.3), and that the dyeing requirements have been adhered to (see 3.4). The Government reserves the right to exclude from consideration for acceptance any material for which the in-process inspection has indicated nonconformance.



Source: https://assist.dla.mil -- Downloaded: 2026-10-16T11:32Z
Check the source to verify that this is the current version before use.

4.4.3 Yard-by-yard examination. The yard-by-yard examination shall be as specified in MIL-STD-655. The fabric quality for all shades shall be quality level 10.

4.4.3.1 Limits of slubs and knots. Only slubs and knots which exceed "D" for slubs and "C" for knots on the Sears Fabric Defect Scale (see 6.8) shall be scored.

4.4.3.2 Examination for length. The examination for length shall be as specified in MIL-STD-655.

4.4.3.3 Examination for back marking and compliance with the Wool Products Labeling Act. The examination for back marking and compliance with the Wool Products Labeling Act shall be as specified in MIL-STD-655.

4.4.3.4 Examination for shade match and finish, individual rolls. A sample from each roll in the lot shall be examined visually for shade (see 3.4.2), finish and appearance (see 3.6). A roll shall be unacceptable if it fails to meet the requirements for shade, finish or appearance. The sample shall be a 4-inch by 20-inch swatch of the cloth. A sample shall be drawn from each roll in the lot.

4.4.3.5 Examination for defect marking (stringing of defects). The examination for defect marking (stringing of defects) shall be as specified in MIL-STD-655.

4.4.4 End item testing. The cloth shall be tested for the applicable characteristics indicated in table II. The methods of testing specified in FED-STD-191 wherever applicable and as listed in table II shall be followed. The physical and chemical values specified in section 3 apply to the results of the determinations made on a sample unit for test purposes as specified in the applicable test method. The sample unit shall be 3-1/2 continuous yards full width of the finished cloth. The lot shall be unacceptable if one or more sample units fail to meet any test requirement specified. All test reports shall contain the individual values utilized in expressing the final results. The sample size shall be in accordance with the following:

| Lot size (yards) | Sample size (sample units) |
|---|---|
| 800 or less | 2 |
| 801 up to and including 22,000 | 3 |
| 22,001 and over | 5 |



Source: https://assist.dla.mil -- Downloaded: 2026-10-16T11:32Z
Check the source to verify that this is the current version before use.

TABLE II. End item testing

| Characteristic | Requirement paragraph | Test method |
|---|---|---|
| Fiber content (finished cloth): | | |
| Wool (type I) | 3.8 | 2101 |
| Nylon and wool (type II) | 3.3.1.2 | 2530 1/ |
| Polyester and wool (type III) | 3.3.1.3 | 2102 |
| Mothproofing | 3.4.1 | 2/ |
| Colorfastness to: | | |
| Wet drycleaning | 3.4.3 | 5622 |
| Crocking | 3.4.3 | 5651 |
| Perspiration | 3.4.3 | 5680 |
| Light (after 80 standard fading hours) | 3.4.3 | 5660 |
| Dry heat (sublimation), at 325°F ± 6°F (type III only) | 3.4.3 | 5642 |
| Weight | 3.5 | 5041 |
| Yarn ply: | | |
| Warp | 3.5 | Visual 3/ |
| Filling | 3.5 | Visual 3/ |
| Yarns per inch | 3.5 | 5050 |
| Breaking strength | 3.5 | 5100 |
| Shrinkage | 3.5 | 5558 |
| Weave | 3.5.2 | Visual 3/ |
| Pilling (type III) | 3.6.1 | 5320 4/ |
| pH | 3.6.2 | 2811 |

1/ Nylon percent = $\frac{S - R}{S} \times 100$

Where: S = Weight of dry chloroform extracted specimen
R = Weight of residual fiber



Source: https://assist.dla.mil -- Downloaded: 2026-10-16T11:32Z
Check the source to verify that this is the current version before use.

2/ The test for percent mothproofing compound shall be as specified in MIL-C-43665.

3/ One determination per sample unit and the results reported as "pass" or "fail".

4/ The pilling test shall be conducted in accordance with Method 5320, except that five specimens of the test cloth and one specimen of the standard sample shall be used concurrently.

4.4.5 Packaging inspection. The sampling and inspection of the preservation and packing marking shall be in accordance with the requirements of PPP-P-1132.

5. PACKAGING

5.1 Put-up and preservation. Put-up and preservation shall be level A or Commercial as specified (see 6.2).

5.1.1 Levels A and Commercial. The cloth shall be put-up and preserved in accordance with the applicable requirements of PPP-P-1132.

5.2 Packing. Packing shall be level A, B or Commercial as specified (see 6.2).

5.2.1 Levels A, B and Commercial. The cloth shall be packed in accordance with the applicable requirements of PPP-P-1132.

5.3 Marking. In addition to any special marking required by the contract or purchase order, shipments shall be marked in accordance with the applicale requirements of PPP-P-1132.

6. NOTES

(This section contains information of a general or explanatory nature that may be helpful, but is not mandatory.)

6.1 Intended use. The cloths covered by this document are for use in service, semi-dress, dress uniforms and functional clothing used by the Department of Defense.

6.2 Acquisition requirements. Acquisition documents must specify the following:

a. Title, number, and date of this specification.
b. Type and class required (see 1.2).



Source: https://assist.dla.mil -- Downloaded: 2026-10-16T11:32Z
Check the source to verify that this is the current version before use.

c. Issue of DODISS to be cited in the solicitation, and if required, the specific issue of individual documents referenced (see 2.1.1 and 2.2).
d. When a first article is required (see 3.1, 4.3, and 6.3).
e. Whether polyester top or cut tow is required for type II cloth (see 3.3.1.2).
f. Nylon blend when type II cloth is required (if other than specified in 3.3.1.2).
g. Whether polyester top or cut tow is required for type III cloth (see 3.3.1.3).
h. Color required (see 3.4).
i. Minimum length if other than specified (see 3.7).
j. Levels of preservation and packing (see 5.1 and 5.2).
k. When weather-resistant grade fiberboard shipping containers are required for level B packing (see 5.2.1).

6.3 First article. When a first article is required, it shall be inspected and approved under the appropriate provisions of FAR 52.209. The first article should be a preproduction sample. The contracting officer should specify the appropriate type of first article and the number of units to be furnished. The contracting officer should also include specific instructions in acquisition documents regarding arrangements for selection, inspection, and approval of the first article.

6.4 Standard sample. For access to standard samples, address the contracting activity issuing the invitation for bids or request for approval.

6.5 Colors, types and classes of cloth used by the Services. The colors of cloth required by the Services are as follows:

| Service | Color | Type | Class | Weight (ounces) |
|---|---|---|---|---|
| Army | Olive Green 108 | I | 1 | 18 |
| | Army Green 44 | I or II | 2 | 16 |
| | Army Green 44 | I | 5 | 15 |
| | Army Green 44 | I | 7 | 12 |
| | Army Green 44 | I | 8 | 12 |
| | Army Green 489 | III | 1 | 14 |
| | Army Green 489 | III | 2 | 12 |
| | Army Green 489 | III | 3 | 11.3 |
| Navy | Blue 3346 | I | 3 | 16 |
| | Blue 3346 | I | 5 | 15 |
| | Blue 3346 | I | 7 | 12 |



Source: https://assist.dla.mil -- Downloaded: 2026-10-16T11:32Z
Check the source to verify that this is the current version before use.

| Service | Color | Type | Class | Weight (ounces) |
|---|---|---|---|---|
| Coast Guard | Blue 3362 | III | 3 | 11.3 |
| Marine Corps | Green 2234 | I | 5 | 15 |
| | Green 2207 and Blue 2305 | I | 8 | 12 |

6.6 Suggested dyestuff formulations. Suggested but not mandatory, dyestuff formulations for Army Green 44, Army Green 489, Olive Green 108, Marine Corps Green 2234 and Navy Shade Blue 3346 are as listed herein. The standard shade samples have been dyed with these formulations.

Wool component for Army Green 44 and Army Green 489:

Acid Green 70
Acid Green 58
Acid Orange 85
Acid Orange 86

The ratio of Acid Green 70 to the Acid Green 58 shall be 1:1 for equal strengths of the two dyes. The formulation has been shown to provide optimum colorfastness properties when dyed with either ammonium sulfate or ammonium acetate.

NOTE: Since Army Green 44 is essentially a solid shade, no specific blends of primaries are recommended; however, if a system of blending primaries is used, shade difference between primaries should be kept at a minimum in order to avoid a two-tone or heathery effect which is not acceptable.

Polyester component for Army Green 489:

| | | |
|---|---|---|
| Disperse Blue 62 | | Disperse Blue 27, CI 60767 |
| Disperse Yellow 23 CI 26070 | | Disperse Yellow 23, CI 26070 |
| Disperse Red 59 | or | Disperse Red 4, CI 60755 |
| Disperse Violet 18 | | Disperse Yellow 42, CI 10338 |



Source: https://assist.dla.mil -- Downloaded: 2026-10-16T11:32Z
Check the source to verify that this is the current version before use.

Olive Green 108:

Acid Orange 85
Acid Blue 165
Acid Green 70
Acid Green 58
Acid Orange 86

Marine Corps Green 2234:

The standard sample for Marine Corps Green 2234 was blended with approximately 13 percent white wool and 87 percent green wool dyed with a formulation of neutral premetallized dyes as follows:

Neutral Premetallized Grey RLX (no index number)
Acid Yellow 128
Acid Brown 45

Other premetallized dyes or combinations of premetallized dyes producing the required shade and colorfastness properties will be acceptable.

Navy Shade Blue 3346:

Mordant Black 9, CI 16500
Mordant Red 27
Mordant Blue 7, CI 17940

6.6.1 Shade control. Shade control of those shades dyed on fabrics in the 16-ounce and lighter weight constructions is critical and the contractor is accordingly cautioned to exercise special care in color matching such shades (see 3.4).

6.7 Finish. The finish of this cloth is critical and the contractor is accordingly cautioned to insure that the amount of twist in the yarns and the subsequent setting and dry finishing of the fabric are adequately controlled to preclude the possibility of movement of the fiber to the fabric surface during wear, thus increasing the degree of cover beyond that shown by the standard sample (see 6.4).

6.8 Fabric defect scales. Sears Fabric Defect Replica Kits are available from:

Sears Roebuck and Company
Department 817, (ATTN: BSC 23-29)
Sears Tower
Chicago, IL 60684



Source: https://assist.dla.mil -- Downloaded: 2026-10-16T11:32Z
Check the source to verify that this is the current version before use.

6.9 Subject term (key word) listing.

Extended Cold Weather Clothing System
Fabric
Uniform

6.10 Changes from previous issue. Marginal notations are not used in this revision to identify changes with respect to the previous issue due to the extensiveness of the changes.

MILITARY INTERESTS:

Custodians:

Army - GL
Navy - NU
Air Force - 11

Review activities:

Army - MD
Air Force - 82, 99
DLA - CT

User activities:

Navy - MC, CG

PREPARING ACTIVITY:

Army - GL

(Project 8305-0354)



Source: https://assist.dla.mil -- Downloaded: 2026-10-16T11:32Z
Check the source to verify that this is the current version before use.

# STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

## INSTRUCTIONS

1. The preparing activity must complete blocks 1, 2, 3, and 8. In block 1, both the document number and revision letter should be given
2. The submitter of this form must complete blocks 4, 5, 6, and 7
3. The preparing activity must provide a reply within 30 days from receipt of the form.

NOTE This form may not be used to request copies of documents, nor to request waivers, or clarification of requirements on current contracts Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

| I RECOMMEND A CHANGE: | 1 DOCUMENT NUMBER<br>MIL-C-883K | 2 DOCUMENT DATE (YYMMDD)<br>19[illegible] September 21 |
|---|---|---|

3 DOCUMENT TITLE
CLOTH, SERGE, WOOL, WOOL AND NYLON, POLYESTER AND WOOL

4 NATURE OF CHANGE (*Identify paragraph number and include proposed rewrite, if possible Attach extra sheets as needed*)

5 REASON FOR RECOMMENDATION

6. SUBMITTER

| a. NAME (Last, First, Middle Initial) | b. ORGANIZATION | |
|---|---|---|
| c. ADDRESS (Include Zip Code) | d. TELEPHONE (Include Area Code)<br>(1) Commercial<br>(2) AUTOVON (If applicable) | 7. DATE SUBMITTED (YYMMDD) |

8. PREPARING ACTIVITY

| a. NAME<br>U S Army Natick RD&E Center | b. TELEPHONE (Include Area Code)<br>(1) Commercial: 508-651-5221<br>(2) AUTOVON: 256-5221 |
|---|---|
| c. ADDRESS (Include Zip Code)<br>Commander, U S Army Natick RD&E Center<br>ATTN STRNC-ES<br>Natick, MA 01760-5014 | IF YOU DO NOT RECEIVE A REPLY WITHIN 45 DAYS, CONTACT<br>Defense Quality and Standardization Office<br>5203 Leesburg Pike, Suite 1403, Falls Church, VA 22041-3466<br>Telephone (703) 756-2340 AUTOVON 289-2340 |

Source: https://assist.dla.mil -- Downloaded: 2026-03-16 14:22
Check the source to verify that this is the current version before use.