DOD-C-70463(AR)
AMENDMENT 1
8 May 1987

MILITARY SPECIFICATION

CARTRIDGE 5.56MM:
PLASTIC, BALL, PRACTICE, M862

This Amendment forms a part of Military Specification DOD-C-70463(AR), dated 26 January 1984, and is approved for use within the US Army Armament Munitions and Chemical Command, and is available for use by all Departments and Agencies of the Department of Defense.

PAGE 3

3.4 Residual stress: Delete in its entirety and substitute the following:

"Residual stress: The cartridge case shall be subjected to a 1% mercurous nitrate solution for 15 minutes. The cartridge case shall not split in the J, K, L, or M section of the metal case.".

3.7 Velocity: Change "2.5M" to "4.57M (15ft.)".

PAGE 4

3.14.2 Metal integrity: Delete the word "folds".

PAGE 8 & 9

4.3.4.1 Table II. QUALITY CONFORMANCE INSPECTION. Delete in its entirety and substitute the following:

"See note 1 below.

CRITICAL				
1.	Case split in K, L, or M location (6)	100%	3.2	Visual
2.	Perforated case (7)	100%	3.2	Visual
3.	Primer cocked (33)	100%	3.2	Visual
4.	Primer inverted (34)	100%	3.2	Visual
5.	Primer above flush	100%	3.2	Gage
MAJOR				
101.	Cartridge corroded or stained (2)	.25%	3.2	Visual
102.	Head round (3)	.25%	3.2	Visual

FSC N/A

FSC 1305

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T03:29Z
Check the source to verify that this is the current version before use.

103.	Case dent (5)	.25%	3.2	Visual
104.	Case split in I, S, or J location (6)	.25%	3.2	Visual
105.	Case draw scratch (8)	.25%	3.2	Visual
106.	Beveled underside of head (10)	.25%	3.2	Visual
107.	Case metal scaly (12)	.25%	3.2	Visual
108.	No chamfer on head (rim) (13)	.25%	3.2	Visual
109.	Primer loose (35)	.25%	3.2	Visual
110.	Lubrication missing	.25%	3.2	Visual
111.	Primer missing	.25%	3.2	Visual
112.	Weight of cartridge over maximum	.25%	3.2	Gage
MINOR				
201.	Cartridge discolored or dirty	1.5%	3.2	Visual
202.	Case scratch (9)	1.5%	3.2	Visual
203.	Illegible or missing headstamp	1.5%	3.2	Visual
204.	Defective head (19)	1.5%	3.2	Visual
205.	Defective mouth (20)	1.5%	3.2	Visual
206.	Bullet dent (22)	1.5%	3.2	Visual
207.	Bullet scratch (23)	1.5%	3.2	Visual
208.	Bullet, upset (crooked) point (28)	1.5%	3.2	Visual
209.	Nicked or dented primer (36)	1.5%	3.2	Visual

NOTES 1/ Refer to MIL-STD-636 (NATO) Caliber 7.62mm section 1 for visual defect standards for the characteristics that have a number in parenthesis. The number in parenthesis refers to the corresponding callout in MIL-STD-636.".

PAGE 12

Table III A: Delete 3a and substitute the following:

"a.	Perforation in firing pin indent in primer cup 2/	0	1".

Custodian:
Army-AR

Preparing activity:
Army-AR

(Project 1305-AC53)

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T03:29Z
Check the source to verify that this is the current version before use.