INCH-POUND

MIL-A-70604 (AR)
AMENDMENT 1
23 November 1990

MILITARY SPECIFICATION

AMINE BONDING AGENT

This amendment forms a part of Military Specification MIL-A-70604 (AR), dated 22 April 88, and is approved for use within the US Army Armament, Munitions and Chemical Command and is available for use by all Departments and Agencies of the Department of Defense.

PAGE 3

3.1 Composition. Delete Table I in its entirety and substitute the following:

"Table I. Chemical and Physical Properties for Amine Bonding Agent

Characteristic	Requirement Min.	Max.	Applicable Test Paragraph
Total Amine, eq/100g	1.1	1.6	4.5.2
Ammonia, ppm	---	500	4.5.4
Moisture, %	---	0.85	4.5.5
Viscosity, 25 C, cps	500	1,000	4.5.6"

PAGE 8

4.4.3.1 Sampling. Change the table to the following:

Number of containers in batch	Number of containers to be sampled
2 - 200	2
Over - 200	5"

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T03:47Z
Check the source to verify that this is the current version before use.

PAGE 9

4.5.1 Secondary amine. Delete in its entirety.

PAGE 13

4.5.3 Tertiary amine. Delete in its entirety.

PAGE 14

4.5.4.2 Reagents. Delete paragraph a. in its entirety and substitute the following:

"a. Sodium hydroxide, 10M. Add 40 grams of AR Grade NaOH to 80 ml of DI water in a 100 ml volumetric flask, dissolve and dilute to volume with deionized water."

PAGE 16

5.2 Marking. Change "LONG TERM STORAGE SHOULD BE BELOW 32 DEGREES F TO PRESERVE PRODUCT QUALITY" to the following: "LONG TERM STORAGE SHOULD BE AT OR BELOW 0 DEGREES F TO PRESERVE PRODUCT QUALITY".

Custodian:
Army-AR

Preparing activity
Army-AR

(Project 6810-A047)

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T03:47Z
Check the source to verify that this is the current version before use.