MILITARY SPECIFICATION

OBTURATING BANDS, PLASTIC, RIGID, HIGH IMPACT POLYVINYL CHLORIDE (MOLDED)

This Amendment forms a part of Military Specification MIL-O-60540 (AR), dated 30 June 1966, and is approved for use within the US Army Armament, Munitions and Chemical Command, and is available for use by all Departments and Agencies of the Department of Defense.

PAGE 1

Add the following new paragraphs:

"2.2 Other publications. The following document(s) form a part of this specification to the extent specified herein. Unless otherwise specified, the issues of the documents which are DOD adopted shall be those listed in the issue of the DODISS specified in the solicitation. Unless otherwise specified, the issues of documents not listed in the DODISS shall be the issue of the nongovernment documents which is current on the date of the solicitation.

AMERICAN SOCIETY FOR TESTING AND MATERIALS

ASTM D 256	-	Impact Resistance of Plastics and Electrical Insulating Materials.
ASTM D 638	-	Tensile Properties of Plastics.
ASTM D 1243	-	Dilute Solution Viscosity of Vinyl Chloride Polymers.

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103).

2.3 Order of precedence. In the event of a conflict between the text of the specification and the references cited herein (except for associated detail specifications, spectification sheets or MS standards), the text of this specification shall take precedence. Nothing in this specification, however, shall supersede applicable laws and regulations unless a specific exemption has been obtained."

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T00:41Z
Check the source to verify that this is the current version before use.

3.2 Delete in its entirety and substitute the following:

"3.2 Material. The material shall consist of polyvinyl chloride resin of high molecular weight, suitably compounded with heat stabilizers, a suitable elastomer, lubricants and pigments. No re-grind or scrap will be allowed.

3.2.1 Inherent viscosity. Polyvinyl chloride (PVC) resin shall have an inherent viscosity greater than 0.65 when tested IAW paragraph 4.4.5.

3.2.2 Tensile strength. The minimum tensile strength of PVC compound shall be 6,000 pounds per square inch (p.s.i.) when tested IAW paragraph 4.4.6.

3.2.3 Tensile modulus. The tensile modulus of PVC compound shall be 380,000 p.s.i. minimum when tested IAW paragraph 4.4.7.

3.2.4 Izod impact strength. The izod impact strength at 23°C shall not be less than 19 foot - pound nor more than 22 foot - pound when tested IAW paragraph 4.4.8."

PAGE 3

Add the following new paragraphs:

"4.4.5 Inherent viscosity. The inherent viscosity shall be tested in accordance with ASTM D 1243.

4.4.6 Tensile strength. The tensile strength shall be tested as specified in ASTM D 638.

4.4.7 Tensile modulus. The tensile modulus shall be tested as specified in ASTM D 638.

4.4.8 Izod impact strength. The izod impact strength range shall be tested as specified in ASTM D 256."

Custodian:
Army - AR

Preparing activity:
Army - AR

(Project 1395-A229)

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T00:41Z
Check the source to verify that this is the current version before use.